Title	Leaching behaviour of elements and evaluation of pre-treatment methods for municipal solid waste incinerator residues in column leaching tests.
Author(s)	Kim, Sang-Yul; Tanaka, Nobutoshi; Matsuto, Toshihiko; Tojo, Yasumasa
Citation	Waste Management and Research, 23(3), 220-229 https://doi.org/10.1177/0734242X05055322
Issue Date	2005-06
Doc URL	http://hdl.handle.net/2115/13784
Rights	Copyright © 2005 by International Solid Waste Association
Type	article (author version)
File Information	wmr3.pdf

[Instructions for use](#)

Leaching Behaviour of Elements and Evaluation of Pre-treatment Methods for Municipal Solid Waste Incinerator (MSWI) Residues in Column Leaching Tests

Sang-Yul Kim, Nobutoshi Tanaka, Toshihiko Matsuto, Yasumasa Tojo

Department of Environmental and Resource Engineering,

Hokkaido University,

Kita 13 Nishi 8, Kita-ku, Sapporo, Hokkaido, 060-8628, Japan

Phone: +81-11-706-6830

Fax: +81-11-707-6585

Corresponding author: Sang-Yul, Kim

Phone: +81-11-706-6830

Fax: +81-11-707-6585

Email: sykim@eng.hokudai.ac.jp

Abstract

Two new pre-treatment methods (water-washing/carbonation and carbonation/phosphate stabilisation) of municipal solid waste (MSW) incinerator residues were evaluated by column leaching tests under aerobic conditions and anaerobic conditions (which were changed to aerobic conditions after 10 months). A mixture of bottom ash and fly ash (5:1 ratio) was pre-treated using each method. Shredded incombustible residues (SIR) were added to each ash preparation in proportions similar to the ratios present in landfills. For comparison, landfill wastes typical of Japan, *i.e.*, a mixture of bottom ash, chelating-pre-treated fly ash, and SIR, were also examined. Leachate samples were collected periodically and analysed over a 15-month period.

When compared to chelating pre-treatment, both water-washing/carbonation and carbonation/phosphate stabilisation reduced the leaching of Pb, Al, and Cu by about 1-2 orders of magnitude. Moreover, the initial concentrations of Ca and Pb in leachates from column of water-washing/carbonation were 56-57% and 84-96% less than those from column of carbonation/phosphate stabilisation. Therefore, water-washing/carbonation was considered to be a promising approach to obtain early waste stabilisation and to reduce the release of heavy metals to near-negligible levels. The leaching behaviour of elements was also discussed.

KEYWORDS: MSW incinerator residues, pre-treatment, water washing, carbonation, phosphate stabilisation, heavy metals, column leaching tests, leaching behaviour

1. Introduction

Approximately 75% of all municipal solid waste (MSW) has been incinerated over a couple of decades in Japan. This has increased the proportion of MSW incinerator residues ending up in landfills. According to the Japanese white paper on the environment (2003), MSW incineration residues (bottom ash and fly ash) and incombustible wastes account for more than 50% of total wastes landfilled in Japan, and is expected to increase further since the location of landfill sites becomes difficult to secure.

In Japan, MSW incinerator fly ash must be pre-treated prior to its deposition in landfills, according to the Waste Disposal and Public Cleansing Law (1991). The pre-treatment options are: 1) melting and solidification; 2) solidification by cement; 3) stabilisation using chemical agents; and 4) extraction with acid or other solvents. Among these pre-treatment methods, stabilisation using chemical agents is commonly used in Japan because it is a simple and relatively inexpensive method that produces negligible volume expansion. Chelating agents, such as thiol ($-SH$) or dithiocarbamate ($-NH-CSSH$) groups, have been widely used (Tanaka 1995). In contrast to fly ash, MSW incinerator bottom ash is added directly to landfills with no legally required pre-treatment. However, it has been reported that MSW incinerator bottom ash contains 20 to 50 times larger concentrations of Cd, Cu, Pb, and Zn than does unpolluted soil (Sakanakura 1999). In Japan, leachates from several landfills contained hazardous trace metals (Pb, Cd, Zn, Cu, and Hg) in concentrations greater than allowed by the criteria for Japanese wastewater discharge (Tanaka 2000). The location of landfill sites has become more difficult because of vastly increased public concern on the leaching of toxic heavy metals from MSW incinerator residues. In this context, the leaching of toxic heavy metals from MSW incinerator bottom ash is of growing concern in Japan.

To address this problem, previous work examined the effects of some simple and cost effective pre-treatment methods on mixtures of bottom ash and fly ash using several batch leaching tests (Kim et al. 2003). It was demonstrated that water-washing effectively removed the major elements from the mixtures of bottom ash and fly ash, and also reduced the leachability of trace metals, such as Pb and Cd; carbonation significantly reduced the levels of Ca, as well as trace metals in leachate, and phosphate stabilisation appreciably lessened the extent to which heavy metals, particularly Pb, leached, even under acidic conditions. However, uncertainty exists on the long term availability and mobility of heavy metals retained in the landfill when atmospheric air starts to diffuse into the landfill waste during maturation phase, which causes the redox potential to raise and where sulphides may be oxidized. Therefore, it is important to understand whether

metals continue to be immobilized within a landfill, in particular whether progressing aerobic conditions may lead to the release of heavy metals. However, relatively few such studies have been carried out on column leaching tests.

The purposes of this work were to evaluate the effectiveness of water-washing/carbonation and carbonation/phosphate stabilisation under aerobic conditions, anaerobic conditions, and changing conditions from anaerobic to aerobic conditions in column leaching experiments, and to understand the leaching characteristics of potential pollutants under such conditions.

2. Materials and Methods

2.1 Materials

Bottom ash, fly ash, chelating-pre-treated fly ash (this chelating agent included dithiocarbamates group), and shredded incombustible residues (SIR) were directly obtained from a MSW incinerator in Sapporo (Japan). SIR is defined as the residues screened by a vibrating screen after shredding bulky MSW and ferrous metal recovery by a magnetic separator. Table 1 shows the physical composition of the SIR sample. The stoker mass-burn incinerator has a processing capacity of 300 tons per day and is equipped with an electric precipitator. The flue gas is treated with injection of dry $\text{Ca}(\text{OH})_2$ prior to the electrostatic precipitators from which the fly ash was sampled from the outlet. Chelating-pre-treated fly ash and a water-quenched bottom ash were sampled separately at each ash pit, which serves as temporary storage before transfer to a landfill site. For the immobilisation of heavy metals in fly ash, 0.5% (v/w) chelating agent and 25% (w/w) aluminium sulphate (as a coagulating agent) were applied to fly ash as a solution. After drying at 105°C, the bottom ash that passed through a 16-mm sieve (95% of the total) was used. The chemical composition and ignition loss of the bottom ash and fly ash are summarized in Table 2. Prior to the pre-treatments, bottom ash and fly ash were mixed at a ratio of 5:1 on a dry weight basis (based on actual data for landfill waste in Sapporo). This ash mixture is subsequently referred to as “B-F ash.”

2.2 Methods

2.2.1 Pre-treatment Processing

The processing conditions for each pre-treatment are based on previous work (Kim et al. 2003).

(a) Water-washing and Carbonation (W-C)

The B-F ash was washed with distilled water, using a liquid/solid (L/S) ratio of 5:1, and a washing time of 30 min. After the washing process, the solids were separated from the liquid and were dried at 105°C for the subsequent carbonation treatment. Then 7 kg dry weight of the solids was set at 15% moisture content with distilled water before filled in column. An acrylic column (inner diameter 15.6 cm, height 100 cm) was filled with the wet B-F ash (15% moisture content)

to a depth of about 40 cm; thus the bulk density was approximately 0.92 ton m^{-3} . Then 10% CO_2 (90% N_2) gas was injected into the column from the bottom at a constant flow rate of 5 Lmin^{-1} for 300 min. The concentration of CO_2 in the gas outlet was not detected until about 90 min, then increased exponentially for about 240 min, and became constant at around 9% afterwards, which was defined as the saturation of carbonation in this study. The calculated amount of CO_2 absorbed by B-F ash was about $0.48 \text{ mmol CO}_2 \text{ g}^{-1}$ dry B-F ash. If it is assumed that the total amount of CO_2 adsorbed reacted with Ca(OH)_2 in B-F ash, the CaCO_3 that would form is $0.48 \text{ mmol CaCO}_3 \text{ g}^{-1}$ dry B-F ash. The pre-treated B-F ash (referred to as “W-C pre-treated B-F ash”) was oven dried at 105°C and stored in polyethylene bags.

The W-C pre-treated B-F ash was examined by the leaching test specified in Notification No. 13 (JLT-13) of the Environment Agency of Japan (Environmental Agency, Japan 1973). W-C pre-treated B-F ash (10 g) was mixed with 100 mL of distilled water. The suspension was mixed for 6 h at room temperature and filtered through a $1\text{-}\mu\text{m}$ glass fiber filter. The results are presented in Table 3. Leaching concentrations of soluble salts (Cl, Na, and K) and some trace metals (Cu, Pb, and Zn) from W-C pre-treated B-F ash were lower than those of untreated B-F ash by 73.6-84.1% and 65.3-99.8%, respectively. Leaching of Ca was also considerably reduced by 54.9% when compared to that of untreated B-F ash. However, there was no clear difference between the levels of Cr in W-C pre-treated B-F ash and in untreated B-F ash.

(b) Carbonation and Phosphate Stabilisation (C-P)

The carbonation process was the same as described above. Subsequently, the carbonated B-F ash was mixed with a phosphoric acid solution ($0.16 \text{ mol H}_3\text{PO}_4$ per kg of carbonated B-F ash) for 10 min and aged for 30 min in air. An L/S ratio of 0.5 was used. The pre-treated B-F ash (referred to as “C-P pre-treated B-F ash”) was dried at 105°C and stored in polyethylene bags. As the results of the JLT-13 leaching test, unlike the results of water-washing and carbonation (W-C) pre-treatment, C-P pre-treatment resulted in levels of soluble salts (Cl, Na, and K) that were almost the same as levels from untreated B-F ash; but the leaching of Ca, Cu, and Pb was reduced by 76%, 76.5%, and 99.9%, respectively when compared to the untreated B-F ash (Table 3).

2.2.2 Column Leaching Tests

Transparent acrylic plastic columns (inner diameter 15.6 cm, height 1 m) were filled with SIR and the B-F ash pre-treated by water-washing/carbonation or carbonation/phosphate stabilisation; these columns are subsequently referred to as “column W-C” and “column C-P”, respectively. The mixture ratio of SIR to B-F ash was 1:9 on a dry weight basis, which was based on actual data for landfill waste in Sapporo. The initial water content of each sample was preset at 15% with distilled water before packed manually in the column. Each column contained about 12 kg

mixture ash of SIR and B-F ash on a dry weight basis (the bulk density of approximately $0.91\text{--}0.95\text{ ton m}^{-3}$). A thermostat controlled the temperature at $30^{\circ}\text{C} \pm 3^{\circ}\text{C}$. For comparison, a mixture of bottom ash, chelating-pre-treated fly ash, and SIR was also filled in a column (referred to as “column STD”) with the same ratios and conditions as for columns W-C and C-P. Column STD is prepared to simulate representative landfill wastes in Japan.

Layers of quartz-sand (1 cm deep) were placed at the top and bottom of each column to ensure a uniform feed water distribution and to prevent the formation of channels. An aerobic column and an anaerobic column were constructed for each three columns: column STD, column W-C, and column C-P (Table 4). For aerobic conditions, the top and bottom of the columns were open to air. Also, three points for gas sampling were set up at intervals of about 30 cm from the top of aerobic columns, in order to examine aerobic conditions in the waste mixture. The concentrations of O_2 in the columns ranged from 18-21% (data not shown). For anaerobic conditions, on the other hand, gas bags were connected to the top of the anaerobic columns to measure the compositions and amount of gas generated from the waste mixture, and S-type glass pipes were connected with glass flasks at the bottom to prevent air penetration (Figure 1). Anaerobic columns were purged with 99.9% nitrogen gas after sampling for leachate and gas (every week).

During column leaching experiments, experimental conditions were altered twice, in order to examine their effects on the leaching behaviour of elements; the change in pH of supply water from distilled water to pH 3 water which was adjusted with HNO_3 solution at the L/S of 1.2, and the change of anaerobic conditions to aerobic conditions at the L/S of 2.0, by making the top and bottom of anaerobic columns open to air.

To mimic the annual average rainfall in Japan, 600 mL of distilled water was fed onto each column once every week, which is equivalent to an L/S of 0.05 per week; the leachate was sampled twice: 12 h after a feeding and just prior to the next feeding. Only small differences in the concentrations of elements were found between the two separately collected leachate samples, so the data presented here are from the first sample (12 h leachate). Leachate was collected and analysed over the 15-month period. In column leaching experiments, L (l) refers to the accumulated amount of collected leachate and S (kg) is the dry weight of B-F ash and SIR in the column.

2.2.3 Geochemical Modeling

The computer program MINTEQA2 version 3.11 (Allison et al. 1991) was used to interpret the leaching behaviour of heavy metals from all columns. Input files in MINTEQA2 program contain total concentrations of inorganic elements measured in leachates as well as the pH and ionic strength, which was fixed at the measured value. No solids were allowed to precipitate. Potential solubility-controlling minerals were selected on the basis of (1) the likeliness of their presence or

formation under the experimental conditions, and/or (2) saturation indices (SI), and/or (3) model-predicted curve shapes that follow the thermodynamic log activities of heavy metals of interest versus pH graphs. The thermodynamic log activities of heavy metals were calculated from analytical total concentrations using MINTEQA2, taking into account the ionic strength for each sample.

2.2.4 Analytical Methods

Heavy metals in acidified filtrates (<pH 2) were analysed by GF-AAS (Hitachi Z-8200) or flame AAS (Hitachi 170-50A and/or Hitachi A-2000). The concentrations of Cl^- were determined by ion chromatography (TOSOH CM-8). Biological oxygen demand for 5 days (BOD_5) was determined by the methods of the Japan Society for Analytical Chemistry (JSAC, 1994). The pH and Eh (redox potential) of aqueous samples were determined with a glass electrode (HORIBA D-24).

3. Results and Discussion

3.1 pH

Figure 2 shows the pH of leachates as functions of L/S ratios. The leachate pH values in all columns were established early and did not change substantially with L/S ratios, even after the feeding of acidic water (pH 3).

In column STD, leachate pH values were very high (pH 11.9-12.4) because of the presence of $\text{Ca}(\text{OH})_2$ and alkali metal hydroxides. The gap between the pH values under aerobic versus anaerobic conditions in column STD became larger with increasing L/S ratios (or time), which seemed to be higher CO_2 concentrations under aerobic conditions than under anaerobic conditions. Column STD under aerobic conditions was always open to atmospheric CO_2 , while the amount of CO_2 gas produced by microbial activities was considered to be negligible under anaerobic conditions at high pH. In columns W-C and C-P, on the other hand, the pH values under aerobic conditions remained near 8.2, except in the initial stage. However, in the case of anaerobic conditions in column W-C, the pH values stayed at 9-9.5 until the L/S reached 2.0; at that point, the anaerobic conditions were replaced by aerobic conditions and the pH of the leachate dropped to 8.1-8.3. This lower pH values are considered due to carbonation through the interaction between atmospheric CO_2 and calcium ion in leachate. This will be discussed later (see to 3.2).

If it is assumed that the buffering of leachate solutions primarily is by calcite (CaCO_3) (Meima & Comans 1997; Johnson & Furrer 2002), it would take approximately 9500 years until the entire stock of calcite was used up. The rough estimation was carried out as follows: Assuming that fifty percent of Japanese average annual rainfall (1,600 mm) infiltrate the leachate production will be $0.8 \text{ m}^3 \text{ m}^{-2} \text{ year}^{-1}$). The solubility of CaCO_3 at pH 8.3 corresponds to about $25 \text{ mgL}^{-1} \text{ Ca}$ at

ambient partial pressure of CO₂. Therefore, the amount of wash out of Ca becomes 20 g year⁻¹. Meanwhile, about 0.48 mol kg⁻¹ of CaCO₃ in dry B-F ash (see to 2.2.1(a)) corresponds to 190 kg Ca in a landfill of 10 m depth (10 m³ ≈ 10 ton B-F ash). The buffer lifetime of B-F ash amounts theoretically to about 9500 years. It should be noted that this calculation assumes ambient partial pressure of CO₂. The buffer lifetime would be shorter if the CO₂ produced by biodegradation is considered. However, the organic content in bottom ash is not high enough to significantly alter the buffer lifetime of B-F ash.

3.2 Ca

Although the leachate pH was nearly the same, the concentrations of Ca in the first leachate sampled from the W-C column were 56-57% less than those from the C-P column (Fig. 3(a)). According to a previous study (Kim et al. 2003), this discrepancy was produced by the water-washing pre-treatment, which can remove some soluble species such as gypsum (CaSO₄), CaCl₂, CaO, and Ca(OH)₂ from MSWI ash. The calculated Ca²⁺ activities in column STD were similar to those predicted from Ca(OH)₂ in both aerobic and anaerobic conditions (Fig. 3(b)), suggesting that they were controlled primarily by Ca(OH)₂. However, the Ca²⁺ activities deviated from those predicted from Ca(OH)₂ during the latter part of aerobic conditions and after the change from anaerobic to aerobic conditions (see to arrows in Fig. 3(b)), indicating that carbonation occurred slowly through the interaction with atmospheric CO₂. On the other hand, in the case of columns W-C and C-P, the Ca²⁺ activities followed those predicted from CaCO₃·xH₂O under aerobic conditions, while the Ca²⁺ activities under anaerobic conditions were above those predicted from CaCO₃·xH₂O and then approached the activity line of CaCO₃·xH₂O during the latter part of aerobic conditions and after the change from anaerobic to aerobic conditions (see to arrows in Fig 3(b)). These results suggested that the lack of CO₂ gas under anaerobic conditions caused CaCO₃·xH₂O precipitates to form slowly.

3.3 Al

Figure 4(a) shows that the leaching of Al in column STD increased to 34-45 mg L⁻¹, with L/S ratios, while the concentrations of Al in columns W-C and C-P decreased until an L/S of about 0.8, and levelled out at 1-3 mg L⁻¹ afterwards, except for those under anaerobic conditions in column W-C. The calculated Al³⁺ activities in highly alkaline leachate (column STD) were similar to those in equilibrium with crystalline Al(OH)₃ (gibbsite) (Figure 4(b)), suggesting that Al concentrations in column STD were controlled by crystalline Al(OH)₃. On the other hand, the calculated Al³⁺ activities in columns W-C and C-P were similar to those in equilibrium with amorphous Al(OH)₃, suggesting that Al concentrations in columns W-C and C-P were controlled by amorphous Al(OH)₃. Similar results were reported by Fruchter et al. (1990)

3.4 Cu and Pb

As shown in Figure 5(a), the concentrations of Cu under aerobic conditions in column STD

constantly decreased from 21.7 to 1.8 mg L⁻¹ with L/S ratios, which seemed to show little effect of chelating-pre-treatment from the beginning. On the other hand, under anaerobic conditions in column STD, leachate Cu decreased about 1-2 orders of magnitude less than those under aerobic conditions until the L/S reached 0.8 (at about 5 months). According to the results of the JLT-13 test (Table 3), bottom ash has more soluble Cu than fly ash (2.12 mg L⁻¹ Cu for bottom ash and 0.15 mg L⁻¹ Cu for fly ash). And that of the chelating-pre-treated fly ash was less than 0.01 mg L⁻¹ (data not shown). Furthermore, considering large amount of bottom ash in columns (5 times larger than fly ash on a dry weight basis), most Cu are considered to be released from bottom ash. Therefore, it is difficult to explain a sharp decrease (until the L/S reached 0.8) under anaerobic conditions with only small portion of the chelating-pre-treated fly ash. One plausible explanation is that surplus chelating agents dissolved from the chelating-pre-treated fly ash may react slowly with the Cu leached from bottom ash under anaerobic conditions. After that, Cu sharply increased from 0.95 to 3.6 mg L⁻¹ at an L/S of 0.8 and then decreased again. The sudden increase of Cu (from 1.17 to 3.67 mg L⁻¹) was observed after the change from anaerobic to aerobic conditions. Similar leaching behaviour was observed for Pb in column STD and is discussed later. In columns W-C and C-P, on the other hand, the leaching concentrations of Cu decreased about 1-2 orders of magnitude less than those in column STD.

The concentrations of Pb under aerobic conditions in column STD decreased from 4.63 to 0.02 mg L⁻¹ with increasing L/S ratios (or time). On the other hand, under anaerobic conditions in column STD, the leaching behaviour of Pb had two patterns, as already observed for Cu: leachate Pb decreased from 4.27 to 0.3 mg L⁻¹ until the L/S reached 0.8 (at about 5 months), and increased from 0.3 to 1.92 mg L⁻¹ at an L/S of 0.8 and increased once again from 0.93 to 3.18 mg L⁻¹ after the change from anaerobic to aerobic conditions (Figure 5(b)). Considering the characteristics of chelating agents, which have higher affinities for Cu and Pb than for the other elements (Sakanakura 1999), insoluble chelating complexes with Cu and Pb seemed to break up at an L/S of 0.8 under anaerobic conditions for some unknown reason (e.g. unexpected infiltration of O₂ during sampling). Several reports on the re-release of metals immobilized in chelating-pre-treated fly ash have appeared in Japan (Kamiishi & Takahashi 1988; Noma et al. 1989; Yuki et al. 1997; Sakanakura 1999). Sakanakura (1999) indicated that interactions with air and water evaporation are the crucial causes to weaken the bonding capacity of chelating agents.

On the other hand, the leaching of Pb from columns W-C and C-P decreased to 0.002 mg L⁻¹ at an L/S of about 0.5 and stayed less than the detection limit (0.002 mg L⁻¹) throughout the experimental period. Furthermore, the initial concentration of Pb from column W-C was 84-96 % less than that from column C-P, probably because of the water-washing pre-treatment, as observed for Ca. The effect of water-washing pre-treatment on Pb suggested that water-washing may not only remove readily soluble Pb species but may also reduce the leaching of Pb by

removing a significant amount of Cl, thereby precluding the formation of Cl complexes of Pb, which would have been more soluble (Cernuschi et al. 1990; Kim et al. 2002).

3.5 Cr

The leachate concentrations of Cr for all columns exhibited significantly different behaviour depending on aerobic or anaerobic conditions, but they seemed to be little affected by pre-treatment methods (Fig 6). Cr concentrations under aerobic conditions were constant (about 0.01-0.06 mg L⁻¹ Cr), whereas Cr concentrations under anaerobic conditions decreased to the detection limit (0.001 mg L⁻¹ Cr) within an L/S of 0.5 and were not detected until an L/S of 2.0, and increased more than 1-2 orders of magnitude (about 0.01-0.1 mg L⁻¹ Cr) upon changing to aerobic conditions.

These findings suggested that chromates formed during incineration would be slowly reduced under anaerobic conditions and release again when the aerobic phase set in. The Eh-pH diagram for CrO₄²⁻/Cr₂O₃ showed the valence change of Cr depending on aerobic or anaerobic conditions (data not shown).

4. Conclusions

In this study, two new alternative pre-treatments (water-washing/carbonation and carbonation/phosphate stabilisation) for MSW incinerator residues were examined using column leaching tests and were compared with a conventional chelating agent pre-treatment method. The following conclusions were obtained:

Compared to a conventional chelating agent pre-treatment (column STD), both water-washing/carbonation (column W-C) and carbonation/phosphate stabilisation (column C-P) pre-treatments reduced the leachability of Al, Cu, and Pb by about 1-2 orders of magnitude. In particular, the initial concentrations of Ca and Pb in leachate from the column of water-washing/carbonation were 56-57% and 84-96% less than those from the column of carbonation/phosphate stabilisation, although the leachate pHs were nearly the same, which is probably due to the effects of the water-washing pre-treatment. For columns W-C and C-P, carbonation played a significant role in neutralizing MSWI residues, resulting in very low solubility of most trace metals in the leachate.

Of the two new methods, water-washing/carbonation would be better than carbonation/phosphate stabilisation because of the significant reduction of initial concentrations of some trace metals and soluble salts as well as the strong buffering capacity of B-F ash (about 9500 years until the depletion of CaCO₃). Therefore, water-washing/carbonation was considered as promising approach to obtain earlier waste stabilisation and to reduce the release of heavy metals to near-negligible levels.

In terms of leaching characteristics of the elements in the leachate, most compounds in the fly

ash/bottom ash mixtures were qualitatively interpreted with pH, time, O₂, and CO₂ conditions. It was found that the leaching of Ca was controlled primarily by CaCO₃·xH₂O (pH 7.13-9.57) and Ca(OH)₂ (pH 11.7-12.8), respectively. It was also found that CO₂ was the important factor affecting leaching behaviour of Ca. Carbonation through the interaction with CO₂ gas tended to occur slowly. The leaching of Al was controlled primarily by amorphous Al(OH)₃ (pH 7.13-9.57) or crystalline Al(OH)₃ (pH 11.7-12.8), respectively. It is noted that a late mobilisation of Pb and Cu was observed in chelating-pre-treated fly ash (dithiocarbamate group). For Cr, atmospheric O₂ was the decisive factor affecting leaching behaviour. Significantly less Cr leached from columns under anaerobic conditions because of the reduction of Cr. Therefore, careful attention should be given to Cr(VI) which was highly mobile under aerobic conditions and after the change from anaerobic to aerobic conditions.

5. Reference

1. Abbas, Z., Steenari, B.M., & Lindqvist, O. (2001) A study of Cr(VI) in ashes from fluidized bed combustion of municipal solid waste: leaching, secondary reactions and the applicability of some speciation methods. *Waste Management* **21**, 725-739.
2. Allison, J.D., Brown, D.S. & Novo-Gradac, K.J. MINTEQA2/PRODEFA2, A geochemical assessment model for environmental systems: Version 3.0 User's manual; Environmental Research Laboratory, U.S.EPA: Athens, GA, 1991.
3. Cernuschi, S., Giugliano, M. & De Poli, I. (1990) Leaching of residues from MSW Incineration. *Waste Management & Research* **8**, 419-427.
4. Environment Agency, Japan, Testing methods for metals in industrial wastes, Notification No. 13 of the Environment Agency, February 17, 1973, in Japanese
5. Fruchter, J.S., Rai, D. & Zachara, J.M. (1990) Identification of solubility-controlling solid phases in a large fly ash field lysimeter. *Environmental Science & Technology* **24** (8), 1173-1179
6. Johnson, C.A. & Furrer, G. (2002) Influence of biodegradation processes on the duration of CaCO_3 as a pH buffer in municipal solid waste incinerator bottom ash. *Environmental Science & Technology* **36**, 215-220.
7. JSAC (1994) Water Analysis 4th edition, The Japan Society for Analytical Chemistry, Hokkaido branch, Japan (in Japanese).
8. Kamiishi, H. & Takahashi, T. (1998) Stabilisation of chelating-pre-treated fly ash (in Japanese). Proceedings of the 9th annual conference of the Japan Society of Waste Management Experts, 791-793.
9. Kim, S.Y., Matsuto, T. & Tanaka, N (2002) Solubility and adsorption characteristics of Pb in leachate from MSW incinerator bottom ash. *Waste Management & Research* **20** (4), 373-381.
10. Kim, S.Y., Matsuto, T. & Tanaka, N (2003) Evaluation of pre-treatment methods for landfill disposal of residues from municipal solid waste incineration. *Waste Management & Research* **21** (5), 416-423.
11. Marani, D., Macchi, G. & Pagano, M. (1995) Lead precipitation in the presence of sulphate and carbonate: Testing of thermodynamic predictions. *Water Research* **29**(4), 1085–1092.
12. Meima, J.A. & Comans, R.N.J. (1997) Geochemical modelling of weathering reaction in municipal solid waste incinerator bottom ash. *Environmental Science and Technology* **31**, 1269-1276.
13. Ministry of the Environment, Japanese White Paper on the Environment 2003.
14. Noma, Y., Kita, A., Takanobe, K. & Kodama, M. (1989) Long term stability of EP fly ash with chelating agent (in Japanese). Proceedings of the 1st annual conference of the Japan Society of Waste Management experts, 173-176.
15. Sakanakura, H. (1999) Study on stabilisation of heavy metal in municipal solid waste

- incinerator residues by chelating agents (in Japanese). PhD thesis pp 2 & 45-48
16. Tanaka N. (2000) Construction and management of MSW landfill. 1st edition. Gihoudo publication. Japan, 137-138.
 17. Tanaka Y. (1995) Recent performance on the treatment of heavy metals by chelating methods (in Japanese). Sangyo to Kankyo **24(9)**, 77–79.
 18. Wagman, D.D., Evans, W.H., Parker, V.B., Halow, I., Bailey, S.M. & Schumm, R.H. (1968) Selected values of chemical thermodynamic properties. NBC Technical Note 270-273.
 19. Weast, R.C. (1987) Handbook of Chemistry and Physics, 68th edition. CRC Press, Cleveland, Ohio.
 20. Yuki, O., Kawaguchi, S., Ohno, K., Moriyama, N. & Urushiyama, E. (1997) Long term stability of chelating-pre-treated fly ash in column leaching tests (in Japanese). Journal of Japan waste management association **50 (217)**, 134-137

Table 1. The physical composition of shredded incombustible residues (SIR) used in this study

Component	% (weight)
Glass	34.4
Stone	28.6
Plastics	21.5
Metals	5.3
Paper & Wood	4.1
Others (i.e. soil)	6.2
Total	100.0

Table 2. Properties of the bottom and fly ash used in this study

Element	Concentration ¹⁾		Method
	Bottom ash	Fly ash	
Al (%)	5.4	5.0	FAAS
Ca (%)	10.1	12.8	FAAS
Cl (%)	0.89	12.4	IC
Fe (%)	2.5	0.7	FAAS
K (%)	1.2	4.1	FAAS
Na (%)	1.6	5.1	FAAS
Si (%)	14.5	8.2	HF ²⁾ /FAAS
Cd (mg kg ⁻¹)	3.2	102	GF-AAS
Cu (mg kg ⁻¹)	9700	1130	GF-AAS
Cr (mg kg ⁻¹)	208	126	GF-AAS
Mg (mg kg ⁻¹)	8350	10300	GF-AAS
Mn (mg kg ⁻¹)	547	430	GF-AAS
Pb (mg kg ⁻¹)	1240	2810	GF-AAS
Zn (mg kg ⁻¹)	2290	8100	GF-AAS
Ignition loss ³⁾ (%)	7.7	3.9	

¹⁾ HNO₃/HCl total digestion except for Si, ²⁾ HF digestion, and ³⁾ Ignition loss: 600°C for 3 hr

FAAS: flame atomic absorption spectroscopy

GF-AAS: Graphite furnace AAS, IC: ion chromatography

Table 3. Concentrations of elements and pH in the leachate after JLT-13 test
(unit mg L⁻¹, except for pH)

	Bottom ash	Fly ash	STD B-F ash ¹⁾	Untreated B-F ash	W-C pretreated B-F ash	C-P pretreated B-F ash	Detection limit
pH	12.4	12.5	12.3	12.4	10.36	9.64	
Ca	510	2663	905	921	415	221	1
Cd	NA	0.004	0.0006	ND ²⁾	ND	0.0005	0.0005
Cl	520	10480	2147	2002	528	2031	5
Cr	0.004	0.018	0.014	0.006	0.016	0.007	0.001
Cu	2.12	0.15	1.33	1.79	0.62	0.42	0.1
K	110	3453	560	668	116	643	0.1
Na	250	3598	538	736	117	556	0.1
Pb	1.56	58.26	1.17	4.66	0.008	0.003	0.002
Zn	1.84	2.29	1.40	3.31	ND	ND	0.2

¹⁾ STD B-F ash means “standard mixture ash” which based on actual rate of bottom ash and chelating-pretreated fly ash (5:1 ratio) for landfill waste in Sapporo.

²⁾ ND means “less than the detection limit”

Table 4. Experimental conditions for each column

Condition	Column STD	Column W-C	Column C-P
Pre-treatment method	Chelating pretreatment	Water washing /Carbonation	Carbonation/Phosphate Stabilization
Pre-treated Material	Fly ash	B-F ¹⁾ ash (5:1 ratio)	B-F ash (5:1 ratio)
Mass of waste mixture	12 kg on a dry weight basis (Bottom ash 75 wt%, Fly ash 15 wt%, and SIR ²⁾ 10 wt%)		
Bulk density	0.91-0.95 ton m ⁻³		
L/S ratios (periods)	L/S of 3 (15 months)		
pH conditions of artificial rain (distilled water)	No control (until L/S of 1.2) pH 3 water from L/S of 1.2 to 3		
Initial water content	15%		
Temperature	30 ± 3 °C		
Aerobic conditions and Anaerobic conditions*			

¹⁾ B-F ash means a mixture of bottom and fly ash

²⁾ SIR stands for Shredded Incombustible Residues

*After 10 months (L/S 2) anaerobic columns were changed to aerobic columns by making them open to air

Fig. 1 Set-up for column leaching experiments under semi-aerobic and anaerobic conditions

Fig. 2 Leachate pH and redox potential (Eh) versus L/S ratio for each column

Fig. 3 Concentrations of Ca as functions of L/S ratio, and plot of calculated Ca^{2+} activities for various leachates, compared to activities predicted from Ca(OH)_2 , CaCO_3 , and $\text{CaCO}_3 \cdot x\text{H}_2\text{O}$ at total inorganic carbon = 10 mg/L.

Fig. 4 Concentrations of Al as functions of L/S ratio, and plot of calculated Al^{3+} activities for various leachates, compared to activities predicted from amorphous $Al(OH)_3$ and crystalline $Al(OH)_3$ (gibbsite)

Fig. 5 Concentrations of Cu and Pb as functions of L/S ratio.

Fig. 6 Concentrations of Cr as functions of the L/S ratio.