Title	Photochemical hydrogen evolution from aqueous triethanolamine solutions sensitized by binaphthol-modified titanium(IV) oxide under visible-light irradiation
Author(s)	Ikeda, Shigeru; Abe, Chigusa; Torimoto, Tsukasa; Ohtani, Bunsho
Citation	Journal of Photochemistry and Photobiology A Chemistry, 160(1-2), 61-67 https://doi.org/10.1016/S1010-6030(03)00222-3
Issue Date	2003-08-07
Doc URL	http://hdl.handle.net/2115/14647
Type	article (author version)
File Information	JPAP2003-160-1-2.pdf

[Instructions for use](#)

Photochemical Hydrogen Evolution from Aqueous Triethanolamine Solutions Sensitized by Binaphthol-Modified Titanium(IV) Oxide under Visible-Light Irradiation

Shigeru Ikeda,^{a,b} Chigusa Abe,^b Tsukasa Torimoto,^{a,b} and Bunsho Ohtani^{*,a,b}

^a Catalysis Research Center, Hokkaido University, Sapporo 060-0811, Japan

^b Graduate School of Environmental Earth Science, Hokkaido University, Sapporo 060-0810, Japan

* Corresponding author. Tel: +81-11-706-3673; fax: +81-11-706-4925. *E-mail address:* ohtani@cat.hokudai.ac.jp (B. Ohtani).

Abstract

Surface modification of titanium(IV) oxide (TiO_2) powders with 1,1'-binaphthalene-2,2'-diol ($\text{bn}(\text{OH})_2$), having two phenolic hydroxyls and atropisomeric chirality, in refluxed ethanol led to the formation of a deep yellow-colored surface complex, giving visible-light absorption at a wavelength below ca. 550-600 nm. Quantitative analyses of the surface complex revealed that absorption intensity at 450 nm in diffuse reflection measurement was almost proportional to its amount and that its amount depended strongly on the amount of surface hydroxyl groups of TiO_2 but not on the crystal structure of TiO_2 , anatase and rutile. The $\text{bn}(\text{OH})_2$ complexation was also applied to platinized TiO_2 to drive photocatalytic molecular hydrogen (H_2) evolution from

deaerated triethanolamine solutions under visible-light irradiation at a wavelength even longer than 540 nm. The photonic efficiency of the photocatalytic reaction at 450 nm was estimated to be 0.02% for bn(OH)_2 -modified TiO_2 (JRC-TIO-3) loaded with 0.1 wt% of platinum. On the basis of these experimental results, the reaction mechanism, which involves visible-light excitation of the surface complex, injection of electrons from the complex to TiO_2 , and migration of the electrons to platinum deposits, where reduction of H^+ takes place to give H_2 , was elucidated.

Keywords: titanium(IV) oxide; 1,1'-binaphthalene-2,2'-diol; surface complex; visible light; sensitization; photocatalytic reaction

1. Introduction

It is generally of great importance to control the activity of TiO_2 photocatalysts by modification of their bulk and/or surface properties in compliance with different needs [1,2]. One of the intriguing subjects in both academic research and industrial research is development of new TiO_2 -photocatalytic systems with enhanced activities under visible-light irradiation compared with the simply TiO_2 -photocatalyzed processes, since bare TiO_2 can absorb light in the ultraviolet range, which corresponds to only ca. 3% of the energy of sunlight. Several strategies and methods for modifying the optical properties of TiO_2 particles, e.g., doping of a transition metal [3,4], plasma treatments [5] and nitrogen doping [6,7], have been proposed, and photoactivity under visible-light irradiation has been proved in some limited reactions. Much interest has also been shown in surface modification of TiO_2 with transition metal complexes and/or organic dyes for construction of dye-sensitized photocatalytic systems that work under visible-light irradiation [8,9] as well as for improvement of the efficiency of dye-sensitized solar cells [10-12].

On the other hand, in order to clarify the reaction mechanism of the photocatalytic reaction of organic molecules, structural characteristics of these compounds adsorbed on TiO₂ surface have been extensively investigated using various spectroscopic techniques [13-19]. In the course of these studies, it was proved that colorless aromatic compounds having phenolic hydroxyls such as catechol and salicylic acid react with TiO₂ particles to form colored surface complexes [15-19]. Thus, it is expected that a novel visible-light-induced photocatalytic system can be developed by using the photoabsorption of surface complexes on TiO₂ particles. Recently, we have demonstrated that 1,1'-binaphthalene-2,2'-diol (bn(OH)₂), having two phenolic hydroxyls and atropisomeric chirality, reacts with TiO₂ and gives a colored surface complex, which works as catalyst for water reduction in the presence of a sacrificial donor under visible-light irradiation [20].

In this paper, we describe in detail the structural characteristics of the surface TiO₂-bn(OH)₂ complex and some mechanistic aspects of visible light-induced photoactivity.

2. Experimental

2.1. Materials

Several kinds of titanium oxide (TiO₂) powders, those from commercial sources (Degussa P25, Degussa F281, Ishihara ST-01, Ishihara CR-EL, Hombikat UV-100, Showa Denko F-6, and Idemitsu UF), reference catalysts supplied from the Catalysis Society of Japan (TIO-2 and TIO-3), and powders synthesized by the HyCOM method [21,22] followed by calcination at 573 K under O₂, were used. The properties of these TiO₂ powders are summarized in Table 1. Ethanol (Wako), methanol (Wako), triethanolamine (2,2',2''-nitrilotrisethanol, TEOA; Wako), chloroplatinic acid (H₂PtCl₆·6H₂O, Wako), and

1,1'-binaphthalene-2,2'-diol (bn(OH)_2 , racemate; Aldrich), were used without further purification.

2.2. Preparation of bn(OH)_2 -adsorbed TiO_2

In a typical experiment, 0.5 g of TiO_2 powder was suspended in an ethanolic solution of bn(OH)_2 (0.14 mol dm^{-3} , 25 cm^3), and the resulting suspension was refluxed for 8 h under an argon (Ar) atmosphere. The solid was collected by centrifugation (ca. 3500 rpm), washed twice with ca. 10 cm^3 of ethanol, and dried under reduced pressure at ambient temperature. Ultraviolet and visible-light diffuse reflection (DR) spectra were obtained using a Hamamatsu Photonics C7473-6 Photonic Multi-Channel Analyzer, and the data were converted to Kubelka-Munk (KM) function. Based on the contents of carbon and ash components quantified by elemental analysis, the amount of adsorbed bn(OH)_2 was estimated with assumption that the remaining ash was only composed of TiO_2 . Since the carbon components in most of the samples were less than 2 wt% and the elemental analysis of organic compounds includes less than 0.3% of error, estimated amounts may include a large quantity of error. However, we could confirm reproducibility within 10% on some selected samples. Platinized TiO_2 powder, prepared by photoplatinization in deaerated aqueous methanol solution containing $\text{H}_2\text{PtCl}_6 \cdot 6\text{H}_2\text{O}$ [24], was also modified with bn(OH)_2 by the same procedure as that used for unplatinized TiO_2 powder.

2.3. Photoirradiation and product analysis

The bn(OH)_2 -modified or bare TiO_2 powder (50 mg) and an aqueous TEOA (10 vol%) or methanol (50 vol%) solution (5 cm^3) were placed in a glass tube (transparent at $> 300 \text{ nm}$, 18 mm in diameter and 180 mm in length), and the suspensions were photoirradiated under Ar at 298 K with vigorous magnetic stirring (1000 rpm). Photoirradiation was performed using a high-pressure mercury arc (Eiko-sha, 400 W) or a

xenon arc (Ushio UXR-300DU, 300 W) with a Y-44, Y-50, O-55, or O-59 optical filter (Asahi Techno Glass) to cut out light of wavelength shorter than 430, 490, 540 or 580 nm, respectively. Liberated hydrogen (H_2) was analyzed using a gas chromatograph (GC, Shimadzu GC-8A) equipped with an MS-5A column (GL Sciences) and a TCD detector. Photonic efficiency, a molar ratio of product (twice the amount of H_2) to incident photons, was estimated at 450 nm using a JASCO CT-101T monochromator equipped with a xenon arc. The incident photon flux was estimated using a Molelectron POWER MAX5200 laser power meter.

3. Results and Discussion

3.1. Structure of TiO_2 modified with $bn(OH)_2$

Figure 1 shows ultraviolet and visible DR spectra of Degussa P25, TIO-3, and TiO_2 powders treated with an ethanolic $bn(OH)_2$ solution. Untreated P25 and TIO-3 gave absorption in the ultraviolet region below ca. 400 nm and 410 nm, respectively, corresponding to their band-gap photoabsorption. The gaps were reported to be ca. 3.0 eV (410 nm) for rutile (TIO-3) and 3.2 eV (390 nm) for anatase [25], and P25, a mixture of anatase and rutile, might give an intermediate spectrum. Treatment of the colorless compound $bn(OH)_2$ induced striking changes in the spectral features of these TiO_2 powders: the color of the powders became deep yellow after $bn(OH)_2$ treatment, giving visible-light absorption below ca. 550-600 nm. Due to the overlap of the fundamental band gap photoabsorption of TiO_2 , the exact position of the peak, if present, of newly appearing visible-light absorption could not be determined. However, the shapes in the visible range and the absorption edge positions of the two $bn(OH)_2$ -treated TiO_2 powders were quite similar; there seemed to be no significant dependence on the crystal form, anatase and rutile of TiO_2 .

To identify the surface species, the amounts of bn(OH)_2 attached to several TiO_2 powders were quantified by elemental analysis of carbon and ash components. Figure 2 shows plots of absorption intensity at 450 nm of bn(OH)_2 -treated TiO_2 powder (I_{450}) and its BET surface area (S) as a function of the amount of adsorbed bn(OH)_2 per unit weight of TiO_2 (M_{bn}). It is clear from this figure that there is an almost linear relation between M_{bn} and I_{450} of several TiO_2 powders. This suggests that the bn(OH)_2 species adsorbed on TiO_2 give visible light absorption, independent of the kind of bare TiO_2 powder. Since I_{450} was measured in KM function which contains a term of light scattering as well as that of absorption and thus it depends on the light scattering properties of bare TiO_2 powders, deviation of a plot (g) higher from a linear line might be caused by the scattering properties of these TiO_2 powders (consisting of amorphous) which seem a different from the ordinary crystalline powders. It is also noted that a plot (e) seems to slightly deviate lower from a linear line. Although there is no clear basis at present, this might be due to the presence of another type of a surface complex on the sample (e), having lower absorption coefficient than that on other ordinal TiO_2 powders (see below). A linear relationship was also observed between M_{bn} and S for all TiO_2 powders except for the amorphous TiO_2 (Idemitsu UF), which showed a relatively high density of bn(OH)_2 adsorption and as is discussed in the following section.

As already reported by several workers [15-19], white TiO_2 particles and colloids turn yellow upon immersion in a solution containing phenols such as salicylic acid and catechol. The development of the yellow color is a clear indication of the formation of surface TiO_2 -salicylate and TiO_2 -catecholate complexes, and the absorption bands in the visible range were assigned to intramolecular ligand-to-metal charge transfer transition [18,19]. Thus, the observed visible-light absorption in the present experiment is attributable to the formation of a surface TiO_2 - bn(OH)_2 complex. According to previous reports on TiO_2 -salicylate and TiO_2 -catecholate surface complexes [16-19], there appears to be two different structures of the complex. One structure is formed by chelation of a surface titanium atom with two hydroxyl groups in a bn(OH)_2 molecule (“chelation”, a 1:2

adduct) and the other is formed by binding of each phenolic hydroxyl group in $\text{bn}(\text{OH})_2$ to the surface titanium atom (“esterification”, a 2:2 adduct), both of which are induced by intermolecular dehydration of surface and phenolic hydroxyls, as shown in Scheme 1. Although there is no experimental method for discriminating these two possible structures of the surface complex in the samples, the fact that a yellow-colored powder giving a similar absorption spectrum in the visible light range below ca. 550 nm was also obtained by the reaction of TiO_2 with 2-naphthol, which has only one phenolic hydroxyl group (data not shown), suggested that the latter structure (“esterification”) could interpret the present results of $\text{bn}(\text{OH})_2$, but did not exclude the former structure (“chelation”). Further studies for clarification of the structure are now underway.

Previous studies on the quantification of surface hydroxyls (Ti-OH) on TiO_2 by sodium hydroxide titration [26] have shown that the density of Ti-OH is almost constant, ca. 2.5 hydroxyls nm^{-2} , among several polycrystalline TiO_2 powders except for amorphous samples, which have a relatively high density of Ti-OH, ca. 16 hydroxyls nm^{-2} [27]. Assuming surface complexation through dehydration between Ti-OH with the hydroxyl groups in $\text{bn}(\text{OH})_2$ as discussed above and uniform and similar chemical properties of Ti-OH in TiO_2 samples, a linear relationship between M_{bn} and S, as shown in Fig. 2, seems quite reasonable for the samples of TiO_2 having almost the same Ti-OH surface density. Deviation of the Idemitsu UF ((g) in Fig. 2) is thought to be due to its higher density of surface Ti-OH. From the reciprocal slope of Fig. 2 (lower), the surface density of $\text{bn}(\text{OH})_2$ on the ordinary polycrystalline samples was estimated to be 0.8 $\mu\text{mol m}^{-2}$ or 0.48 molecules nm^{-2} . The density was ca. 1/5 of the above estimated Ti-OH density, and approximately half (or little less) of Ti-OH was used for surface complexation when the 2:2 adduct was presumed. This estimation of surface coverage is consistent with the estimated coverage, half or a little less, using the cross-sectional area of a $\text{bn}(\text{OH})_2$ molecule (ca. 1 nm^2) in the surface structure shown in Scheme 1. It is reasonable to assume that the loosely packed arrangement of $\text{bn}(\text{OH})_2$ is caused by its large molecular size and a mismatching of the Ti-OH spatial arrangement to anchor $\text{bn}(\text{OH})_2$. On the other

hand, the higher density of bn(OH)_2 on Idemitsu UF was attributed to the sufficiently high density of Ti-OH to allow close packing of bn(OH)_2 on the surface. The estimated density of bn(OH)_2 on UF, ca. $2.8 \text{ molecules nm}^{-2}$, was three-times larger than that estimated from the cross-sectional area. This might be caused, at least partly, by underestimation of its BET surface area; surface adsorption of nitrogen was measured after evacuation at 383 K, which was $> 100 \text{ K}$ lower than that for the other TiO_2 samples, to minimize the thermal effect on its structure [28] and at the same time to allow water to remain on the surface.

Thus, a part of the surface of bn(OH)_2 -modified TiO_2 particles remains uncovered with bn(OH)_2 , and it is therefore expected that photoinduced reactions can be driven by bn(OH)_2 -modified TiO_2 with photoabsorption by surface complexes and with redox reactions by photoexcited electrons (or holes) on the unmodified bare surface.

3.2. Photoreactivity of platinized TiO_2 modified with bn(OH)_2

Photoinduced reduction of water to produce H_2 from an aqueous solution containing a sacrificial electron donor, methanol or TEOA, was conducted as a test reaction of photoactivity of the bn(OH)_2 -modified TiO_2 . Preliminary experiments revealed the requirement of platinization to make active sites on the surface for H_2 production. Therefore, before the photoactivity test, a small amount of platinum (Pt) particles was deposited on TiO_2 (0.05-2 wt%, corresponding to ca. 0.2-5% of surface coverage [29]) followed by modification with bn(OH)_2 . Consistent with this small coverage of Pt particles on TiO_2 , M_{bn} on platinized (2 wt%) TIO-3 ($40 \mu\text{mol g}^{-1}$) was comparable or even larger than that on bare TIO-3 ($32 \mu\text{mol g}^{-1}$). One possible explanation for this small increment is attachment of bn(OH)_2 to the surface of Pt particles. We tried to obtain the absorption spectrum of bn(OH)_2 complex on platinized TiO_2 but failed due to interference by gray-colored Pt particles. Another possible explanation is an increase in Ti-OH during the Pt photodeposition process; the formation of Ti-OH induced by band-gap excitation of TiO_2 has been reported in relation with a phenomenon of photoinduced super

hydrophilicity [30].

Figure 3 shows H₂ liberation from aqueous methanol and TEOA solutions under ultraviolet light irradiation (> 300 nm) over bn(OH)₂-modified and unmodified TiO₂ (TIO-3). In all the experimental runs, a linear increase in the molar amount of H₂ was observed. Due to the lower solubility of TEOA in water, the concentrations of these two electron donors were different (50 and 10 vol% for methanol and TEOA, respectively), and pH of an aqueous TEOA solution (originally ca. 11) was not adjusted to be neutral. The electron-donating ability, therefore, can not be discussed on the basis of these results. It is notable that bn(OH)₂-modified TiO₂ showed almost the same or an even slightly higher rate than that of unmodified TiO₂ in the aqueous methanol suspension, suggesting negligible or at most only partial coverage of the surface of Pt particles by bn(OH)₂. On the other hand, when TEOA was used as a sacrificial electron donor, the H₂-liberation rate was halved by the bn(OH)₂ modification. It was presumed that access of TEOA, the size of which is much larger than that of methanol, to the bare (not covered with bn(OH)₂) surface was restricted. In a TiO₂-photocatalyzed reaction using photoexcited electrons and positive holes in TiO₂, adsorption of a reaction substrate such as TEOA on bare TiO₂ is required.

Figure 4 shows the time courses of H₂ liberation from unmodified and bn(OH)₂-modified TiO₂ (TIO-3) from an aqueous TEOA solution under visible-light irradiation (> 430 nm). H₂ liberation from the bn(OH)₂-modified TiO₂ suspension was observed, while, as predicted from the negligible photoabsorption of bare TiO₂ in the visible region (Fig. 1), no appreciable liberation of H₂ from unmodified TiO₂ was detected [20]. The total amount of evolved H₂ after 80 h of irradiation reached more than 40 μmol. Since the amount of bn(OH)₂ on 50 mg of TIO-3 was estimated to be 2 μmol (corresponding to 24 μmol of H atoms based on the assumption of the structure shown in Scheme 1), the total H₂ yield was more than 20-times greater than the molar amount of bn(OH)₂, indicating that the photoinduced reaction proceeded catalytically. It is also notable that the rate of H₂ production decreased gradually. This may be due to

decomposition or leaching of the surface complex during the reaction. At present, however, there is no experimental evidence to elucidate the decrease of adsorbed bn(OH)_2 , mainly because of the interference by Pt deposits, which causes greatly reduced diffuse reflection and difficulty in evaluating DR spectra with high accuracy and reproducibility. In the second run of irradiation after Ar bubbling to purge liberated H_2 and other volatile compounds such as ammonia, the initial rate ($0.65 \mu\text{mol h}^{-1}$) was less than half of that in the first run ($1.7 \mu\text{mol h}^{-1}$) but was more than 30% higher than the rate in the final stage of the first run ($0.48 \mu\text{mol h}^{-1}$). These facts indicate that accumulation of a volatile by-product(s) accounts at least partly for the deactivation during the course of irradiation. Under visible-light irradiation, negligible H_2 liberation was observed when methanol was used as a sacrificial electron donor instead of TEOA even at high pH (similar to the TEOA solution), though methanol worked efficiently when TiO_2 was photoexcited under ultraviolet-light irradiation (see Fig. 3).

Figure 5 shows dependence of the rate of H_2 liberation on the wavelength of irradiated light for bn(OH)_2 -modified TiO_2 (TIO-3) loaded with 0.5 wt% of Pt. The H_2 liberation required irradiation at a wavelength of $< 580 \text{ nm}$; no H_2 was produced under photoirradiation at a wavelength longer than 580 nm . This wavelength dependence corresponded to photoabsorption of TiO_2 - bn(OH)_2 complexes shown in Fig. 1, i.e., the observed visible light-induced H_2 liberation was derived from photoexcitation of the surface bn(OH)_2 complex on TiO_2 .

Figure 6 shows dependence of the rate of H_2 liberation on the amount of Pt deposits for bn(OH)_2 -modified TiO_2 (TIO-3). No H_2 liberation was observed in the absence of loaded Pt. The highest activity of ca. $7 \mu\text{mol h}^{-1}$ was observed when 0.1 wt% of Pt was deposited on TiO_2 (TIO-3), and the photonic efficiency of this powder was estimated to be ca. 0.02% [20]. Further loading reduced the activity, presumably due to reduction of photoabsorption by the bn(OH)_2 surface complex and/or enhanced deactivation of the photoexcited complex. A previous study on characterization of Pt deposits on P25 TiO_2 powder [29] revealed that the optimum Pt deposition for P25 (0.1

wt%), the surface area of which is similar to that of TIO-3, corresponds to the minimum amount of Pt loading required to distribute at least one Pt deposit (ca. 2 nm) on each TiO₂ particle. The Pt deposits act as active sites for H₂ liberation through reduction of H⁺ with photoexcited electrons of the surface bn(OH)₂ complex that have migrated presumably *via* TiO₂.

The TiO₂ powders such as Ishihara ST-01 and HyCOM, both of which consist of anatase crystallites, also produced H₂ under the visible-light irradiation at > 430 nm. The rates of H₂ liberation were 0.5 μmol h⁻¹ for ST-01 with 2 wt% of Pt and 3.7 μmol h⁻¹ for HyCOM with 1 wt% of Pt, respectively [20]. Although the activity of these samples is thought to depend on the amount of Pt loading, similar to that in Fig. 6, and although the amount of Pt deposits for these samples has not been optimized, a comparison of the trends in H₂ liberation rates for the three samples with those of M_{bn} (Fig. 2) indicates that there are no simple proportional relations between them. The relatively lower activity of ST-01, consisting of less crystallized anatase particles, i.e., having a larger number of defects, in spite of larger M_{bn}, suggested the importance of crystallinity of TiO₂, as has been reported for the photocatalytic activity of platinized TiO₂ for dehydrogenation of alcohol [22]. In the presumed mechanism, as discussed in the following section, photoexcited electrons in the surface bn(OH)₂ complex are injected into TiO₂ and migrate in TiO₂ to reach the Pt deposit, and the crystallinity governs the efficiency of the electron migration. Anyway, highly active photocatalytic systems are to be constructed by selection of suitable TiO₂.

As suggested in the preliminary paper [20], visible light-induced H₂ evolution is thought to proceed through a sensitizing mechanism initiated by excitation of the surface complex by visible light followed by electron injection into the conduction band of TiO₂. Such a surface charge transfer has been studied and has been confirmed for a TiO₂-catecholate surface complex system [17]. The injected electrons in the TiO₂ particles migrate to the platinum deposits, where reduction of H⁺ takes place to give H₂. TEOA must work as a sacrificial electron donor to reduce the oxidized form of the surface

complex. A schematic model of the overall reaction is shown in Scheme 2. Judging from the wavelength of the bn(OH)_2 complex absorption edge, ca. 580 nm (ca. 2.1 eV), and the fact that the complex in an excited state can inject electrons into the conduction band of TiO_2 , the ground-state electronic level of the complex should be ca. 1 V negative from the upper edge of the valence band in TiO_2 . Methanol could inject electrons into the ground state, but negligible H_2 was liberated as described above. The difference in the adsorption abilities of a bn(OH)_2 -modified surface, but not a bare TiO_2 surface, and/or in the reactivity of the oxidized form of bn(OH)_2 complex toward TEOA and methanol might cause the distinction of these sacrificial donors.

4. Conclusions

The present study has shown that derivatization of a semiconductor surface with a simple aromatic compound as a complexation reagent can induce a visible-light-induced photocatalytic ability. Although a similar photosensitized water reduction system, which includes a surface complex between TiO_2 and 8-hydroxylquinoline, has been demonstrated [31], the present system, proved to drive a photocatalytic reaction under visible-light irradiation, can be further extended. In the present study, we used only a racemate of bn(OH)_2 , but when optically active (R)- and (S)- bn(OH)_2 's are used as complexing agents, we can expect stereoselective photocatalytic reactions (of, for example, phenylethylamine having a chiral carbon center, which has been confirmed to work as an electron donor in the present system) through chiral modification. Further studies along this line are now under way.

Acknowledgements

The authors are grateful to the Catalysis Society of Japan for supplying TiO₂ samples. HyCOM TiO₂ was a generous gift from Dr. Hiroshi Kominami (Kinki University). This research was partly supported by a Grant-in-Aid for Scientific Research on Priority Areas (No. 14050007) from The Ministry of Education, Culture, Sports, Science and Technology. Financial support by The Sumitomo Foundation is acknowledged. Mr. Tetsuzo Habu and Mr. Kazuhiro Matsudaira (The Technical Division of the Catalysis Research Center, Hokkaido University) are acknowledged for their assistance in the construction of the photoirradiation apparatuses. The authors would also like to thank the staff of the Center for Instrumental Analysis, Hokkaido University for their assistance in elemental analyses.

References

- [1] M. Schiavello (Ed.), *Heterogeneous Photocatalysis*, John Wiley & Sons, Chichester, 1997.
- [2] A. Fujishima, K. Hashimoto, and T. Watanabe, *TiO₂ Photocatalysis, Fundamentals and Applications*, BKC, Inc., Tokyo, 1999.
- [3] W. Choi, A. Termin, M. R. Hoffmann, *J. Phys. Chem.* 98 (1994) 13669.
- [4] M. Anpo, Y. Ichihashi, M. Takeuchi, H. Yamashita, *Res. Chem. Intermed.* 24 (1998) 143.
- [5] K. Takeuchi, I. Nakamura, O. Matsumoto, S. Sugihara, M. Ando, T. Ihara, *Chem. Lett.* (2000) 1354.
- [6] S. Sato, *Chem. Phys. Lett.* 123 (1986) 126.
- [7] R. Asahi, T. Morikawa, T. Ohwaki, K. Aoki, Y. Tada, *Science*, 293 (2001) 269.
- [8] R. Abe, K. Hara, K. Sayama, K. Domen, H. Arakawa, *J. Photochem. Photobiol. A: Chem.* 137 (2000) 63.
- [9] D. Chatterjee, A. Mahata, *J. Photochem. Photobiol. A: Chem.* 153 (2002) 199.

- [10] A. Hagfeldt, M. Grätzel, *Acc. Chem. Res.*, 33 (2000) 269.
- [11] K. Hara, K. Sayama, Y. Ohga, A. Shinpo, S. Suga, H. Arakawa, *Chem. Commun.* (2001) 569.
- [12] J. J. He, G. Benko, F. Korodi, T. Polivka, R. Lomoth, B. Akermark, L. C. Sun, A. Hagfeldt, V. Sundstrom, *J. Am. Chem. Soc.* 124 (2002) 4922.
- [13] P. A. Connor, K. D. Dobson, A. J. McQuillan, *Langmuir* 11 (1995) 4193.
- [14] T. Awatani, K. D. Dobson, A. J. McQuillan, B. Ohtani, K. Uosaki, *Chem. Lett.* (1998) 849.
- [15] B. A. Borgias, S. R. Cooper, Y. B. Koh, K. N. Raymond, *Inorg. Chem.* 23 (1984) 1009.
- [16] R. Rodrigues, M. A. Blesa, A. E. Regazzoni, *J. Colloid Interface Sci.* 177 (1996) 122.
- [17] Y. Liu, J. I. Dadap, D. Zimdars, K. B. Eisenthal, *J. Phys. Chem. B.* 103 (1999) 2480.
- [18] J. Moser, S. Punchihewa, P. P. Infelta, M. Grätzel, *Langmuir* 7 (1991) 3012.
- [19] A. E. Regazzoni, P. Mandelbaum, M. Matsuyoshi, S. Schiller, S. A. Bilmes, M. A. Blesa, *Langmuir* 14 (1998) 868.
- [20] S. Ikeda, C. Abe, T. Torimoto, B. Ohtani, *Electrochemistry* 70 (2002) 442.
- [21] H. Kominami, J.-i. Kato, Y. Takada, B. Ohtani, J.-i. Kawaguchi, M. Kozawa, S.-i. Nishimoto, T. Inui, K. Izawa, *J. Chem. Soc. Faraday Trans.* 91 (1995) 1103.
- [22] H. Kominami, T. Matsuura, K. Inui, B. Ohtani, S.-i. Nishimoto, Y. Kera, *Chem. Lett.* (1995) 693.
- [23] T. Torimoto, N. Nakamura, S. Ikeda, B. Ohtani, *Phys. Chem. Chem. Phys.* 4 (2002) 5910.
- [24] S. Ikeda, N. Sugiyama, B. Pal, G. Marci, L. Palmisano, H. Noguchi, K. Uosaki, B. Ohtani, *Phys. Chem. Chem. Phys.* 3 (2001) 267.
- [25] L. Kavan, M. Grätzel, S. E. Gilbert, C. Klemenz, H. J. Scheel, *J. Am. Chem. Soc.* 118 (1996) 6716.
- [26] B. Ohtani, S.-w. Zhang, S.-i. Nishimoto, T. Kagiya, *J. Chem. Soc. Faraday Trans.* 88

- (1992) 1049.
- [27] S. Sato, T. Kadowaki, *Electrochemistry* 57 (1989) 1151.
- [28] B. Ohtani, Y. Ogawa, S.-i. Nishimoto, *J. Phys. Chem. B* 101 (1997) 3746.
- [29] B. Ohtani, K. Iwai, S.-i. Nishimoto, S. Sato, *J. Phys. Chem. B* 101 (1997) 3349.
- [30] R. Wang, N. Sakai, A. Fujishima, T. Watanabe, K. Hashimoto, *J. Phys. Chem. B* 103 (1999) 2188.
- [31] V. H. Houlding, M. Grätzel, *J. Am. Chem. Soc.* 105 (1983) 5695.

Figure and Scheme Captions

Figure 1. Ultraviolet and visible light DR spectra of (I) P25, (II) TIO-3, (I') bn(OH)_2 -modified P25, and (II') bn(OH)_2 -modified TIO-3.

Figure 2. Relations between M_{bn} and I_{450} (upper) or S (lower) for (a) Degussa P25, (b) Degussa F281, (c) Ishihara ST-01, (d) Ishihara CR-EL, (e) Hombikat UV-100, (f) Showa Denko F-6, (g) Idemitsu UF, (h) TIO-2, (i) TIO-3, and (j) HyCOM. Open circles, filled circles, open triangles, and filled triangles denote rutile, anatase, their mixtures, and amorphous, respectively.

Figure 3. Time courses of H_2 liberation by unmodified (open symbols) and bn(OH)_2 -modified (closed symbols) TIO-3 (2 wt% Pt) suspended in a deaerated aqueous methanol (squares) or TEOA (circles) solution under ultraviolet-light ($> 300 \text{ nm}$) irradiation.

Figure 4. Time courses of H_2 liberation by unmodified (open circles) and bn(OH)_2 -modified (closed circles) TIO-3 (1 wt% Pt) suspended in a deaerated aqueous TEOA solution under visible-light ($> 430 \text{ nm}$) irradiation.

Figure 5. Dependence of rate of H_2 liberation by bn(OH)_2 -modified TIO-3 loaded with 0.5 wt% of Pt on wavelength of photoirradiated light: (A) $> 430 \text{ nm}$, (B) $> 490 \text{ nm}$, (C) $> 540 \text{ nm}$, (D) $> 580 \text{ nm}$.

Figure 6. Dependence of rate of H_2 liberation by bn(OH)_2 -modified TIO-3 on amount of Pt deposits. Rate of H_2 liberation was estimated from the slope of the time course curve in the initial 2 h of photoirradiation.

Scheme 1. Schematic illustration of the reactions between Ti-OH and phenolic hydroxyl group in bn(OH)_2 through (i) chelation (a 1:2 adduct) and (ii) esterification (a 2:2 adduct), both of which are accompanied by the liberation of water.

Scheme 2. Proposed model for overall reaction of visible light-induced photocatalytic H_2 evolution by bn(OH)_2 -modified TiO_2 loaded with platinum.

Figure 1. S. Ikeda, C. Abe, T. Torimoto, and B. Ohtani

Figure 2. S. Ikeda, C. Abe, T. Torimoto, and B. Ohtani

Figure 3. S. Ikeda, C. Abe, T. Torimoto, and B. Ohtani

Figure 4. S. Ikeda, C. Abe, T. Torimoto, and B. Ohtani

Figure 5. S. Ikeda, C. Abe, T. Torimoto, and B. Ohtani

Figure 6. S. Ikeda, C. Abe, T. Torimoto, and B. Ohtani