Title	Fulde-Ferrell-Larkin-Ovchinnikov State in a Perpendicular Field of Quasi-Two-Dimensional CeCoIn ₅
Author(s)	Kumagai, K.; Saitoh, M.; Oyaizu, T.; Furukawa, Y.; Takashima, S.; Nohara, M.; Takagi, H.; Matsuda, Y.
Citation	Physical Review Letters, 97(22), 227002 https://doi.org/10.1103/PhysRevLett.97.227002
Issue Date	2006
Doc URL	http://hdl.handle.net/2115/17116
Rights	Copyright © 2006 American Physical Society
Type	article
File Information	PRL97-22.pdf

[Instructions for use](#)

Fulde-Ferrell-Larkin-Ovchinnikov State in a Perpendicular Field of Quasi-Two-Dimensional CeCoIn₅

K. Kumagai,¹ M. Saitoh,¹ T. Oyaizu,¹ Y. Furukawa,¹ S. Takashima,² M. Nohara,² H. Takagi,² and Y. Matsuda^{3,4}

¹*Division of Physics, Graduate School of Science, Hokkaido University, Sapporo 060-0810, Japan*

²*Department of Advanced Materials Science, University of Tokyo, Kashiwanoha, Kashiwa, Chiba 277-8581, Japan*

³*Department of Physics, Kyoto University, Kyoto 606-8502, Japan*

⁴*Institute for Solid State Physics, University of Tokyo, Kashiwanoha, Kashiwa, Chiba 277-8581, Japan*

(Received 15 May 2006; published 27 November 2006)

A Fulde-Ferrell-Larkin-Ovchinnikov (FFLO) state was previously reported in the quasi-2D heavy fermion CeCoIn₅ when a magnetic field was applied parallel to the *ab* plane. Here, we conduct ¹¹⁵In NMR studies of this material in a *perpendicular* field, and provide strong evidence for FFLO in this case as well. Although the topology of the phase transition lines in the *H-T* phase diagram is identical for both configurations, there are several remarkable differences between them. Compared to *H* ∥ *ab*, the FFLO phase for *H* ⊥ *ab* is confined in a much narrower region at the low-*T*-high-*H* corner in the *H-T* plane, and the critical field separating the FFLO and non-FFLO superconducting states almost ceases to have a temperature dependence. Moreover, directing *H* ⊥ *ab* results in a notable change in the quasiparticle excitation spectrum within the planar node associated with the FFLO transition.

DOI: 10.1103/PhysRevLett.97.227002

PACS numbers: 74.70.Tx, 71.27.+a, 74.25.Dw, 76.60.Cq

In spin singlet superconductors, superconductivity is suppressed by a magnetic field as a consequence of its coupling to the electronic orbital angular momentum (vortices) or to the conduction electron spins (Pauli paramagnetism). When Pauli pair breaking dominates over the orbital effect, an exotic superconducting phase was predicted to appear by Fulde and Ferrell and by Larkin and Ovchinnikov (FFLO) at high fields and low temperatures [1,2]. In the FFLO state, pair breaking due to the Pauli paramagnetic effect is reduced by the formation of a new pairing state ($\mathbf{k}_\uparrow, -\mathbf{k} + \mathbf{q}_\downarrow$), with $|\mathbf{q}| \sim 2\mu_B H / \hbar v_F$ (v_F is the Fermi velocity) between the Zeeman split parts of the Fermi surface, instead of ($\mathbf{k}_\uparrow, -\mathbf{k}_\downarrow$) pairing in ordinary BCS superconductors. A fascinating aspect of the FFLO state is that an inhomogeneous superconducting phase with a spatially oscillating order parameter $\Delta(\mathbf{r}) = \Delta_0 \cos(\mathbf{q} \cdot \mathbf{r})$ and spin polarization shows up in the vicinity of the upper critical field H_{c2} [1–13]. It has been shown that in the presence of a substantial orbital effect, 2D planar nodes appear periodically perpendicular to the Abrikosov vortex lattice [4,8,11,13].

Despite the straightforward nature of the theoretical prediction, actual observations of the FFLO state have turned out to be extremely difficult. In fact, no solid evidence, which is universally accepted as proof of the FFLO state, has turned up in any superconductors thus far. Recently, a new candidate for the realization of the FFLO phase has been found in heavy fermion CeCoIn₅ [14] with a quasi-2D electronic structure [15], when the magnetic field is applied *parallel* to the *ab* plane (*H* ∥ *ab*). Heat capacity measurements revealed a second order phase transition line within the superconducting state, indicating a new superconducting phase at the high-*H*-low-*T* corner in the *H-T* phase diagram [16,17]. At the transition line, ultrasound velocity measurements revealed the collapse

of the flux line lattice tilt modulus [18]. In addition, thermal conductivity displays a kink [19]. Moreover, recent NMR measurements indicate clear evidence of the spatially inhomogeneous quasiparticle structure inside the new superconducting phase [20]. All of these results are precisely expected in a FFLO state. CeCoIn₅ appears to meet, in an ideal way, some strict requirements placed on the existence of the FFLO state. First, the superconducting-normal transition at H_{c2} is in the first order, indicating that superconductivity is limited by the Pauli paramagnetic effect [21–23]. Second, it has been pointed out that the FFLO state is readily destroyed by impurities [10,11], but this material is in the extremely clean regime [24]. Third, the superconducting symmetry is most likely to be the *d* wave [21,25,26], which extends the stability of the FFLO state [9,10,12].

While there is growing experimental evidence that the FFLO state can indeed be realized in CeCoIn₅, several unexpected features have been found. One of the most intriguing features is a remarkable *T* and *H* dependence of the phase boundary between the FFLO and non-FFLO superconducting state (hereafter referred to as the BCS state); $H_{\text{FFLO}}^{\parallel}$ exhibits an unusually large shift to higher fields with higher temperatures [16,17]. Although a number of theories were considered to explore the FFLO state before the experimental results of CeCoIn₅ were reported, none of them predicted such a large *T* dependence of $H_{\text{FFLO}}^{\parallel}$. Moreover, it seems to be widely believed that the 2D nature of CeCoIn₅ is essential for the formation of the FFLO state. This is because both the strong reduction of the orbital pair breaking in a parallel field and the nesting properties of the quasi-2D Fermi surface are expected to stabilize the FFLO state, as discussed in layered organic superconductors [5,27]. This is supported by the torque measurements that indicate the disappearance of the FFLO

state when the magnetic field is slightly tilted out of the ab plane [16]. On the other hand, specific heat measurements show an anomaly for $H \perp ab$ just below $H_{c2}^{\perp}$ at low temperatures, similar to $H \parallel ab$ [17]. Thus, whether the FFLO state can exist when $H \perp ab$ is controversial, and its clarification is very important for understanding the FFLO state in CeCoIn_5 .

We here direct our attention to the superconducting state of CeCoIn_5 in a *perpendicular* field ($H \perp ab$). We present evidence for the FFLO state in this case as well. We show that directing the magnetic field towards the c axis results not only in a dramatic change in the FFLO region in the H - T phase diagram, but also in a notable change in the quasiparticle excitation spectrum within the FFLO nodal sheets.

High quality single crystals of CeCoIn_5 with $T_c = 2.3$ K were grown by a flux method. ^{115}In ($I = 9/2$) NMR measurements were performed using a phase-coherent pulsed NMR spectrometer. Experiments were always carried out in a magnetic field $\mathbf{H}$ perpendicular to the ab plane under the field-cooled condition. We reduced the *radio frequency* excitation power to more than 1/100 times smaller than that used in ordinary experiments in order to avoid Joule heating. Spectra were obtained from a convolution of Fourier transform signals of the spin echo which were measured at 20 kHz intervals. The tetragonal crystal structure of CeCoIn_5 consists of alternating layers of CeIn_3 and CoIn_2 , and this has two inequivalent ^{115}In sites per unit cell. We report NMR results at the In(1) site with axial symmetry in the CeIn_3 layer. The sample orientation was verified within 3° by observing the resonance lines of the quadrupole split satellites of the In(1). The Knight shift ^{115}K was obtained from the ^{115}In line using a gyromagnetic ratio of $^{115}\gamma = 9.3295$ MHz/T.

Figure 1(a) depicts the temperature evolution of the NMR spectrum displayed as a function of the Knight shift in sample 2 at $H = 4.80$ T just below $H_{c2}^{\perp} = 4.95$ T at $T = 0$ for $H \perp ab$. Upon entering the superconducting state [$T_c(H) = 0.48$ K], the NMR intensity is strongly reduced. One immediately notices that the NMR spectrum changes dramatically below $T_c(H)$. While the NMR spectrum is nearly symmetrical above $T_c(H)$, the spectrum at $T = 0.46$ K exhibits a shoulder structure at lower frequencies. This shoulder structure is followed by a double peak structure, which clearly shows up below $T = 0.43$ K. The double peak structure persists down to the lowest temperature (70 mK), but the intensity of the higher resonance line decreases with decreasing temperature. Figures 1(b)–1(d) display the spectra in sample 1, which is taken in a different batch from sample 2, at 4.6, 4.8, and 4.85 T, respectively. At 4.8 and 4.85 T, the change in the spectrum just below $T_c(H)$ is pronounced; a distinct double peak structure is observed. However, the double peak structure was not observed well below $T_c(H)$, though the spectrum exhibits a broadening at higher frequencies (at higher Knight shift). On the other hand, for $H = 4.6$ T, shown in Fig. 1(b), the spectrum

FIG. 1 (color online). ^{115}In -NMR spectra of CeCoIn_5 (samples 1 and 2) as a function of the Knight shift when going from a normal state (black lines) to a superconducting state (red or gray lines) at (a) $H = 4.8$ T (sample 2), (b) 4.60 T (sample 1), (c) 4.80 T (sample 1), and (d) 4.85 T (sample 1). The intensity is normalized by the largest peak intensity.

shifts smoothly toward the low frequency side below $T_c(H)$ without showing the double peak anomaly.

The anomalous behavior of the spectrum can also be seen clearly by plotting the Knight shift, which is defined as the peak position of the spectrum. Figure 2 and the inset depict the temperature dependence of the Knight shift when going across the normal-to-superconducting transition. In the normal state, the Knight shift is nearly T independent and its value is close to the one reported previously [28]. As shown in the inset of Fig. 2, the Knight shift at $H \leq 4.7$ T decreases monotonically with decreasing temperature in the superconducting state below $T_c(H)$. This behavior, together with the NMR spectrum shown in Fig. 1(b), are typical in the BCS state. As shown in the main panel of Fig. 2, above $H = 4.7$ T, the Knight shift changes dramatically below $T_c(H)$. The Knight shift exhibits a jump at $T_c(H)$ and splits into two values. While the Knight shift of the lower resonance line is reduced from the value in the normal state, the Knight shift of the higher resonance line is strongly enhanced. Interestingly, for sample 1, the Knight shift for the lower resonance line exhibits an overshoot behavior just below $T_c(H)$. The jump in the

FIG. 2 (color online). The T dependence of the Knight shift, ^{115}K , at $H = 4.8$ (●), 4.85 (◇), and 4.90 T (▲) for sample 1, and also at $H = 4.8$ T (○) for sample 2. $T_c(H) = 0.48, 0.4$, and 0.22 K at $H = 4.8, 4.85$, and 4.9 T, respectively. The inset shows the detail of the low field region below $H = 4.7$ T for sample 1. The solid and dotted lines are guide for eyes.

Knight shift, along with the overshoot behavior, definitely indicates the first order nature of the superconducting-to-normal transition.

We measured the NMR spectrum for several crystals in different batches and always observed spectra similar to the ones shown in Fig. 1(a) or 1(c) below $T_c(H)$ in a narrow field range between $H = 4.7$ to 4.9 T. We therefore conclude that the double peak structure in the narrow region at the high- H -low- T corner in the H - T plane is a common feature in the NMR spectrum, though the relative intensity of the peak just below $T_c(H)$ is sample dependent.

We stress that the double peak structure and its temperature evolution in the perpendicular field bear a striking resemblance to those in the parallel field (see Fig. 2 in Ref. [20]). As seen in Fig. 2, the Knight shift of the lower resonance line is close to the Knight shift at $H = 4.6$ T, indicating that the origin of the lower resonance line, which dominates well below $T_c(H)$, is the same as the resonance line in the BCS state. Therefore, as discussed in Ref. [20], the appearance of the higher resonance peak is a manifestation of the new quasiparticle region that appeared as a result of spatial modulation of the superconducting order parameter in the FFLO state. Moreover, it has been shown that the temperature evolution of the higher resonance peak can be accounted for semiquantitatively by considering the inhomogeneous distribution of the shielding currents passing across the planar nodes that are periodically aligned perpendicular to the flux line lattice. We note that the sample-dependent double peak structure may be explained by the distribution of the ac-shielding currents which are seriously influenced by the surface condition of the sample.

Thus, the present NMR data lead us to conclude that the FFLO state is indeed realized for $H \perp ab$. The occurrence of the first order transition at $H_{c2}^\perp$ implies that the Pauli paramagnetic effect dominates near $H_{c2}^\perp$ in this case as well. We first argue the requirement for the FFLO forma-

tion with respect to the Pauli effect for $H \perp ab$. Such a requirement can be quantitatively described by the Maki parameter $\alpha = \sqrt{2}H_{\text{orb}}/H_P$ [3], which is the ratio of the orbital limiting upper critical field H_{orb} and the Pauli limiting field H_P . It has been shown that the required minimum value of the Maki parameter for the formation of the FFLO state is $\alpha = 1.8$ [4]. The orbital limited fields obtained from the initial slope of H_{c2} , $dH_{c2}/dT|_{T=T_c}$ through the relation $H_{\text{orb}} = -0.7T_c dH_{c2}/dT$, are 38.6 and 17.7 T for $H \parallel ab$ and $H \perp ab$, respectively. Assuming $H_P \approx H_{c2}(0)$, the Maki parameters for $H \parallel ab$ and $H \perp ab$ are estimated to be $\alpha^\parallel = 4.6$ and $\alpha^\perp = 5.0$, respectively. Thus $\alpha^\perp$ greatly exceeds the minimum value of 1.8 for the FFLO state. We note that $\alpha^\perp$ is even larger than $\alpha^\parallel$. The extremely large $\alpha^\perp$ can be attributed to the strongly enhanced Pauli paramagnetic susceptibility in the normal state. In fact, the Pauli susceptibility for $H \perp ab$ is nearly twice as large as that for $H \parallel ab$ [17].

We next discuss the FFLO region in the H - T phase diagram. The absence of the double peak anomaly in the spectrum below $H = 4.7$ T indicates that the critical field $H_{\text{FFLO}}^\perp$ separating the FFLO and the BCS state lies in a very narrow range between 4.7 and 4.75 T below $T_c(H)$, though its precise T dependence is difficult to determine. Figure 3(a) displays the H - T phase diagram for $H \perp ab$ as determined by the present measurements, while Fig. 3(b) displays the diagram for $H \parallel ab$ reported previously [17,19]. It should be noted that the specific heat measurements showed an anomaly in the vicinity of $H_{\text{FFLO}}^\perp$ [17]. Obviously, the topology of the phase transition lines for both configurations is identical in that the FFLO line branches from the first order superconducting-to-normal transition line.

Despite the striking resemblance in the phase diagrams of both configurations, there are distinguishing differences

FIG. 3 (color online). H - T phase diagrams at low temperatures and high fields for $H \perp ab$ (left panel) and $H \parallel ab$ (right panel). The colored portions display the FFLO and BCS regions. The open circles are H_{c2} determined by the NMR experiments. The black and green (gray) lines represent the upper critical fields which are in the first and the second order, respectively. The red or dark gray dashed and solid lines represent the phase boundary separating the FFLO and BCS states. For $H \perp ab$, precise determination of the phase boundary between the FFLO and the BCS states is difficult in the present experiments.

between them. For $H \perp ab$, the FFLO phase occupies a tiny high- H -low- T corner in the H - T phase diagram, compared to the case for $H \parallel ab$. In addition, $H_{\text{FFLO}}^{\perp}$ almost ceases to have a temperature dependence, in striking contrast to $H \parallel ab$. Moreover, for $H \perp ab$, the end point of the FFLO transition line appears close to the end point of the first order transition, though the end point of the first order transition line is difficult to determine explicitly by the experiments. Some theories that attempt to describe the FFLO state have predicted that the critical field separating the FFLO and BCS states is nearly temperature independent [4,6,10]. In this respect, the phase diagram for $H \perp ab$ seems to be close to the phase diagram of *conventional* FFLO theories, although such a simple comparison should be scrutinized.

In addition to the shrinkage of the FFLO region, the directing H towards the c axis also results in a notable change in the quasiparticle excitation spectrum. We can examine the quasiparticle structure inferred from the NMR spectrum. The well-separated double resonance lines provide two important pieces of information for the quasiparticle excitations in the FFLO state. First, the quasiparticles excited around the FFLO planar nodes are spatially well separated from those excited around vortex cores. According to recent theory, the quasiparticles are not excited in the region where the vortex lines intersect the planar node, because of the bound states due to the π shift of the pair potential associated with the planar node [13]. This indicates that the quasiparticle regions within the vortex line do not spatially overlap with those in the FFLO planar nodes. Second, the Knight shift of the higher resonance line is strongly enhanced from the normal state value, as shown by open circles in the main panel of Fig. 2. This immediately indicates that the quasiparticle state within the planar nodes created in the FFLO state for $H \perp ab$ should be distinguished from the normal state. The strongly enhanced Knight shift for $H \perp ab$ indicates that the paramagnetic moments are enhanced within the nodal sheets. The results for $H \perp ab$ are in sharp contrast with the results for $H \parallel ab$, wherein the Knight shift of the higher resonance line coincides with the normal state value at very low temperature. Thus, the quasiparticles in the planar nodes in the case of $H \parallel ab$ are in a state similar to the normal state [20].

We finally discuss the difference between $H \parallel ab$ and $H \perp ab$. The confinement of the FFLO phase in a much narrower region in the H - T plane for $H \perp ab$ indicates that the FFLO state is more stable for $H \parallel ab$. This may be related to the shape of the Fermi surface with a quasi-2D nature, though the origin of the remarkable T dependence of $H_{\text{FFLO}}^{\parallel}$ is unknown. At present, the origin of the enhancement of the paramagnetic moment in the FFLO sheets observed only for $H \perp ab$ is also an open question. We stress that the role of antiferromagnetic fluctuations near the quantum critical point [29] on the FFLO state is not well understood so far. In fact, very recent heat capacity

measurements under pressure clearly demonstrate that antiferromagnetic fluctuations are unfavorable for the stability of the FFLO state [30]. How the antiferromagnetic fluctuations affect both the FFLO phase diagram and the quasiparticle excitation spectrum in the FFLO state calls for further investigations.

To summarize, ^{115}In NMR studies in CeCoIn_5 revealed the presence of the FFLO state in a perpendicular magnetic field as well. The FFLO phase diagram in a perpendicular field bears resemblance to that in a parallel field. However, several notable differences, not only in the FFLO phase diagram but also in the quasiparticle excitations within the FFLO planar nodes, were found between the two different configurations.

We thank M. Ichioka, R. Ikeda, K. Machida, K. Maki, and H. Shimahara for valuable discussions.

-
- [1] P. Fulde and R. A. Ferrell, Phys. Rev. **135**, A550 (1964).
 - [2] A. I. Larkin and Y. N. Ovchinnikov, Sov. Phys. JETP **20**, 762 (1965).
 - [3] K. Maki, Phys. Rev. **148**, 362 (1966).
 - [4] L. W. Gruenberg and L. Gunther, Phys. Rev. Lett. **16**, 996 (1966).
 - [5] H. Shimahara, Phys. Rev. B **50**, 12 760 (1994).
 - [6] H. Burkhardt and D. Rainer, Ann. Phys. (Berlin) **506**, 181 (1994).
 - [7] A. I. Buzdin and J. P. Brison, Phys. Lett. A **218**, 359 (1996).
 - [8] M. Tachiki *et al.*, Z. Phys. B **100**, 369 (1996).
 - [9] H. Shimahara and D. Rainer, J. Phys. Soc. Jpn. **66**, 3591 (1997).
 - [10] D. F. Agterberg and K. Yang, J. Phys. Condens. Matter **13**, 9259 (2001).
 - [11] H. Adachi and R. Ikeda, Phys. Rev. B **68**, 184510 (2003).
 - [12] H. Won *et al.*, Phys. Rev. B **69**, 180504(R) (2004).
 - [13] T. Mizushima, K. Machida, and M. Ichioka, Phys. Rev. Lett. **95**, 117003 (2005).
 - [14] C. Petrovic *et al.*, J. Phys. Condens. Matter **13**, L337 (2001).
 - [15] H. Shishido *et al.*, J. Phys. Soc. Jpn. **71**, 162 (2002).
 - [16] H. A. Radovan *et al.*, Nature (London) **425**, 51 (2003).
 - [17] A. Bianchi *et al.*, Phys. Rev. Lett. **91**, 187004 (2003).
 - [18] T. Watanabe *et al.*, Phys. Rev. B **70**, 020506(R) (2004).
 - [19] C. Capan *et al.*, Phys. Rev. B **70**, 134513 (2004).
 - [20] K. Kakuyanagi *et al.*, Phys. Rev. Lett. **94**, 047602 (2005).
 - [21] K. Izawa *et al.*, Phys. Rev. Lett. **87**, 057002 (2001).
 - [22] A. Bianchi *et al.*, Phys. Rev. Lett. **89**, 137002 (2002).
 - [23] T. Tayama *et al.*, Phys. Rev. B **65**, 180504(R) (2002).
 - [24] Y. Kasahara *et al.*, Phys. Rev. B **72**, 214515 (2005).
 - [25] R. Movshovich *et al.*, Phys. Rev. Lett. **86**, 5152 (2001).
 - [26] P. M. C. Rourke *et al.*, Phys. Rev. Lett. **94**, 107005 (2005), and references therein.
 - [27] M. A. Tanatar *et al.*, Synth. Met. **133**, 215 (2003).
 - [28] N. J. Curro *et al.*, Phys. Rev. B **64**, 180514(R) (2001).
 - [29] T. Park *et al.*, Nature (London) **440**, 65 (2006); Y. Nakajima *et al.*, J. Phys. Soc. Jpn. **75**, 023705 (2006); J. Paglionione *et al.*, Phys. Rev. Lett. **91**, 246405 (2003); A. Bianchi *et al.*, *ibid.* **91**, 257001 (2003); V. A. Sidorov *et al.*, *ibid.* **89**, 157004 (2002).
 - [30] C. F. Miclea *et al.*, Phys. Rev. Lett. **96**, 117001 (2006).