Title	ON THE ADSORPTION OF CARBON MONOXIDE ON PLATINUM CATALYST.
Author(s)	KWAN, Takao
Citation	JOURNAL OF THE RESEARCH INSTITUTE FOR CATALYSIS HOKKAIDO UNIVERSITY, 1(2), 110-116
Issue Date	1949-11
Doc URL	http://hdl.handle.net/2115/24605
Type	bulletin (article)
File Information	1(2)_P110-116.pdf

[Instructions for use](#)

ON THE ADSORPTION OF CARBON MONOXIDE ON PLATINUM CATALYST.

By Takao KWAN.

For elucidating the mechanism of contact catalysis it is necessary to have information on the adsorbed state of the reactant. As regard to that of hydrogen on the metallic catalysts investigated hitherto by many workers the conclusive evidence has been obtained for the existence of hydrogen atoms on the catalyst's surface. As to the adsorbed state of the other reactants only few data are available even with such simple molecule as carbon monoxide or carbon dioxide.

Among these carbon monoxide might be one of the most interesting reactant both from the fundamental and industrial point of view, inasmuch as it yields by hydrogenation, notwithstanding so simple a structure, such variety of product at varying condition of the reaction, as those of Fischer-Tropsch synthesis for hydrogenation, methanol synthesis etc.

With regard to the former reaction KODAMA and co-workers¹⁾ proposed from the kinetical investigation that carbide was formed by the dissociation of carbon monoxide into carbon and oxygen atom in contradiction to CRANFORD²⁾.

According to BEECK and co-workers³⁾ who observed the relative amount of adsorption of various gases to that of carbon monoxide on nickel film found that the latter is twice as large as that of hydrogen suggesting that carbon monoxide molecule as well as the dissociated hydrogen atom occupies one adsorption site on the surface or that carbon monoxide is adsorbed without dissociation.

The present author has previously investigated the adsorption of hydrogen on reduced nickel, cobalt and platinum and concluded having recourse to the statistical mechanical method that each of metal atoms on the catalyst's surface are equally capable of adsorbing a dissociated hydrogen atom⁴⁾. Extending the latter conclusion it may be assumed

1) MATSUMURA, KODAMA and TARAMA; J. Ind. Chem. Soc. Japan, 43 (1940) 420.

2) CRANFORD; Trans. Far. Soc., 35 (1939) 946.

3) BEECK, SMITH and WHEELER; Proc. Roy. Soc., 177 (1940) 64.

4) KWAN and IZU; "Catalyst" 4 (1948) 22, 44 written in Japanese.

that every metal atom at the catalyst surface behaves physically identical even in the case of carbon monoxide adsorption.

On the basis of the assumption the adsorbed state of carbon monoxide on platinum catalyst is investigated in the present work by the similar method by determining the adsorption isotherm with special precaution for the thermodynamical equilibrium.

Materials and Experimental Procedure

Carbon monoxide; Carbon monoxide was prepared by dropping formic acid from the dropping funnel into an evacuated flask containing concentrated sulphuric acid at $90^{\circ}\sim 100^{\circ}\text{C}$ and passed through a trap immersed in liquid air and then stored in a reservoir which was beforehand highly evacuated.

Platinum black; 0.93 gr platinum black once used for the hydrogen adsorption was used here again.

The apparatus and the procedure for measurement of the adsorption was quite the same as those described in the foregoing paper.

Experimental Results

Measured quantity of carbon monoxide was admitted into the reaction vessel containing the platinum catalyst and maintained at a desired temperature. Although the adsorption rate was fairly rapid as in the case of hydrogen, the equilibrium pressure was determined about 20 hours after admission by approaching both from desorption and adsorption side similarly as in the previous case. Typical result is shown in Fig. 1 by the plot of the observed pressure against time elapsed along with occasionally varied temperature shown by annexed figures.

Fig. 1 Reversibility of carbon monoxide adsorption on platinum catalyst.

After the equilibrium was thus attained and appropriate pressure

was read off additional portions of carbon monoxide are admitted successively into the reaction vessel and the corresponding equilibrium pressure were similarly determined in each case. The reversibility of the adsorption was assured over the whole range of adsorbed quantity although this was not the case with nickel or cobalt or iron at a lower adsorbed quantity.⁵⁾

Calculating now the adsorbed quantity from the equilibrium pressure and the known quantity of admitted gas, adsorption isotherms were worked out at 180°, 200°, 220°, 280° and 300°C and at pressures lower than 1 mm Hg. The result is shown in Fig. 2.

Fig. 2 Adsorption isotherm of carbon monoxide on platinum black.

measurement was now dipped after that into an alcohol bath cooled at -80°C. No pressure increases above that due to the relevant thermal expansion was observed showing that the evolution of carbon dioxide and hence the appropriate decomposition may be practically ignored in the present case.

Differential heat of adsorption $\Delta\epsilon$ was derived from the usual expression,

$$\Delta\epsilon = RT^2 \left(\frac{\partial \log P}{\partial T} \right)_x$$

separately from the isotherms at 280°C and 300°C on one hand and from those at 180°, 200° and 220°C on the other hand inasmuch as the catalyst

The observed isotherms were found to be expressed by Freundlich's adsorption formulae as that,

$$x = CP^{1/n}, \quad n = 2.7$$

where x is the adsorbed quantity and P the equilibrium pressure.

The reported ready decomposition of carbon monoxide in the presence of metallic catalysts into carbon and carbon dioxide has not taken place as shown by the following control experiment.

The U-tube connected directly to the reaction vessel and immersed into liquid air during the adsorption

5) KWAN and IZU; "Catalyst" 5 (1949) 43.

was treated with hydrogen at 350°C between the observation of the former group of isotherms and that of the latter one and such procedure is known by experience liable to disturb the reproducibility of the catalyst's activity. The results are shown in the Table below.

As shown by the Table $\Delta\epsilon$ is affected neither by the temperature range at which it is determined nor by x within the experimental error.

TABLE 1 Heat of adsorption of carbon monoxide on platinum catalyst (Kcal/mole)

x in cc	0,039	0,063	0,100
From isotherms at			
280° and 300 C	11	11	10
180°, 200° and 220° C	11	11	10

Statistical Mechanical Treatment

Adsorption isotherm of diatomic molecules δ formed by atoms δ_1 and δ_2 is statistical mechanically derived introducing a set of function p , q and θ due to HORIUTI⁵⁾ as follows ;

$$\frac{\theta}{1-\theta} = \frac{q^{\delta(a)}}{p^{\delta(a)}} \quad (1.1)$$

$$\frac{\theta}{1-2\theta} = \frac{q^{\delta_1(a)}}{p^{\delta_1(a)}} = \frac{q^{\delta_2(a)}}{p^{\delta_2(a)}} \quad (1.2)$$

where $\delta(a)$ denotes the molecule δ , $\delta_1(a)$ and $\delta_2(a)$ dissociated atoms respectively at the adsorbed state.

At adsorption equilibrium we have that,

$$p^{\delta} = p^{\delta(a)} \quad (2.1)$$

$$\text{or } p^{\delta} = p^{\delta_1(a)} p^{\delta_2(a)} \quad (2.2)$$

respectively for the case when δ is undissociated or dissociated at the adsorbed state. In the former case we have from Eq. (1.1) and (2.1) as that,

$$\frac{\theta}{1-\theta} = \frac{q^{\delta(a)}}{p^{\delta}} \quad (3.1)$$

and in the latter as that,

$$\left(\frac{\theta}{1-2\theta} \right)^2 = \frac{q^{\delta_1(a)} q^{\delta_2(a)}}{p^{\delta}} \quad (3.2)$$

*) The θ must be equal because of the stoichiometrical relation for δ_1 and δ_2 .

5) HORIUTI; J. Res. Inst. Catalysis, This Volume, (1948) 8.

Since p^δ is however denoted from its definition as that,

$$p^\delta = \frac{Q^\delta}{N^\delta} = \frac{kTQ^\delta}{P} \quad (4)$$

where P is the pressure and Q the partition function, Eq. (3.1) and (3.2) are now respectively expressed as that,

$$\frac{\theta}{1-\theta} = \frac{q^{\delta(a)} P}{kTQ^\delta} \quad (5.1)$$

$$\left(\frac{\theta}{1-2\theta}\right)^2 = \frac{q^{\delta_1(a)} q^{\delta_2(a)} P}{kTQ^\delta} \quad (5.2)$$

Eqs. (5.1) and (5.2) are further transformed in a suitable form for calculation respectively as that,*)

$$\frac{\theta}{1-\theta} = q^{\delta(a)} e^{T \frac{\partial \log q^{\delta(a)}}{\partial T}} \frac{P}{Q_0^\delta} e^{\frac{\Delta \epsilon}{kT}} \quad (6.1)$$

$$\left(\frac{\theta}{1-2\theta}\right)^2 = q^{\delta_1(a)} q^{\delta_2(a)} e^{T \frac{\partial \log q^{\delta_1(a)} q^{\delta_2(a)}}{\partial T}} \frac{P}{Q_0^\delta} e^{\frac{\Delta \epsilon}{kT}} \quad (6.2)$$

where

$$Q_0^\delta = kT \frac{(2\pi mkT)^{\frac{3}{2}}}{h^3} \frac{8\pi^2 I kT}{sh^2} \left(1 - e^{-\frac{h\nu}{kT}}\right)^{-1} e^{\frac{\epsilon_0}{kT}}$$

h ; Planck constant

k ; Boltzmann constant

s ; Symmetry number

m, I and ν ; Mass, moment of inertia and fundamental frequency of gaseous molecule δ .

$q^{\delta(a)}, q^{\delta_1(a)}$ and $q^{\delta_2(a)}$; Function particular to the adsorbed state of $\delta(a)$,

$$\delta_1(a) \text{ and } \delta_2(a) \text{ denoted as } q^{\delta_1(a)} = \prod \left(1 - e^{-\frac{h\nu_i}{kT}}\right)^{-1} e^{-\frac{\epsilon_0 + \frac{1}{2}h\nu_i}{kT}} \text{ etc.}$$

where ν_i 's are frequency of normal vibration at the adsorbed state.

Taking now $\delta \equiv CO$ and assuming $h\nu_i \gg kT$ in q 's and hence

$$q^{\delta(a)} e^{T \frac{\partial \log q^{\delta(a)}}{\partial T}} = 1, \quad q^{\delta_1(a)} q^{\delta_2(a)} e^{T \frac{\partial \log q^{\delta_1(a)} q^{\delta_2(a)}}{\partial T}} = 1$$

*Cf. the foot note on P. 93.

On the Adsorption of Carbon Monoxide on Platinum Catalyst.

the calculation of the covered fraction of the surface was carried out at temperature 300°C and at pressures 0,01 and 0,1 mm Hg using the observed heat of adsorption 11 Kcal/mole and the following molecular constants of carbon monoxide molecule respectively for Eq. (6. 1) and (6. 2).

$$I = 14,37 \times 10^{-40} \quad g. \text{ cm}^2 * \quad \nu = 2168,80 \text{ cm}^{-1} *$$

On the other hand the covered fraction of the surface θ_{obs} was determined from the adsorbed quantity and the surface area of the catalyst assuming every platinum atom on the surface equally capable of adsorbing carbon or oxygen atom.

The particle size of platinum black estimated by the diffuseness observation of the Debye-Scherrer pattern of the electron diffraction was found, as mentioned in the previous paper⁵⁾, appreciably smaller than that given by B.E.T. method although in the case of nickel the particle size estimated by either of the methods was found satisfactorily coincident with each other. Without inquiring into the above discrepancy θ_{obs} was calculated on the basis of $280 \times 10^4 \text{ cm}^2/\text{gr}$ or the particle size 10 Å due to the electron diffraction method as well as of $14 \times 10^4 \text{ cm}^2/\text{gr}$ due to B.E.T. method assuming that 10^9 Pt atoms per square centimeter are capable of adsorbing each one carbon or oxygen atom. The results are shown together with those given by statistical mechanical calculation in the following Table.

TABLE 2 The relation between the equilibrium pressure P and the covered fraction
 $T = 300^\circ\text{C}$ $\Delta\epsilon = 11 \text{ Kcal/mole}$

θ	Equil. Pressure mm Hg	0,01	0,1
	Remark		
θ_{calc}	$\text{CO} \rightleftharpoons \text{CO}(a)$	10^{-12}	10^{-11}
	$\text{CO} \rightleftharpoons \text{C}(a) + \text{O}(a)$	10^{-6}	3×10^{-6}
θ_{obs}	Electron diffraction	3×10^{-4}	7×10^{-4}
	B. E. T.	6×10^{-3}	10^{-2}

As seen from the Table assumed adsorbed state of $\text{CO}(a)$ fails exclusively to account for the experiment whereas $\text{C}(a) + \text{O}(a)$ or the

*) SPONER; Molekulspektren, Berlin 1936.

6) KWAN; This Journal p. 89

dissociated state fits in with regard to the accuracy of the basic data; in the case of undissociated adsorption θ_{obs} should be different according as carbon monoxide occupies one or two Pt atoms but this makes no difference with the above conclusion.

Conclusion is that carbon monoxide is adsorbed on platinum being dissociated into carbon and oxygen atom.

In conclusion, the present author wish to express my sincere thanks to the Director of the Institute J. HORIUTI for his kind interest and valuable discussion on this work.

The Research Institute for Catalysis
Hokkaido University
Sapporo, Japan