

HOKKAIDO UNIVERSITY

Title	Robust dye-sensitized overall water splitting system with two-step photoexcitation of coumarin dyes and metal oxide semiconductors
Author(s)	Abe, Ryu; Shinmei, Kenichi; Hara, Kohjiro; Ohtani, Bunsho
Citation	Chemical Communications, 24, 3577-3579 https://doi.org/10.1039/b905935k
Issue Date	2009-06-28
Doc URL	http://hdl.handle.net/2115/43142
Rights	Chem. Commun., 2009, 3577-3579 Reproduced by permission of The Royal Society of Chemistry (RSC)
Туре	article (author version)
File Information	CC24_3577-3579.pdf



ARTICLE TYPE

Robust Dye-sensitized Overall Water Splitting System with Two-step Photoexcitation of Coumarin Dyes and Meal Oxide Semiconductors

Ryu Abe,*^{*a,b*} Kenichi Shinmei,^{*b*} Kohjiro Hara^{*c*} and Bunsho Ohtani^{*a,b*}

Received (in XXX, XXX) Xth XXXXXXXX 200X, Accepted Xth XXXXXXXX 200X 5 First published on the web Xth XXXXXXXX 200X DOI: 10.1039/b000000x

Photocatalytic splitting of water into H_2 and O_2 under visible light irradiation is achieved using a coumarin dye-adsorbed lamellar niobium oxide for hydrogen evolution.

- 10 Water splitting using semiconductor photocatalysts has been extensively studied as a candidate for hydrogen (H_2) prodcution using solar energy. Althought many photocatalysts that work efficiently under ultraviolet (UV) irradiation have been developed, only a few visible light responsive
- ¹⁵ photocatalysts have been reported for overall water splitting, *i.e.*, the simultaneous production of H_2 and O_2 .¹⁻³ The difficulty in achieving overall water splitting using visible light is primarily due to the difficulty in tuning the band levels of inorganic, especially oxide, semiconductor photocatalysts.
- ²⁰ Scaife pointed out in 1980 that it is intrinsically difficult to develop an oxide semiconductor photocatalyst having both a sufficiently negative conduction band level for H_2 production and a narrow band gap allowing visible light absorption, because of the deeply positive level of the valence band
- ²⁵ formed by the O-2p orbital.⁴ Recent studies have therefore focused on the hybridization of the O-2p with other orbital such as N-2p (*e.g.* oxynitrides),¹ as well as the construction of two-step photoexcitation systems^{2,3} using shuttle redox mediators such as IO_3^-/I^- . On the other hand, various organic
- ³⁰ dyes, including Ru-complexes, have shown to possess both a sufficiently negative energy level (LUMO) for H₂ production as well as visible light absorption.⁵ Furthermore, fine-tuning of energy levels (HOMO and LUMO) of organic dyes is much easier compared to oxides, as has been shown for dye-
- ³⁵ sensitized solar cells.⁶ However, such a simple dye molecule by itself cannot oxidize water into O_2 . The evolution of O_2 from water, which requires the abstraction of four electrons, is hard for the simple dye molecules. Although non-sacrificial H₂ production using a combination of a dye-sensitized
- ⁴⁰ photocatalyst with a reversible iodine redox mediator (I_3^-/I^-) has been demonstrated,⁷ overall water splitting using a dyesensitized photocatalyst has not yet been achieved in an aqueous solution, possibly due to the lack of stability of the dye molecule, especially in its oxidized state.
- The present paper reports the first example of overall water splitting under visible light using a simple organic dye as a photosensitizer for the H_2 production part. We found that coumarin dyes with an oligo-thiophene moiety between the donor and acceptor parts show reversible oxidation-reduction
- $_{50}$ cycles stably even in an aqueous solution. These dyes can be used as stable photocatalysts for stoichiometric production of H₂ and triiodide (I₃⁻) from an aqueous solution containing an

iodide (I⁻) electron donor when combined with an internally platinized layered niobium oxide (Pt/H₄Nb₆O₁₇) ⁵⁵ semiconductor.⁷ Overall water splitting was then achieved by combining the coumarin dye-adsorbed Pt/H₄Nb₆O₁₇ with tungsten oxide (WO₃) photocatalyst, which can reduce I₃⁻ back to I⁻ accompanied by the oxidation of water into O₂ under visible light irradiation.

A coumarin dye (C343) was purchased from Aldrich. Other coumarin dyes (NKX series)^{6-a} were provided by Hayashibara Biochemical Laboratories, Inc. Japan. The molecular structures are shown in Fig. 1. These dye were adsorbed on the surface of internally platinized potassium niobate (Pt/H₄Nb₆O₁₇), which
 ⁶⁵ was prepared by the previously reported method.^{7-c} The Detailed preparation procedures of coumarin dye-adsorbed Pt/H₄Nb₆O₁₇ photocatalyst and IrO₂-Pt/WO₃ photocatalyst, are provided in the supporting information, with other experimental conditions for photocatalytic activity test and electrochemical measurements.



Fig. 1 Molecular structures of coumarin dyes

Fig. 2 shows the time course of H_2 evolution over coumarin 80 dye-adsorbed Pt/H₄Nb₆O₁₇ photocatalysts suspended in aqueous potasium iodide (KI) solution under visible light irradiation. Steady H₂ evolution proceeded over the NKX-2677 and NKX-2697 dye-adsorbed photocatalysts (Fig. 2-a), $_{85}$ and nearly the same amount of I_3^- anion as H_2 gas was detected in the solutions after the reaction in both cases (e.g., H₂: 48 μ mol; I₃⁻: 47 μ mol for NKX-2677). The molar amount of evolved H₂ exceeded the amount of the dye molecules contained in 50 mg of photocatalyst powder (NKX-2677: ca. 90 0.55 µmol; NKX-2697: ca. 0.52 µmol). The diffuse reflectance spectra for these photocatalysts after the reaction was found to be almost the same as before the reaction, except for a slight shift of the absorption edge to a shorter wavelength, as shown in Fig. 3-a (spectra of NKX-2697 are 95 shown in Fig. S1). This shift is attributable to the change in alignment of the dye molecules on the surface of the Pt/H₄Nb₆O₁₇ semiconductor during the stirring in the aqueous solution rather than to the decomposition of dye molecules, because a similar shift was also observed when the 100 photocatalysts were stirred in an aqueous KI solution in the dark. The findings indicate that the following reactions took place over the NKX-2677 and NKX-2697 dye-adsorbed $Pt/H_4Nb_6O_{17}$ photocatalysts under visible light irradiation:

(1) S + hv ($\lambda > 400 \text{ nm}$) \rightarrow S* (excitation of dye)

5 (2) $S^* \rightarrow S^+ + e^-$ (electron injection to $H_4 Nb_6 O_{17}$) (3) $e^- + H^+ \rightarrow 1/2 H_2$ (H₂ production on Pt) (4) $S^+ + I^- \rightarrow S + 1/2 I_2$ (1/2 I_3^-) (regeneration of dye)



Fig. 2 Time course of photocatalytic H_2 evolution by coumarin dyeadsorbed Pt/H₄Nb₆O₁₇ photocatalysts (50 mg) suspended in a 0.1 M ₂₀ aqueous KI solution (100 mL) under visible light ($\lambda > 400$ nm).



Fig. 3 Diffuse reflectance spectra of coumarin dye-adsorbed Pt/H4Nb6O17

photocatalysts before and after the reaction in Fig. 2.

On the other hand, the rate of H_2 production gradually decreased with irradiation time in the case of other coumarin ³⁵ dyes (C-343, NKX-2311, and NKX-2587), as shown in Fig. 2b, while the rates of H_2 production were relatively high in initial period. The molar amount of liberated I_3^- was smaller than the amount of H_2 evolved in each case (*e.g.*, H_2 : 32 µmol; I_3^- : 25 µmol for NKX-2311). The diffuse reflectance

- ⁴⁰ spectra of these dyes changed significantly by the reaction, as shown in Fig. 3. Such a significant change was not observed when the photocatalysts were stirred in the dark, indicating that the change in the spectra was caused by photochemical processes and not by physical processes such as desorption of
- ⁴⁵ dye molecules from the $Pt/H_4Nb_6O_{17}$ surface. It is likely that the oxidized state (S⁺) of these dyes reacted with water before accepting an electron from the I⁻ anions and then became photo-inactive species. It is to be noted that the rate of H₂ evolution was negligibly low when the collected photocatalyst
- ⁵⁰ powder was irradiated again in a fresh KI solution, while in the case of NKX-2677 and NKX-2697, the dyes exhibited almost the same rate of H₂ production again.

To examine the stability of the dye molecules in the aqueous solution, the oxidation and reduction behaviors of ⁵⁵ these dyes were analyzed by cyclic voltammetry (CV) in both

aqueous and acetonitrile (AN) solutions. Since these dyes, except for C-343, are barely soluble in an aqueous solution with a neutral pH, the CV measurements were carried out using nano-porous TiO₂ electrodes with the dyes adsorbed on 60 them.^{6-c} Fig. 4 shows the CV profiles of NKX-2311, NKX-2587, and NKX-2677 in water or dehydrated AN solution containing 0.1 M of LiClO₄ as a supporting electrolyte (CV curves of NKX-2697 are shown in Fig. S2). In all cases, a current peak was observed with an applied anodic potential 65 above +0.4 V (vs. reference), which indicates oxidation of the dye molecule into an oxidized state (S^+) . On the other hand, the reduction behavior strongly depended on the structure of the dye molecule. In the case of NKX-2677, a reversible current peak was observed during the reversed cathodic 70 scanning in both solvents, indicating that the oxidized state (S^{+}) possesses a relatively long lifetime even in water and can be reduced back to the original state by accepting an electron during cathodic potential sweep (Fig. 4-a). Such a reversible oxidation-reduction behavior of NKX-2677 and NKX-2697 75 was observed even in repeated CV scanning several times. Although this reversible behavior was observed for NKX-2587 in AN, the reduction current peak was much lower than the oxidation peak in water (Fig. 4-b). In the case of NKX-2311, the reduction current peak was much lower than the 80 oxidation peak even in AN, and no reduction peak was observed in water (Fig. 4-c). These results indicated that the oxidized state of these dyes (NKX-2311, NKX-2587) reacted with the H₂O molecules irreversibly and formed inactive species, as suggested by the results of the photocatalytic 85 reactions (Fig. 2 and 3). Considering molecular structure of the coumarin dyes used, it is concluded that a thiophene $\begin{array}{c} \underset{\substack{0 \\ (a) \\ (b) \\ (c) \\ (c$ - in H,O (x 2) S a significa in H₂O (x 5) form of the uyes in water. in CH,CN in CH₂CN 9€ Curren 0.5

Fig. 4 CV curves of coumarin dyes absorbed on a porous TiO₂ ¹⁰⁰ electrode in a dehydrated acetonitrile (AN) or aqueous solution containing 0.1 M of LiClO₄ as a supporting electrolyte: the scan rate was 100 mV s⁻¹. Ag/AgCl in saturated aqueous NaCl solution and Ag/Ag⁺ in 0.01 M AgNO₃ acetonitrile solution were used as a reference electrode in aqueous and AN solutions, respectively.

0.6 0.8 1.0 0.2 0.4 0.6 0.8 1.0

tial / V vs. RE

-2

1.0 0.2

0.4

0.8

tial / V vs. RE

0.2

95

0.4 0.6

0.0

¹⁰⁵ Overall water splitting under visible light was then attempted by combining the dye-adsorbed Pt/H₄Nb₆O₁₇ photocatalyst with the WO₃ photocatalyst for O₂ evolution.² In the present study, IrO₂ and Pt co-loaded WO₃ photocatalyst ¹¹⁰ (IrO₂-Pt/WO₃) was applied to achieve steady O₂ evolution in the presence of the I₃⁻ anion in aqueous KI solution. It was found that the IrO₂-Pt/WO₃ showed better activity for O₂ evolution than Pt/WO₃ in the presence of I₃⁻ in KI solution.

As shown in Fig. 5, the combination of NKX-2677-adsorbed $Pt/H_4Nb_6O_{17}$ and IrO_2-Pt/WO_3 yielded simultaneous H_2 and O_2 evolution in an almost stoichiometric ratio. The reaction proceeded without appreciable deactivation even after 48-h ⁵ photoirradiation. The total amount of evolved H_2 , ca. 116 µmol, exceeded the amount of dye molecules adsorbed on $Pt/H_4Nb_6O_{17}$ (ca. 0.55 µmol). It is to be noted that no gas evolution was observed in darkness (the 4th run). Also, no H_2 evolution was observed when only IrO_2 -Pt/WO₃ was ¹⁰ irradiated in KI solution.



Fig. 5 Time courses of photocatalytic evolution of H_2 (closed) and ²⁵ O₂ (open) using a mixture of coumarin dye-adsorbed (circles: NKX2677, triangles: NKX 2587, square: NKX2311) Pt/H₄Nb₆O₁₇ (50 mg) and IrO₂-Pt/WO₃ (100 mg) suspended in a 5 mM of KI aqueous solution under visible light ($\lambda > 400$ nm). Arrows indicate evacuation of gas phase.

30

- These results demonstrate that overall water splitting proceeded with a two-step photoexcitation combined with a redox cycle between I_3^- and I^- . The first step involves water reduction to H_2 and I^- oxidation to I_3^- over NKX-2677as adsorbed Pt/H₄Nb₆O₁₇ photocatalyst, and the second step involves I_3^- reduction to I^- and water oxidation to O_2 over IrO_2 -Pt/WO_3. Steady and simultaneous H_2 and O_2 evolution was also achieved by using NKX-2697, which has three thiophene rings (Fig. S3). On the other hand, the rate of gas
- ⁴⁰ evolution using NKX-2587, which has one thiophene ring, drastically decreased with prolonged irradiation time. In the case of the NKX-2311 dye, which has no thiophene ring, only a small amount of H_2 was evolved in the initial period. These results again indicate that the oligo-thiophene moiety in the
- ⁴⁵ coumarin dyes plays an essential role to stabilize dye molecules during photocatalytic overall water splitting. One possible explanation for the necessity of the poly-thiophene unit is that the positive charge of the oxidized dye is delocalized over the oligo-thiophene moiety and its reactivity
- ⁵⁰ toward H₂O is lowered, while the positive charge can accept an electron from the Γ anion regenerating the original ground state of the dye. We have examined the effect of light irradiation on the dyes adsorbed on nanocrystalline TiO₂ films under ambient conditions and found that the dyes, not only
- ⁵⁵ coumarin dyes, containing an oligothiophene moiety showed higher stability compared to those without oligothiophene moiety.⁸ The transient absorption spectroscopy have strongly suggested that the positive charge in such dye lacated on the

oligo-thiophene moiety.⁸ The results in stability test under ambient condition have also suggested that the dyes with oligo-thiophene moiety have durability to O_2 molucules, not only to H₂O. Actually, H₂ production stably proceeded over NKX-2677 dye-sensitized photocatalysts even when the reaction was initiated in the presence of considerable amount of O₂ in gas phase (e.g., 200 µmol of O₂).

In summary, dye-sensitized overall water splitting under visible light irradiation was demonstrated for the first time using a simple organic dye molecule as a photosensitizer for H_2 evolution, WO₃ photocatalyst for O₂ evolution, and I_3^{-}/I^{-} 70 redox couple as a shuttle redox mediator. The photocatalytic activity test and electrochemical measurements indicated that the oxidized states of the coumarin dyes having oligothiophene unit in their structure are stable even in water to achieve sustaining overall water splitting. Although, at 75 present, the quantum efficiency of dye-sensitized H₂ evolution is still low (e.g., < 0.1% at 500 nm for the NKX-2677 system), improvements in efficiency are in progress by structural design of the dye molecules optimized for both H₂ production and I⁻ oxidation, as well as optimization of ⁸⁰ lamellar niobate.

Notes and references

 ^a Catalysis Research Center, Hokkaido University, N-21, W-10, Sapporo, 001-0021, Japan, Fax: +81 11-706-9129; Tel:+81 11-706-9129; E-mail:
 ⁸⁵ ryu-abe@cat.hokudai.ac.jp

^b Graduate School of Environmental Earth Science, Hokkaido University, Sapporo 060-0810, Japan

^c National Institute of Advanced Industrial Science and Technology (AIST), 1-1-1 Higashi, Tsukuba 305-8565, Japan

- ⁹⁰ † Electronic Supplementary Information (ESI) available: The Detailed preparation procedures of photocatalyst, detailed experimental conditions for photocatalytic activity test and electrochemical measurements, results on NKX-2697 adsorbed photocatalyst, potential diagram with reaction scheme. See DOI: 10.1039/b000000x/
- 95 1 K. Maeda, K. Teramura, D. Lu, T. Takata, N. Saito, Y. Inoue and K. Domen, *Nature*, 2006, **440**, 295.
- 2 (a) K. Sayama, K. Mukasa, R. Abe, Y. Abe, H. Arakawa, *Chem. Commun.*, 2001, 2416; (b) R. Abe, T. Takata, H. Sugihara and K. Domen, *Chem. Commun.*, 2005, 3829; (c) R. Abe, K. Sayama and H. Sugihara, *J. Phys. Chem. B*, 2005, **109**, 16052; (d) M. Higashi, R. Abe, K. Teramura, T. Takata, B. Ohtani and K. Domen, *Chem. Phys. Lett.*, 2008, **452**, 120.
- 3 (a) A. Kudo, H. Kato and I. Tsuji, *Chem. Lett.*, 2004, 33, 1534; (b) H. Kato, Y. Sasaki, A. Iwase and A. Kudo, *Bull. Chem. Soc. Jpn.*, 2007, 80, 2457.
- 4 D. E. Scaife, *Solar Energy*, 1980, **25**, 41.
- (a) T. Kajiwara, K. Hashimoto, T. Kawai, T. Sakata, J. Phys. Chem. 1982, 86, 4516; (b) H. Misawa, H. Sakuragi, Y. Usui, K. Tokumaru, Chem. Lett. 1983, 1021; (c) T. Shimizu, T. Iyoda, Y. Koide, J. Am.
- 110 Chem. Soc., 1985, **107**, 35; (d) R. Abe, K. Hara, K. Sayama, K. Domen and H. Arakawa, J. Photochem. Photobiol. A: Chem. 2000, **137**, 63.
- 6 (a) K. Hara, Z. S. Wang, T. Sato, A. Furube, R. Katoh, H. Sugihara, Y. Dan-oh, C. Kasada, A. Shinpo, S. Suga, *J. Phys. Chem. B*, 2005, 109, 15476; (b) D. P. Hagberg, T. Marinado, K. M. Karlsson, K. Nonomura, P. Qin, G. Boschloo, T. Brinck, A. Hagfeldt and L. Sun, *J. Org. Chem.* 2007, 72, 9550; (c) T. A. Heimer, S. T. D'Arcangelis, F. Farzad, J. M. Stipkala and G. Meyer, *J. Inorg. Chem.* 1996, 35, 5319.
 7 (a) Y. I. Kim, S. J. Atherton, E. S. Brigham and T. E. Mallouk, *J. Phys.*
- 7 (a) Y. I. Kim, S. J. Atherton, E. S. Brigham and T. E. Mallouk, *J. Phys. Chem.* 1993, **97**, 11802; (b) G. B. Saup, T. E. Mallouk, W. Kim and
 R. H. Schmehl, *J. Phys. Chem. B*, 1997, **101**, 2508; (c) R. Abe, K.

Sayama and H. Arakawa, J. Photochem. Photobiol. A: Chem. 2004, 166, 115.

8 R. Katoh, A. Furube, S. Mori, M. Miyashita, K. Sunahara, N. Koumura and K. Hara, *Energy Environ. Sci.*, 2009, DOI:
 5 10.1039/b900372j