Title	Identifying catalyst in Li-N-H system by x-ray absorption spectroscopy
Author(s)	Isobe, Shigehito; Hino, Satoshi; Ichikawa, Takayuki; Kojima, Yoshitsugu
Citation	Applied Physics Letters, 99(1), 013101 https://doi.org/10.1063/1.3606534
Issue Date	2011-07-04
Doc URL	http://hdl.handle.net/2115/46882
Rights	Copyright 2011 American Institute of Physics. This article may be downloaded for personal use only. Any other use requires prior permission of the author and the American Institute of Physics. The following article appeared in Appl. Phys. Lett. 99, 013101 (2011) and may be found at https://dx.doi.org/10.1063/1.3606534
Type	article
File Information	APL99-1_013101.pdf

[Instructions for use](#)

Identifying catalyst in Li-N-H system by x-ray absorption spectroscopy

Shigehito Isobe,^{1,a)} Satoshi Hino,² Takayuki Ichikawa,² and Yoshitsugu Kojima²

¹Graduate School of Engineering, Hokkaido University, N-13 W-8, Sapporo 060-8628, Japan

²Institute for Advanced Materials Research, Hiroshima University, 1-3-1 Kagamiyama, Higashi-Hiroshima 739-8530, Japan

(Received 9 March 2011; accepted 11 June 2011; published online 5 July 2011)

Chemical bonding states of titanium compounds in LiH and LiNH₂ mixture, which have been a candidate for a hydrogen storage material, have been examined by x-ray absorption spectroscopy measurement as the characterization of the catalysts. The results of x-ray absorption near-edge structure indicated that the Ti atoms in the Ti compounds, which had the catalytic effect on the kinetics of the hydrogen desorption properties, had a common electronic (chemical bonding) state. Additionally, this common electronic state of the Ti catalysts agrees with that of TiCl₃·5NH₃. These results indicated that TiCl₃·5NH₃ could act as the catalyst. © 2011 American Institute of Physics. [doi:10.1063/1.3606534]

Hydrogen storage in solid state is the key factor that is affecting the use of fuel cell vehicles. Since P. Chen's report,¹ Li-N-H system has been paid much attention for one of the promising hydrogen storage systems.^{2–9} Lithium nitride absorbs and desorbs a large amount of hydrogen in the two consecutive reactions as follows:

Theoretically, a large amount (10.4 mass%) of hydrogen (2H₂/(Li₃N+2H₂)) is accessible in these two reactions. Ichikawa *et al.* chose LiNH₂ and LiH as the starting materials and investigated the hydrogenation and dehydrogenation properties of the mixture, focusing on the following reaction:^{3,4}

They determined the mechanisms of the reaction and also reported several potential catalysts such as Ti, Fe, Ni, Co (Ref. 3). In addition, two part ammonia mediated reactions were suggested in their work.⁴ One is the decomposition of LiNH₂ to Li₂NH with ammonia emission, the other is the reaction of LiH and the ammonia with hydrogen desorption. Moreover, it was clarified that some catalysts, especially titanium compounds such as TiCl₃, were effective for improving hydrogen storage kinetics on this system.^{3,5} However, we have not been able to characterize the catalysts, which have superior effect on hydrogen desorption, by x-ray diffraction (XRD) measurement.⁵ It was difficult to observe the catalysts, because they were quite small amount and highly dispersed in the mixtures. Then, in order to characterize the catalysts, we have performed synchrotron radiation (SR) x-ray absorption spectroscopy (XAS). The results showed that the chemical bonding states of the titanium compounds, which had catalytic effect, were almost same. It is known that TiCl₃ reacts with NH₃ to form TiCl₃·*n*NH₃ (Ref. 10). This compound could show catalytic effect in the ammonia mediated reaction,

playing a role as a kind of ammonia carrier. In the present work, we identified the chemical bonding state of the titanium compounds, considering that the bonding state should be significant on understanding the catalytic effect.

The powder of LiH (95% purity) was purchased from Sigma-Aldrich and LiNH₂ (95%) was from Strem Chemicals. To achieve nanometer-scale contact among LiNH₂, LiH, and 1 mol. % additive, the mixtures were mechanically ball-milled (P7, Fritsch) at 400 rpm under 1 MPa hydrogen (99.99999%) atmosphere at room temperature for 2 h. As one of the additives, the powder of TiCl₃ (99.999%) and MgCl₂ (99.9%) with micron size were purchased from Sigma-Aldrich. Other additives, the titanium ammine complexes (TiCl₃·*n*NH₃), were synthesized from TiCl₃ and NH₃. TiCl₃ reacted exothermically with sufficient amount (and 1:3 molar ratio) of 0.5 MPa ammonia at room temperature forming TiCl₃·5NH₃ (and TiCl₃·3NH₃, respectively). TiCl₃·4NH₃ and TiCl₃·NH₃ were derived by heating of TiCl₃·5NH₃ under vacuum at 50 and 170 °C, respectively.¹⁰ We have confirmed the chemical composition of TiCl₃·*n*NH₃ by weight change caused by ammonia absorption and desorption. The hydrogen desorption properties of the composites were examined by thermal desorption mass spectroscopy (TDMS) (Anelva M-QA200TS) combined with thermogravimetry (TG) (Rigaku TG8120) at a temperature range from 25 °C to 450 °C with a heating rate of 5 °C/min. This equipment was especially designed and built up for using it inside the glovebox filled with purified argon, which permitted simultaneous measurements by TG and TDMS without exposing the samples to air at all. The XAS measurements were carried out at the BL19B2 beam-line of SPring-8 SR facility in Japan.¹¹ This beam-line is a hard x-ray bending magnet beam-line. All the samples were prepared in the glove box which is filled with purified Ar gas. The samples were formed to the 1 cm diameter pellet by 600 kg/cm² press. To avoid the oxidation of the samples during the XAS measurement, the samples were protected by the polyimide film with 8 μm thickness.

Figure 1 shows Ti *K*-edge x-ray absorption near-edge structure (XANES) spectra of TiCl₃·*n*NH₃ (*n* = 1, 3, 4, and 5). The shape of each spectrum is slightly different. Especially, with respect to the height of pre-edge peak (4965–4970 eV),

^{a)} Author to whom correspondence should be addressed. Electronic mail: isobe@eng.hokudai.ac.jp. Tel.: +81 11 706 6772. FAX: +81 11 706 6772.

FIG. 1. Ti *K*-edge XANES spectra of $\text{TiCl}_3 \cdot n\text{NH}_3$ ($n = 1, 3, 4$, and 5).

the order is $\text{TiCl}_3 \cdot 5\text{NH}_3 > \text{TiCl}_3 \cdot 4\text{NH}_3 \approx \text{TiCl}_3 \cdot 3\text{NH}_3 > \text{TiCl}_3 \cdot \text{NH}_3$. This order should be originated from the difference in symmetry of environmental atoms around titanium atom.⁹ On the other hand, the position of each *K*-edge (4965–4970 eV) is almost the same. From these spectra, it is indicated that the valence of titanium in $\text{TiCl}_3 \cdot n\text{NH}_3$ ($n = 1, 3, 4$, and 5) is almost the same. Figure 2 shows Ti *K*-edge XANES spectra of $\text{TiCl}_3 \cdot 5\text{NH}_3$, $\text{LiH} + \text{LiNH}_2$ with 1 mol.% TiCl_3 and TiCl_3 itself. As reported in Ref. 6, the hydrogen desorption property of $\text{LiH} + \text{LiNH}_2$ with 1 mol.% TiCl_3 is superior than $\text{LiH} + \text{LiNH}_2$, the Ti *K*-edge XANES spectrum of $\text{LiH} + \text{LiNH}_2$ with 1 mol.% TiCl_3 is quite different from TiCl_3 itself. Here, the unidentified Ti *K*-edge XANES spectrum of $\text{LiH} + \text{LiNH}_2$ with 1 mol.% TiCl_3 completely agrees with that of $\text{TiCl}_3 \cdot 5\text{NH}_3$. This means the chemical bonding state of TiCl_3 ballmilled with $\text{LiH} + \text{LiNH}_2$ is quite similar with that of $\text{TiCl}_3 \cdot 5\text{NH}_3$. Figure 3 shows TDMS and TG profiles with heating rate $5^\circ\text{C}/\text{min}$ for hydrogen and ammonia gases from the composites of $\text{LiH} + \text{LiNH}_2$ with 1 mol.% TiCl_3 and $\text{LiH} + \text{LiNH}_2$ with 1 mol.% $\text{TiCl}_3 \cdot 5\text{NH}_3$. The hydrogen desorption properties of them are quite similar with each other, which means that $\text{TiCl}_3 \cdot 5\text{NH}_3$ has catalytic effect. Figure 4 shows Ti *K*-edge XANES spectra of $\text{LiH} + \text{LiNH}_2$ with 1 mol.% $\text{TiCl}_3 \cdot n\text{NH}_3$ ($n = 1, 3, 4$, and 5). Those results indicate that the chemical bonding states of $\text{TiCl}_3 \cdot n\text{NH}_3$ are changed to be a particular state by ballmilled with $\text{LiH} + \text{LiNH}_2$. The particular state agrees with

FIG. 2. Ti *K*-edge XANES spectra of $\text{TiCl}_3 \cdot 5\text{NH}_3$, $\text{LiH} + \text{LiNH}_2$ with 1 mol.% TiCl_3 and TiCl_3 itself.

FIG. 3. TDMS and TG profiles with heating rate $5^\circ\text{C}/\text{min}$ for hydrogen and ammonia gases from the composites of $\text{LiH} + \text{LiNH}_2$ with 1 mol.% TiCl_3 and $\text{LiH} + \text{LiNH}_2$ with 1 mol.% $\text{TiCl}_3 \cdot 5\text{NH}_3$.

that of $\text{TiCl}_3 \cdot 5\text{NH}_3$. Here, the mechanism of the catalytic effect should be discussed. As mentioned in the introduction, the ammonia intermediated reaction was suggested for explaining the hydrogen desorption mechanism in this $\text{LiH} + \text{LiNH}_2$ hydrogen storage system, as reported by Ichikawa *et al.*^{4,7} Moreover, TiCl_3 catalyst can not only modify the reaction kinetics of hydrogen desorption, but also suppress the ammonia emission during the hydrogen desorption, as shown in Ref. 3. Kim *et al.* demonstrated that the reaction kinetics determined the product channel in this process without affecting the thermodynamic stability of LiNH_2 (Ref. 12). Therefore, we considered that the role of TiCl_3 catalyst was a kind of ammonia carrier in this system. TiCl_3 would make the reaction kinetics of $\text{LiH} + \text{NH}_3$ faster and then promote the decomposition of LiNH_2 to Li_2NH . Here, it was expected that MgCl_2 could be a good catalyst in this system, because MgCl_2 could absorb NH_3 and form ammine complex just like TiCl_3 (Ref. 13). Figure 5 shows TDMS profiles of the composites of $\text{LiH} + \text{LiNH}_2$ and $\text{LiH} + \text{LiNH}_2$ with 1 mol.% MgCl_2 shown in Fig. 5 (Heating rate: $5^\circ\text{C}/\text{min}$;

FIG. 4. Ti *K*-edge XANES spectra of $\text{LiH} + \text{LiNH}_2$ with 1 mol.% $\text{TiCl}_3 \cdot n\text{NH}_3$ ($n = 1, 3, 4$, and 5).

FIG. 5. TDMS profiles with heating rate 5 °C/min for hydrogen and ammonia gases from the composites of LiH + LiNH₂ and LiH + LiNH₂ with MgCl₂.

Detected gases: H₂, NH₃), two profiles show almost the same desorption property in each composite. Consequently, MgCl₂ does not show any catalytic effect in this Li-N-H system. The results indicate that the existence of titanium element is required to be effective catalysts in this system.

In this paper, we used synchrotron radiation XAS to determine the chemical bonding state of titanium in Li-N-H system. Among them, Ti *K*-edge XANES spectrum of TiCl₃·5NH₃ agreed with that of Ti-compound in Li-N-H system, indicating that the chemical bonding state of titanium, which has catalytic effect on hydrogen desorption property in Li-N-H system, is quite similar with TiCl₃·5NH₃. Then, we considered the catalytic role of TiCl₃ to be a kind of

ammonia carrier, and thus examined the catalytic effect of MgCl₂, which similarly reacted with ammonia to TiCl₃. It was found that the existence of titanium element was required to be effective catalysts, because MgCl₂ could not act as a good catalyst in this system.

The authors would like to acknowledge Dr. T. Honma for performing the XAS measurement in SPring-8. This work was partially supported by the Research Fellowships of the Japan Society for the Promotion of Science for Young Scientists (JSPS), and Hydro Star project of New Energy and Industrial Technology Development Organization (NEDO).

- ¹P. Chen, Z. Xiong, J. Luo, J. Lin, and K. L. Tan, *Nature* **420**, 302 (2002).
- ²P. Chen, Z. Xiong, J. Luo, J. Lin, and K. Tan, *J. Phys. Chem. B* **107**, 10967 (2003).
- ³T. Ichikawa, S. Isobe, N. Hanada, and H. Fujii, *J. Alloys Compd.* **365**, 271 (2004).
- ⁴T. Ichikawa, N. Hanada, S. Isobe, H. Leng, and H. Fujii, *J. Phys. Chem. B* **108**, 7887 (2004).
- ⁵S. Isobe, T. Ichikawa, N. Hanada, H. Leng, M. Fichtner, O. Kircher, and H. Fujii, *J. Alloys Compd.* **404**, 439 (2005).
- ⁶S. Isobe, T. Ichikawa, Y. Kojima, and H. Fujii, *J. Alloys Compd.* **446–447**, 360 (2007).
- ⁷S. Isobe, T. Ichikawa, S. Hino, and H. Fujii, *J. Phys. Chem. B* **109**, 14855 (2005).
- ⁸S. Isobe, T. Ichikawa, H. Leng, H. Fujii, and Y. Kojima, *Thermochim. Acta* **468**, 35 (2008).
- ⁹T. Tsumuraya, T. Shishidou, and T. Oguchi, *Phys. Rev. B* **77**, 235114 (2008).
- ¹⁰D. Nicholls and T. A. Ryan, *J. Inorg. Nucl. Chem.* **39**, 961 (1977).
- ¹¹<http://www.spring8.or.jp/>
- ¹²T. Elmøe, R. Sørensen, U. Quaaed, C. Christensen, J. Nørskov, and T. Johannessen, *J. Mater. Chem.* **15**, 4106 (2005).
- ¹³K. Kim, M. Allendorf, V. Stavila, and D. Sholl, *Phys. Chem. Chem. Phys.* **12**, 9918 (2010).