Title	Evaluation of electron–hole recombination properties of titanium(IV) oxide particles with high photocatalytic activity
Author(s)	Murakami, Shin-Ya; Kominami, Hiroshi; Kera, Yoshiya; Ikeda, Shigeru; Noguchi, Hidenori; Uosaki, Kohei; Ohtani, Bunsho
Citation	Research on Chemical Intermediates, 33(3-5), 285-296 https://doi.org/10.1163/156856707779238612
Issue Date	2007
Doc URL	http://hdl.handle.net/2115/48672
Rights	The original publication is available at springerlink.com
Type	article (author version)
File Information	ResChemInterm33_285.pdf

[Instructions for use](#)

Evaluation of electron-hole recombination properties of titanium(IV) oxide particles of high photocatalytic activity

Shin-ya Murakami^a, Hiroshi Kominami^{a, b, *}, Yoshiya Kera^{a, b}, Shigeru Ikeda^{c, †}, Hidenori Noguchi^d, Kohei Uosaki^d, and Bunsho Ohtani^c

^aDepartment of Applied Chemistry, Faculty of Science and Engineering, Kinki University, Kowakae, Higashiosaka, Osaka 577-8502, Japan. E-mail: hiro@apch.kindai.ac.jp

^bOpen Research Center, Kinki University, Kowakae, Higashiosaka, Osaka 577-8502, Japan.

^cCatalysis Research Center, Hokkaido University, Sapporo 001-0021, Japan.

^dDivision of Chemistry, Graduate School of Science, Hokkaido University, Sapporo 060-0510, Japan.

Electron-hole recombination in nano-sized titanium(IV) oxide (TiO₂) particles of various physical properties, which had been proved to be highly active photocatalysts, was evaluated by quantitative analysis of reduced titanium species (Ti³⁺) that might be formed at crystalline defective sites in TiO₂ particles through photoirradiation in the presence of a hole scavenger under deaerated conditions. These highly active photocatalyst samples were synthesized by hydrothermal crystallization in organic media (HyCOM method) and post-calcination. The Ti³⁺ density decreased with the elevation in calcination temperature (T_c) and linear correlation was observed between the Ti³⁺ density and rate constant for electron-hole recombination evaluated by femtosecond pump-probe diffuse reflection spectroscopy. Reaction rate (R_{Ag}) and the amount of silver ion (Ag⁺) adsorbed on TiO₂ particles ([Ag⁺]_{ads}) were measured in photocatalytic silver metal deposition along with oxygen formation from an aqueous Ag⁺ solution under deaerated conditions, and the slope of the R_{Ag}-[Ag⁺]_{ads} plot was determined. Kinetic investigation of this reaction showed that the reciprocal of the slope approximately related to the ratio of the rates for electron-hole recombination and electron trapping (k_r/k_e

ratio). The k_r/k_e ratio decreased as T_c increased, and logarithm of the k_r/k_e ratio was linearly related with the Ti^{3+} density. ~~These quantitative analyses were easily performed and~~ These two parameters were used as a measure for the recombination properties of TiO_2 photocatalysts of various physical properties.

1. Introduction

The adsorbability, ability of adsorbing chemical substances, of titanium(IV) oxide (TiO_2) is one of the significant factors determining the overall photocatalytic activity because the reaction proceeds via surface reactions between adsorbed substrate(s) and electrons (e^-) and holes (h^+) that are generated by photoabsorption of TiO_2 particles. In most of cases, the amount of substrate(s) adsorbed on the surface of TiO_2 powders can be measured directly and precisely. Another important factor should be property of e^-h^+ recombination, while this had been much difficult to be determined directly. Recent papers have reported that rate of e^-h^+ recombination for several kinds of TiO_2 powders are directly evaluated using femtosecond pump-probe diffuse reflection spectroscopy (PP-DRS) [1-4]. Relatively high spatial and chronological densities of absorbed photons in the pump-probe measurements induces multiple numbers of e^-h^+ in each particle at the same time, i.e., within the lifetime of geminate e^-h^+ , and thereby second-order kinetics can be adopted for the decay of trapped e^- by recombination with h^+ . The second-order rate constants thus obtained might not be applied to the estimation of actual rate of photocatalytic reaction operated under continuous photoirradiation of the lower intensity, in which e^-h^+ is expected to undergo geminate recombination in first-order kinetics. However, the rate constants must reflect the number (correctly speaking, the density within the depth of photoabsorption) of recombination centers, assuming e^-h^+ recombination occurs at those sites, though no structural information could be obtained from the pump-probe measurements.

Crystalline defects are one of the most probable candidates of site for the e^-h^+

recombination. A sol method reported so far for the quantitative estimation of crystalline defects in TiO_2 involves the evaluation of density of reduced species (Ti^{3+}) produced in TiO_2 particles under irradiation in the presence of strong h^+ -trapping agent, i.e., reductants; when an aqueous suspension of TiO_2 containing methanol or triethanolamine is photoirradiated under argon (Ar) atmosphere, the suspension turns blue or blue-grey due to formation of so-called Ti^{3+} species. Almost linear relation between the Ti^{3+} density and the second-order rate constant for the e^- - h^+ recombination obtained by the femtosecond laser spectroscopy suggested that the Ti^{3+} density is a measure of number (or density) of recombination centers in TiO_2 samples [4, 5].

In previous studies, we have shown that nano-crystalline anatase TiO_2 of a large surface area with sufficient crystallinity is obtained by high-temperature hydrolysis of titanium alkoxides with a limited amount of water dissolved in organic solvents and concomitant crystallization (HyCOM) [6,7]. Since HyCOM TiO_2 possesses high thermal stability, physical properties of HyCOM TiO_2 powders can be controlled in a wide range by changing post-calcination temperature (T_c) [7]. [The anatase form of HyCOM \$\text{TiO}_2\$ was preserved even after calcination at 1073 K.](#) The HyCOM TiO_2 powders were used for photocatalytic silver metal (Ag) deposition together with oxygen (O_2) evolution from silver ion (Ag^+) solution under deaerated conditions [8]. An almost linear relation was observed between the rate of photocatalytic reaction (R_{Ag}) and the amount of Ag^+ adsorbed on the TiO_2 ($[\text{Ag}^+]_{\text{ads}}$), which indicates that the rate is proportional to the amount of substrate adsorbed on the particles and thereby the adsorbability is one of decisive factors determining the reaction rate. Another important finding was that the slope of the R_{Ag} - $[\text{Ag}^+]_{\text{ads}}$ plot for HyCOM calcined at 973 K (1.3) was ca. three times larger than that for Degussa P-25 (0.45). Taking that both the adsorbability and the e^- - h^+ recombination rate may determine the overall rate of photocatalytic reaction into consideration, the difference in the recombination properties between the two samples might reflect the observed difference in the slope.

In the present study, HyCOM TiO₂ samples of various physical properties were prepared and their e⁻-h⁺ recombination properties were analyzed by comparing their density of Ti³⁺ produced under deaerated conditions in the presence of h⁺ scavenger and the slope of [Ag⁺]_{ads}-R_{Ag} plot.

2. Experimental

2.1. Sample Preparation.

HyCOM TiO₂ powders were synthesized by a procedure reported previously [7,8]. The as-prepared powders were calcined in a box furnace at various temperatures under a flow of air (30 cm³ min⁻¹); the sample in a combustion boat was heated to the desired temperature at a rate of 10 K min⁻¹, kept at that temperature for 1 h, and then cooled to room temperature. The thus-calcined sample is designated HyCOM(T_c), e.g., HyCOM(973) means a sample calcined at 973 K. Commercial TiO₂ samples, Degussa P-25 and Ishihara ST-01, were used as a reference in most of the experiments because these are known to be active photocatalysts.

Characterization of TiO₂ powders was performed in the same ways reported in the previous papers [7, 8].

2.2 Quantitative analysis of Ti³⁺ density

The amount of reduced species of TiO₂, Ti³⁺, was measured quantitatively using methyl viologen (MV²⁺) as a final electron acceptor as follows [5]. A sample TiO₂ powder (50 mg) was suspended in an aqueous triethanolamine solution (10%; 5 cm³) and irradiated by a 400-W high-pressure mercury arc (> 300 nm) under Ar for 24 h. A deaerated aqueous solution containing 62.5 μmol of MV²⁺ was added to the photoirradiated reaction mixture. The resulting pale blue suspension containing the reduced form of MV²⁺, methyl viologen cation radical (MV^{•+}) was filtered and the supernatant solution was loaded into a quartz cell (light path length 1 mm). These operations were performed in an Ar purged glovebox

(UN-650F, United Instruments) to avoid fading of Ti^{3+} and/or MV^{2+} by O_2 . From the absorbance of solution at around 600 nm measured by a sensor array photometer (LASA 20, TOA DKK Ltd.) and reported value of the absorption coefficient of $13700 \text{ dm}^3 \text{ mol}^{-1} \text{ cm}^{-1}$ at 606 nm [9], the molar amount of Ti^{3+} was estimated on the assumption that equimolar amount of Ti^{3+} and MV^{2+} react to produce MV^{2+} . On the basis of pH-dependence of electron transfer from the photoreduced several (anatase and rutile) TiO_2 samples to MV^{2+} , it has been concluded that the electronic energy level of so-called Ti^{3+} species is located just below the bottom of conduction band, i.e., the energy level of reduced species in TiO_2 seemed are not so different each other.⁵ The linear correlation of this Ti^{3+} density and density of defective sites, leading to electron-hole recombination, in TiO_2 has been proved in our previous paper⁵ and will be discussed in the section of Results and Discussion.

2.3 Measurement of $[\text{Ag}^+]_{\text{ads}}$ and R_{Ag} in silver system

The amount of surface-adsorbed Ag^+ under conditions similar to the photocatalytic reaction was measured in the dark by inductively coupled plasma (ICP) emission spectroscopy (Shimadzu ICPS-1000III) taking the difference in Ag^+ concentration before and after addition of TiO_2 into silver sulfate (Ag_2SO_4) solutions of various concentrations.

TiO_2 powder (50 mg) was suspended in $0.5\text{-}25 \text{ mmol dm}^{-3}$ Ag_2SO_4 aqueous solution (5.0 cm^3) in a glass tube, purged with Ar for at least 30 min, and then sealed off with a rubber stopper. The suspension was photoirradiated at 298 K in a way similar to that for the Ti^{3+} -density measurement. After the irradiation, amount of evolved O_2 was measured by a Shimadzu GC-8A gas chromatograph. Ratio of Ag/O_2 was determined to be almost 4, indicating that the reaction ($4\text{Ag}^+ + 2\text{OH}^- \rightarrow 4\text{Ag} + \text{O}_2 + 2\text{H}^+$) occurred with stoichiometry. The catalyst was recovered by centrifugation, washed repeatedly with distilled water, and dried overnight at 333 K. The photodeposited Ag was dissolved with concentrated HNO_3 (1.0 cm^3) and measured by ICP emission spectroscopy.

2. 4 Determination of recombination rate constant by PP-DRS

Second-order rate constants for e^-h^+ recombination in HyCOM TiO_2 samples were evaluated by PP-DRS using a femtosecond laser system. The details have been reported [4, 5] and briefly described below. An argon-ion-laser pumped Ti:sapphire laser (mode-locked; Spectra-Physics, Tsunami: 3960-L-2S) was used with a regenerative amplifier (Quantronix, 4812RGA/4823S/C) synchronously pumped by a mode-locked YLF laser (Quantronix, 527DP-H) to generate ca 100 fs pulses. The pulses were split into two almost identical beams to pump two optical parametric generation (OPG) and optical parametric amplification (OPA) systems (Light Conversion, TOPAS). One of the two output beams of 620 nm was used as a probe beam (ca. 1.5 mJ pulse⁻¹) and the other was used as pump beam (0.03-0.1 mJ pulse⁻¹) after frequency doubling by a BBO crystal. These beams were collinearly focused and overlapped at the sample of dry TiO_2 powder and resulting diffuse reflected probe beam was detected by a photodiode and accumulated as absorption ($1 - R/R_0$, where R and R_0 represent the intensity at a given delay and that in the absence of a pump pulse, respectively). The procedure of kinetic data analyses is described in the discussion section. Unfortunately, data for a part of HyCOM samples, which had been calcined at relatively higher temperature, could be obtained, since small amount of residual organic species originating from organic solvent and starting materials used in the synthesis produced long-lived colored species during PP-DRS measurements, which obscured the actual reflectance change due to their accumulation in the sample.

3. Kinetics model for photocatalytic Ag deposition

Prior to a discussion on the slope in $R_{Ag}-[Ag^+]_{ads}$ plot, a model used for photocatalytic reactions in aqueous TiO_2 suspensions containing Ag^+ is discussed. The model consists of recombination and trapping of e^-h^+ generated in the TiO_2 particles by photoirradiation as

shown in eqs. 1-3.

In a system containing no strong electron donors (h^+ scavenger), h^+ trapping by surface-adsorbed H_2O and/or surface hydroxyls are practically negligible [14,15], and the photocatalytic reactions shown here proceed via e^- -trapping by a surface-adsorbed Ag^+ . Under these conditions, rate of $\text{e}^- \cdot \text{h}^+$ accumulation is assumed to be zero by steady-state approximation as follows:

$$d[\text{e}^- \cdot \text{h}^+]/dt = I\phi - k_r[\text{e}^- \cdot \text{h}^+] - k_e C_e[\text{e}^- \cdot \text{h}^+] = 0 \quad (4)$$

where I is the flux of incident photons, ϕ is an efficiency of $\text{e}^- \cdot \text{h}^+$ generation with TiO_2 photoabsorption, C_e is the surface concentration of adsorbed Ag^+ , and k_e and k_r are the rate constants for e^- -trapping by surface-adsorbed Ag^+ and recombination, respectively. An absorption coefficient of anatase TiO_2 in the wavelength range of main ultraviolet emission from a mercury arc seems to be enough large to assume all the photons are absorbed and we assumed that the term $I\phi$ remained constant independent of the kinds of TiO_2 samples. The steady-state concentration $[\text{e}^- \cdot \text{h}^+]$ is obtained from eq. 4 as follows:

$$[\text{e}^- \cdot \text{h}^+] = I\phi / (k_r + k_e C_e) \quad (5)$$

The rate of Ag metal deposition (R_{Ag}) corresponding to the overall rate of this reaction system is derived as

$$R_{\text{Ag}} = k_e C_e [\text{e}^- \cdot \text{h}^+] = I\phi \cdot k_e C_e / (k_r + k_e C_e) \quad (6)$$

Assuming that the $\text{e}^- \cdot \text{h}^+$ recombination is much faster than e^- -trapping ($k_r \gg k_e C_e$), R_{Ag} can be simplified as follows.

$$R_{\text{Ag}} = I\phi \cdot k_e C_e / (k_r + k_e C_e) \cong \alpha (k_e / k_r) [\text{Ag}^+]_{\text{ads}} \quad (7)$$

where $I\phi$ and C_e are replaced by α and $[\text{Ag}^+]_{\text{ads}}$ (surface concentration of adsorbed Ag^+).

4. Results and discussion

4.1 The Ti^{3+} density of HyCOM TiO_2

The effect of calcination temperature on the physical properties and photocatalytic activity of HyCOM TiO_2 powders has been reported in the previous papers [8, 10]. The crystallite sizes of HyCOM samples gradually increased with elevating T_c whereas the BET surface area decreased, showing crystal growth and sintering of the anatase crystallites upon calcination (Figure 1). Photocatalytic activity, R_{Ag} , increased with the T_c increase, even though $[\text{Ag}^+]_{\text{ads}}$ decreased along with the decrease in S_{BET} (data not shown), suggesting that another factor enhanced R_{Ag} . [line break]

The Ti^{3+} density decreased along with T_c . Figure 2 shows the plot of the Ti^{3+} density as function of their S_{BET} of HyCOM TiO_2 samples. The decrease in the Ti^{3+} density shows that the amount of the surface defects was reduced upon calcination at higher temperature due to a so-called annealing effect. A noteworthy point is the liner relationship shown in Figure 1(a), i.e., appreciable Ti^{3+} density in samples of relatively small surface area obtained by the higher-temperature calcination, suggested that the present method could measure defects in the bulk, as well as those on the surface. The femtosecond PP-DRS measurement revealed that rate of e^-h^+ recombination for HyCOM TiO_2 decreased with elevation in T_c [2]. In the PP-DRS measurements, the decay of surface-trapped electrons by the recombination with positive holes could be observed; second-order kinetics could reproduce the decay curves and therefore we could calculate the second-order rate constant, k_r , on some assumptions.² Figure 3 shows the plot of the Ti^{3+} density and k_r from PP-DRS, suggesting a proportional relation between them. As has been well known, the unit of second-order rate constants contains the inversed concentration of intended chemical species. Since the photoexcitation and recombination occur in the solid materials, we determined k_r in the unit of $\text{cm}^3 \text{ps}^{-1}$. The Ti^{3+} density provides an insight into the defective state of TiO_2 and k_r [gives us structural information in TiO_2 , i.e., defects and/or anion vacancy, and k_r] from PP-DRS reflects rate of

the e^-h^+ recombination. Therefore, the proportionality between them seems reasonable. These results support that calcination improves the crystallinity and reduces crystal defects acting as a recombination centers for e^-h^+ , resulting in smaller probability of the recombination. Hereafter, the Ti^{3+} density determined by the present method is used as a measure of the recombination property of TiO_2 powders. Relationship between R_{Ag} and the Ti^{3+} density of HyCOM samples is shown in Figure 4. R_{Ag} increased with decreasing the Ti^{3+} density, indicating that the recombination property of TiO_2 powders is more dominant than the adsorbability for Ag^+ over the reaction rate for the present Ag deposition and O_2 evolution. The importance of the crystallinity of photocatalyst or high-temperature calcination in photocatalytic O_2 evolution systems has been reported by many researchers [11-13].

4.2 Evaluation of recombination property through kinetic analysis; a R_{Ag} - $[Ag^+]_{ads}$ plot

According to eq. 6, R_{Ag} should be proportional to $[Ag^+]_{ads}$. In fact, a linear relation was observed for each TiO_2 sample between R_{Ag} and $[Ag^+]_{ads}$ ~~in the multi-point plot~~ as shown in Figure 5 when $[Ag^+]_{ads}$ was intentionally changed using several solutions of different initial Ag^+ concentration. The slopes of straight lines correspond to $\alpha \cdot k_e/k_r$ and those for HyCOM(973) and P-25 in this ~~multi-point~~ plot were 1.26 and 0.45, respectively. In order to discuss the recombination property of TiO_2 , the reciprocal of the slope, i.e., $k_r/(\alpha k_e)$ will be used hereafter as relative k_r/k_e ratio, since this ratio is calculated by normalization of the reaction with $[Ag^+]_{ads}$ to exclude the dependence of the rate on $[Ag^+]_{ads}$. It should be noticed that the k_r/k_e ratio is relative because absolute value of α ($= I\phi$) was not calculated and assumed to be constant not depending on the kind of TiO_2 samples.

~~Figure 4(b) shows plots of R_{Ag} and $[Ag^+]_{ads}$ for the experiment using a Ag_2SO_4 solution containing $50 \text{ mmol dm}^{-3} Ag^+$, extracted from the plot of Figure 4(a).~~ The slopes of the straight lines connecting the plot obtained from the experiment using a Ag_2SO_4 solution

containing $50 \text{ mmol dm}^{-3} \text{ Ag}^+$ and the origin for HyCOM(973) and P-25 were 1.25 and 0.41, respectively, and are almost identical to those (1.26 and 0.45, respectively) obtained by multi-point plot (Figure 5). Therefore, the k_r/k_e ratios for the rest of samples were calculated, for convenience, using the data of R_{Ag} and $[\text{Ag}^+]_{\text{ads}}$ when the experiments were performed using a $50 \text{ mmol dm}^{-3} \text{ Ag}^+$ solution.

Figure 6 shows plots of k_r/k_e ratio against S_{BET} . The k_r/k_e ratio diminished with decreasing S_{BET} similar to the behavior of the Ti^{3+} density (Figure 2); although the relation between the k_r/k_e ratio and the Ti^{3+} density is ~~seems not strictly to be~~ proportional, it is clear that there is a positive correlation between them (Figure 7). ~~At present, we have no information on the dependence of k_e , reactivity of e^- with Ag^+ , on the structure of TiO_2 photocatalysts and if we assume k_e of reactivity large when calcined at higher temperature, i.e., small S_{BET} , due to, for example, removal of surface hydroxyls as an insulator layer, the plots of k_r/k_e ratio and Ti^{3+} density become less deviated from a linear line.~~ Another factor worth noting is probable over estimation of k_r/k_e ratio for the samples adsorbing relatively large amount of Ag^+ . To introduce eq. 6, we assumed that $k_r \gg k_e C_e$ and a linear relationship between R_{Ag} and $[\text{Ag}^+]_{\text{ads}}$ when was observed except at very low concentrations. However, a tendency of downward deviation is seen, especially in the plots for P-25, suggesting that the slope has been underestimated for the samples of larger $[\text{Ag}^+]_{\text{ads}}$, i.e., those of larger S_{BET} obtained by calcination at the lower temperature. These results show that the k_r/k_e ratio can be used as the indicator of recombination property as well as the Ti^{3+} density.

The present evaluation methods were applied for a commercial TiO_2 , Ishihara ST-01, having large BET surface area ($297 \text{ m}^2 \text{ g}^{-1}$). Although the Ti^{3+} density was not measured, the extremely large k_r/k_e ratio (97.8) for the present photocatalytic reaction suggests a high recombination efficiency for ST-01 TiO_2 . Calcination of ST-01 at 973 K decreased the S_{BET} to $39 \text{ m}^2 \text{ g}^{-1}$, which was almost identical to that of HyCOM(923) ($39 \text{ m}^2 \text{ g}^{-1}$). However, the Ti^{3+} density and the k_r/k_e ratio for ST-01(973) ($50 \text{ } \mu\text{mol g}^{-1}$ and 8.1) were 1.6 and 6.6 times

larger than those for HyCOM (973) ($32 \mu\text{mol g}^{-1}$ and 1.23), respectively. The result indicates that density of defective sites in ST-01 is larger than that for HyCOM comparing the samples of similar S_{BET} and that Ti^{3+} density and k_r/k_e ratio strongly depend on the preparation conditions as well as calcination conditions.

5. Conclusions

The actual rate of photocatalytic Ag deposition and O_2 formation was almost proportional to the surface concentration of substrate ($[\text{Ag}^+]_{\text{ads}}$) but when the effect of such substrate concentration was excluded, another effect relating to the e^- - h^+ recombination could be discussed. On the basis of this kinetic analysis, we have determined the k_r/k_e ratio and compared with the Ti^{3+} densities for TiO_2 samples of various physical properties. It was found that these parameters were correlated with each other and also with k_r evaluated by femtosecond PP-DRS measurement. Thus, the recombination properties of TiO_2 powders can be conveniently evaluated by two novel methods and it is concluded that the photocatalytic activity should be discussed by considering the effects of e^- - h^+ recombination.

Acknowledgement

This work was partly supported by a Grant-in-Aid for Scientific Research on Priority Areas (417) from the Ministry of Education, Culture, Science, and Technology (MEXT) of Japan. We thank Nippon Aerosil and Ishihara Sangyo for their supply of Degussa P-25 and ST-01 powders, respectively.

References

1. D. P. Colombo, Jr, and R. M Bowman, *J. Phys. Chem.* 1995, **99**, 11752.
2. B. Ohtani, R. M Bowman, D. P. Colombo, Jr, H. Kominami, H. Noguchi, and K. Uosaki, *Chem. Lett.* 1998, 579.
3. A. Furube, T. Asahi, H. Masuhara, H. Yamashita and M. Anpo, *J. Phys. Chem.* 1999, **103**, 3120.
4. S. Ikeda, N. Sugiyama, B. Pal, G. Marci, L. Palmisano, H. Noguchi, K Uosaki and B. Ohtani, *Phys. Chem. Chem. Phys.* 2001, **3**, 267.
5. S. Ikeda, N. Sugiyama, S.-y. Murakami, H. Kominami, K. Kera, H. Noguchi, K. Uosaki, T. Torimoto, B. Ohtani, *Phys. Chem. Chem. Phys.*, 2003, **5**, 778.
6. H. Kominami, Y. Takada, H. Yamagiwa, Y. Kera, M. Inoue and T. Inui, *J. Mater. Sci. Lett.* 1996, **15**, 197.
7. H. Kominami, M. Kohno, Y. Takada, M. Inoue, T. Inui and Y. Kera, *Ind. Eng. Chem. Res.* 1999, **38**, 3925.
8. H. Kominami, S.-y. Murakami, Y. Kera and B. Ohtani, *Catal. Lett.* 1998, **56**, 125.
9. T. Watanabe and K. Honda, *J. Phys. Chem.* 1982, **86**, 2617.
10. H. Kominami, S.-y. Murakami, J.-i. Kato, Y. Kera, B. Ohtani, *J. Phys. Chem. B*, 2002, **106**, 10501.
11. H. Kominami, S.-y. Murakami, M. Kohno, Y. Kera, K. Okada, B. Ohtani, *Phys., Chem. Chem. Phys.*, 2001, **3**, 4102.
12. H. Kominami, K.-i. Yabutani, T. Yamamoto, Y. Kera and B. Ohtani, *J. Mater. Chem.*, 2001, **11**, 3222
13. Y. Oosawa, M. **Graetzel**, *J. Chem. Soc., Faraday Trans. 1* 1988, **84**, 197.
14. B. Ohtani, Y. Okugawa, S.-i. Nishimoto, and T. Kagiya, *J. Phys. Chem.* 1987, **91**, 3350.
15. B. Ohtani, M. Kakimoto, S.-i. Nishimoto, and T. Kagiya, *J. Phys. Chem.* 1988, **92**, 5773.

Foot note

†Present address: Research Center for Solar Energy Chemistry, Osaka University

Figure captions

Figure 1 BET surface area (S_{BET}) (circle) and crystallite size (square) of ~~of~~ HyCOM samples calcined at various temperatures (T_c)

Figure 2 The plots of Ti^{3+} density of HyCOM samples calcined at various temperatures as a function of their BET surface area (S_{BET}).

Figure 3 Correlation between k_r from PP-DRS and Ti^{3+} density of HyCOM samples.

Figure 4 Rate of photocatalytic Ag deposition (R_{Ag}) as a function of Ti^{3+} density of HyCOM samples.

Figure 5 Rate of photocatalytic Ag deposition (R_{Ag}) as functions of amount of adsorbed Ag^+ ($[\text{Ag}^+]_{\text{ads}}$) on HyCOM-A(973) (open) and P-25 (closed) ~~in the multi-point plot.~~

Figure 6 The plots of k_r/k_e ratio of HyCOM samples calcined at various temperatures as a function of their BET surface area (S_{BET}).

Figure 7 Correlation between Ti^{3+} density and logarithm of k_r/k_e ratio of HyCOM samples calcined at various temperatures.

Murakami et al. Fig. 1

Murakami et al. Fig. 2

Murakami et al. Fig. 3

Murakami et al., Fig. 4

Murakami et al Fig. 5

Murakami et al. Fig. 6

Murakami et al., Fig. 7