Title	Photoelectrochemical Characteristics of Semiconductor-Metal/SPE/Metal Cells
Author(s)	Uosaki, Kohei; Kita, Hideaki
Citation	Journal of The Electrochemical Society, 130(11), 2179-2184 https://doi.org/10.1149/1.2119548
Issue Date	1983
Doc URL	http://hdl.handle.net/2115/50256
Rights	© The Electrochemical Society, Inc. 1983. All rights reserved. Except as provided under U.S. copyright law, this work may not be reproduced, resold, distributed, or modified without the express permission of The Electrochemical Society (ECS). The archival version of this work was published in J. Electrochem. Soc. 1983 volume 130, issue 11, 2179-2184.
Type	article
File Information	JES130-11_2179-2184.pdf

[Instructions for use](#)

the society for solid-state
and electrochemical
science and technology

Journal of The Electrochemical Society

Photoelectrochemical Characteristics of Semiconductor–Metal/SPE/Metal Cells

Kohei Uosaki and Hideaki Kita

J. Electrochem. Soc. 1983, Volume 130, Issue 11, Pages 2179-2184.
doi: 10.1149/1.2119548

**Email alerting
service**

Receive free email alerts when new articles cite this article - sign up in the box at the top right corner of the article or [click here](#)

To subscribe to *Journal of The Electrochemical Society* go to:
<http://jes.ecsdl.org/subscriptions>

Manuscript submitted Dec. 27, 1982; revised manuscript received May 20, 1983.

REFERENCES

1. S. Menezes, A. Heller, and B. Miller, *This Journal*, **127**, 1268 (1980).
2. Y. Nakato, T. Ohnishi, and H. Tsubomura, *Chem. Lett.*, 883 (1975).
3. Y. Nakato, K. Abe, and H. Tsubomura, *Ber. Bunsenges. Phys. Chem.*, **80**, 1002 (1976).
4. R. H. Wilson, L. A. Harris, and M. E. Gerstner, *This Journal*, **124**, 1233 (1977).
5. L. A. Harris, M. E. Gerstner, and R. H. Wilson, *ibid.*, **124**, 1511 (1977).
6. P. A. Kohl, S. N. Franck, and A. J. Bard, *ibid.*, **124**, 225 (1977).
7. M. Tomkiewicz and J. M. Woodall, *ibid.*, **124**, 1436 (1977).
8. H. P. Maruska and A. K. Ghosh, *Solar Energy Mater.*, **1**, 411 (1979).
9. D. Elliott, D. L. Zellmer, and H. A. Laitinen, *This Journal*, **117**, 1343 (1970).
10. J. Kane, H. P. Schweizer, and W. Kern, *ibid.*, **123**, 270 (1976).
11. F. Möllers and R. Memming, *Ber. Bunsenges. Phys. Chem.*, **76**, 469 (1972).
12. T. A. Chertykorteve, D. M. Skob, and V. I. Veselovskii, *Elektrokhimiya*, **14**, 1260 (1978).
13. A. K. Ghosh, C. Fishman, and T. Feng, *J. Appl. Phys.*, **49**, 3490 (1978).
14. F. Decker, J. Melsheimer, and H. Gerischer, *Isr. J. Chem.*, **22**, 195 (1982).
15. N. Tarr and D. Pulfrey, *IEEE Trans. Electron Devices*, **ed-27**, 771 (1980).
16. H. J. Hovel, "Semiconductor and Semimetals, Vol. 11: Solar Cells," Academic Press, New York (1975).
17. K. J. Vetter, "Elektrochemische Kinetik," Springer-Verlag, Berlin-Göttingen-Heidelberg (1961).
18. A. J. Bard and L. R. Faulkner, "Electrochemical Methods," J. Wiley & Sons, New York (1980).
19. V. G. Levich, "Physico-Chemical Hydrodynamics," Prentice-Hall, Englewood Cliffs, NJ (1962).
20. W. Badawy, F. Decker, and K. Doblhofer, *Solar Energy Mater.*, **8**, 363 (1983).
21. B. Miller, S. Menezes, and A. Heller, *This Journal*, **126**, 1483 (1979).
22. W. E. Pinson, *Nature*, **269**, 316 (1977).
23. S. J. Fonash, "Solar Cell Device Physics," Academic Press, New York (1981).
24. B. Bressel and H. Gerischer, *Ber. Bunsenges. Phys. Chem.*, In press.
25. E. L. Goldstein and M. R. Van de Mark, *Electrochim. Acta*, **27**, 1079 (1982).

Photoelectrochemical Characteristics of Semiconductor-Metal/SPE/Metal Cells

Kohei Uosaki* and Hideaki Kita

Department of Chemistry, Faculty of Science, Hokkaido University, Sapporo 060, Japan

ABSTRACT

A solid polymer electrolyte (SPE) photoelectrochemical cell, semiconductor-metal/SPE/Pt, is proposed as a new device to convert solar energy to electrical and/or chemical energy. The photoelectrochemical characteristics of TiO_2 -Pt/SPE and TiO_2 -Au/SPE were studied as well as those of the whole cell systems TiO_2 -Pt/SPE/Pt and TiO_2 -Au/SPE/Pt. By above bandgap energy illumination of the TiO_2 -metal side, negative photovoltage and anodic photocurrent were observed, as reported at TiO_2 electrodes. In whole cell systems, i.e., TiO_2 -Pt/SPE/Pt and TiO_2 -Au/SPE/Pt, the conversion of light to electricity was achieved without using electrolyte solution.

The conversion of solar energy to chemical and/or electrical energy by photoelectrochemical (1, 2) and photocatalytic (3, 4) methods has been studied very extensively. Both methods have advantages and disadvantages. In the photoelectrochemical method, the products can be obtained separately. That is particularly useful when water is decomposed photoelectrochemically. Electricity can be generated, but the presence of electrolyte is essential in this system. On the other hand, the photocatalytic method does not require electrolyte, but the products, e.g., oxygen and hydrogen, are generated in the same compartment. Thus an extra separation process is required and no electricity can be obtained.

The advantages of a solid polymer electrolyte (SPE) in water electrolysis (5), organic electrochemistry (6), and fuel cells (7) have been well recognized and the application of SPE to photoelectrochemical cells should also be advantageous. Recently, Skotheim and Lundström have constructed all-solid photoelectrochemical cells using poly(ethylene oxide) as the SPE (8).

Here, we propose a new type of SPE photoelectrochemical cell that contains layers of a semiconductor as a sensitizer, a metal, an ion exchange membrane as an SPE, and a metal. We report the photoelectro-

chemical characteristics of TiO_2 -Pt/SPE and TiO_2 -Au/SPE as well as those of TiO_2 -Pt/SPE/Pt and TiO_2 -Au/SPE/Pt. By using this type of cell, even electrolyte-free photoelectrolysis of water may be possible, as shown in Fig. 1.

Experimental

Nafion 315 perfluorinated cation exchange membrane was used as an SPE material. The deposition of metal on the SPE was carried out by the electrolytic plating method suggested by Takenaka and Torikai (9, 10). After a swelling treatment in boiling water for 30 min, the membrane was set as a separator in the cell shown in Fig. 2. The upper compartment was filled with a metal salt (H_2PtCl_6 or HAuCl_4) solution and the other compartment was filled with an NaBH_4 (1M)- NaOH (1M) solution. NaBH_4 diffused through the membrane and reduced the metal salt to the metal on the membrane surface at the upper compartment. After several hours, the solution of the upper compartment became colorless, suggesting most of the salt was reduced, and the surface of the membrane at the upper compartment became black. The amount of metal deposited was 4-12 $\text{mg} \cdot \text{cm}^{-2}$. Hereafter this configuration is called Pt/SPE or Au/SPE. In some cases, after washing the membrane thoroughly with distilled water, the other side of the membrane was also coated with a metal

* Electrochemical Society Active Member.

Key words: energy conversion, semiconductor, photoelectrochemistry, solid polymer electrolyte.

Fig. 1. Schematic diagram of proposed SPE photoelectrochemical cell.

in the same way. At least one side of the membrane was coated with platinum. This configuration is called Pt/SPE/Pt or Au/SPE/Pt. The side coated with either Pt or Au will be called side 1 and the side always coated with Pt will be called side 2 in the rest of this paper. Side 1 was further coated with TiO_2 by drops of a TiO_2 (Merck, Anatase) powder suspension (2g TiO_2 /25 cm^3 distilled water), following the method used by Davidson *et al.* for the coating of Pt wire with TiO_2 (11). The membrane was then dried in an oven at 70°C for 15–20 hr. After this treatment, most of the TiO_2 powder came off but some remained on the metal. This configuration is

Fig. 2. Schematic diagram of the cell used for the electroless plating of SPE. Solution (A) is a metal salt solution and solution (B) is an $\text{NaBH}_4(1\text{M})$ - $\text{NaOH}(1\text{M})$ solution.

called TiO_2 -Au/SPE, TiO_2 -Pt/SPE, TiO_2 -Au/SPE/Pt, or TiO_2 -Pt/SPE/Pt.

The (photo)electrochemical characteristics of TiO_2 -Pt/SPE and TiO_2 -Au/SPE electrodes were studied in the cell shown in Fig. 3.

A potentiostat (Nikko Keisoku, NPGS-301S) was used to control the electrode potential. A platinum wire and a silver/silver chloride electrode were used as a counter and a reference electrode, respectively. The working electrode, TiO_2 -Pt or TiO_2 -Au, is disk shaped and 2.5 cm in diameter. A gold ring was used as a current collector.

The photoelectrochemical characteristics of whole cells, TiO_2 -Pt/SPE/Pt and TiO_2 -Au/SPE/Pt, were studied in a cell shown in Fig. 4.

Results

The cyclic voltammograms of Pt/SPE and TiO_2 -Pt/SPE in 0.5M H_2SO_4 are shown in Fig. 5. It is clear from the figure that the electrochemical characteristics of Pt/SPE are similar to those of a Pt electrode. The real surface area of Pt was calculated as ca. 1125 cm^2 , i.e., the roughness factor was ca. 230, from the area of the oxide reduction peak. By comparing the

Fig. 3. A cell used for the measurements of (photo)electrochemical characteristics of TiO_2 -Pt/SPE and TiO_2 -Au/SPE electrodes.

Fig. 4. A cell used for the measurements of photoelectrochemical characteristics of TiO_2 -Pt/SPE/Pt and TiO_2 -Au/SPE/Pt.

Fig. 5. Cyclic voltammograms of Pt/SPE (—) and TiO_2 -Pt/SPE (---) in 0.5M H_2SO_4 . Sweep rate was $30 \text{ mV} \cdot \text{sec}^{-1}$.

area of the oxide reduction peak in the cyclic voltammogram of TiO_2 -Pt/SPE with that of Pt/SPE, the coverage of the Pt surface by TiO_2 was calculated as ca. 35%, i.e., a significant portion of Pt was still exposed, as observed with TiO_2 -coated Pt wire. The cyclic voltammograms of TiO_2 -Au/SPE in 0.5M H_2SO_4 before and after photoelectrochemical measurements are shown in Fig. 6. From the cyclic voltammogram of Au/SPE which is not shown here, the real area of Au was calculated as ca. 100 cm^2 , i.e., roughness factor was ca. 20. By comparing the cyclic voltammogram of Au/SPE and that of TiO_2 -Au/SPE, the coverage of Au surface by TiO_2 was calculated as 75%. The cyclic voltammogram of TiO_2 -Au/SPE after the photoelectrochemical measurements shows that the nature of gold on the SPE changed and indeed a change in the appearance of the membrane surface was observed. Thus a better method for depositing Au on the SPE should be developed. When the TiO_2 -metal side was illuminated by a 500W Xe lamp through an infrared absorbing filter, a negative photovoltage was developed, as observed with Pt wire coated with TiO_2 , and is shown in Fig. 7. The time course of photovoltage of TiO_2 -Pt illuminated by 360 nm monochromatic light is also shown in Fig. 7. The photovoltage was small and the time constant was large when the electrode was illuminated with monochromatic light. The wavelength dependence of the photovoltage is shown in Fig. 8 and is similar to

Fig. 6. Cyclic voltammograms of TiO_2 -Au/SPE in 0.5M H_2SO_4 before (—) and after (---) photoelectrochemical measurements. Sweep rate was $100 \text{ mV} \cdot \text{sec}^{-1}$.

Fig. 7. Photoeffect on the potential of TiO_2 -Pt on SPE in 1M NaOH illuminated by 500W Xe lamp with infrared absorbing filter (—) and by 360 nm monochromatic light (---).

that of Pt/ TiO_2 powders (12). These results support the view that the photoresponse was due to absorption of light by TiO_2 . Anodic photocurrents were also observed potentiostatically. A typical photocurrent-time relation at TiO_2 -Pt/SPE is shown in Fig. 9.

The photocurrent-potential relations at TiO_2 -Pt/SPE and TiO_2 -Au/SPE are shown in Fig. 10 and are quite different from those of TiO_2 electrodes. It is clear that the photocurrents were strongly affected by the underlying metals. There are peaks in the relations and the peak potentials coincide with those at which oxides of the metals are formed.

The results reported so far are all for TiO_2 -Pt/SPE and for TiO_2 -Au/SPE and not those for whole cell systems, i.e., TiO_2 -Pt/SPE/Pt or TiO_2 -Au/SPE/Pt. For the whole cell systems, both compartments of the cell shown in Fig. 4 were filled with distilled water, not an electrolyte solution, and then the water in the Pt side (side 2) of the compartment was drained off. This compartment was then filled with N_2 gas. When the TiO_2 -metal side (side 1) and the Pt side (side 2) were connected by an electrometer and the TiO_2 -metal side was illuminated by light, the potential of TiO_2 -metal became more negative than that of Pt. When the two sides were connected with a resistor of finite resistance, a photocurrent (TiO_2 -metal as an anode and Pt as a cathode) was observed. Thus the conversion of light to electricity without electrolyte solution was achieved. A typical time course of the

Fig. 8. Photovoltage-wavelength dependence of TiO_2 -Pt/SPE in 1M NaOH. The photovoltages are not calibrated for photon numbers.

Fig. 9. A typical photocurrent-time relation of $\text{TiO}_2\text{-Pt/SPE}$ in 1M NaOH at 0.5V (vs. Ag/AgCl).

photocurrent is shown in Fig. 11. The larger the resistance, the larger the time constant of this process. The wavelength dependence of the photocurrent, which is shown in Fig. 12, again confirms that photocurrents were due to the absorption of light by TiO_2 . After the measurements, TiO_2 remained on the metal surface as shown by the reflection spectrum in Fig. 13.

The cell performance of $\text{TiO}_2\text{-Pt/SPE/Pt}$ cell was determined by changing the resistor which connected the $\text{TiO}_2\text{-metal}$ side to the Pt side and is shown in Fig. 14. The characteristics of the cells were relatively poor compared with those of TiO_2 electrodes (13).

The quantitative detection of the reaction product by using a membrane polarographic detector (MPD) (14) was tried but failed because of too low an efficiency.

By adding ethanol to the water of the $\text{TiO}_2\text{-metal}$ compartment, the photocurrent increased by several times but by not as much as observed in photocatalytic systems (15, 16).

Discussion

When the $\text{TiO}_2\text{-metal}$ side (side 1) of the $\text{TiO}_2\text{-metal/SPE}$ was illuminated by light of greater than bandgap energy, electron-hole pairs were generated

Fig. 10. Photocurrent-potential relations of $\text{TiO}_2\text{-Pt/SPE}$ in 1M NaOH (— Δ —) and in 0.5M H_2SO_4 (— $\times$ —) and of $\text{TiO}_2\text{-Au/SPE}$ in 0.5M H_2SO_4 (— $\circ$ —).

Fig. 11. A typical time course of photocurrent of $\text{H}_2\text{O/TiO}_2\text{-Pt/SPE/Pt/N}_2$ cell when $\text{H}_2\text{O/TiO}_2\text{-Pt}$ side was illuminated by 360 nm monochromatic light.

where p^+ and e^- are the hole and electrons generated at side 1 by the light. In analogy to ordinary photoelectrochemical systems, the holes oxidized water

When the circuit was open, the electrons accumulated on side 1, the Fermi level of $\text{TiO}_2\text{-metal}$ was raised and the potential of $\text{TiO}_2\text{-metal}$ became negative by the illumination as shown in Fig. 7. In the potentiostatic condition, electrons could be removed from $\text{TiO}_2\text{-metal}$ through an external wire and anodic photocurrent was observed, as shown in Fig. 9. The reason for the effect of the metal substrate on the photocurrent potential is not clear, but the coincidence of photocurrent peak potential with oxide formation potential suggests that change of the po-

Fig. 12. Photocurrent-wavelength dependence of $\text{H}_2\text{O/TiO}_2\text{-Pt/SPE/Pt/N}_2$ cell.

Fig. 13. Reflection spectrum of $\text{TiO}_2\text{-Pt/SPE}$ after the photoelectrochemical measurements.

tential distribution at $\text{TiO}_2\text{-metal(oxide)}$ interface has some effect on the relations. The relatively large exposure of metal substrate is a complicating factor.

In whole cell systems, *i.e.*, TiO-Au/SPE/Pt and $\text{TiO}_2\text{-Pt/SPE/Pt}$, reactions [1] and [2] also occurred and, at open circuit, electrons accumulated at the $\text{TiO}_2\text{-metal}$ side (side 1) and the potential of $\text{TiO}_2\text{-metal}$ became more negative than that of Pt (side 2). When the $\text{TiO}_2\text{-metal}$ and Pt were connected with a resistor of finite resistance, electrons flowed through the resistance and H^+ moved through the SPE to Pt of side 2 as confirmed by anodic photocurrent. One of the possible reactions at side 2 was the hydrogen evolution reaction

Thus a possible net reaction is photodecomposition of water

However, in the present experimental condition, this reaction did not take place as the potential of the $\text{TiO}_2\text{-Pt}$ side was much more positive than the reversible hydrogen electrode potential as shown in Fig. 7.

The comparison between the photovoltage generated by 500W Xe lamp illumination and the one generated by 360 nm monochromatic light suggests that the potential of $\text{TiO}_2\text{-Pt}$ may become negative enough to proceed through reaction [4] by increasing the intensity of light. The reaction which seemed to take place at side 2 in the present experimental condition was the reduction of oxygen due to the small amount of oxygen in side 2 despite the nitrogen purge

The light-electricity conversion efficiency was also very low, possibly for several reasons. The short-circuit reactions at the $\text{TiO}_2\text{-metal}$ surface (side 1), such as oxygen reduction and hydrogen evolution reactions, consumed electrons at side 1 and, thus, reduced the conversion efficiency

Fig. 14. Photovoltage (E_{ph})-output power (W_{ph})-photocurrent (i_{ph}) relations of $\text{H}_2\text{O/TiO}_2\text{-Pt/SPE/Pt/N}_2$ cell under illumination of 500W Xe lamp with infrared absorbing filter (Toshiba, IRA-20).

The use of a metal which is an inactive catalyst for reactions [6] and [7] as a substrate may improve the efficiency. The rate of reaction [2] seemed to be slow and the recombination reaction [8] effectively competed with reaction [2] and reduced the conversion efficiency

The increase of the photocurrent by the addition of ethanol supports this argument. The prevention of reactions [6], [7], and [8] and the acceleration of reaction [2] would increase not only the light-electricity conversion efficiency but also the electrochemical potential of the electron at the $\text{TiO}_2\text{-Pt}$ side, *i.e.*, the possibility of electrolyte-free photoelectrolysis of water.

It must be noted that most of the photoelectrochemical and photocatalytic systems presently available can be constructed as SPE photoelectrochemical cells, *e.g.*, $\text{Ru(bpy)}_3\text{Cl}_2\text{-M/SPE/M}$ (17) and $\text{Ru(bpy)}_3\text{Cl}_2\text{-RuO}_2\cdot\text{TiO}_2\text{-M/SPE/M}$ (18) where M is the metal substrate.

Conclusion

The SPE photoelectrochemical cell is proposed as a new device to convert solar energy to electrical and/or chemical energy. The conversion of light to electricity without the intervention of an electrolyte solution was achieved in $\text{TiO}_2\text{-Pt/SPE/Pt}$ and $\text{TiO}_2\text{-Au/SPE/Pt}$ cells. An increase of light intensity with a smaller contribution of short-circuit reactions at the $\text{TiO}_2\text{-metal}$ surface may make electrolyte-free photoelectrolysis of water possible, although it was not attained in this work.

Acknowledgment

Dr. H. Nakajima and Mr. K. Hayashi are acknowledged for the preparation of Pt/SPE/Pt and Au/SPE/Pt . Thanks are due to Dr. A. Mills for his useful information on MPD. This work was partly supported by a Grant-in-Aid for Scientific Research, Ministry of Education, Science and Culture, 56740177.

Manuscript submitted March 29, 1983; revised manuscript received June 21, 1983. This was Paper 250 presented at the Detroit, Michigan, Meeting of the Society, Oct. 17-21, 1982.

Hokkaido University assisted in meeting the publication costs of this article.

REFERENCES

1. A. Fujishima and K. Honda, *Nature*, **238**, 37 (1972).
2. K. Rajeshwar, P. Singh, and J. Dubow, *Electrochim. Acta*, **23**, 1117 (1978), a review of work published up to early 1978.
3. T. Kawai and T. Sakata, *Chem. Phys. Lett.*, **72**, 87 (1980).
4. M. Grätzel, *Ber. Bunsenges. Phys. Chem.*, **84**, 981 (1980).
5. B. V. Tilak, P. W. T. Lu, J. E. Colman, and S. Srinivasan, in "Comprehensive Treatise of Electrochemistry," Vol. 2, J. O'M. Bockris, B. E. Conway, E. B. Yeager, and R. E. White, Editors, Chap. 1, Plenum, New York (1981).
6. A. Ogumi, K. Nishio, and S. Yoshizawa, *Electrochim. Acta*, **26**, 1779 (1981).
7. K. Kordesch, in "Comprehensive Treatise of Electrochemistry," Vol. 3, J. O'M. Bockris, B. E. Conway, E. B. Yeager, and R. E. White, Editors, Chap. 3, Plenum, New York (1981).
8. T. Skotheim and I. Lundström, *This Journal*, **129**, 894 (1982).
9. H. Takenaka and E. Torikai, *Nippon Kokai (Pat.)* 55-38934 (1980).
10. A. Ogumi, K. Nishio, and S. Yoshizawa, *Denki Kagaku*, **49**, 212 (1981).
11. R. S. Davidson, R. M. Slater, and R. P. Meek, *J. Chem. Soc., Faraday Trans. 1*, **75**, 2507 (1979).
12. K. Uosaki and H. Kita, *This Journal*, **129**, 1752 (1982).
13. A. Fujishima, K. Kohayakawa, and K. Honda, *Bull. Chem. Soc. Jpn.*, **48**, 1041 (1975).
14. A. Mills, A. Harriman, and G. Porter, *Anal. Chem.*, **53**, 1254 (1981).
15. T. Kawai and T. Sakata, *J. Chem. Soc., Chem. Commun.*, 694 (1980).
16. T. Kawai and T. Sakata, *Proceedings of Seventh International Congress on Catalysis, Part B*, 1198 (1980).
17. M. Noumann-Spallart and K. Kalyanasundaram, *Ber. Bunsenges. Phys. Chem.*, **85**, 704 (1981).
18. E. Borgarello, J. Kiwi, E. Pelizzetti, M. Visca, and M. Grätzel, *Nature*, **289**, 158 (1981).

Electrochemical Solar Cells with Layer-Type Semiconductor Anodes

Stabilization of the Semiconductor Electrode by Selective Polyindole Electrodeposition

L. Fornarini, F. Stirpe, and B. Scrosati*

Istituto di Chimica Fisica, University of Rome, Rome, Italy

ABSTRACT

The electropolymerization of indole has been investigated on platinum and molybdenum diselenide electrodes. When performed in the dark, the electropolymerization is selectively directed to the surface defects of the semiconductor. The effect of this surface treatment is investigated and discussed. The results indicate that the electropolymerization of indole effectively blocks the defect sites and produces a stable improvement on the output characteristics of photoelectrochemical cells with layer-type semiconductor anodes.

Photoelectrochemical cells based on layered semiconductors (i.e., MoSe_2 or WSe_2) have both good solar to electrical energy conversion efficiency and stability against photocorrosion (1). However, the performance of these cells is largely influenced by the surface morphology of the semiconductor (2-5). Crystals with surface defects, such as steps between the van der Waals layers, show poor photoresponses. The unsaturated atoms at the edge of a step have dangling bonds exposed to the electrolyte, introducing new surface states close to the conduction band. These states act as recombination centers and promote, by tunneling of the majority carriers, back reactions of photogenerated redox species. Moreover, the contact of a surface parallel to the c-axis with the electrolyte creates a new electric field which drives the photogenerated carriers toward this region where they eventually recombine (2-5).

Consequently, large effort is presently devoted to the study of surface treatments capable of controlling these undesired morphological limitations (4, 6). Bard *et al.* (7) have proposed stabilizing the semiconductor surface by dark electropolymerization of o-phenylenediamine, specifically directed toward the blockage of the defective sites. Such a selective action is favored by the fact that only the surface defects of the semiconductor allow passage of appreciable current in the dark.

Following this direction, we have started a systematic study on electrocrystallization and electrodeposition processes on layered semiconductors. In a previous work (8), the feasibility of selective electrodeposition, in general, has been analyzed and discussed. In this paper, the effect of this type of surface treatment is further investigated by examining the polyindole electrodeposition on a single-crystal molybdenum diselenide photoanode.

Experimental

The molybdenum diselenide, MoSe_2 , crystals were kindly provided by Dr. F. Lévy of the Polytechnic of Lausanne. The semiconductor crystals were attached with a conductive silver paste to a brass current collector. This was then potted and sealed with epoxy resin on a Teflon holder. The counterelectrode was a platinum wire, spirally arranged around the semiconductor photoanode.

Conventional three-electrode glass cells have been used for the electrodeposition and output characteristic studies. These studies were performed by controlling the voltage with a potentiostat driven by a function generator and recording the current-voltage curves with an X-Y recorder or a computerized acquisition data system.

A halogen lamp was used to irradiate the photoelectrodes. The illumination intensity and uniformity were controlled by a light intensity meter.

* Electrochemical Society Active Member.

Key words: photovoltaic, semiconductor, surfaces.