Title	Photopotential Behavior of Platinized TiO ₂ Particles
Author(s)	Uosaki, Kohei; Kita, Hideaki
Citation	Journal of The Electrochemical Society, 129(8), 1752-1753 https://doi.org/10.1149/1.2124269
Issue Date	1982
Doc URL	http://hdl.handle.net/2115/50258
Rights	© The Electrochemical Society, Inc. 1982. All rights reserved. Except as provided under U.S. copyright law, this work may not be reproduced, resold, distributed, or modified without the express permission of The Electrochemical Society (ECS). The archival version of this work was published in J. Electrochem. Soc. 1982 volume 129, issue 8, 1752-1753.
Type	article
File Information	JES129-8_1752-1753.pdf

[Instructions for use](#)

the society for solid-state
and electrochemical
science and technology

Journal of The Electrochemical Society

Photopotential Behavior of Platinized TiO₂ Particles

Kohei Uosaki and Hideaki Kita

J. Electrochem. Soc. 1982, Volume 129, Issue 8, Pages 1752-1753.
doi: 10.1149/1.2124269

**Email alerting
service**

Receive free email alerts when new articles cite this article - sign up in the box at the top right corner of the article or [click here](#)

To subscribe to *Journal of The Electrochemical Society* go to:
<http://jes.ecsdl.org/subscriptions>

posites, made by the process described here and reported by one of the authors in a separate paper (4), appears to approach that of pure lead. Initial deep cycling experiments of battery cells made with small FP/Pb composite grids indicate that grid growth is negligible compared with unreinforced pure lead grids.

Fabrication of larger scale FP/Pb composite grids and demonstrations of their performance in battery cells is underway. Deep cycling tests with small FP/Pb grids are continuing in order to determine eventual failure mechanisms.

Acknowledgment

Part of this work was sponsored under contract N60921-80-C-0243 from Naval Surface Weapons Center, R. A. Sutula, program manager. We are indebted to C&D Batteries, an Allied Company, for building and deep cycle testing battery cells containing Fiber FP/Pb composite grids. Their support, cooperation, and permission to publish are gratefully acknowledged.

Manuscript submitted Jan. 18, 1982; revised manuscript received April 2, 1982. This was Paper 57 presented at the Denver, Colorado, Meeting of the Society, Oct. 11-16, 1981.

Any discussion of this paper will appear in a Discussion Section to be published in the June 1983 JOURNAL. All discussions for the June 1983 Discussion Section should be submitted by Feb. 1, 1983.

Publication costs of this article were assisted by E. I. du Pont de Nemours and Company, Incorporated.

REFERENCES

1. J. L. Weininger and C. R. Morelock, *This Journal*, **122**, 1161 (1975).
2. D. M. Goddard, W. C. Harrigan, D. L. Dull, and M. F. Amateau, Aerospace Corp., El Segundo, CA, Aerospace Rept. ATR-78, 8162-2 (November 1977).
3. "St. Joe Lead—A Metal For The Future," Reference Manual published by St. Joe Lead Company, Clayton, MO 63105 (1979).
4. C. M. Dacres, S. M. Reamer, R. A. Sutula, and I. A. Angres, *This Journal*, **128**, 2060 (1981).

Photopotential Behavior of Platinized TiO₂ Particles

Kohei Uosaki* and Hideaki Kita

Department of Chemistry, Faculty of Science, Hokkaido University, Sapporo 060, Japan

The photocatalytic generation of hydrogen from water is one of the attractive means of the conversion of solar energy into chemical energy (1-3). Pt/SrTiO₃ (1) and Pt/TiO₂ (2) were shown to be able to decompose water photocatalytically. Photocatalysts dispersed in the liquid phase are considered to behave as short-circuited photoelectrochemical cells (4), and we have demonstrated that the measurement of the potential of suspended catalysts provides useful information concerning their reaction mechanism (5). Recently Dunn *et al.* reported the usefulness of electrochemical measurements in the characterization of suspended photocatalysts (6, 7).

To provide further information on the mechanism of photocatalytic decomposition of water on these catalysts, we report here the photoeffect on the potential of platinized catalysts suspended in NaOH solution.

The platinized TiO₂ catalysts (2 weight percent Pt) were prepared by impregnating TiO₂ (anatase) with H₂PtCl₆ solutions (8). The impregnates were dried in air at 110°-120°C for 16 hr and then reduced in hydrogen at 300°C for 2 hr. The catalysts (0.2g) were suspended in 70 ml of 1N NaOH solution in a cell with main and reference compartments separated by a Luggin capillary and a stopcock. A quartz window was mounted on the main compartment. A gold-plated platinum wire and an Ag/AgCl electrode were used as a measuring probe (9) and a reference electrode, respectively. A 500W xenon lamp with a monochromator (Ritsu Oyo Kogaku) was used as a light source. Illuminating the probe electrode was avoided. Purified helium gas was passed through the solution for 30 min prior to the measurement. During the measurement, the catalyst-containing solution was stirred magnetically.

The potential-time relation of the catalysts under pulsed illumination of 360 nm monochromatic light is shown in Fig. 1. The potential shifted negatively under illumination and reached some steady value, according to

$$E(t) = E(0) + \Delta E_{st}(1 - e^{-t/\tau}) \quad [1]$$

where $E(t)$ and $E(0)$ are the potentials at time t and

in dark, respectively, ΔE_{st} is the difference between the potential in dark and the steady potential, and τ is the time constant (~ 30 sec for this process). After the interruption of light, the potential returns to the original value, $E(0)$, by

$$E(t') = \Delta E_{st} e^{-t'/\tau} \quad [2]$$

where t' is the time after the interruption of light and

Fig. 1. The potential-time relation of Pt/TiO₂ catalyst in 1N NaOH under pulsed illumination of 360 nm monochromatic light.

* Electrochemical Society Active Member.

Key words: photocatalyst, semiconductor, titanium dioxide.

τ is the time constant (~ 45 sec for this process¹). The wavelength dependence of ΔE_{st} shown in Fig. 2 clearly indicates that the photoeffect on the catalyst potential is created by the absorption of light by TiO_2 ($E_g = 3$ eV). This effect will be explained by considering the band structure of Pt/ TiO_2 catalyst shown in Fig. 3. This is based on a model that considers Pt and TiO_2 electrodes at short circuit. In the dark, the bands of TiO_2 bend up toward $\text{TiO}_2/\text{electrolyte}$ and TiO_2/Pt interfaces. When the catalysts are illuminated by the bandgap light, hole-electron pairs are formed. Due to the band-bending, the holes and the electrons move toward the $\text{TiO}_2/\text{electrolyte}$ interface and the interior of TiO_2 , respectively. The holes at the $\text{TiO}_2/\text{electrolyte}$ interface tend to react with OH^-

while the electrons are unable to react with water because the Fermi level of the catalysts is not high enough. Thus the Fermi level of the catalysts rises, i.e., the potential becomes more negative so that the rate

¹ Preliminary experiments show that the time constant of the decay of photopotential of sintered Pt/ TiO_2 electrode is considerably larger (~ 20 min) than that of this process.

Fig. 2. The effect of the wavelength of the light on ΔE_{st} . The values of ΔE_{st} are not calibrated for the photon numbers.

Fig. 3. The band structure of Pt/ TiO_2 catalyst in (a) dark and (b) under illumination. CB and VB are the conduction and valence band, respectively, and E_F is the Fermi level.

of electron consumption by reaction [B] at the Pt surface becomes equal to the hole consumption rate

When the potential becomes more negative, the degree of band-bending in TiO_2 becomes smaller and the electron-hole recombination rate increases. Reaction [C], which can be considered as the hole-electron recombination via adsorbed states, is also accelerated when the potential becomes negative

Thus the potential does not exceed some steady value at which the rate of electron excitation is equal to that of electron consumption by the reaction with H_2O and the recombination. In this system, the steady potential is positive compared with the reversible hydrogen electrode potential, suggesting no hydrogen evolution at an atmospheric pressure.

When the illumination is interrupted, the electron-hole pairs are no longer generated and the adsorbed hydrogen atoms are consumed by reaction [C] and the back-reaction of reaction [A]. Thus the potential returns to the original value. The relatively short time constant of this process compared with the time constants of the decay of photostimulated emf at a platinum coated with pigmentary TiO_2 (10) and at a sintered Pt/ TiO_2 electrode, suggests that the reaction [C] is responsible for the quick return of the potential to the original value in this process.

In summary, we have demonstrated that the measurements of the potential of photocatalysts provide useful information on the mechanism of the photocatalytic water decomposition reaction.

Acknowledgment

Thanks are due to Dr. Akiko Aramata for her interest.

Manuscript submitted Oct. 6, 1981; revised manuscript received Jan. 4, 1982.

Any discussion of this paper will appear in a Discussion Section to be published in the June 1983 JOURNAL. All discussions for the June 1983 Discussion Section should be submitted by Feb. 1, 1983.

Publication costs of this article were assisted by Hokkaido University.

REFERENCES

1. F. T. Wagner and G. A. Somorjai, *Nature*, **285**, 559 (1980).
2. S. Sato and J. M. White, *Chem. Phys. Lett.*, **72**, 83 (1980).
3. T. Kawai and T. Sakata, *ibid.*, **72**, 87 (1980).
4. M. Miyake, H. Yoneyama, and H. Tamura, *J. Catal.*, **58**, 22 (1979).
5. H. Kita, K. Shimazu, Y. Kakuno, and A. Aramata, *J. Catal.*, **74**, 323 (1982).
6. W. Dunn, Y. Aikawa, and A. J. Bard, *This Journal*, **128**, 222 (1981).
7. W. Dunn, Y. Aikawa, and A. J. Bard, *J. Am. Chem. Soc.*, **103**, 3456 (1981).
8. S. J. Tauster, S. C. Fung, and R. L. Garten, *ibid.*, **100**, 170 (1978).
9. J. F. van der Plas and E. Barendrecht, *Electrochim. Acta*, **25**, 1477 (1980).
10. R. S. Davidson, R. M. Slater, and R. R. Meek, *J. Chem. Soc., Faraday Trans. I*, 2507 (1979).