Title	In vitro synthesis of polyhydroxyalkanoate (PHA) incorporating lactate (LA) with a block sequence by using a newly engineered thermostable PHA synthase from <i>Pseudomonas</i> sp. SG4502 with acquired LA-polymerizing activity
Author(s)	Tajima, Kenji; Han, Xuerong; Satoh, Yasuharu; Ishii, Ayako; Araki, Yuji; Munekata, Masanobu; Taguchi, Seiichi
Citation	Applied Microbiology and Biotechnology, 94(2), 365-376 https://doi.org/10.1007/s00253-011-3840-z
Issue Date	2012-04
Doc URL	http://hdl.handle.net/2115/52295
Rights	The original publication is available at www.springerlink.com
Type	article (author version)
File Information	AMB94-2_365-376.pdf

[Instructions for use](#)

**In vitro synthesis of polyhydroxyalkanoate (PHA)
incorporating lactate (LA) with a block sequence by using
a newly engineered thermostable PHA synthase from
Pseudomonas sp. SG4502 with acquired LA-polymerizing
activity**

Kenji Tajima^{†,*}, Xuerong Han[†], Yasuharu Satoh, Ayako Ishii, Yuji Araki, Masanobu
Munekata, and Seiichi Taguchi*

*Division of Biotechnology and Macromolecular Chemistry, Faculty of Engineering, Hokkaido
University, N13W8, Kita-ku, Sapporo 060-8628, Japan*

*Corresponding author

e-mail address: ktajima@eng.hokudai.ac.jp

telephone number: +81 11 706-7816

fax number: +81 11 706-7816

e-mail address: staguchi@eng.hokudai.ac.jp

Footnote [†]These authors contributed equally to this work.

Abstract

Recently, we succeeded in isolating a thermotolerant bacterium, *Pseudomonas* sp. SG4502, which is capable of accumulating polyhydroxyalkanoate (PHA) even at 55 °C, as a source of thermostable enzymes. In this study, we cloned a *pha* locus from the bacterium and identified two genes encoding PHA synthases (PhaC1_{SG} and PhaC2_{SG}). Two mutations, Ser324Thr and Gln480Lys, corresponding to those of a lactate (LA)-polymerizing enzyme (LPE) from mesophilic *Pseudomonas* sp. 61-3 were introduced into PhaC1_{SG} to evaluate the potential of the resulting protein as a “thermostable LPE”. The mutated PhaC1_{SG} [PhaC1_{SG}(STQK)] showed high thermal stability in synthesizing P(LA-*co*-3HB) in an in vitro reaction system under a range of high temperatures. Requirement of 3HBCoA as a priming unit for LA polymerization by the LPE has been suggested in both of the in vitro and in vivo experiments. Based on the finding, the PhaC1_{SG}(STQK)-mediated synthesis of a LA-based copolymer with a block sequence was achieved in the in vitro system by sequential feeding of the corresponding two substrates. This in vitro reaction system using the thermostable LPE provides us with a versatile way to synthesize the various types of LA-based copolymers with desired sequence patterns, random or block, depending on the way of supplying hydroxyalkanoates (mixed or sequential feeding).

Keywords polyhydroxyalkanoate (PHA), thermal stability, block sequence, LA-polymerizing enzyme (LPE), in vitro synthesis, *Pseudomonas* sp. SG4502

Introduction

Polyhydroxyalkanoates (PHAs) are a class of aliphatic polyesters that are accumulated as carbon and energy storage materials in numerous bacteria under nutrient-limited conditions (Anderson et al. 1990; Lee 1996). The PHAs have attracted much attention because they have properties similar to those of common thermoplastics and can be produced from renewable resources (Jendrossek et al. 1996; Jendrossek et al. 2002). Because of their superior properties, PHAs are expected to be applicable to a wide range of agricultural, marine and medical fields. PHA synthases are the key enzymes for PHA synthesis and produce PHA by polymerizing (*R*)-hydroxyalkanoyl moieties of (*R*)-hydroxyalkanoyl coenzymeAs (HACoAs) with concomitant release of CoA molecules (Rehm 2003; Taguchi et al. 2004), and the types of repeating units incorporated into PHAs are mainly based on the substrate specificities of the PHA synthases employed. PHA synthases are divided into four classes (classes I to IV) on the basis of their activities toward substrates with different carbon chain lengths and their subunit compositions (Rehm 2003). PHAs are generally produced by *in vivo* methods using whole bacterial cells, and *in vivo* methods are suitable for large-scale PHA production. On the other hand, *in vitro* methods are not suitable for large-scale PHA production, but they have several attractive features, such as incorporation of the unnatural repeating units with controlled fractions and the ability to sensitively monitor this incorporation, which cannot be performed by *in vivo* methods. In particular, the reactivity and polymerization activity of PHA synthase toward unnatural substrates can be efficiently evaluated by *in vitro* methods (Han et al. 2011; Taguchi et al. 2008; Tajima et al. 2009) by measuring yield and molecular weight and analyzing structure of a product.

Like PHA, polylactate (PLA) is also a bio-based polyester produced from biomass. PLA is the most popular biodegradable plastic and has been widely studied all over the world (Carrasco et al. 2010; Fukushima et al. 2009; Inkinen et al. 2011; Nampoothiri et al. 2010; Pang et al. 2010; Saulnier et al. 2004; Tsuji 2005). It is a very attractive material, but its

application is limited in part due to its brittle properties, such as poor elongation, slow crystallization rate, and so on. One of the methods to improve the properties of PLA is copolymerization (Abe et al. 1997; Haynes et al. 2007) with another repeating unit. For example, Abe et al. and Haynes et al. (Abe et al. 1997; Haynes et al. 2007) reported the synthesis of copolymers containing LA and 3HA units by the ring-opening copolymerization of (*S, S*)-lactide with (*R*)- β -butyrolactone and by the ring-opening copolymerization of (*S, S*)-lactide using PHA as a macroinitiator. The synthesized copolymers had better properties than those of the PLA homopolymer (Abe et al. 1997; Haynes et al. 2007).

We recently developed a copolymerization method using an LA-polymerizing enzyme (LPE) (Taguchi et al. 2008; Tajima et al. 2009), which was engineered from the PHA synthase from *Pseudomonas* sp. 61-3 by evolutionary engineering (Matsumoto et al. 2010; Taguchi et al. 2004; Taguchi 2010). In other studies, we attempted to screen the LPE among various natural and mutant PHA synthases belonging to classes I to IV (Rehm 2003) by using a two-phase reaction system (TPRS) (Taguchi et al. 2008; Taguchi 2010; Tajima et al. 2009). As a result of these screenings, a double mutant [PhaC1_{Ps}(STQK)] of PHA synthase from *Pseudomonas* sp. 61-3, which had two amino acids substitutions, Ser325Thr and Glu481Lys, was found to exhibit LA-polymerizing activity, and *Escherichia coli* carrying an LACoA supply pathway and this engineered enzyme produced LA-based polyesters (Taguchi et al. 2008; Tajima et al. 2009). To date, only class II PHA synthases from *Pseudomonas* species have been reported as LPEs (Matsumoto et al. 2010; Taguchi et al. 2008; Tajima et al. 2009; Yamada et al. 2010; Yang et al. 2011), and active efforts to obtain superior LPEs capable of incorporating LA units with high ratios and of efficiently producing LA-based copolymers with high yields have been made throughout the world (Yamada et al. 2010; Yang et al. 2011).

Thermostable PHA synthesis enzymes are required in order to develop in vitro systems for sustainable, long-term reactions for producing PHA. However, the isolation of enzymes involved in PHA synthesis has been limited to mesophilic strains thus far. In our

efforts to realize this goal, we very recently succeeded in isolating a thermotolerant bacterium, *Pseudomonas* sp. SG4502, which is capable of accumulating PHA even at 55 °C, as a potential source of thermostable enzymes (Satoh et al. 2011). This bacterium was able to grow between 30 °C and 55 °C and to synthesize polymers composed of various repeating units with 4 to 12 carbon atoms, suggesting that it could serve as a thermostable catalyst efficient in incorporating LA unit into the PHA chain. In this study, therefore, we attempted to clone and analyze PHA synthase genes from *Pseudomonas* sp. SG4502 and to evaluate the PHA synthase (PhaC1_{SG}) as a thermostable catalyst. Furthermore, we have presented here the first in vitro synthesis of PHA containing LA unit with a block sequence by utilizing the LPE derivative with STQK mutation of the newly isolated PhaC1_{SG}. This finding provides us with the attractive potentiality of the in vitro system equipped with thermostable PHA synthase in order to synthesize the various types of any copolymers with desired sequence patterns.

Materials and methods

Materials

Chloroform, methanol, adenosine triphosphate (ATP), and coenzymeA (CoA) were purchased from Wako Pure Chemical Industries (Osaka, Japan). (*R*)-LA lithium salt and (*R*)-3HB sodium salt were products of Sigma-Aldrich Japan (Tokyo, Japan) and MP Bio Japan K.K. (Tokyo, Japan), respectively. All other chemicals were of reagent grade or better.

Strains, plasmids, primers, and growth conditions

The strains, plasmids, and primers used in this study are shown in Table 1. *Escherichia coli* (*E. coli*) was grown at 37 °C in Luria-Bertani (LB) medium. When needed,

ampicillin (Ap, 100 $\mu\text{g}\cdot\text{mL}^{-1}$) or kanamycin (Km, 25 $\mu\text{g}\cdot\text{mL}^{-1}$) was added to medium. *Pseudomonas* SG4502 (NITE P-578) was grown at 45 °C in LB medium (Sato et al. 2011).

Cloning of *pha* locus from *Pseudomonas* sp. SG4502

Two primers, ORF1_FW and phaD_RV (Table 1) (Zhang et al. 2001), were used to obtain a PHA operon from *Pseudomonas* sp. SG4502. DNA was amplified by two-step touchdown polymerase chain reaction (PCR) using genomic DNA from *Pseudomonas* sp. SG4502 as a template. Takara LA Taq polymerase (Takara Shuzo, Kyoto, Japan) was used as a DNA polymerase. The temperature protocol consisted of an initial 1 min denaturation at 94°C, followed by 10 cycles of 94 °C for 30 s and 70 °C for 5 min, followed by 20 cycles of 94 °C for 30 s and 68 °C for 5 min, with a final elongation step of 68 °C for 10 min. The PCR product was ligated with a vector, pCR2.1-TOPO. The ligation mixture was used for the transformation of *E. coli* JM109 and then was plated onto LB agar plates with ampicillin, isopropylthiogalactoside (IPTG), and 5-Bromo-4-Chloro-3-Indolyl- β -D-Galactoside (X-gal). Approximately 2000 white colonies with ampicillin resistance were obtained, and candidates for plasmid preparation were selected by confirming DNA insertion into a vector with colony-direct PCR using universal primers. A plasmid containing the PCR product was designated as pCR-phaSG.

Sequencing of a DNA fragment from *Pseudomonas* sp. SG4502

The plasmid, pCR-phaSG, was isolated from *E. coli* with a Quantum Prep Plasmid Midiprep Kit (Bio-Rad Laboratories, Hercules, CA). The nucleotide sequence was determined by the dye-terminator method using an ABI PRISM Big-Dye Terminator Cycle Sequencing Ready Reaction Kit (Perkin Elmer, Wellesley, MA) and an ABI PRISM 310 Genetic Analyzer (Perkin Elmer). Primer walking method was used for sequencing the DNA insert and specific primers were designed based on the results of sequencing.

Preparation and assay of AcoE, PCT, and PHA synthases

AcoE from *Ralstonia eutropha* (currently *Cupriavidus necator*) ATCC17699 (H16 strain) was used as acetyl-CoA synthetase (ACS) to form acetyl-CoA (AcCoA) (Proefert et al. 1992). A gene encoding AcoE was amplified by PCR using a set of specific primers (Table 1), and then the amplified DNA fragment was introduced into pQE80 (Qiagen Japan K.K. Tokyo, Japan). Propionate CoA transferase (PCT) from *Clostridium propionicum* was employed for supplying LACoA and 3HBCoA to a PHA synthase ACS and PCT were prepared according to the methods previously described (Han et al. 2009). *Pseudomonas* sp. 61-3 and SG4502 were used as sources of PHA synthases. The PHA synthases (PhaC1s) from *Pseudomonas* sp. 61-3 and *Pseudomonas* sp. SG4502 were described as PhaC1_{ps} and PhaC1_{SG}, respectively. The reactivities of PHA synthase from *Pseudomonas* sp. 61-3 towards LACoA and 3HBCoA were acquired and increased, respectively, by the introduction of double mutations (Taguchi et al. 2004; Taguchi et al. 2008; Tajima et al. 2009). A gene encoding PHA synthase with two mutations [PhaC1_{SG}(STQK)], Ser324Thr and Gln480Lys, was chemically synthesized by GenScript USA Inc. (NJ, USA). The engineered PHA synthases, PhaC1_{ps}(STQK) from *Pseudomonas* sp. 61-3 and PhaC1_{SG}(STQK) from *Pseudomonas* sp. SG4502, were prepared by using a His-tag system according to the method described in a previous paper (Satoh et al. 2003; Tajima et al. 2009). The activities towards (*R*, *S*)-3HBCoA of the purified enzymes were measured according to the methods described in previous papers (Han et al. 2009; Satoh et al. 2003; Tajima et al. 2004).

Thermal stability test

PHA synthase dissolved in 100 mM sodium phosphate buffer (pH 7.5) was maintained at 30, 37, 45, and 55 °C for 10 min. Then other enzymes and reagents required for enzymatic synthesis of PHA (please refer next section) were added to a reaction mixture for PHA production. After incubation at 30 °C for 72 h, the formed polymer was purified and weighed.

The protein particle size was observed to evaluate thermal stability of PHA synthase (Golub et al. 2007). Four hundred micro liter of PHA synthase ($0.5\text{mg}\cdot\text{mL}^{-1}$) dissolved in 100 mM sodium phosphate buffer (pH 7.5) was put into a sample cell kept at 37 °C. The time-course change in a protein particle size at 37 °C was measured by the dynamic light scattering method using a particle size analyzer UPA-UT151 (Nikkiso Co., Ltd., Tokyo, Japan). The same experiment was conducted twice to confirm the reproducibility of the experiments.

Enzymatic synthesis of P(LA-*co*-3HB) by an in vitro reaction system using an LPE.

To evaluate PHA synthase as a thermostable LPE under conditions close to those of an in vivo production system (Matsumoto et al. 2010; Taguchi et al. 2008; Taguchi 2010), we attempted to synthesize the P(LA-*co*-3HB) by employing an in vitro PHA synthesis system developed by R. Jossek and A. Steinbüchel (Fig. 1) (Jossek et al. 1998). PHA synthesis using the in vitro reaction system was initiated by addition of the purified PHA synthase [PhaC1_{PS}(STQK) or PhaC1_{SG}(STQK): $0.5\text{ mg}\cdot\text{mL}^{-1}$] into a reaction mixture containing 100 mM sodium phosphate buffer (pH 7.5), total 200 mM substrates [(*R*)-LA and (*R*)-3HB], 10 mM acetate, 30 mM ATP, 2 mM CoA, 10 mM MgCl₂, BSA ($0.2\text{ mg}\cdot\text{mL}^{-1}$), pyrophosphatase (0.4 U), AcoE ($0.2\text{ mg}\cdot\text{mL}^{-1}$), and PCT ($0.2\text{ mg}\cdot\text{mL}^{-1}$). Reactions were performed in 5 ml of total volume at 30 °C, 37 °C and 45 °C. After incubation for 72 h, 5 mL of chloroform was poured into the reaction tube. The chloroform and aqueous phases were mixed by a vortex mixer, and then the tube was incubated for 3 h at 70 °C to completely dissolve the product into the chloroform. After cooling the solution to room temperature, the chloroform (lower) phase was filtered through a 0.2 µm poly(tetrafluoroethylene) (PTFE) membrane to remove insoluble materials such as denatured enzymes, and then the filtrate was concentrated to approximately 1 ml using an evaporator. Ten milliliters of methanol was added, and then the solution was stored at 4 °C for 16 h to precipitate the polymer. The obtained precipitate was collected using a 0.2 µm PTFE membrane, and the dried powder was used for the analysis.

Measurements

The ^1H NMR spectra of the polymers were obtained using a Bruker MSL400 spectrometer (400 MHz) at a 90° pulse with a 4 ms, 3,000 Hz spectral width and a 4 s repetition rate. The COSY spectrum was recorded in deuterated chloroform (CDCl_3) at 25°C using a Bruker MSL400 spectrometer (400 MHz) and the chemical shifts were reported in ppm using tetramethylsilane (TMS) as an internal reference. The molar ratios of 3HB and LA units in copolymers were calculated from the ratios of the area of methine protons in 3HB units to that in LA units. The molecular weights of the obtained polymers were determined by gel-permeation chromatography (GPC) using tandem TSKgel Super HZM-H columns (6.0 mm I.D. $\times$ 150 mm; TOSOH, Tokyo) using chloroform as an eluate, and the calibration was performed using polystyrene samples as standards. The formation of CoA derivatives was confirmed HPLC analysis as previously described (Han et al. 2011; Satoh et al. 2003; Tajima et al. 2004).

Results

Cloning of the *pha* locus from *Pseudomonas* sp. SG4502

To date, class II *pha* gene loci have been cloned from several *Pseudomonas* strains, including *P. stutzeri* (Chen et al. 2004), *P. mendocina* (Hein et al. 2002), *P. aeruginosa* (Timm et al. 1992), *P. putida* (Kim et al. 2003), and *Pseudomonas* sp. 61-3 (Matsusaki et al. 1998). In the *pha* loci, there are two PHA synthase genes (*phaC1* and *phaC2*) and one PHA depolymerase gene (*phaZ*), which is located between *phaC1* and *phaC2*. An expected gene fragment of about 5.2 kbp was obtained by PCR using genomic DNA of *Pseudomonas* sp. SG4502 as a template. A plasmid containing the 5.2 kbp DNA fragment was designated as pCR-phaSG. The nucleotide sequencing analysis of the inserted gene fragment revealed three ORFs of 1680 bp, 906 bp, and 1692 bp in length (accession no. AB448740). The polypeptides

designated as PhaC1_{SG}, PhaZ_{SG}, and PhaC2_{SG} were composed of 559, 301, and 563 amino acid residues with molecular masses of 62.6 kDa, 33 kDa, and 63.0 kDa, respectively. A database search with the Protein BLAST program (<http://blast.ncbi.nlm.nih.gov/Blast.cgi>) for the ORFs showed that their amino acid sequences had high homology with those of PhaC1, PhaZ, and PhaC2 from *Pseudomonas* species (Chen et al. 2004; Hein et al. 2002; Kim et al. 2003; Matsusaki et al. 1998; Timm et al. 199) (Table 2). Figure 2 shows the partial sequence alignments of PhaC1s and PhaC2s from *Pseudomonas* strains. It has been reported that all PHA synthases contain a putative lipase box, [Gly–Xaa–(Ser/Cys)–Xaa–Gly–Gly], in which the essential active site serine is replaced with a cysteine in the PHA synthase (Rehm et al. 2002; Steinbüchel et al. 1992). In both PhaC1_{SG} and PhaC2_{SG}, the putative lipase boxes including a cysteine residue were also conserved (Fig. 2). Furthermore, Amara et al. have reported that the highly conserved Cys-296, Asp-452, and His-453 in PhaC1 from *P. aeruginosa* ATCC 15692 were considered to constitute the catalytic triad (Amara et al. 2003). Since these amino acids (Fig. 2: Cys-295, Asp-450, and His-451 for PhaC1_{SG}; Cys-298, Asp-455, and His-456 for PhaC2_{SG}) were conserved in the sequences deduced from *phaC1_{SG}* and *phaC2_{SG}*, they may constitute a catalytic triad in each PHA synthase.

Assay of PhaC1_{SG}(STQK)

It has been reported that the reactivities of PHA synthase from *Pseudomonas* sp. 61-3 towards LACoA and 3HBCoA were acquired and increased, respectively, by the introduction of the double mutations (Taguchi et al. 2004; Taguchi et al. 2008; Tajima et al. 2009). Therefore, the corresponding mutations, Ser324Thr and Gln480Lys, were introduced into PhaC1_{SG} from *Pseudomonas* sp. SG4502 to make PhaC1_{SG}(STQK). As expected, the reactivity of PhaC1_{SG}(STQK) towards 3HBCoA was increased in the same manner as that of PhaC1_{PS}(STQK) (Table 3, run 2) (Matsumoto et al. 2009; Taguchi et al. 2004; Taguchi 2010). The specific activities of PhaC1_{SG}(STQK) and PhaC1_{PS}(STQK) were examined at 30, 37, and

45 °C. The specific activity of PhaC1_{SG}(STQK) at 45 °C reached almost four times that at 30 °C and was temperature-dependent (Table 3, runs 2 and 4). We also tried to measure the specific activity at 55 °C, but the substrate, 3HBCoA, decomposed at this high temperature. On the other hand, the specific activity of PhaC1_{PS}(STQK) decreased at 37 °C and was completely diminished at 45 °C (Table 3, runs 5–7), probably because of the low thermal stability of PhaC1_{PS}(STQK).

Thermal stability of PhaC1_{SG}(STQK)

To compare the thermal stabilities of PhaC1_{SG}(STQK) and PhaC1_{PS}(STQK), polymers were synthesized by the in vitro reaction system (Fig. 1) after heat-treatment at various temperatures for 10 min. The yields of polymers are shown in Fig. 3 as relative yields compared to those produced by PHA synthases treated at 30 °C. While the yields by PhaC1_{PS}(STQK) drastically decreased above 37 °C, the yields by PhaC1_{SG}(STQK) were constant up to 45 °C, suggesting PhaC1_{SG}(STQK) had a higher thermal stability than PhaC1_{PS}(STQK).

In addition, the time-course changes in protein particle sizes of PhaC1_{SG}(STQK) and PhaC1_{PS}(STQK) at 37 °C were also measured by the dynamic light scattering method as an index of the thermal stabilities of PHA synthases. The protein particle size of PhaC1_{PS}(STQK) rapidly increased and then decreased (Fig. 4). This drastic change in the particle size of PhaC1_{PS}(STQK) could be explained by the denaturation and aggregation of the protein molecules. In contrast, the particle size of PhaC1_{SG}(STQK) remained virtually constant, suggesting that PhaC1_{SG}(STQK) was more stable than PhaC1_{PS}(STQK).

From these results, it was suggested that PhaC1_{SG}(STQK) had higher thermal stability than that of PhaC1_{PS}(STQK) from a mesophilic *Pseudomonas* and could be used as a thermostable PHA synthase.

Enzymatic synthesis of P(LA-*co*-3HB) by an in vitro reaction system using PhaC1_{SG}(STQK) or PhaC1_{PS}(STQK) as a catalyst

To analyze the potential of PhaC1_{SG}(STQK) as a thermostable LPE, in vitro synthesis of P(LA-*co*-3HB) was performed at various temperatures. Before the in vitro synthesis, a reaction mixture without PHA synthase was prepared and then incubated at 30 °C to confirm the formation of (*R*)-LACoA and (*R*)-3HBCoA in the in vitro reaction system. HPLC analyses clearly showed the formations of (*R*)-3HBCoA and (*R*)-LACoA (data not shown). Then, PhaC1_{SG}(STQK) or PhaC1_{PS}(STQK) was added to a reaction mixture containing 100 mM each (*R*)-LA and (*R*)-3HB as substrate precursors. The reaction mixtures became turbid after several hours, and precipitates formed in all the reaction mixtures. ¹H NMR spectra and GPC analyses of the products confirmed the production of P(LA-*co*-3HB) by both PhaC1_{SG}(STQK) and PhaC1_{PS}(STQK) (Table 4). The molar ratios of LA units in the polymers were around 65 mol% (Table 4, runs 2, 3, 5, and 6), and the temperature dependent LA-incorporation ratios were not observed for either PhaC1_{SG}(STQK) or PhaC1_{PS}(STQK). The yields of P(LA-*co*-3HB)s by PhaC1_{SG}(STQK) were higher than those by PhaC1_{PS}(STQK) (Table 4, runs 2, 3, 5, and 6). Whereas PhaC1_{SG}(STQK) had the polymerizing activity at 45 °C (Table 3, run 4), polymer was not obtained at 45 °C (Table 4, run 4). Since ACS and PCT originated from mesophilic bacteria; therefore, this could be due to the denaturation of ACS and/or PCT during a reaction.

From the results of the characterization and in vitro synthesis, PhaC1_{SG}(STQK) and PhaC1_{PS}(STQK) would have similar reactivities towards LACoA and 3HBCoA.

Control of molar ratios of LA and 3HB units in polymers

In general, the physical properties of PHA vary with the repeating unit compositions in the polymers. It is easy to control the repeating unit composition in PHA in vitro; that is one advantage of in vitro PHA synthesis. To confirm the possibility of control in the repeating

unit composition, (*R*)-LA and (*R*)-3HB were added to the reaction mixture at various molar ratios (LA/3HB: 0/100, 50/50, 75/25, 90/10, and 100/0). The proton NMR spectra of the copolymers obtained from the reaction mixtures with PhaC1_{SG}(STQK) are shown in Fig. 5. The intensities of methine (5.16 ppm) and methyl (1.59 ppm) proton peaks in LA-LA*-LA increased with the increase of LA fraction in the copolymers. The methine and methylene proton peaks (LA-3HB*-LA) were shifted to the low magnetic field side by the direct linkages with LA units. This data provides direct evidence for the increased concentration of LA repeating unit in the copolymers. The 3HB unit molar ratios in copolymers were calculated from the ratios of the area of methine protons in 3HB units to that in LA units. The repeating unit compositions, yields, and molecular weights of products synthesized by PhaC1_{SG}(STQK) or PhaC1_{PS}(STQK) at various LA/3HB ratios are summarized in Table 5. The molar ratios of LA in the polymer increased with the increase of the (*R*)-LA concentration in the reaction mixture, suggesting that it is possible to control the repeating unit ratios in the polymers. The maximal molar ratios of LA in the polymers synthesized by the PhaC1_{PS}(STQK) and PhaC1_{SG}(STQK) were 60 mol% (Table 5, run 7) and 87 mol% (Table 5, run 4), respectively. The yields of the polymers decreased with the increase in the ratio of (*R*)-LA (Table 5, runs 1–4). In the experiment using only (*R*)-LA, the PLA homopolymer could not be synthesized (Table 5, runs 5 and 10).

Synthesis of a copolymer with a block sequence by PhaC1_{SG}(STQK) treated with 3HBCoA

Currently, the active polyester synthase has been suggested to form a homodimer considering class I and II polyester synthases (Rehm 2007), and dimerization of PHA synthase is significantly induced in the presence of substrate (Rehm et al. 2001) or trimeric CoA analogs (3-hydroxybutyryl)₃CoA (Wodzinska et al. 1996), respectively. To date, LA-homopolymer has not been synthesized in our in vitro experiments, in which only LACoA

was supplied to a LPE (Taguchi et al. 2008; Tajima et al. 2009). Therefore, synthesis of a polymer by PhaC1_{SG}(STQK) treated with 3HBCoA was performed to confirm that a priming step by a favorable substrate such as 3HBCoA was necessary for LA-polymerization by a LPE. PhaC1_{SG}(STQK) was incubated with 1 mM (*R*)-3HBCoA for 9 h in 100 mM sodium phosphate buffer (pH 7.5). After the confirmation of a disappearance of (*R*)-3HBCoA by HPLC analysis, LA and other components (ATP and enzymes) were added into the reaction mixture. After additional incubation (total 72 h), a product was purified by the same method described in the Experimental section.

The proton NMR spectra of P(3HB), a chemically synthesized block copolymer P(3HB-*b*-LA), and a product obtained from a reaction mixture including PhaC1_{SG}(STQK) pretreated with 3HBCoA are shown in Fig. 6. The proton NMR spectrum of the product obviously differs from that of P(LA-*co*-3HB) with a random sequence [Figs. 5-(b) and (c)] and is the same with that of the chemically synthesized block copolymer [Fig. 6-(b)]. A unimodal peak was observed in the GPC chart of the product. In addition, no polymer was synthesized by PhaC1_{SG}(STQK) untreated with 3HBCoA. The repeating unit composition and weight average molecular weight of the product were 3HB/LA = 30/70 and 2.7×10^5 , respectively. From these results, it was suggested that the product synthesized by PhaC1_{SG}(STQK) treated by 3HBCoA was a copolymer with a block sequence.

Discussion

For efficient *in vitro* enzymatic production of PHA, the stability of an enzyme is essential because denaturation of the enzyme occurs during the course of the reaction. The thermal stability of the enzyme is a key factor. In general, the reaction rate increases depending on the reaction temperature. It is therefore significantly important to obtain thermostable enzyme for efficient enzymatic production with high yields. In this study, we

have succeeded in cloning the genes encoding PHA synthases from the previously isolated thermotolerant bacterium *Pseudomonas* sp. SG4502, which was capable of producing PHA even at 55 °C (Sato et al. 2011). Moreover, the thermal stability test of the recombinant enzyme clearly showed the high thermal stability. To date, various PHA synthases have been obtained from *Pseudomonas* species, but there have been no reports on a PHA synthase with high thermal stability. Therefore, this is the first report of a thermostable PHA synthase from *Pseudomonas* species.

At this stage, we have not addressed the exact reason why the PHA synthase of *Pseudomonas* sp. SG4502 is thermostable. As mentioned above, the result of the homology search using the BLAST program showed that PhaC1_{SG} had high homology to PhaC1_{PS} (86 % amino acid identity; Table 2). Therefore, we next compared the amino acid compositions of PhaC1_{SG} and PhaC1_{PS} to reveal the reasons for the differences in their thermal stabilities. PhaC1_{SG} has more hydrophobic residues, especially proline and leucine (Fig. 7). A plausible hydrophobic interaction formed by these amino acids could be effective to gain resistance against high temperature-induced protein denaturation. In addition, proline has also been reported to play crucial roles in the thermal stability because of its rigid structure (Watanabe et al. 1997). On the other hand, the numbers of cationic and anionic amino acids and cysteine residues were the same in both PHA synthases (PhaC1_{SG} and PhaC1_{PS}), suggesting that electrostatic interactions and disulfide linkages are not related to the differences in thermal stability between PhaC1_{SG} and PhaC1_{PS}.

Since the two amino acid substitutions, Ser325Thr and Gln481Lys, in a PHA synthase from *Pseudomonas* sp. 61-3 were previously demonstrated to gain reactivity towards LACoA and enhance reactivity towards 3HBCoA, the corresponding mutations were introduced into PhaC1_{SG} to evaluate the potential of the resulting protein as a thermostable LPE. As expected, the reactivities of the thus-constructed PhaC1_{SG}(STQK) towards 3HBCoA and LACoA were increased and acquired, respectively, in the same manner as those of the PHA synthase from

Pseudomonas sp. 61-3 (Tables 3 and 4). Since the repeating unit compositions in the polymers produced by PhaC1_{SG}(STQK) and PhaC1_{PS}(STQK) were almost the same (Table 4), PhaC1_{SG}(STQK) and PhaC1_{PS}(STQK) would have similar substrate specificities towards 3HBCoA and LACoA. Considering the high homologies between PhaC1_{SG} and PhaC1_{PS} (Table 2), the alteration of the substrate specificity in PhaC1_{SG}(STQK) could be due to conformational changes identical to those occurring in PhaC1_{PS}(STQK).

Very recently, Shozui et al. reported that a copolymer containing 96 mol% LA was produced in recombinant *E. coli* expressing PhaC1_{PS}(STQK) (Shozui et al. 2010). However, in our in vitro study, the maximal molar ratios of LA in the polymers synthesized by the PhaC1_{PS}(STQK) and PhaC1_{SG}(STQK) were up to 60 mol% (Table 5, run 7) and 87 mol% (Table 5, run 4), respectively. Since PhaC1_{SG}(STQK) and PhaC1_{PS}(STQK) had similar substrate specificities towards 3HBCoA and LACoA, the higher production of P(87 mol% LA-co-3HB) by PhaC1_{SG}(STQK) in the in vitro reaction system may have been due to the increase in the reaction rate with the reaction temperature elevation. Therefore, the increase in the reaction rate is essential for the high yield production of LA-enriched polymers, and the high thermal stability of PhaC1_{SG}(STQK) could be a significantly useful feature as an LPE. Furthermore, LPEs are derived from class II PHA synthases that can polymerize various kinds of 3HAs. In fact, the in vivo synthesis of P[LA-co-3HB-co-3-hydroxyvalerate], P[LA-co-3HB-co-3-hydroxyhexanoate (3HHx)], and P[LA-co-3-hydroxyalkanoates (3HAs)], has been achieved by PhaC1_{PS}(STQK) (Matsumoto et al. 2011; Shozui et al. 2010; Shozui et al. 2011). For PhaC1_{SG}, it has been confirmed that *P. putida* GPp104 expressing PhaC1_{SG} was able to produce various PHAs, including 3HB, 3HHx, 3-hydroxyoctanoate, 3-hydroxydecanoate, 3-hydroxydodecanoate (unpublished data), and it would be possible to synthesize various polyesters including LA by using PhaC1_{SG}(STQK) as an LPE. Thus, the synthesis of various kinds of polyesters including LA is one of the advantages of the enzymatic synthesis using an

LPE (Taguchi 2010), and more efficient enzymatic production will be achieved by using the thermostable LPE from *Pseudomonas* sp. SG4502.

However, to date, a polyester consisting of the complete 100 mol% LA (PLA) has not been produced by PhaC1_{SG}(STQK) and PhaC1_{PS}(STQK) either in vitro or in vivo (Matsumoto et al. 2010; Shozui et al. 2010; Shozui et al. 2011; Song et al. 2011; Taguchi et al. 2008; Tajima et al. 2009). Notably, the fact that a polymer was not produced in an in vitro system that contained only LACoA without other HACoAs strongly suggests the necessity of coexistence of preferable substrates such as 3HBCoA in LA-based polyester production by LPEs. So far copolymers containing 96 mol% LA and 99.3 mol% LA were produced in recombinant *E. coli* (Shozui et al. 2010) and *Corynebacterium glutamicum* (Song et al. 2011) by using PhaC1_{PS}(STQK), respectively. As demonstrated in these bacterial systems, a small amount of an intrinsic HACoA exists within a cell, therefore, it may act as a priming molecule for the reaction of LPE in vivo also.

Currently the trial synthesis of homopolymers and block copolymers have been attempted by using natural or artificially mutated bacterial strains (Hu et al. 2011; Penderson et al. 2006). In microbial polymer production system, finely regulated synthesis of the repeating units might be difficult because of significant effect of metabolic background of the microbial cells. On the other hand, the in vitro polymerization system has a potential for generation of various copolymers finely incorporating unnatural repeating units with a block sequence. Considering the necessity of 3HBCoA for LA incorporation, we attempted to make LA-based copolymer with PhaC1_{SG}(STQK) by supplying 3HBCoA as a primary substrate and followed by LACoA as a secondary substrate into the reaction system. Based on the identical NMR profiling with chemically synthesized P(3HB-*b*-LA), we have finally demonstrated the first synthesis of the block-type polymer containing LA (Fig. 6). For this achievement, requirement of 3HBCoA as a priming unit for LA incorporation into the polymer chain is very advantageous to prepare structurally finely regulated P(3HB-*b*-LA), while P(LA-*b*-3HB)

generation seems to be not easy. Most recently, the in vitro system provided us with the first finding that 2-hydroxybutyrate can be incorporated into the polymer by class I PHA synthase from *Ralstonia eutropha* (Han et al. 2011) as well as LPE [PhaC1_{PS}(STQK)] (unpublished data). Moreover, another unnatural 2-hydroxyalkanoate, glycolate, was found to be as a repeating unit incorporated into the polymer chain using the same LPE (Matsumoto et al. 2011). To our knowledge, this is the first report to synthesize a copolymer with block sequence by an in vitro reaction system, and it will be possible to produce novel biopolyesters incorporating natural and unnatural repeating units with random or block sequences, depending on the way of supplying substrates.

In conclusion, we cloned a *pha* locus from thermotolerant *Pseudomonas* sp. SG4502 and revealed that the locus contained two genes encoding PHA synthases (PhaC1_{SG} and PhaC2_{SG}) to establish a PHA production system with long-term stability and high yield. The two amino acid substitutions, Ser324Thr and Gln480Lys, which were previously demonstrated to confer the reactivity towards LACoA with enhanced 3HBCoA reactivity in a PHA synthase from *Pseudomonas* sp. 61-3, were introduced to construct a mutated PHA synthase [PhaC_{SG}(STQK)] (Ser324Thr/Gln480Lys). The enzyme also showed high activity even at 45 °C and was able to synthesize P(LA-*co*-3HB)s with high yields. The molar ratios of LA in the copolymers were controllable in the range of 0 to 87 mol%, and the yield and weight-average molecular weight of P(80 mol% LA-*co*-3HB) were 0.70 g•L⁻¹ and 1.4×10⁵, respectively. To date, although several mutated PHA synthases from mesophilic *Pseudomonas* species have been reported as LPEs (Matsumoto et al. 2010; Taguchi et al. 2008; Taguchi 2010; Tajima et al. 2009; Yamada et al. 2010; Yang et al. 2011), there have been no reports of LPEs with high thermal stabilities. Therefore, PhaC1_{SG}(STQK) is the first thermostable LPE. The P(LA-*co*-3HB) production at higher temperature (45 °C) could not be performed, probably because of the low thermal stabilities of the enzymes, ACS and PCT, employed for HACoAs supply; however, such production will be possible with thermostable

ACSs and PCTs. Such studies of this line are now in progress and will be reported in the near future.

Acknowledgements

First of all, we would like to greatly thank Professor Tohru Dairi of Hokkaido University for his valuable comments on this paper. We thank Mr. Eiji Yamada of Hokkaido University for his technical support in NMR measurements. We also thank Dr. Tokuo Matsushima and Mr. Tetsuya Toriyabe for their technical assistance. This work was supported by a grant from the Global COE Program (Project No. B01: Catalysis as the Basis for Innovation in Materials Science) and by Grant-in-Aid for Scientific Research (No. 21310060 and 21760632) from the Ministry of Education, Culture, Sports, Science, and Technology, Japan. This work was partially supported by the Regional Innovation Cluster Program (Global Type) and by Northern Advancement Center for Science & Technology (NOASTEC).

References

- Abe H, Doi Y, Hori Y, Hagiwara T (1997) Physical properties and enzymatic degradability of copolymers of (*R*)-3-hydroxybutyric acid and (*S, S*)-lactide. *Polymer* 39:59–67
- Amara AA, Rehm BHA (2003) Replacement of the catalytic nucleophile cysteine-296 by serine in class II polyhydroxyalkanoate synthase from *Pseudomonas aeruginosa*-mediated synthesis of a new polyester: identification of catalytic residues. *Biochem J* 374:413–421
- Anderson AJ, Dawes EA (1990) Occurrence, metabolism, metabolic role, and industrial uses of bacterial polyhydroxyalkanoates. *Microbiol Rev* 54:450–472
- Carrasco F, Pagès P, Gámez-Pérez J, Santana OO, MasPOCH ML (2010) Processing of poly(lactic acid): characterization of chemical structure, thermal stability and mechanical properties. *Polym Degrad Stab* 95:116-125
- Chen JY, Liu T, Zheng Z, Chen JC, Chen GQ (2004) Polyhydroxyalkanoate synthases PhaC1 and PhaC2 from *Pseudomonas stutzeri* 1317 had different substrate specificities. *FEMS Microbiol Lett* 234:231–237
- Fukushima K, Abbate C, Tabuani D, Gennari M, Camino G (2009) Biodegradation of poly(lactic acid) and its nanocomposites. *Polym Degrad Stab* 94:1646-1655
- Golub N, Meremyanin A, Markossian K, Eronina T, Chebotareva N, Asryants R, Muronets V, Kurganova B (2007) Evidence for the formation of start aggregates as an initial stage of protein aggregation. *FEBS Lett* 581:4223-4227
- Han X, Satoh Y, Tajima K, Matsushima T, Munekata M (2009) Chemo-enzymatic synthesis of polyhydroxyalkanoate by an improved two-phase reaction system (TPRS). *J Biosci Bioeng* 108:517–523

- Han X, Satoh Y, Satoh T, Matsumoto K, Kakuchi T, Taguchi S, Dairi T, Munekata M, Tajima K (2011) Chemo-enzymatic synthesis of polyhydroxyalkanoate (PHA) incorporating 2-hydroxybutyrate by wild-type class I PHA synthase from *Ralstonia eutropha*. Appl Microbiol Biotechnol 92:509–517
- Haynes D, Abayasinghe NK, Harrison GM, Burg KJ, Smith DW, Jr (2007) In situ copolyesters containing poly(L-lactide) and poly(hydroxyalkanoate) units. Biomacromolecules 8:1131–1137
- Hein S, Paletta JR, Steinbüchel A (2002) Cloning, characterization and comparison of the *Pseudomonas mendocina* polyhydroxyalkanoate synthases PhaC1 and PhaC2. Appl Microbiol Biotechnol 58:229–236
- Hu D, Chung AL, Wu LP, Zhang X, Chen JC, Chen GQ (2011) Biosynthesis and characterization of polyhydroxyalkanoate block copolymer P3HB-*b*-4HB. Biomacromolecules 12:3166–3173
- Inkinen S, Hakkarainen M, Albertsson AC, Södergård A. (2011) From lactic acid to poly(lactic acid) (PLA): characterization and analysis of PLA and its precursors. Biomacromolecules 12:523-532
- Jendrossek D, Schirmer A, Schlegel HG (1996) Biodegradation of polyhydroxyalkanoic acids. Appl Microbiol Biotechnol 46:451–463
- Jendrossek D, Handrick R (2002) Microbial degradation of polyhydroxyalkanoates. Annu Rev Microbiol 56:403–432
- Jossek R, Steinbüchel A (1998) In vitro synthesis of poly(3-hydroxybutyric acid) by using an enzymatic coenzyme A recycling system. FEMS Microbiol Lett 168:319–324

- Kim TK, Shin HD, Seo MC, Lee JN, Lee YH. (2003) Molecular structure of PCR cloned PHA synthase genes of *Pseudomonas putida* KT2440 and its utilization for medium-chain-length polyhydroxyalkanoate production. *J Microbiol Biotechnol* 13:182–190
- Lee SY (1996) Bacterial polyhydroxyalkanoates. *Biotechnol Bioeng* 49:1–14
- Matsumoto K, Shozui F, Satoh Y, Tajima K, Munekata M, Taguchi S (2009) Kinetic analysis of engineered polyhydroxyalkanoate synthases with broad substrate specificity. *Polym J* 41:237–240
- Matsumoto K, Taguchi S (2010) Enzymatic and whole-cell synthesis of lactate-containing polyester: toward the complete biological production of polylactate. *Appl Microbiol Biotechnol* 85:921–932
- Matsumoto K, Ishiyama A, Sakai K, Shiba T, Taguchi S (2011) Biosynthesis of glycolate-based polyesters containing medium-chain-length 3-hydroxyalkanoates in recombinant *Escherichia coli* expressing engineered polyhydroxyalkanoate synthase. *J Biotechnol* 156:214–217
- Matsusaki H, Manji S, Taguchi K, Kato M, Fukui T, Doi Y (1998) Cloning and molecular analysis of the poly(3-hydroxybutyrate) and poly(3-hydroxybutyrate-co-3-hydroxyalkanoate) biosynthesis genes in *Pseudomonas* sp. strain 61-3. *J Bacteriol* 180:6459–6467
- Nampoothiri KM, Nair NR, John RP (2010) An overview of the recent developments in polylactide (PLA) research. *Bioresour Technol* 101:8493–8501
- Pang X, Zhuang X, Tang Z, Chen X (2010) Polylactic acid (PLA): research, development and industrialization. *Biotechnol J* 5:1125–1136

- Penderson EN, McChalicher CWJ, Sreenc F (2006) Bacterial synthesis of block copolymers. *Biomacromolecules* 7:1904–1911
- Priefert H, Steinbüchel A (1992) Identification and molecular characterization of the acetyl coenzyme A synthetase gene (*acoE*) of *Alcaligenes eutrophus*. *J Bacteriol* 174(20):6590–6599
- Rehm BHA, Qi Q, Beermann BB, Hinz HJ, Steinbüchel A (2001) Matrix-assisted in vitro refolding of *Pseudomonas aeruginosa* class II polyhydroxyalkanoate synthase from inclusion bodies produced in recombinant *Escherichia coli*. *Biochem J* 358:263–268
- Rehm BHA, Antonio RV, Spiekermann P, Amara AA, Steinbüchel A (2002) Molecular characterization of the poly(3-hydroxybutyrate) (PHB) synthase from *Ralstonia eutropha*: in vitro evolution, site-specific mutagenesis and development of a PHB synthase protein model. *Biochim Biophys Acta* 1594:178–190
- Rehm BHA (2003) Polyester synthases: natural catalysts for plastics. *Biochem J* 376:15–33
- Rehm BHA (2007) Biogenesis of microbial polyhydroxyalkanoate granules: a platform technology for the production of tailor-made bioparticles. *Curr Issues Mol Biol* 9:41–62
- Satoh Y, Tajima K, Tannai H, Munekata M (2003) Enzyme-catalyzed poly(3-hydroxybutyrate) synthesis from acetate with CoA recycling and NADPH regeneration in vitro. *J Biosci Bioeng* 95:335–341
- Satoh Y, Tajima K, Nakamoto S, Han X, Matsushima T, Ohshima T, Kawano S, Erata T, Dairi T, Munekata M (2011) Isolation of a thermotolerant bacterium producing medium-chain-length polyhydroxyalkanoate. *J Appl Microbiol* 111:811–817

- Saulnier B, Ponsart S, Coudane J, Garreau H, Vert M (2004) Lactic acid-based functionalized polymers via copolymerization and chemical modification. *Macromol Biosci* 15:232-237
- Shozui F, Matsumoto K, Nakai T, Yamada M, Taguchi S (2010) Biosynthesis of novel terpolymers poly(lactate-co-3-hydroxybutyrate-co-3-hydroxyvalerate)s in lactate-overproducing mutant *Escherichia coli* JW0885 by feeding propionate as a precursor of 3-hydroxyvalerate. *Appl Microbiol Biotechnol* 85:949–954
- Shozui F, Matsumoto K, Motohashi R, Yamada M, Taguchi S (2010) Establishment of a metabolic pathway to introduce the 3-hydroxyhexanoate unit into LA-based polyesters via a reverse reaction of β -oxidation in *Escherichia coli* LS5218. *Polym Degrad Stab* 95:1340–1344
- Shozui F, Matsumoto K, Motohashi R, Sun J, Satoh T, Kakuchi T, Taguchi S (2011) Biosynthesis of a (LA)-based polyester with a 96 mol% LA fraction and its application to stereocomplex formation. *Polym Degrad Stab* 96:499–504
- Song Y, Matsumoto K, Yamada M, Gohda A, Brigham CJ, Sinskey AJ, Taguchi S (2011) Engineered *Corynebacterium glutamicum* as an endotoxin-free platform strain for lactate-based polyester production. *Appl Microbiol Biotechnol* in press
- Steinbüchel A, Hustede E, Liebergesell M, Pieper U, Timm A, Valentin H (1992) Molecular basis for biosynthesis and accumulation of polyhydroxyalkanoic acids in bacteria. *FEMS Microbiol Rev* 9:217–230
- Taguchi S, Doi Y (2004) Evolution of polyhydroxyalkanoate (PHA) Production system by “enzyme evolution”: successful case studies of directed evolution. *Macromol Biosci* 4:145–156

- Taguchi S, Yamada M, Matsumoto K, Tajima K, Satoh Y, Munekata M, Ohno K, Kohda K, Shimamura T, Kambe H, Obata S (2008) A microbial factory for lactate-based polyesters using a lactate-polymerizing enzyme. *Proc Natl Acad Sci USA* 105:17323–17327
- Taguchi S (2010) Current advances in microbial cell factories for lactate-based polyesters driven by lactate-polymerizing enzymes: towards the further creation of new LA-based polyesters. *Polym Degrad Stab* 95:1421–1428
- Tajima K, Satoh Y, Nakazawa K, Tannai H, Erata T, Munekata M (2004) Chemoenzymatic synthesis of poly(3-hydroxybutyrate) in a water-organic solvent two-phase system. *Macromolecules*, 37:4544–4546
- Tajima K, Satoh Y, Satoh T, Itoh R, Han XR, Taguchi S, Kakuchi T, Munekata M (2009) Chemo-enzymatic synthesis of poly(lactate-co-(3-hydroxybutyrate)) by a lactate-polymerizing enzyme. *Macromolecules* 42:1985–1989
- Timm A, Steinbüchel A (1992) cloning and molecular analysis of the poly(3-hydroxyalkanoic acid) gene locus of *Pseudomonas aeruginosa* PAO1. *Eur J Biochem* 209:15–30
- Tsuji H. (2005) Poly(lactide) stereocomplexes: formation, structure, properties, degradation, and applications. *Macromol Biosci* 5:569-597
- Watanabe K, Hata Yasuo, Kizaki H, Katsube Y, Suzuki Y (1997) The refined srystal structure of *Bacillus cereus* oligo-1,6-glucosidase at 2.0 Å thermostabilization. *J Mol Biol* 269:142–153

- Wodzinska J, Snell K, Rhomberg A, Sinskey AJ, Biemann K, Stubbe J (1996) Polyhydroxybutyrate synthase: evidence for covalent catalysis. *J Am Chem Soc* 118:6319–6320
- Yamada M, Matsumono K, Shimizu K, Uramoto S, Nakai T, Shozui F, Taguchi S (2010) Adjustable mutations in lactate (LA)-polymerizing enzyme for the microbial production of LA-based polyesters with tailor-made monomer composition. *Biomacromolecules* 11:815–819
- Yang TH, Jung YK, Kang HO, Kim TW, Park SJ, Lee SY (2011) Tailor-made type II *Pseudomonas* PHA synthases and their use for the biosynthesis of polylactic acid and its copolymer in recombinant *Escherichia coli*. *Appl Microbiol Biotechnol* 90:603–614
- Zhang G, Hang X, Green P, Ho KP, Chen GQ (2001) PCR cloning of type II polyhydroxyalkanoate biosynthesis genes from two *Pseudomonas* strains. *FEMS Microbiol Lett* 198:165–170

Figure Legends

- Fig. 1 Enzymatic synthesis of P(LA-*co*-3HB) by an in vitro reaction system using an LPE
- Fig. 2 Partial alignments of the deduced amino acid sequence of the PHA synthases from *Pseudomonas* sp. SG4502 (SG4502-C1, C2) with those from *P. stutzeri* (Pstu-C1, C2), *P. mendocina* (Pmen-C1, C2), *P. aeruginosa* PAO1 (Paer-C1, C2), *P. putida* (Pput-C1, C2), *Pseudomonas* sp. 61-3 (Pseu613-C1, C2). PhaC1s and PhaC2s refer to PhaC1_{SG} and PhaC2_{SG}, respectively.
- Fig. 3 Comparison of thermal stabilities between PhaC1_{SG}(STQK) and PhaC1_{Ps}(STQK)
- Fig. 4 Time-course changes in protein particle sizes of PhaC1_{SG}(STQK) (solid rhombus) and PhaC1_{Ps}(STQK) (solid square) at 37 °C. The protein particle sizes were determined by dynamic light scattering method
- Fig. 5 ¹H NMR spectra of (a) P(3HB); (b) P(62 mol% LA-*co*-3HB) (Table 5, run 2); (c) P(80 mol% LA-*co*-3HB) (Table 5, run 3) produced by PhaC1_{SG}(STQK). CDCl₃ and TMS were used as a solvent and an internal standard
- Fig. 6 ¹H NMR spectra of (a) P(3HB); (b) chemically synthesized block copolymer, P(3HB-*b*-LA); (b) a product synthesized by PhaC1_{SG}(STQK) treated with 3HBCoA
- Fig. 7 Alignments of the amino acid sequence of the engineered PHA synthases from *Pseudomonas* sp. SG4502 [PhaC1_{SG}(STQK)] and *Pseudomonas* sp. 61-3 [PhaC1_{Ps}(STQK)]. The asterisks mean the mutation points.

Table titles

- Table 1 Bacterial strains, plasmids, and primers
- Table 2 Homologies of amino acid sequences deduced from the ORF1, 2, and 3 to those of PHA synthases and depolymerases from other *Pseudomonas* species
- Table 3 Specific activities of PhaC1_{SG}(STQK) and PhaC1_{Ps}(STQK) at various temperatures
- Table 4 Yields of P(LA-*co*-3HB)s produced by PhaC1_{SG}(STQK) and PhaC1_{Ps}(STQK) at various temperatures
- Table 5 Control of molar ratios of LA and 3HB in polymers

Putative lipase box

	295										450				451					
SG4502-C1	-	-	-	G	A	C	S	G	G	-	-	-	V	N	D	H	I	-	-	-
Pstu-C1	-	-	-	G	A	C	S	G	G	-	-	-	T	T	D	H	I	-	-	-
Pmen-C1	-	-	-	G	A	C	S	G	G	-	-	-	T	T	D	H	I	-	-	-
Paer-C1	-	-	-	G	A	C	S	G	G	-	-	-	L	N	D	H	I	-	-	-
Pput-C1	-	-	-	G	A	C	S	G	G	-	-	-	T	N	D	H	I	-	-	-
Pseu613-C1	-	-	-	G	A	C	S	G	G	-	-	-	T	N	D	H	I	-	-	-

	298										455				456					
SG4502-C2	-	-	-	G	A	C	A	G	G	-	-	-	I	N	D	H	I	-	-	-
Pstu-C2	-	-	-	G	A	C	A	G	G	-	-	-	I	N	D	H	I	-	-	-
Pmen-C2	-	-	-	G	A	C	A	G	G	-	-	-	I	N	D	H	I	-	-	-
Paer-C2	-	-	-	G	A	C	A	G	G	-	-	-	I	T	D	H	I	-	-	-
Pput-C2	-	-	-	G	A	C	A	G	G	-	-	-	S	N	D	H	I	-	-	-
Pseu613-C2	-	-	-	G	A	C	A	G	G	-	-	-	I	N	D	H	I	-	-	-

(a) P(3HB)

(b) P(62 mol% LA-co-3HB)

(c) P(80 mol% LA-co-3HB)

(a) P(3HB)

(b) Chemically synthesized P(3HB-*b*-59 mol% LA)

(c) Product

PhaC1_{SG}(STQK)	1: MNKIAE-DLQROASEHTLSLNPVVGLRGKDLLSSTRQVLVQALRQPLHSTRHVAHFGVQL	59
PhaC1_{Ps}(STQK)	1: MSNKNSSDDLNRQASENTLGLNPVIGLRGKDLLTSARMVLTQAIKQPIHSVKHVAHFGIEL	60
PhaC1_{SG}(STQK)	60: KNVLLGQADLKPEDGDRRFADPAWSHNPLYRRYMQLYLAWRQELHDWIEHSNLPQDISR	119
PhaC1_{Ps}(STQK)	61: KVMFGKSKLQPESDDRRFNDPAWSONPLYKRYLQTYLAWRKELHDWIGNSKLSEQDINR	120
PhaC1_{SG}(STQK)	120: GHFVINLLTEALAPSNSLANPAALKRFFETGGKSLLDGLGHLAKDLVNNGGLPSQVNMEEA	179
PhaC1_{Ps}(STQK)	121: AHFVITLMTTEAMAPTNSAANPAAVKRFFETGGKSLLDGLTHLAKDLVNNGGMPSQVDMGA	180
PhaC1_{SG}(STQK)	180: FEVGKNLALTEGAVVFRNDLLELIQYRNPTEQVHARPLLIVPPQINKFYVFDLSPDKSLV	239
PhaC1_{Ps}(STQK)	181: FEVGKSLGTTEGAVVFRNDVLELIQYRNPTEQVHERPLLIVPPQINKFYVFDLSPDKSLA	240
PhaC1_{SG}(STQK)	240: RFALRSGLQTFILSWRNPTKTQREWGLSTYIEALKEAVEAVLAITGSTDLNMLGACSGGI	299
PhaC1_{Ps}(STQK)	241: RFCLSNNOQTFIWSWRNPTKAQREWGLSTYIDALKEAVDVVSAITGSKDINMLGACSGGI	300
PhaC1_{SG}(STQK)	300: TTAALLGHYAARGEQPIHALTLLVTVLDTEIETQFSLFVDEQTLAAKRRSYQAGVLEGR	359
PhaC1_{Ps}(STQK)	301: TCTALLGHYAALGEKKVNAALTLLVTVLDTTLDLQVALFVDEKTLAAKRRHSYQAGVLEGR	360
PhaC1_{SG}(STQK)	360: NLAKLFAWMRPNDLIWNYWNNYLLGRQPPAFDIIYWNNDTTRLPATLHGDLIELFKTNP	419
PhaC1_{Ps}(STQK)	361: DMAKVFAWMRPNDLIWNYWNNYLLGNEPPVFDILEWNNDTTRLPAAFHGDLIEMFKNNP	420
PhaC1_{SG}(STQK)	420: LPRPGALEVCGTPIDLKQVKSDLYCVAGVNDHITPWEACYRSARLFGGSTEFVLSNSGHI	479
PhaC1_{Ps}(STQK)	421: LVRANALEVSGTPIDLKQVTADIYSLAGTNDHITPWKSCYKSAQLFGGKVEFVLSSSGHI	480
PhaC1_{SG}(STQK)	480: KAILNPPGNPKARFMTGNGELPTEPKAWQENATKQIDSWWLHWQAWLTERSGPLKKAPGK	539
PhaC1_{Ps}(STQK)	481: KAILNPPGNPKSRYMTSTD-MPATANEWQENSTKHSTDWHLHWQAWQAERSGKLLKSPTS	539
PhaC1_{SG}(STQK)	540: LGNKQYPSGEAAPGTIVHER	559
PhaC1_{Ps}(STQK)	540: LGNKAYPSGEAAPGTIVHER	559

Table 1 Bacterial strains, plasmids and primers used in this study

name	relevant characteristics or genotype	source or reference
Strains		
<i>Pseudomonas</i> sp. SG4502	Wild type; PHA+	NITE P-578
<i>E. coli</i> JM109	<i>recA1, endA1, gyrA96, thi, hsdR17, supE44, relA1, Δ(lac-proAB)/F'[traD36, proAB+, lacIq, lacZ</i>	Toyobo
<i>E. coli</i> BL21	F <i>ompT hsdS_B(r_B⁻m_B⁻)gal dcm</i>	Invitrogen
<i>E. coli</i> BL21(DE3)	F <i>ompT hsdS_B(r_B⁻m_B⁻)gal dcm</i> (DE3)	Invitrogen
Plasmids		
pCR2.1-TOPO	TA cloning vector, Ap ^r , Km ^r ; α-lacZ/MCS; P _{lac} , 3.9 kb	Invitrogen
pREP4	LaqI ^q expression plasmid, Km ^r	Qiagen
pQE80	N-terminus His-tagged fusion protein expression vector, Ap ^r ; MCS; P _{T5} ; <i>lacI</i> ^q	Qiagen
pQE30	N-terminus His-tagged fusion protein expression vector, Ap ^r ; MCS; P _{T5}	Qiagen
pQEAcoE	pQE30 derivative; acetylCoA synthetase gene (<i>acoE</i>) from <i>Cupriavidus necator</i> ATCC17699	This study
pQECPP	pQE30 derivative; propionate CoA transferase gene (<i>pct</i>) from <i>Clostridium propionicum</i> JCM1430	Han et al. 2009
pCR-phaSG	pCR2.1-TOPO derivative; <i>pha</i> locus from <i>Pseudomonas</i> sp. SG4502	This study
pQC1SG(WT)	pQE80 derivative; <i>phaC1_{SG}</i> (WT) from <i>Pseudomonas</i> sp. SG4502	This study
pQC1SG(STQK)	pQE80 derivative; <i>phaC1_{SG}</i> (STQK) from <i>Pseudomonas</i> sp. SG4502	This study
Primers		
ORF1_FW	5'-CCA(C/T)GACAGCGGCCTGTTACCTG-3'	Zhang et al. 2001
phaD_RV	5'-TCGACGATCAGGTGCAGGAACAGCC-3'	Zhang et al. 2001
SP(<i>acoE</i> -Bam)	5'-CGGGATCC ATGTCCGCCATCGAATCGGTGA-3'	This study
AP(<i>acoE</i> -Hind)	5'-CCCAAGCTT TCACTGCGCTGCTGAGC-3'	This study
SP(<i>phaC1_{SG}</i> -Bam)	5'-CGGGATCC AACAAGATCGCCGAAGACCTACAG-3'	This study
AP(<i>phaC1_{SG}</i> -Kpn)	5'-GGGGTACC TCATCGTTGGTGCACGTAGGTTCC-3'	This study

Table 2 Homologies of amino acid sequences deduced from the ORF1, 2, and 3 to those of PHA synthases and depolymerases from other *Pseudomonas* species

bacterial species	ORF1	ORF2	ORF3	reference
	PhaC1	PhaZ	PhaC2	
<i>Pseudomonas stutzeri</i>	89%	95%	89%	(Chen et al. 2004)
<i>Pseudomonas mendocina</i>	89%	94%	89%	(Heinet al. 2002)
<i>Pseudomonas aeruginosa</i> PAO1	89%	93%	88%	(Timm et al. 1992)
<i>Pseudomonas putida</i>	87%	92%	84%	(Kim et al. 2003)
<i>Pseudomonas</i> sp. 61-3	86%	92%	86%	(Matsusaki et al. 1998)

Table 3 Specific activities of PhaC1_{SG}(STQK) and PhaC1_{Ps}(STQK) at various temperatures

run	PHA synthase	temperature (°C)	specific activity ^a (U•g-protein ⁻¹)
1	PhaC1 _{SG} (WT)	30	1.0
2	PhaC1 _{SG} (STQK)	30	2.5
3		37	7.2
4		45	9.5
5	PhaC1 _{Ps} (STQK)	30	6.7
6		37	3.8
7		45	n.d. ^b

^aDetermined by measuring concentration of CoA released during the polymerization reaction of 3HBCoA.

^bKey: n.d., not determined.

Table 4 Yields of P(LA-*co*-3HB)s produced by PhaC1SG(STQK) and PhaC1Ps(STQK) at various temperatures

run	PHA synthase	temperature (°C)	molar ratio in a reaction mixture (<i>R</i>)-LA/(<i>R</i>)-3HB	molar ratio in a polymer ^a (<i>R</i>)-LA/(<i>R</i>)-3HB	yield (g•L ⁻¹)	M _w × 10 ^{-5b}	M _w /M _n
1	PhaC1 _{SG} (WT)	30	50/50	n.d. ^c	n.d.	n.d.	n.d.
2	PhaC1 _{SG} (STQK)	30	50/50	60/40	0.51	1.5	2.1
3		37	50/50	63/37	0.77	1.5	2.0
4		45	50/50	n.d.	n.d.	n.d.	n.d.
5	PhaC1 _{Ps} (STQK)	30	50/50	64/36	0.32	1.7	1.9
6		37	50/50	67/33	0.13	n.d.	n.d.
7		45	50/50	n.d.	n.d.	n.d.	n.d.

^aDetermined by measuring concentration of CoA released during the polymerization reaction of 3HBCoA.

^bDetermined by GPC using polystyrene samples as standards in chloroform.

^cKey: n.d., not determined.

Table 5 Control of molar ratios of LA and 3HB in polymers

run	PHA synthase	temperature (°C)	molar ratio in a reaction mixture (<i>R</i>)-LA/(<i>R</i>)-3HB	molar ratio in a polymer ^a (<i>R</i>)-LA/(<i>R</i>)-3HB	yield (g•L ⁻¹)	$M_w \times 10^{-5b}$	M_w/M_n
1	PhaC1 _{SG} (STQK)	37	0/100	0/100	1.10	5.3	2.3
2		37	50/50	62/38	0.68	1.5	2.0
3		37	75/25	80/20	0.70	1.4	1.7
4		37	90/10	87/13	0.30	n.d.	n.d.
5		37	100/0	n.d. ^c	n.d.	n.d.	n.d.
6	PhaC1 _{PS} (STQK)	30	0/100	0/100	1.74	5.1	3.8
7		30	50/50	60/40	0.30	1.8	2.0
8		30	75/25	n.d.	n.d.	n.d.	n.d.
9		30	90/10	n.d.	n.d.	n.d.	n.d.
10		30	100/0	n.d.	n.d.	n.d.	n.d.

^aDetermined by measuring concentration of CoA released during the polymerization reaction of 3HB-CoA.

^bDetermined by GPC using polystyrene samples as standards in chloroform.

^cKey: n.d., not determined.