Title	Application of zerovalent iron impregnated chitosan-caboxymethyl-β-cyclodextrin composite beads as arsenic sorbent
Author(s)	Tajuddin Sikder, M.; Tanaka, Shunitz; Saito, Takeshi; Kurasaki, Masaaki
Citation	Journal of Environmental Chemical Engineering, 2(1), 370-376 https://doi.org/10.1016/j.jece.2014.01.009
Issue Date	2014-03
Doc URL	http://hdl.handle.net/2115/54749
Type	article (author version)
Additional Information	There are other files related to this item in HUSCAP. Check the above URL.
File Information	Final paper- JECE.pdf (本文)

[Instructions for use](#)

1 Application of zerovalent iron impregnated chitosan-
2 caboxymethyl- β -cyclodextrin composite beads as a arsenic
3 sorbent

4 M. Tajuddin Sikder^{a, b, *}, Shunitz Tanaka^{a, c}, Takeshi Saito^d, Masaaki Kurasaki^{a, c}

5 ^aDivision of Environmental Science Development, Graduate School of Environmental
6 Science, Hokkaido University, 060-0810 Sapporo, Japan.

7 ^bDepartment of Environmental Science, Stamford University Bangladesh, Dhaka-1209,
8 Bangladesh

9 ^cGroup of Environmental Adaptation Science, Faculty of Environmental Earth Science,
10 Hokkaido University, 060-0812 Sapporo, Japan.

11 ^dLaboratory of Environmental Health Sciences, Faculty of Health Sciences, Hokkaido
12 University, 060-0812 Sapporo, Japan.

13
14 ***Corresponding author:** Dr. M Tajuddin Sikder, Department of Environmental Science,
15 Stamford University Bangladesh, 44 Satmoshjid Road, Dhanmondi, Dhaka-1209,
16 Bangladesh.

17 Tel: +88-0171150758, E-mail: sikder@ees.hokudai.ac.jp, sikder.stamford@gmail.com

Abstract

Nano zerovalent iron impregnated chitosan-carboxymethyl β -cyclodextrin complex has been successfully tested for arsenic removal. Addition of chitosan enhances the stability of Fe^0 particles and the carboxymethyl β -cyclodextrin gives the composite more active sites to interact with the target ions. Removal of arsenic (III) and arsenic (V) was studied through batch adsorption at pH 6.0 under equilibrium and dynamic conditions. Prepared beads were characterized by FT-IR, SEM, BET and XPS. The rate of reduction can be expressed by pseudo-second-order reaction kinetics plus the equilibrium data were well fitted to Langmuir adsorption models. Equilibrium is achieved after 3 h and As (III) and As (V) were reduced to $<20 \mu\text{g/L}$ which accounts 99% of the total removal below the Bangladesh standard ($50 \mu\text{g L}^{-1}$). The adsorption capacity was calculated from Langmuir model and found to be 18.51 mg/g and 13.51 mg/g for As (III) and As (V), respectively. The adsorbent can be separated magnetically and thus reused successfully for the removal of total inorganic arsenic from water. So, this adsorbent can be a potential material for the remediation of contaminated surface and ground water.

Key words: Arsenic, Removal, Chitosan, Zero valent iron, cyclodextrin, Nanocomposite, Adsorption,

1. Introduction

Arsenic (As) is a dangerous toxicant that poses risk to humans and environment. As contaminated groundwater have been reported in many regions of the world such as Argentina, Bangladesh, Chile, China, India, Japan, Mexico, Mongolia, Nepal, Philippines, Poland, Taiwan, Thailand, Vietnam, and some parts of the United States [1-5]. In Bangladesh, approximately half of the total population is at risk of drinking As-contaminated water from tube wells which resulted in approximately 9,100 deaths and 125,000 disability in 2001 [6]. A nationwide survey reported 27% arsenic contaminated shallow-tube wells (STWs) with elevated As contamination above the Bangladesh standard of 0.05 mg/L [7]. It was also reported by another study that more than 8,000 villages had As contamination in 80% of all STWs above the Bangladesh standard of 0.05 mg/L [8]. The presence of arsenic in water is extremely detrimental to human health [9, 10]. Thus, there is a growing interest in using low-cost methods and materials to remove arsenic from potable water before it may cause significant contamination.

The removal of arsenic by various methods has been adequately reviewed where activated carbon [11], activated alumina [12] and Red mud [13] have extensively used. Zero-valent iron powders (Fe^0) have been extensively used for in situ remediation of water polluted with As in aqueous solution [14-16]. The oxidation of nano-zerovalent iron (NZVI) by water and oxygen produces ferrous iron to give magnetite, depending upon redox conditions and pH which eventually facilitates the magnetic separation [14].

61

62 However, low adsorption due to high diffusion and initial cost has made these technologies
 63 incompetent. In addition, NZVI exhibits high agglomeration, high mobility, lack of stability,
 64 and low reducing specificity in water, and thus must be used with surface stabilizers such as
 65 chitosan (CS), alginate, activated carbon, and others porous structures [17].

66 CS (2-Amino-2-deoxy- β -D-glucopyranose; $\text{C}_6\text{H}_{13}\text{NO}_5$) is an important natural polymer has
 67 found extensive application of adsorbing several metal ions because of its excellent
 68 biocompatibility, biodegradability, and lack of toxicity [18]. Because the amino groups of
 69 CS have the ability to form chelating complexes with various heavy-metal ions, CS-NZVI
 70 should have the removal applicability of total inorganic arsenic.

71 In addition, β -cyclodextrin (β -CD; $\text{C}_{42}\text{H}_{70}\text{O}_{35}$), a cyclic oligosaccharide has been
 72 immobilized or grafted with supportive materials, and active functional groups have been
 73 introduced to enhance its adsorption capacity for metal ions, e.g., carboxymethyl β -CD
 74 (CM β -CD) [19]. The coupling of CM β -CD with functionalized CS followed by the
 75 entrapment of NZVI is expected in this study to facilitate the removal of arsenic from
 76 wastewater. Accordingly, a new CS-NZVI-CM β -CD bead was synthesized in our previous
 77 study by incorporating all the above mentioned potent of CS, CM β -CD and NZVI and the
 78 bead was successfully tested for chromate anion (CrO_4^{2-}) and cationic copper (Cu^{2+})

removal and the removal mechanism was elucidated clearly for metal ions. It was also said about the potentiality of this bead for the arsenic removal [20]. Some papers have reported only CS and activated carbon bearing NZVI beads for As (III) and As (V) removal, but haven't specially studied the combine effects of CS, CM β -CD and NZVI onto arsenic removal [21-25]. In the current studies, both As (III) and As (V) were aimed to remove down to minimum contamination limit (MCL) of 50 μ g/L recommend by Bangladesh Government in the near neutral pH. Herein, a novel arsenic sorbent, NZVI-impregnated porous CS-CM β -CD complex, which has been previously synthesized and successfully tested, is reported. These beads were then evaluated and applied towards the removal of arsenic from arsenic contaminated water.

2. Materials and methods

2.1 Reagents, bead preparation and characterization

Stock solutions of As (III) and As (V) were prepared by dissolving NaAsO₂ (Sigma Aldrich) and Na₂HAsO₄·7H₂O (Fisher Scientific), respectively in deionized water. All other chemicals were of analytical grade purity and were used without further purification. Milli-Q water (Millipore-Gradient A10, Milli-Q Gradient ZMGG) was used in every step where necessary.

CS-NZVI-CM β -CD beads were prepared according to the procedures described in detail in our previous study [20]. Briefly, CM- β -CD sodium salt was complexed with CS flakes in 2% (v/v) acetic acid followed by the addition of 1,3-bis (2,2-diethyl-1,3-dioxolan-4-yl-

100 methyl) carbodiimide in water to obtain CS-CM β -CD gel. Then, different proportion of
101 NZVI (electrolytic powder finer than 100 mesh, 98% purity) was gently added to CS-CM β -
102 CD gel in centrifuge tubes and the resulting mixture was then dropped into the alkaline
103 solution with constant stirring to form CS-NZVI-CM β -CD beads [20, 26, 27]. The
104 characterization of the bead was performed with a Hitachi S-4000 scanning electron
105 microscope (SEM) (Ibaraki, Japan); brunauer-emmett-teller (BET) (Bel-Japan-Inc);
106 fluorescence microscopy (Olympus IX70); fourier transform infrared (FTIR) spectroscopy
107 (FT210, Horiba, Japan) and x-ray photoelectron spectroscopy (XPS) as per the methods
108 described by Sikder et al. 2013 [20]. The beads are reported nearly spherical in shape,
109 blackish and uniform in size with a mean diameter of 2.5 ± 0.10 μ m (Fig. 1a). The result
110 from the image of fluorescence microscopy also suggests the presence of NZVI in CS-
111 CM β -CD interior with no agglomeration. Fig. 1b shows the ashen color macroporous
112 morphology of CS-NZVI-CM β -CD beads [20].

114 2.2 The adsorption batch experiment

115 Adsorption experiments were carried out using batch equilibrium technique in aqueous
116 solutions at pH 2-9 and 298-323 K. In general, a known amount of CS-NZVI-CM β -CD
117 beads with 30 mL aqueous solution of As (III) and As (V) of the desired concentration was
118 taken and shaking in a thermostatic water bath incubator (Hi TEC; BT-23, Japan) or in a
119 shaking mixture (SHM-100) with 120 rpm for a given time. The pH of the solution was
120 carefully checked with a pH meter (Model HM-25R, DKK-TOA Corporation, Tokyo,

Japan) and adjusted with NaOH or HCl solution, if necessary. Except some special cases, the adsorbent mass was 0.1 g; adsorbate dosage was 1 to 20 mg/L; pH was 6.0; and the shaking time was 12 h to achieve complete equilibrium. After a shaking time completed, the CS-NZVI-CM β -CD beads were removed using a strong permanent magnet followed by centrifugation at 2,500 rpm for 5 min. The obtained supernatant was filtered by 0.45 μ m pore size Millipore membrane filters (OmniporeTM, Ireland) to remove the insoluble materials. The As (III) and As (V) contents were measured using an inductively coupled plasma-mass spectrophotometer (ICP-MS; SPQ 6500, Plasma Quadrupole Mass Analyzer, SII-Seiko Instrument, Japan). The lower limit of sensitivity was 0.01 μ g/mL. The accuracy of the analysis was checked by the use of certified standard reference material for As (013–15481, Lot ALK 9912, 1000 ppm) obtained from Wako Pure Chemical Ind. Ltd., Japan. Each equilibrium experiment was performed at triplicate

The accumulated amount of metal ions onto the CS-NZVI-CM β -CD beads was calculated by the following numerical formula;

$$q_t = \frac{C_i - C_e}{W} \times V \quad (4)$$

Where, q_t (mg/g) is the total adsorbed amount in time t (min) C_i and C_e are the initial and equilibrium concentrations (mg/L) of metal ion in the solution, V is the volume and W is the weight (g) of the adsorbent. To describe the efficiency of metal ion removal from the solution, the recovery factor (RF) or percent (%) removal was calculated as follows;

$$RF(\%) = \frac{C_i - C}{C_i} \times 100 \quad (5)$$

Kinetic experiments were performed using different concentration of As (III) and As (V) as initial concentrations with 100 mg of CS-NZVI-CM β -CD beads at pH 6. The suspension was stirred from 0-300 min at 298 K. Samples were collected at different time intervals by the procedure mentioned in the above adsorption experiment. To conduct the equilibrium isotherm studies, 30 mL As (III) and As (V) ions of different concentrations were mixed with 100 mg of CS-NZVI-CM β -CD beads at pH 6.0 and were shaken for 12 h at 298 K, 313 K AND 323 K.

148

2.3 The desorption study

Desorption study was accomplished using 0.1M NaOH (pH 13) or Na₂EDTA (pH 7) as desorption eluants. After adsorption experiments of 1 mg/L As (III) and As (V) ion solution with 100 mg CS-NZVI-CM β -CD beads for 12 h at pH 6.0, the concentration of metal ions in the sorbent were measured. The beads were then washed gently with distilled water to remove unadsorbed metal ions. The amounts of unadsorbed As washed gently with distilled water were measured and found negligible or insignificant and thus it was not considered during desorption study. Desorption was then studied by adding 30 mL of 0.1M NaOH solution to the As (III) and As (V) sorbed CS-NZVI-CM β -CD beads. The regenerated

adsorbent sample was reused in the next cycle of the adsorption experiment. The adsorption-desorption experiments were conducted for five cycles.

3. Results and discussion

3.1 BET analysis

Bigger pore spaces present in the adsorbent are believed to facilitate the mass transfer between the adsorbent and wastewater. In this study, this statement was highly supported by the quick equilibrium achieved within the first 3 hours (Fig. 2a). The pore size distribution of the CS-NZVI-CM β -CD beads was calculated to be 3.5–8.7 μm . BET surface area of the CS-NZVI-CM β -CD beads is obtained as $12.1 \text{ m}^2 \text{ g}^{-1}$ and the pore volume was $2.78 \text{ cm}^3 \text{ g}^{-1}$ (16.35 v/v). The density of the bead was around $>5.85 \text{ g/cm}^3$ where NZVI contributed $>5.0 \text{ g/cm}^3$ indicated the CS-CM β -CD complex can dominate the composite volumetrically and serves as a host for the NZVI particles. The weight of a single dry bead was $\sim 0.005 \text{ g}$, with NZVI constituting 50% of the total weight, and the total shrinkage of the surface area was around 74%. This indicates that NZVI blocked the maximum pores of the CS-NZVI-CM β -CD beads. From the adsorption-desorption (BET) isotherms, the volume of adsorbed N_2 slightly increased with increasing P/P_0 , indicating a small pore size distribution (Fig. 2b).

3.2 Fourier-transform infrared (FTIR) evaluation

To identify possible interactions between CS-NZVI-CM β -CD beads and As (III), the surface functional groups of the adsorbent were observed by FT-IR spectrum before and after the adsorption (Fig. 3). CS-NZVI-CM β -CD has two characteristic peaks at 1654 and 3423 cm⁻¹ are contributed to the N-H or C=O and O-H bending vibration, respectively [20, 28, 29]. The peaks at 1091, 1165 and 1399 cm⁻¹ corresponds to the glycosidic vibration of C-O-C or C-C/ C-O stretch vibration indicating the presence of CM β -CD into the adsorbent (line a in Fig. 3) [20, 28]. A weak bands at 2877 cm⁻¹ ascribes C-H stretch. Adsorption of arsenite species (H₃AsO₃) was evident from the weak band at 710 cm⁻¹ corresponding to the asymmetrical and symmetrical stretching of As-O bond [20, 30]. This infrared absorption must arise from As-O stretch vibrations of adsorbed arsenite species. The results from FTIR showed the complexation between Fe and Arsenic. The characteristic absorption bands for N-H and C-O shifted to 1590 and 1081 cm⁻¹, respectively (line b in Fig. 3) [31, 32]. The peak at 569 cm⁻¹ ascribe to Fe-O group.

3.3 XPS analysis

XPS studies were also employed to comprehend the adsorption mechanism of As (III) and As (V) onto CS-NZVI-CM β -CD beads. The high resolution XPS spectra for the CS-NZVI-CM β -CD beads after As (III) and As (V) reduction were shown in Fig. 4. A single photoelectron peak at 45.5 eV indicates the retention of the oxidation state of As (V) treated with CS-NZVI-CM β -CD beads. In addition, two characteristic peaks corresponding to As

(III) and As (V) were observed at 43.5 and 45.5 eV, respectively (Fig. 4). The earlier XPS studies also support these results [33, 34]. Metal–NH₂ complexes act as mono or bidentate ligands between Fe (III) and As (III) [32]. This process leads to protect the metal precipitation in solution. Photoelectron peaks for 2p_{3/2} and 2p_{1/2} of oxidized iron Fe (III) were found at 711 and 724.5 eV [20]. Of note, the characteristic peak for NZVI at 706.5 eV was absent due to the extensive oxidation of iron by the oxidation-reduction reaction. Hence it could be concluded that after adsorption, partial oxidation of arsenite takes place on the surface of the sorbent.

3.4 Effects of adsorbent dosage and pH

Adsorbent dosage is an important parameter in the removal of metal ions by adsorption. Our studies showed that the removal of both As (III) and As (V) increased when the dose of CS-NZVI-CMβ-CD increased from 0.1 to 1 g/30 mL for initial metal concentrations of 1 mg/L (Fig. 5a). It is evident from Fig. 5a that As (III) and As (V) can be lowered below the Bangladesh standard (50 ppb) and eventually to the international standard level (10 ppb) by increasing the adsorbent dosage. In addition, the removal rates of As (III) and As (V) increased with increasing iron loadings (data not shown). However, the NZVI loading was found to be dependent on the size of the adsorbent. For example, for the 2.5 mm beads used in this study, the maximum NZVI load was 1 g/30 mL to avoid oxidation, corrosion, and loss of iron particles.

The effect of pH on As (III) and As (V) removal was tested using CS-NZVI-CM β -CD beads at the concentration level 2 mg/L for the pH values ranging from 2–9 (Fig. 5b). Elemental As is water insoluble but As salts exhibit a wide range of solubilities depending on pH and the ionic environment. From the pH-pE relation of As (when pH = 0, pE $\approx$ 11) it is known that As can exist in four valency states: –3, 0,+3,+5. Under reducing conditions, the +3 valency state as arsenite, As (III) is the dominant form in water; the +5 valency state as arsenate, As (V) is generally the more stable form in oxygenized environments [11, 35]. Efficient adsorption was found over the wide range of pH where NZVI present in the adsorbent reduced As (V) to As (III) which subsequently gets complexed with oxidized iron and chitosan. Generally, Fe⁰ donates its electrons to protons and is oxidized to Fe (III) whereas the protons are reduced to hydrogen gas [26]. As a result, the bead surface becomes more positively charged, establishing an electrostatic attraction between adsorbent and adsorbate. More than 98% of As (III) and As (V) species were adsorbed at pH ranges from 5 to 7. The adsorption decreased significantly at pH <5.0 and >7.0, because of the high ionic mobility of [H₃O]⁺ in water as compared with most other ions [32, 36, 37].

3.5 Adsorption kinetics

The adsorption of As (III) and As (V) on the CS-NZVI-CM β -CD composite beads was fast and reached equilibrium within 3 h. Adsorption increased with an increase in contact time due to due to the efficient reaction caused by the adsorbent composition of the materials. Pseudo-first-order and pseudo-second-order models were tested. The Lagergren's first-order

equation measures the rate sorption by assuming that one ion is sorbed onto one sorption site and can be expressed as follows [38]:

$$\ln(q_e - q_t) = \ln q_e - k_1 t \quad (6)$$

where q_t is the amount of adsorbate adsorbed (mg/g) at time t , k_1 is the Lagergren's first-order rate constant (min^{-1}). k_1 and q_e at 298K were calculated from the intercept and slope of the plot $\ln (q_e - q_t)$ versus t (Figures not shown). The corresponding correlation coefficients suggest that the pseudo first-order model did not fit well (Table 1). Pseudo second-order model usually applied for analyzing chemisorptions kinetics in solution and the equation can be represented as [38]:

$$\frac{t}{q_t} = \frac{1}{k_2 q_e^2} + \frac{1}{q_e} t \quad (7)$$

Where k_2 (g/mg min) is the second order rate constant and q_e is the equilibrium sorption capacity. k_2 and q_e can be determined experimentally by plotting t/q_t versus t (Figures not shown). The corresponding correlation coefficients derived from the second order equation are healthy and thus assume that one metal ion is sorbed onto two sorption sites on the adsorbent with chemisorptions process (Table 1). Removal of As with iron coated particle has been attributed to ion exchange, specific adsorption to surface hydroxyl groups, or coprecipitation. Improved As adsorption in near alkaline pH range was attributed to a depression of negative solid surface charges in the alkaline region, caused by the presence

of the inorganic electrolyte, enhancing the interactions between the surface sites and arsenic oxyanions.

The removal of As (III) and As (V) can be explained by the respective speciation differences. As(V) in solution above pH 3 is present in anionic forms (AsO_4^{3-} , HAsO_4^{2-} , H_2AsO_4^-) and therefore can be effectively removed by iron hydroxide attached to the surface of the beads [11].

On the other hand, As (III) is present as an anion exclusively above pH 9 (AsO_3^{3-} , HAsO_3^{2-} , H_2AsO_3^-) whereas in the pH interval 6–9 only a small percentage of H_3AsO_3 is dissociated. The responsible mechanism for the removal of arsenic was adsorption on iron-modified adsorbents, which refers to the formation of surface complexes between soluble arsenic species and the surface hydroxyl groups, as arsenic gets in contact with the iron sites [14].

3.6 Equilibrium isotherms

The adsorption isotherms notify specific relation between the equilibrium concentration of adsorbate in the bulk and the adsorbed amount at the surface of adsorbent. The Langmuir adsorption isotherm has been successfully used in many monolayer adsorption processes. The Freundlich isotherm is generally applied to model both monolayer (chemisorption) and multilayer (physisorption) adsorption on heterogeneous surfaces [39-41]. Temkin isotherm model describes indirect adsorbent-adsorbate interaction and assumes that the adsorption energy in the layer would decrease linearly with coverage (Fig. 6) [33].

Langmuir isotherm parameter fits for As (III) and As (V) adsorption on CS-NZVI-CM β -CD beads are in good agreement with observed behavior ($R^2 \geq 0.99$) (Table 2). The adsorption capacity of As (III) and As (V) on CS-NZVI-CM β -CD beads at room temperature (298 K) were 18.51 and 13.51 mg/g, respectively (Fig. 6a) (Table 2). This capacity was observed as high in compare with some existing high performance adsorbents reported in the literature especially, iron chitosan granules (2.24 mg/g for As (V) and 2.32 mg/g for As (III)) [23]; TiO₂-impregnated chitosan bead (6.4 mg/g for As (III) and 4.9 mg/g for As (V)) [42]; activated alumina grains (3.48 mg/g for As (III) and 15.9 mg/g for As (V)) [12]; iron doped activated carbons (0.036 mg/g for As (III)) [24]; Activated carbon (Draco) (3.75 mg/g for As (V)) [43]; Iron-Treated Activated Carbon (25.58 mg/g for As (V)) [11]. In case of Freundlich isotherm, the n values greater than unity are classified as L-type isotherms indicating chemisorption for both As (III) and As (V) and reflecting a high affinity between adsorbate and adsorbent (Fig. 6b) (Table 2). The adsorption data were fitted well with Temkin adsorption isotherm with correlation coefficients ≥ 0.91 indicating chemisorption of the adsorbate onto CS-NZVI-CM β -CD beads (Fig. 6c). The earlier findings were further proved that the adsorption of As (III) and As (V) onto CS-NZVI-CM β -CD beads is a complete chemisorption process. The homogeneous distribution of active sites on CS-NZVI-CM β -CD bead surface and uniform distribution of NZVI into the interior may lead to the experimental data fitted well with Langmuir isotherm model.

3.7. Reusability of the adsorbent

Reusability of any adsorbent is of great importance in view of sustainability and cost-effectiveness. Desorption experiment of As (III) and As (V) was conducted using 0.1 M NaOH at room temperature. The effectiveness of CS-NZVI-CM β -CD beads was checked by following the adsorption-desorption process for five cycles with 1 ppm each of As (III) and As (V) (Fig. 7a). The desorption study was carried out using the fresh desorption solution each time. Subsequent washing of the adsorbent was carried out with distilled water and the cycle was repeated. The beads used in the adsorption experiment were regenerated and reused for five times. It can be clearly observed that both the adsorption and desorption efficiency decrease slightly in each cycle. Around 74% of load were found to be desorbed during desorption cycles. In addition, uniform adsorption-desorption trend was evident from the N₂ adsorption-desorption isotherm (BET isotherm) of CS-NZVI-CM β -CD beads (Fig. 2b). Apparently, the repeated adsorption and desorption performance indicates the CS-NZVI-CM β -CD beads as mechanically and chemically robust for the wastewater treatment. Desorption was sufficiently high at the first 4 cycles and decrease sharply at the fifth cycle. In contrast, the adsorption rate of As (III) and As (V) was identical from cycle 1 to cycle 3. The decrease of both adsorption and desorption may be due to the fact of excessive exhaustion of NZVI by reduction process. Further study and improvement are needed to enhance both the adsorption and desorption performance of CS-NZVI-CM β -CD beads.

The entrapment of NZVI into the CS-CM β -CD complex given them suitability, stability and introduce multiple amide, hydroxyl and carboxyl functional groups could enhance the

adsorption capabilities. CS-NZVI-CM β -CD beads were also tested to treat the mixture of multiple metal ions and good adsorption efficiency was found for each metal. Cadmium (Cd (II)), copper (Cu (II)) and chromium (Cr (VI)) were also evaluated with CS-NZVI-CM β -CD beads and high removal rate was observed in each case (Fig. 7b). This result clearly supports the suitability of this adsorbent for both drinking water and waste water treatment.

4. Conclusion

CS-NZVI-CM β -CD beads have been successfully tested for As (III) and As (V) removal by batch adsorption experiments. This CS-NZVI-CM β -CD bead showed that a combined effect of highly-dispersed NZVI particles and highly functional CS-CM β -CD surface gives a fast kinetics to remove both As (III) and As (V) supported by early equilibrium with high adsorption and respective speciation. The adsorption capacity was found to be 18.51 mg/g and 13.51 mg/g for As (III) and As (V), respectively. It has been demonstrated that CS-NZVI-CM β -CD is capable of adsorption in a wide range of pH. The adsorption mechanism is mostly chemisorption. The strong magnetic property of CS-NZVI-CM β -CD beads facilitates easy separation from solution and could be effectively regenerated with 0.1 M NaOH for repeated usage. So, this study may possibly offer a way to effectively use NZVI in many surface or groundwater remediation situations. Detailed investigation and long-term continued experiments are absolutely necessary to treat contaminated water, to understand the regeneration, and to reuse of the beads. Further specialized study must be carried out to verify whether these beads are applicable to realistic As-contaminated

groundwater or surface water based on ionic strength, natural organic matter, etc. or to develop applicable alternatives.

Conflict of interest statement

The authors declare that there are no conflicts of interest.

Acknowledgements

The authors are greatly indebted to Professor Nobuo SAKAIRI, Professor Bunshi FUGETSU, Professor Syunichi Kawaguchi, Mr. A.K. Vipin, Dr. Parvin Begum, and Mr. Motahar Hossain for useful discussions and directions regarding FTIR, SEM, BET, and XPS analysis.

Reference

- [1] H.M. Anawar, J. Akai, K.M. Mostofa, S. Safiullah, S.M. Tareq, Arsenic poisoning in groundwater: health risk and geochemical sources in Bangladesh, *Environ. Int.* 27 (2002) 597-604.
- [2] U.K. Chowdhury, B.K. Biswas, T.R. Chowdhury, G. Samanta, B.K. Mandal, G.C. Basu, C.R. Chanda, D. Lodh, K.C. Saha, S.K. Mukherjee, S. Roy, S. Kabir, Q. Quamruzzaman, D. Chakraborti, Groundwater arsenic contamination in Bangladesh and West Bengal, India, *Environ. Health Perspectives.* 108 (2000) 393-407.

- 362 [3] A.K. Mitra, B.K. Bose, H. Kabir, B.K. Das, M. Hussain, Arsenic-related health
363 problems among hospital patients in southern Bangladesh, *J. Health Popul. Nutr.*
364 20 (2002) 198-204.
- 365 [4] P.K. Pandey, S. Yadav, S. Nair, A. Bhui, Arsenic contamination of the
366 environment: a new perspective from central-east India, *Environ. Int.* 28 (2002)
367 235-245.
- 368 [5] A.H. Smith, E.O. Lingas, M. Rahman, Contamination of drinking-water by arsenic
369 in Bangladesh: a public health emergency, *Bull. World Health Organ.* 78 (2001)
370 1093-1103.
- 371 [6] K.M. Lokuge, W. Smith, B. Caldwell, K. Dear, A.H. Milton, The effect of arsenic
372 mitigation interventions on disease burden in Bangladesh, *Environ. Health Perspect.*
373 112 (2004) 1172-1177.
- 374 [7] BGS and DPHE, Arsenic contamination of groundwater in Bangladesh, British
375 Geological Survey, UK, BGS Technical Report WC/00/19, 2001.
- 376 [8] BBS (Bangladesh Bureau of Statistics), Statistical pocket book of Bangladesh,
377 Bangladesh bureau of statistics, Government of People's Republic of Bangladesh,
378 Dhaka, Bangladesh, 2010.
- 379 [9] A.H Smith, Cancer risks from arsenic in drinking water, *Environ. Health Perspect.*
380 97 (1992) 259-267.
- 381 [10] A. Davis, M.V Ruby, M. Bloom, R. Schoof, G. Freeman, P.D Bergstorm,
382 Mineralogic constraints on the bioavailability of arsenic in smelter-impacted soils,
383 *Environ. Sci. Technol.* 30 (1996) 392-399.

- 384 [11] K.B. Payne, T.M. Abdel-Fattah, Adsorption of Arsenate and Arsenite by Iron-
385 Treated Activated Carbon and Zeolites: Effects of pH, Temperature, and Ionic
386 Strength, *J. Environ. Sci. Health*. 40 (2005) 723–749.
- 387 [12] T.F. Lin, J.K. Wu, Adsorption of arsenite and arsenate within activated alumina
388 grains: equilibrium and kinetics, *Water Res.* 35 (2001) 2049–2057.
- 389 [13] H. Genç-Fuhrman, J.C Tjell, D. McConchie, Increasing the arsenate adsorption
390 capacity of neutralized red mud (Bauxsol), *J. Colloid Interface Sci.* 271 (2004) 313–
391 320.
- 392 [14] S.R. Kanel, B. Manning, L. Charlet, H. Choi, Removal of Arsenic (III) from
393 Groundwater by Nanoscale Zero-Valent Iron, *Environ. Sci. Technol.* 39 (2005)
394 1291–1298.
- 395 [15] S. Dixit, J.G. Hering, Comparison of arsenic (V) and arsenic(III) sorption onto iron
396 oxide minerals: implications for arsenic mobility, *Environ. Sci. Technol.* 37 (2003)
397 4182-4189.
- 398 [16] C. Su, R.W Puls, Arsenate and arsenite removal by zerovalent iron: kinetics, redox
399 transformation, and implications for in situ groundwater remediation, *Environ. Sci.*
400 *Technol.* 35 (2001) 1487-1492.
- 401 [17] F. He, D. Zhao, Preparation and characterization of a new class of starch-stabilized
402 bimetallic nanoparticles for degradation of chlorinated hydrocarbons in water,
403 *Environ. Sci. Technol.* 39 (2005) 3314–3320.

- 404 [18] Y.C. Chang, D.H. Chen, Preparation and adsorption properties of monodisperse
405 chitosan-bound Fe_3O_4 magnetic nanoparticles for removal of Cu (II) ions, *J. Colloid*
406 *Interface Sci.* 283 (2005) 446–451.
- 407 [19] T.J. Malefetse, B.B. Mamba, R.W. Krause, M.M. Mahlambi, Cyclodextrin-ionic
408 liquid polyurethanes for application in drinking water treatment, *Water SA.* 35
409 (2009) 729–734.
- 410 [20] M.T. Sikder, Y. Mihara, M.S. Islam, T. Saito, S. Tanaka, M. Kurasakia, Preparation
411 and characterization of chitosan-carboxymethyl- β -cyclodextrin entrapped nano zero-
412 valent iron composite for Cu (II) and Cr (VI) removal from wastewater, *Chem. Eng.*
413 *J.* 236 (2014a) 378-387.
- 414 [21] B.A. Manning, M. Hunt, C. Amrhein, J.A. Yarmoff, Arsenic(III) and arsenic(V)
415 reactions with zerovalent iron corrosion products, *Environ. Sci. Technol.* 36 (2002)
416 5455-5461.
- 417 [22] V. Fierro, G. Muñiz, G. Gonzalez-Sánchez, M.L. Ballinas, A. Celzard, Arsenic
418 removal by iron-doped activated carbons prepared by ferric chloride forced
419 hydrolysis, *J. Hazard. Mater.* 168 (2009) 430–437.
- 420 [23] A. Gupta, V.S. Chauhan, N. Sankararamakrishnan, Preparation and evaluation of
421 iron–chitosan composites for removal of As(III) and As(V) from arsenic
422 contaminated real life groundwater, *Water Res.* 43 (2009) 3862–3870.
- 423 [24] G. Muñiz, V. Fierro, A. Celzard, G. Furdin, G. Gonzalez-Sánchez, M.L. Ballinas,
424 Synthesis, characterization and performance in arsenic removal of iron doped

activated carbons prepared by impregnation with Fe(III) and Fe(II), *J. Hazard. Mater.* 165 (2009) 893–902.

[25] K.P. Raven, A. Jain, R.H. Loeppert, Arsenite and arsenate adsorption on ferrihydrite: kinetics, equilibrium, and adsorption envelopes, *Environ. Sci. Technol.* 32 (1998) 344–349.

[26] A.Z.M. Badruddoza, A.S.H. Tay, P.Y. Tan, K. Hidajat, M.S. Uddin, Carboxymethyl- β -cyclodextrin conjugated magnetic nanoparticles as nano-adsorbents for removal of copper ions: Synthesis and adsorption studies, *J. Hazard. Mater.* 185 (2011) 1177–1186.

[27] A. Gupta, M. Yunus, N. Sankararamakrishnan, Zerovalent iron encapsulated chitosan nanospheres – A novel adsorbent for the removal of total inorganic Arsenic from aqueous systems, *Chemosphere* 86 (2012) 150–155.

[28] J.A. Tossell, Theoretical studies on arsenic oxide and hydroxide species in minerals and in aqueous solutions, *Geochim. Cosmochim. Acta* 61 (1997) 1613–1623.

[29] M.T. Sikder, M.S. Islam, T. Kikuchi, J. Suzuki, T. Saito, M. Kurasaki, Removal of copper ions from water using epichlorohydrin cross-linked β -cyclodextrin polymer: Characterization, isotherms and kinetics, *Water Environ. Res.* (2014b). doi:10.2175/WER-D-12-00340.1.

[30] Y. Wan, H. Wu, A. Yu, D. Wen, Biodegradable polylactide/chitosan blend membranes, *Biomacromolecules*. 7 (2006) 1362–1372.

- 445 [31] C. Su, R.W. Puls, Arsenate and arsenite removal by zerovalent iron: effect of
446 phosphate, silicate, carbonate, borate, sulfate, chromate, molybdate, and nitrate,
447 relative to chloride, Environ. Sci. Technol. 35 (2001) 4562–4568.
- 448 [32] M.T. Sikder, T. Kikuchi, J. Suzuki, T. Hosokawa, T. Saito, M. Kurasaki, Removal
449 of Cadmium and Chromium Ions Using Modified α , β , and γ -Cyclodextrin
450 Polymers, Sep. Sci. Technol. 48 (2013) 587-597.
- 451 [33] S. Bang, M.D.Johnson, G.P. Korfiatis, X. Meng, Chemical reactions between
452 arsenic and zerovalent iron in water, Water Res. 39 (2005) 763–770.
- 453 [34] A.J. Varma, S.V. Deshpande, J.F. Kennedy, Metal complexation by chitosan and its
454 derivatives: a review, Carbohydr. Polym. 55 (2004) 77–93.
- 455 [35] S.C. Chien, S. Chen, M. Geethangili, H.B. Huang, Adsorption Characteristics of
456 Aqueous Arsenic(III) and Arsenic(V) in Taiwan Soils, Int. J. Appl. Sci. Eng. 10
457 (2012) 333-344.
- 458 [36] M.S. Islam, Y. Ueno, M.T. Sikder, M. Kurasaki, Phytoremediation of arsenic and
459 cadmium from the water environment using *Micranthemum Umbrosum* (J.F. Gmel)
460 S.F. Blake As A Hyperaccumulator, Int. J. Phytorem. 15 (2013) 1010-1021.
- 461 [37] A.F. Maria, F.G. Carmen, A.D. Manuel, G.S. Vicente, Adsorption of cadmium on
462 carbonaceous adsorbents developed from used tire rubber, J. Environ. Manage. 92
463 (2011) 2193-2200.
- 464 [38] S. Lagergren, Zur theorie der sogenannten adsorption gelöster stoffe, Kungliga
465 Svenska Vetenskapsakad Handl. 24 (1898) 1–39.

- 466 [39] H. Freundlich, Über die adsorption in lösungen (adsorption in solution), Z. Phys.
467 Chem. 57 (1906) 384–470.
- 468 [40] H. Zheng, Y. Wang, Y. Zheng, H. Zhang, S. Liang, M. Long, Equilibrium, kinetic
469 and thermodynamic studies on the sorption of 4-hydroxyphenol on Cr-bentonite,
470 Chem. Eng. J. 143 (2008) 117–123.
- 471 [41] O.S. Thirunavukkarasu, T. Viraraghavan, K.S. Subramanian, O. Chaalal, M.R.
472 Islam, Arsenic removal in drinking water–impacts and novel removal technologies,
473 Energy Sources 27 (2005) 209–219.
- 474 [42] S.M. Miller, J.B. Zimmerman, Novel, bio-based, photoactive arsenic sorbent: TiO₂
475 impregnated chitosan bead, Water Res. 44 (2010) 5722-5729.
- 476 [43] C.P. Huang, P. Fu, Treatment of As(V) containing water by activated carbon, J.
477 Water Pollut. Contr. Fed. 56 (1984) 232.
- 478
- 479

Figure Captions

Fig. 1. SEM image of CS-NZVI-CM β -CD beads; (a) size and spherical shape of the wet beads and (b) the internal network of the pores of CS-NZVI-CM β -CD beads.

Fig. 2. (a) As (III) and As (V) removal efficiency of CS-NZVI-CM β -CD beads (b) Adsorption (ADS) and desorption (DES) isothermal curve of CS-NZVI-CM β -CD beads from BET.

Fig. 3. FTIR spectra of CS-NZVI-CM β -CD beads. Spectrum a: before As (III) ion adsorption; spectrum b: after As (III) adsorption. Initial As (III) concentrations, 1 mg/L; adsorbent dose, 0.10 g; pH 6; temperature, 298 K.

Fig. 4. XPS general spectra of CS-NZVI-CM β -CD beads. CS-NZVI-CM β -CD beads loaded with As (III) and As (V). Initial As (III) and As (V) concentrations, 1 mg/L; adsorbent dose, 0.10 g; pH 6; temperature, 298 K.

Fig. 5. (a) Effects of pH and (b) adsorbent dosage on the adsorption of As (III) and As (V).

Fig. 6. Linearized equilibrium isotherms. (a) Langmuir; (b) Freundlich; (c) Temkin isotherms for As (III) and As (V) adsorption on CS-NZVI-CM β -CD beads.

Fig. 7. Reusability studies of the CS-NZVI-CM β -CD beads with As (III) and As (V).

Table 1 Adsorption kinetics for As (III) and As (V) on CS-NZVI-CM β -CD composite beads.

Initial concentration (mg/L)	Pseudo-first-order model			Pseudo-second-order model		
	K_1 (min ⁻¹)	$q_{e,cal}$ (mg/g)	R^2	K_2 g/(mg.min)	q_e (mg/g)	R^2
As (III)						
1	0.004	1.18	0.82	1.62	0.28	0.99
2	0.007	0.78	0.92	0.20	0.59	0.99
As (V)						
50	0.013	1.01	0.98	0.50	0.29	0.99
100	0.024	0.35	0.97	0.22	0.60	0.99

Table 2 Langmuir, Freundlich and Temkin isotherm model constants and correlation coefficients for sorption of As (III) and As (V) onto CS-NZVI-CM β -CD beads at 298 K and pH 6.

Metal	Langmuir			Freundlich			Temkin		
	b (L/mg)	Q_0 (mg/g)	R^2	K_f (mg/g (L/mg) ^{1/n})	n	R^2	A (L/mg)	B	R^2
As (III)	0.18	18.51	0.99	2.60	1.11	0.91	13.23	3.75	0.91
As (V)	0.06	13.51	0.99	2.70	1.23	0.83	13.67	3.69	0.94