



| | |
|------------------------|--|
| Title | Efficient Microbial Production of Lactate-based Polymers Using Hemicellulose-derived Carbon Sources [an abstract of dissertation and a summary of dissertation review] |
| Author(s) | NDUKO, JOHN MASANI |
| Citation | 北海道大学. 博士(工学) 甲第11482号 |
| Issue Date | 2014-03-25 |
| Doc URL | http://hdl.handle.net/2115/55392 |
| Rights(URL) | http://creativecommons.org/licenses/by-nc-sa/2.1/jp/ |
| Type | theses (doctoral - abstract and summary of review) |
| Additional Information | There are other files related to this item in HUSCAP. Check the above URL. |
| File Information | John_Masani_Nduko_abstract.pdf (論文内容の要旨) |



[Instructions for use](#)

学位論文内容の要旨

博士の専攻分野の名称 博士(工学) 氏名 ジョン マサニ ンドウコ

学位論文題名

Efficient Microbial Production of Lactate-based Polymers Using Hemicellulose-derived Carbon Sources

(ヘミセルロース由来炭素源を利用した乳酸ベースポリマーの効率的な微生物生産)

The biopolymer, polylactic acid (PLA), which is produced from renewable carbon resources, can be used as a plastic replacement for the petrochemical-derived plastics that cause global warming and petroleum depletion problems. The aim of this study was therefore to produce the useful LA-based polyester using the inexpensive carbon sources derived from lignocellulosic biomass. The utilization of lignocellulosic biomass has advantages over the most used starch and sugar-based carbon sources in that lignocellulosic biomass is inedible and inexpensive. These advantages make lignocellulosic biomass an attractive carbon source in establishing a ‘biorefinery’ for the production of LA-based polymers. PLA is a biocompatible and biodegradable material employed in various applications. Recently, LA-based polyester production system has been established in microorganisms using a lactate-polymerizing enzyme (LPE). This system was achieved by cultivating cells expressing LPE to produce LA-based polymers from refined glucose.

In this context, the general introduction including the research theme is described in chapter 1.

In chapter 2, the application of the major lignocellulosic biomass sugar; xylose, for the production of the LA-based polymer, P(lactate-*co*-3-hydroxybutyrate) [P(LA-*co*-3HB)] was reported for the first time in *Escherichia coli* expressing an evolved LPE. The monomer composition and polymer yields of P(LA-*co*-3HB) from xylose were compared with those from glucose. Furthermore, P(LA-*co*-3HB) productivity was compared with that of the most characterized microbial polymer, P(3HB). Analyses of carbon flux and intracellular cofactor level were carried out to understand the differences between the two polymers and between xylose and glucose. The study revealed that xylose could be utilized more efficiently than glucose for the production of P(LA-*co*-3HB) (7.3 g/L) compared to P(3HB) production (4.1 g/L) at flask-scale level. This showed that lactate polymerization conserves carbon than 3HB polymerization, resulting into higher polymer yields. Moreover, xylose was found to give higher LA fractions (60 mol%) in P(LA-*co*-3HB) compared to glucose (47 mol%), which was attributed to the differences in the metabolism of the two sugars that affects the regeneration of the reduced cofactors, NADPH and NADH that are both essential for P(LA-*co*-3HB) synthesis. The results showed the production of P(LA-*co*-3HB) as a potent target for xylose utilization.

In chapter 3, because xylose was demonstrated to be efficiently utilized for the production of LA-enriched P(LA-*co*-3HB), I sought to exploit xylose by optimizing the metabolic pathways. To achieve this, two distinct strategies were employed. First, because xylose uptake consumes ATP, the xylose transport system was engineered by overexpressing an ATP-independent galactitol transporter (GatC), which has also been demonstrated to transport xylose. By overexpressing GatC, P(LA-*co*-3HB) yields of 14.4 g/L were attained, which were the highest polymer yields obtained from xylose or other sugars for the shake-flask scale. Additionally, *E. coli* mutants which have enhanced lactic acid production capacity were employed for P(LA-*co*-3HB) production. This led to the production of P(LA-*co*-3HB) having 73 mol% LA at

6.4 g/L, which was the highest yield for the P(LA-*co*-3HB) with LA-enriched fractions ever reported.

In chapter 4, the utilization of lignocellulosic biomass for the production of polyesters is discussed. Cellulose was hydrolyzed by the recyclable ruthenium catalyst into glucose. However, the hydrolysis reaction formed 5-hydroxymethylfurfural (5-HMF) as a by-product, which was toxic to *E. coli*. Screening of *E. coli* strains identified a 5-HMF resistant strain that was applied for the production of P(3HB) and P[(3HB-*co*-3-hydroxyvalerate (3-HV))]. The strain produced polymers from the hydrolysate with yields that were comparable to those of pure glucose, demonstrating that the strain was resistant against 5-HMF and lignocellulosic biomass could be utilized for polymer production without detoxification steps.

Chapter 5 is the summary of the thesis. In short, for the first time, the major lignocellulosic biomass sugar, xylose, was demonstrated to be efficiently used for P(LA-*co*-3HB) production. Xylose was found to be superior to glucose in giving LA-enriched P(LA-*co*-3HB). Furthermore, the P(LA-*co*-3HB) production system was advanced by engineering the xylose transport system and lactic acid formation-competing pathways to achieve P(LA-*co*-3HB) productivities and LA fractions never achieved before. Finally, the application of lignocellulosic biomass for the production of polymers was demonstrated in a 5-HMF strain, indicating that lignocellulosic biomass could be utilized as good carbon sources thus, replacing pure sugars for the production of polymers.