Title	Photocatalytic O-2 evolution from water over Zn-Cr layered double hydroxides intercalated with inorganic anions
Author(s)	Hirata, Naoya; Tadanaga, Kiyoharu; Tatsumisago, Masahiro
Citation	Materials research bulletin, 62, 1-4 https://doi.org/10.1016/j.materresbull.2014.11.013
Issue Date	2015-02
Doc URL	http://hdl.handle.net/2115/58010
Type	article (author version)
File Information	Zn-Cr LDH photocatalyst final version.pdf

[Instructions for use](#)

Photocatalytic O₂ evolution from water over Zn-Cr layered double hydroxides
intercalated with inorganic anions

Naoya Hirata¹, Kiyoharu Tadanaga^{2*}, and Masahiro Tatsumisago¹

¹ Department of Applied Chemistry, Graduate School of Engineering,
Osaka Prefecture University, 1-1 Gakuen-cho, Naka-ku, Sakai, Osaka 599-8531, Japan

² Faculty of Engineering, Hokkaido University,

Kita-Ku, Sapporo 060-8628, Japan

*Corresponding Author

Kiyoharu TADANAGA(Professor)

Faculty of Engineering, Hokkaido University,

Kita-Ku, Sapporo 060-8628, Japan

E-mail: tadanaga@eng.hokudai.ac.jp

Tel & Fax +81-11-706-6572

Abstract

Zn-Cr layered double hydroxides (LDHs) intercalated with inorganic anions (CO_3^{2-} , Cl^- , SO_4^{2-} and NO_3^-) were synthesized by the co-precipitation method and the anion exchange process. The photocatalytic activity of the LDHs was studied by O_2 evolution from aqueous solution of AgNO_3 as a sacrificial agent. All the prepared LDHs showed photocatalytic activity under either UV and/or visible light irradiation. Besides, the interlayer anions affected the photocatalytic activity of the LDHs. After irradiation, Ag particles were formed on the LDHs by accepting the electrons generated during the photocatalytic reaction.

KEYWORDS: A. inorganic compounds, A. layered compounds, B. intercalation reactions D. catalytic properties

1. Introduction

Photocatalysts have attracted great attention in areas of environmental and energy. TiO_2 and ZnO have been addressed as common photocatalysts by many studies because of their high photocatalytic activity, good chemical stability and low cost [1, 2]. However, they only can be activated under UV light irradiation due to their large band gap. Therefore, in order to utilize maximum solar energy, the development of visible light sensitive photocatalyst has become a hottest topic [3-5].

Layered double hydroxides (LDHs) are a class of anionic clays with the general formula $[\text{M}^{\text{II}}_{1-x}\text{M}^{\text{III}}_x(\text{OH})_2][\text{A}^{n-}_{x/n} \cdot m\text{H}_2\text{O}]$, where M^{II} (Mg^{2+} , Ni^{2+} , Cu^{2+} and Zn^{2+}) and M^{III} (Al^{3+} , Cr^{3+} , Fe^{3+} and Ga^{3+}) are divalent and trivalent metal cations, respectively; A^{n-} is an interlayer anion. LDH consists of the positively charged metal hydroxide layers with anions located in the interlayer for charge compensation of the cationic layers. Because of their potential application in wide range of areas such as catalyst precursors [6], anion exchangers [7], absorbents [8, 9] and bio-active materials [10], LDHs have drawn increasing attention.

In recent years, LDHs have been demonstrated as a potential material in photocatalysis. For example, Silva et al. have reported that Zn-M ($\text{M}=\text{Cr}$, Ti , Ce) LDHs serve as visible-responsive photocatalysts for water splitting [11]. In addition, LDHs are found to exhibit photocatalytic activity for degradation of organic compounds [12, 13], CO_2 conversion [14, 15] and so on. However, almost these reports are about LDHs intercalated

with CO_3^{2-} as the most common interlayer anion. To the best of our knowledge, few reports have described the investigations for the effects of interlayer anions of LDH on its photocatalytic property. On the other hand, we have focused attention on LDHs as ion conducting materials and reported that the ionic conductivities of Mg-Al and Ni-Al LDHs are closely related to the species of interlayer anions [16-18]. In addition, Zn-Cr LDHs intercalated with Cl^- has been reported to be proton conductor [19], while we have proved that Mg-Al and Ni-Al LDHs intercalated with CO_3^{2-} are hydroxide ion conductor [16-18].

In this study, the photocatalytic activity of Zn-Cr LDHs intercalated with various inorganic anions was examined. Zn-Cr CO_3^{2-} LDH was synthesized by the co-precipitation method. Then, Zn-Cr LDHs intercalated with Cl^- , SO_4^{2-} and NO_3^- were prepared by the anion exchange process. The photocatalytic activity of these LDHs was studied by O_2 evolution from aqueous solution of AgNO_3 as a sacrificial agent, under either UV or visible light irradiation.

2. Experimental

2.1. Preparation of samples

Zn-Cr CO_3^{2-} LDH was synthesized by the co-precipitation method [11]. $\text{Zn}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ and $\text{Cr}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$ were dissolved in deionized water in a molar ratio of 2 : 1. The solution was dropped into 2.5 M Na_2CO_3 and 3 M NaOH mixed solution with stirring. The mixture

was aged at 60 °C for 24 h. Then, the resulting purple precipitates were filtrated, washed with distilled water, and dried at 60 °C for overnight.

Zn-Cr Cl^- LDH was prepared by anion exchange process with Zn-Cr CO_3^{2-} LDH as a starting material [20]. First, Zn-Cr CO_3^{2-} LDH was added to an aqueous solution containing 0.005 M HCl and 5 M NaCl with stirring at room temperature under a N_2 flow. After stirring for 24 h, the resulting suspension was filtered and washed with distilled water under a N_2 flow. The remaining precipitates were collected and dried in a vacuum.

The obtained Zn-Cr Cl^- LDH was subjected to further anion exchange [21]. Zn-Cr Cl^- LDH was added to aqueous solution of 0.85 M Na_2SO_4 or 5 M NaNO_3 . The solution was stirred at room temperature for 24 h. Filtration and drying were conducted as described above. Consequently, Zn-Cr LDHs intercalated with SO_4^{2-} and NO_3^- were obtained.

2.2. Characterization

X-ray diffraction (XRD) measurements were performed to identify crystalline phases. Presence of intended anion in the samples was confirmed by Fourier Transform Infrared (FT-IR) spectra. The KBr pellet technique was used for IR measurement. The morphology of the samples was investigated using a scanning electron microscopy (SEM). Optical absorption characteristic was collected using a UV-vis diffuse-reflectance spectroscopy. The specific surface areas were measured by N_2 adsorption on the basis of the Braunauer-Emmett-Teller (BET) equation.

2.3. Photocatalytic reaction

The photocatalytic reaction was carried out in a quartz reaction cell. The prepared LDH powder (40 mg) was dispersed in 0.01 M AgNO_3 aqueous solution (40 mL). Prior to irradiation, the suspension was purged with Ar for 30 min in order to remove dissolved air. Then, the suspension was irradiated using a 300 W Xe lamp for 3 h. In the case of visible light irradiation, a wavelength pass filter ($\lambda > 400$ nm) was employed and the light was irradiated for 5h. The amount of O_2 evolved was estimated by gas chromatograph (GC-8A; Shimadzu Corp.) with Ar as carrier gas. The amount of N_2 measured by gas chromatograph at the same time was regarded as the results of the residual air. Thus, the amount of O_2 from the residual air was estimated from the amount of N_2 , and was subtracted from the measured O_2 amount.

3. Results and discussion

Figure 1 shows XRD patterns of Zn-Cr LDHs prepared by the co-precipitation method and the anion exchange process. The XRD patterns exhibit a series of 00l (l=3, 6) peaks attributed to the layered structure of LDH. The basal spacing of Zn-Cr LDHs is affected by the anion species, suggesting that an interaction between hydroxide layer and interlayer anions is different among the kind of anions.

FT-IR spectra of the obtained Zn-Cr LDHs were measured to identify the interlayer anions, as shown in Figure 2. Zn-Cr CO_3^{2-} LDH prepared by the co-precipitation method shows a strong ν_3 band at around 1380 cm^{-1} with a shoulder at around 1450 cm^{-1} . The intensity of the band at around 1380 cm^{-1} remarkably decreases for the Cl^- -exchanged Zn-Cr LDH. In Zn-Cr LDH exchanged with SO_4^{2-} , a strong band at 1120 cm^{-1} , which is assigned to the ν_3 band of SO_4^{2-} , is observed. In Zn-Cr LDH exchanged with NO_3^- , a band without split is observed at around 1380 cm^{-1} . However, from the XRD results, the basal spacing of Zn-Cr NO_3^- LDH is different from that of Zn-Cr CO_3^{2-} LDH. Thus, the band at around 1380 cm^{-1} in the Zn-Cr LDH exchanged with NO_3^- can be assigned to the ν_3 band of NO_3^- . Although small bands due to CO_3^{2-} ion are still observed in FT-IR spectra of Zn-Cr Cl^- LDH, Zn-Cr SO_4^{2-} LDH and Zn-Cr NO_3^- LDH, these results reveal that Zn-Cr LDHs intercalated with Cl^- , SO_4^{2-} and NO_3^- are obtained by anion exchange process.

Figure 3 shows the SEM images of Zn-Cr LDHs intercalated with CO_3^{2-} , Cl^- , SO_4^{2-} and NO_3^- . All the samples exhibit agglomerated morphology with diameter ranging from 1 to 5 μm . The images prove that the morphology and size of the LDHs did not change obviously during anion exchange process. The UV-vis diffuse reflectance spectrum of Zn-Cr CO_3^{2-} LDH is shown in Figure 4. There are two absorption bands at 410 and 570 nm in the visible region, which can be attributed to the d-d transition $^4\text{A}_{2g}(\text{F}) \rightarrow ^4\text{T}_{1g}(\text{F})$ and $^4\text{A}_{2g}(\text{F}) \rightarrow ^4\text{T}_{2g}(\text{F})$ of Cr^{3+} , respectively [22, 23]. As for Zn-Cr LDHs intercalated with other inorganic anions,

similar spectra were also obtained.

Figure 5 shows the amount of O_2 evolved per hour over Zn-Cr LDHs intercalated with inorganic anions. In all samples, O_2 evolution was confirmed under UV and/or visible light irradiation, and the photocatalytic activity did not change during light irradiation. It can be seen that interlayer anions of the LDH play a key role in determining its photocatalytic property. Zn-Cr Cl^- LDH showed the highest photocatalytic activity among all the prepared samples. After photocatalytic reactions, XRD measurements for Zn-Cr LDHs intercalated with Cl^- and NO_3^- were examined (Figure 6). Both of the patterns show the coexistence of LDH and Ag phases, indicating that Ag^+ accepted the photogenerated electrons and Ag particles were formed. For Zn-Cr Cl^- LDH, AgCl is also observed after photocatalytic reaction because Cl^- in the LDH interlayer reacted with Ag^+ . Recently, Ag/AgX/LDH (X=Br, Cl) composites have been developed as new visible active photocatalysts for the degradation of organic pollutants [24, 25]. Thus, precipitated AgCl on the LDH may also contribute to photocatalytic O_2 evolution. Zn-Cr NO_3^- LDH as well as Zn-Cr Cl^- LDH showed better photocatalytic performance than Zn-Cr LDHs intercalated with divalent anions. The BET surface areas of Zn-Cr LDHs intercalated with CO_3^{2-} , Cl^- , SO_4^{2-} and NO_3^- were 55.4, 27.6, 16.4 and 28.7 m^2/g , respectively. Although the surface area of Zn-Cr NO_3^- LDH is about a half of that of Zn-Cr CO_3^{2-} LDH, NO_3^- intercalated LDH accelerated the photocatalytic O_2 evolution compared with CO_3^{2-} intercalated LDH. Above results imply that the photocatalytic

reaction over the LDH is closely connected with the intercalated anions. The difference in photocatalytic activity is probably related to the reaction between interlayer anions of the LDH and photogenerated holes [26-28]. However, it remains unclear how interlayer anions contribute to the photocatalytic reaction over LDH and further experiments are necessary to elucidate it.

4. Conclusions

Zn-Cr LDHs intercalated with various inorganic anions (CO_3^{2-} , Cl^- , SO_4^{2-} and NO_3^-) were synthesized. All the prepared LDHs showed photocatalytic activity for O_2 evolution from aqueous AgNO_3 solution, under UV and/or visible light irradiation. In addition, interlayer anions affect the photocatalytic properties of Zn-Cr LDHs. In particular, monovalent anion-intercalated LDHs comparatively showed good photocatalytic performance. After the photocatalytic reaction, Ag particles were formed on the LDH, indicating that Ag^+ acted as an electron scavenger.

Acknowledgements

This work was partly supported by a Grant-in-Aid for Scientific Research from the Ministry of Education, Culture, Sports, Science and Technology of Japan, and a grant for research from Nippon Sheet Glass Foundation for Materials Science and Engineering, Japan.

References

- [1] A. Fujishima, T.N. Rao, D.A. Tryk, *J. Photochem. Photobiol. C: Photochem. Rev.*, 1 (2000)1-21.
- [2] N. Daneshvar, D. Salari, A.R. Khataee, *J. Photochem. Photobiol A: Chem.*, 162 (2004) 317-322.
- [3] B. Naik, K.M. Parida, C.S. Gopinath, *J. Phys. Chem. C*, 114 (2010) 19473-19482.
- [4] G. Xi, B. Yue, J. Cao, J. Ye, *Chem. Eur. J.*, 17 (2011) 5145-5154.
- [5] H. Tong, S.X. Ouyang, Y.P. Bi, N. Umezawa, M. Oshikiri, J.H. Ye, *Adv. Mater.* 24 (2012) 229-251.
- [6] M. Behrens, I. Kasatkin, S. Kuhl, G. Weinberg, *Chem. Mater.* 22 (2010) 386-397.
- [7] A.M. Fogg, V.M. Green, H.G. Harvey, D. O'Hare, *Adv. Mater.* 11(1999) 1466-1469.
- [8] P.C. Pavan, G.A. Gomes, J.B. Valim, *Microporous Mesoporous Mater.* 21 (1998) 659-665.
- [9] P.C. Pavan, E.L. Crepaldi, G.D. Gomes, J.B. Valim, *Colloid Surf. A*, 154(1999) 399-410.
- [10] J.H. Choy, J.S. Jung, J.M. Oh, M. Park, J. Jeong, Y.K. Kang, O.J. Han, *Biomaterials*, 25(2004) 3059-3064.
- [11] C.G. Silva, Y. Bouizi, V. Fornes, H. Garcia, *J. Am. Chem. Soc.* 131(2009) 13833-13839.
- [12] M. Shao, J. Han, M. Wei, D.G. Evans, X. Duan, *Chem. Eng. J.*, 168(2011) 519-524.
- [13] K. M. Parida, L. Mohapatra, *Sep. Purif. Technol.*, 91 (2012)73-80.
- [14] K. Teramura, S. Iguchi, Y. Mizuno, T. Shishido, T. Tanaka, *Angew. Chem. Int. Ed.*, 51 (2012) 8008-8011.
- [15] K. Katsumata, K. Sakai, K. Ikeda, G. Carja, N. Matsushita, K. Okada, *Mater. Lett.* 107 (2013) 138-140.
- [16] K. Tadanaga, Y. Furukawa, A. Hayashi, M. Tatsumisago, *Adv. Mater.* 22 (2010) 4401-4404.
- [17] Y. Furukawa, K. Tadanaga, A. Hayashi, M. Tatsumisago, *Solid State Ionics*, 192 (2012) 185-187.

- [18] D. Kubo, K. Tadanaga, A. Hayashi, M. Tatsumisago, *J. Electroanal. Chem.*, 671 (2012) 102-105.
- [19] A.D. Roy, J.P. Besse, *Solid State Ionics*, 46 (1991) 95-101.
- [20] N. Iyi, T. Matsumoto, Y. Kaneko, K. Kitamura, *Chem. Mater.*, 16 (2004) 2926-2932.
- [21] K. Okamoto, T. Sasaki, T. Fujita, N. Iyi, *J. Mater. Chem.*, 16 (2006) 1608-1616.
- [22] J. W. Boclair, P. S. Braterman, *Chem. Mater.*, 10 (1998) 2050-2052.
- [23] J.W. Boclair, P.S. Braterman, J. Jiang, S. Lou, F. Yarberry, *Chem. Mater.* 11 (1999) 303-307.
- [24] H. Fan, J. Zhu, J. Sun, S. Zhang, S. Zhang, S. Ai, *Chem.-Eur. J.*, 19 (2013) 2523-2530.
- [25] J. Sun, Y. Zhang, J. Cheng, H. Fan, J. Zhu, Z. Wang, S. Ai, *J. Mol. Catal. A: Chem.*, 382 (2014) 146-153.
- [26] M. Abdullah, *J. Phys. Chem.*, 94 (1990) 6820-6825.
- [27] M. Sökmen, A. Özkan, *J. Photochem. Photobiol. A*, 147 (2002) 77-81.
- [28] R. Jiang, Y. Guan, H. Zhu, Y. Fu, *Color. Technol.*, 127 (2011) 426-433.

Figure captions

Figure 1 XRD patterns of Zn-Cr LDHs intercalated with inorganic anions.

Figure 2 FT-IR spectra of Zn-Cr LDHs intercalated with inorganic anions.

Figure 3 SEM images of Zn-Cr LDHs intercalated with (a) CO_3^{2-} , (b) Cl^- , (c) SO_4^{2-} , (d) NO_3^- .

Figure 4 UV-vis diffuse reflectance spectrum of Zn-Cr LDH intercalated with CO_3^{2-} .

Figure 5 Yields of O_2 from aqueous solution of AgNO_3 over Zn-Cr LDHs intercalated with inorganic anions.

Figure 6 XRD patterns of Zn-Cr LDHs before and after photocatalytic O_2 evolution reactions from aqueous solution of AgNO_3 under UV light irradiation.