



Title	Amorphous porphyrin glasses exhibit near-infrared excimer luminescence
Author(s)	Morisue, Mitsuhiko; Ueno, Ikuya; Nakanishi, Takayuki; Matsui, Takafumi; Sasaki, Sono; Shimizu, Masaki; Matsui, Jun; Hasegawa, Yasuchika
Citation	RSC advances, 7(37), 22679-22683 https://doi.org/10.1039/c7ra02752d
Issue Date	2017-04-25
Doc URL	http://hdl.handle.net/2115/66172
Rights(URL)	https://creativecommons.org/licenses/by/3.0/
Type	article
Additional Information	There are other files related to this item in HUSCAP. Check the above URL.
File Information	Amorphous porphyrin glasses exhibit near-infrared excimer luminescence .pdf



[Instructions for use](#)



Cite this: *RSC Adv.*, 2017, 7, 22679

Amorphous porphyrin glasses exhibit near-infrared excimer luminescence†

Mitsuhiko Morisue,^a Ikuya Ueno,^a Takayuki Nakanishi,^b Takafumi Matsui,^b Sono Sasaki,^c Masaki Shimizu,^a Jun Matsui^d and Yasuchika Hasegawa^b

The amorphous nature of a series of zinc-porphyrins bearing two 3,4,5-tri(*S*)-3,7-dimethyloctyloxy)phenyl groups at the *meso*-positions, named “porphyrin glass”, were tolerant of π -conjugation engineering in ethynylene-linked dimers. The butadiyne-linked dimeric porphyrin glass formed an intermolecular excimer, which exhibited bright and exceptionally long-lived, near-infrared (NIR) luminescence at approximately 970 nm in the solid state. Therefore, porphyrin glasses overcame a general bottleneck for NIR-luminescence, such as an undesired π -stacked aggregation of a large porphyrin plane in addition to the energy gap law. The formation of amorphous molecular glasses from a series of *meso*-ethynylene-conjugated zinc-porphyrins, named “porphyrin glass”, is described. The butadiyne-linked dimeric porphyrin glass formed an intermolecular excimer, which exhibited solid-state, near-infrared (NIR) luminescence at approximately 970 nm.

Received 7th March 2017
 Accepted 10th April 2017

DOI: 10.1039/c7ra02752d

rsc.li/rsc-advances

Introduction

Metalloporphyrins have been one of the key photofunctional compounds at the forefront of materials science.¹ Near-infrared (NIR) luminescent materials have versatile state-of-the-art applications, in fields such as *in vivo* imaging through the “biological optical window” (800–1350 nm),² light-emitting diodes,³ and broadband optical amplifiers.⁴ However, the wavelength of NIR-luminescence of an organic chromophore barely exceeds 900 nm, with only a few exceptions, such as benzothiadiazole derivatives^{2d,e,3} and polymethine dyes,⁵ as well as porphyrins.⁶ An intrinsic obstacle for NIR luminescence comes from the “energy gap law”. As an optical band-gap narrows, excitons easily dissipate through thermal perturbation from vibrational oscillations.⁷ The *meso*-ethynylene-conjugated porphyrin oligomers exhibit outstanding NIR light-harvesting capacity,^{8,9} based not only on intense linear absorption but also on exceptional two-photon absorption cross-section values.¹⁰ The excellent photoelectronic properties of the porphyrins stem from extended *meso*-ethynylene-

conjugation, but encounter undesired π -stacked aggregation. Such a drawback prevents the ethynylene-conjugated porphyrins from being used in NIR-luminescence applications under matrix-free conditions.¹¹ Amorphous glassy molecules have introduced effective and challenging morphological strategies for attaining photoelectronic functionality that is relevant to molecular formulae.^{12,13} Hence, *meso*-ethynylene-conjugated porphyrin glasses may be potential NIR-luminescent materials.

The present target is based on our serendipitous discovery that a zinc porphyrin bearing two 3,4,5-tri(*S*)-3,7-dimethyloctyloxy)phenyl groups at the *meso*-positions, such as **1**, adopts the form of a solvent-free viscous fluid at room temperature (Fig. 1).¹⁴ Metallocomplexes, including metalloporphyrins, are usually crystalline and barely form amorphous solids with a few exceptions.^{15,16} A deliberate alkylation indicates a potential strategy to provide amorphous molecular glasses. For instance, the introduction of alkyl substituents is crucial for the




Fig. 1 The chemical structures of porphyrin **1** (A) and a photograph of neat **1** as a sticky fluid on a glass slide at room temperature (B).

^aFaculty of Molecular Chemistry and Engineering, Kyoto Institute of Technology, Matsugasaki, Sakyo-ku, Kyoto 606-8585, Japan. E-mail: morisue@kit.ac.jp; Fax: +81-75-724-7806

^bGraduate School of Engineering, Hokkaido University, North 13 West 8, Kita-ku, Sapporo 060-8628, Japan

^cFaculty of Fiber Science and Engineering, Kyoto Institute of Technology, Matsugasaki, Sakyo-ku, Kyoto 606-8585, Japan

^dDepartment of Material and Biological Chemistry, Faculty of Science, Yamagata University, Kojirakawa-cho, Yamagata, 990-8560, Japan

† Electronic supplementary information (ESI) available: Synthetic procedures, GXIS profiles, and emission decay profiles. See DOI: 10.1039/c7ra02752d




morphology of π -conjugated polymers¹⁷ and nonvolatile fluids.^{18,19} Porphyrin fluid **1** prompted us to explore porphyrin glasses with *meso*-ethynylene-conjugations.

Results and discussion

Monomeric porphyrins **1** and **2** showed glass transition temperatures (T_g) at -6 and 19 °C, respectively, in differential scanning calorimetric (DSC) analyses (Scheme 1, Fig. 2), indicating the formation of glass. The results were in sharp contrast with porphyrins incorporating 3,4,5-tri(*n*-alkoxy)phenyl groups at the *meso*-positions, which crystallize without a glass transition from both liquid and liquid crystalline (LC) states.^{19,20} Encouraged by these results, we synthesized **3** and **4** to expand the π -conjugation by connecting two glass-forming porphyrin subunits and aimed to achieve NIR-active porphyrin glasses.

The DSC thermograms of **3** and **4** showed endothermic profiles at 31 °C and 59 °C, respectively, attributed to their glass transitions (Fig. 2), while the others involved enthalpic relaxation. The T_g point shifted to higher temperatures with extended π -conjugations. Porphyrins **1–4** provided neither crystals nor thermotropic LC-phases, even though 3,4,5-tri(*S*)-3,7-dimethyloctyloxyphenyl groups are known as powerful LC-forming units,^{21,22} indicating that the 3,4,5-tri(*S*)-3,7-dimethyloctyloxyphenyl group is an exquisite partner of porphyrin that encumbers the π -stacked interaction. Further investigations of **2–4** were examined in a uniform thin film prepared by a spin-cast method, as shown below.



Scheme 1 Chemical structures of porphyrin **2** and porphyrin dimers **3** and **4**.




Fig. 2 DSC profiles for **1–4** with a 10 °C min^{-1} heating rate.




Fig. 3 The GIXS pattern (inset) and one-dimensional profile of **4** on a silicon wafer observed with a synchrotron X-ray with 0.11° of the incident angle obtained from integrated radial azimuthal angles.

Synchrotron microbeam grazing-incidence X-ray scattering (GIXS) found characteristic amorphous halo patterns at approximately a q ($=2\pi/d$, wherein d refers to spacing) of 13.5 nm^{-1} for **2–4** in spin-cast films on a silicon wafer. However, no periodic spacings were found other than primary intramolecular spacing (Fig. 3). Therefore, the blanched alkyl-chains did indeed govern the intermolecular interactions and disordered porphyrin arrangements in solvent-free bulk solid.

Amorphous molecular glass is expected to be persistent to aggregation-caused fluorescence quenching. Remarkably, the porphyrin glass **4** exhibited broad NIR-luminescence at approximately 970 nm that extended to over 1100 nm (Fig. 4), and the monomeric fluorescence was weakened or extinguished instead. Since none of the electronic absorption bands of **4**




Fig. 4 Emission–excitation correlations of **4** in a spin-cast film on a quartz substrate under air together with an emission spectrum (excitation wavelength = 500 nm) in the upper panel, and excitation (emission wavelength = 970 nm, black line) and absorption (grey line) spectra in the left panel.






Fig. 5 Normalized absorption and emission spectra of neat porphyrin (red) and porphyrin-doped PMMA (10 wt%, blue, and 1 wt% pale blue) (A: **3**, B: **4**) in spin-cast film on a quartz substrate. Emission obtained by excitation at 500 nm.

exceeded 750 nm, the NIR-luminescence was assigned to the intermolecular excited dimer, *i.e.*, the excimer comprised an excited-state intermolecular chromophore associated with a ground-state counterpart, as elucidated below.

Intermolecular excimer formation was evidenced by the dispersion experiments in an amorphous polymer matrix, where 1 and 10 wt% of **4** were doped into an inert poly(methyl methacrylate) (PMMA) film. In the electronic absorption results, the spectral shape of **4** showed no substantial changes regardless of the fraction of **4** used in the PMMA films (1–100 wt%) (Fig. 5 and S2–S4[†]), suggesting the occurrence of marginal intermolecular interactions at the ground state in the neat spin-cast film.²³ However, **4**-doped PMMA films showed monomeric emission at 744 nm, and their NIR-luminescence dramatically weakened. The comparison clearly indicates that an intermolecular excimer formation is indispensable for the NIR-luminescence of porphyrin glass.

Excimer formation was predominantly observed only in **4** among the present porphyrin glasses. For example, **2** and **3** mainly showed monomeric fluorescence, which was accompanied by a weak, broad emission at longer wavelengths. It was deduced that an appropriate internal porphyrin–porphyrin separation of **4** opens a space acceptable for intermolecular excimer formation.

It is remarkable that excimers in the porphyrin glasses surpass general obstacles due to the energy gap law.⁷ Moreover, large π -systems are prone to undesirable π -stacked aggregations. Thus, NIR-luminescent chromophore aggregates have rarely been reported,²⁴ and porphyrins have never been the exception. Unlike structureless emissions from excimers in the




Fig. 6 Emission spectra (red) and electronic absorption (black) (A and B), resonance Raman spectra excited at 532 nm (C and D) of **3** (A and C) and **4** (B and D). Deconvoluted emission peaks with periodic spacings of approximately 1100 cm^{-1} (A) and 1600 cm^{-1} (B) are colored in pale blue and green.

Table 1 NIR luminescence profiles of porphyrin glasses^a

	770 nm		970 nm		$\Phi/\%$
	$\tau_1(\alpha_1)/\text{ns}$	$\tau_2(\alpha_2)/\text{ns}$	$\tau_1(\alpha_1)/\text{ns}$	$\tau_2(\alpha_2)/\text{ns}$	
2	240(0.66)	1311(0.34)	76(0.59)	606(0.41)	0.056
3	231(0.66)	1263(0.34)	132(0.66)	953(0.34)	0.039
4	128(0.54)	756(0.46)	103(0.57)	711(0.43)	0.114

^a Emission lifetime (τ) and normalized pre-exponential factor (α); excitation at 450 nm for **2** and at 500 nm for **3** and **4** (10 wt% **4**-doped PMMA was employed to observe a monomeric component at 770 nm). Tentative emission quantum yield (Φ) was measured for opaque neat drop-cast films by excitation at 450 nm.

solution, the solid-state NIR excimer luminescence bears vibronic features (Fig. 6). The vibronic spacing of approximately 1100 cm^{-1} for **3** and 1600 cm^{-1} for **4** were reminiscent of the resonance Raman vibrational modes of the porphyrin skeleton and ethynylene-linkage (Fig. 6),²⁵ which suggests the presence of exciton–phonon coupling, such as Herzberg–Teller-type dynamic intensity borrowing.^{9,26} We propose that the exciton self-traps to resonantly facilitate radiative decay at the excimer site. Therefore, luminescence remains even at NIR wavelengths.

All the experiments were performed under aerobic conditions, indicating that the NIR-luminescence was relatively persistent to oxygen. The emission lifetimes of the excimer components were considerably elongated ($\tau > 500$ ns) from the monomeric fluorescence ($\tau \approx 100$ ns) (Table 1), in contrast to the very short lifetimes reported for the porphyrin films.²⁷ It was difficult to assign such unusually long-lived luminescence to a singlet exciton, although the photophysical process is the subject under active investigation. The molar extinction coefficient (ϵ) of **4** displays an exceptional order of $10^5 \text{ M}^{-1} \text{ cm}^{-1}$ both



at the Soret and Q bands. The brightness of the emission is defined as the product of the ϵ value and the absolute quantum yield (Φ).²⁸ Although the luminescence efficiency ($\Phi = 0.11\%$ as a tentative magnitude) was still comparable to those of the NIR-luminescent polymethine dyes,⁵ the excellent ϵ magnitude of porphyrin glass **4** ensured sufficient brightness of the NIR-luminescence.

Conclusion

In conclusion, we have developed π -conjugated porphyrin glasses. The amorphous nature of the porphyrin glass was highly tolerant of the *meso*-ethynylene π -conjugation engineering. The excimer luminescence of **4** displayed a remarkable Stokes shift toward the NIR-wavelength region presumably through the aid of exciton-phonon coupling. Ethynylene-conjugated porphyrin glasses have highlighted a new fascinating approach towards developing solid-state NIR-luminescent materials. For instance, their amorphous nature was tolerant of further supramolecular π -electron engineering by employing our supramolecular approach¹⁴ toward NIR-luminescence beyond 1000 nm.²⁹ A further study of NIR-luminescent porphyrin glasses and detailed mechanism of the solid-state NIR-luminescence are currently under active investigation.

Acknowledgements

We are grateful to Prof. H. L. Anderson (University of Oxford) for fruitful discussions, Mr Mitsuru Ohta (Shimadzu Co., Kyoto) for DSC measurements, Ms Kiminori Etou, Dr Yoshihiro Osawa (Otsuka Electronics Co., Shiga) for quantum yield measurements of the NIR luminescence, and Kyoto Integrated Science & Technology Bio-Analysis Center (KIST-BIC) for Raman spectroscopic analysis. The synchrotron radiation experiments were performed at BL45XU in SPring-8 with the approval of RIKEN (Proposal No. 20160041). This study was partly supported by a Grant-in-Aid for Scientific Research on Innovative Areas "New Polymeric Materials Based on Element-Blocks (No. 2401)" (M. M., JP15H00741; J. M., JP15H00720; H. Y., No. 24102012) and KAKENHI (M. M., JP16K05749) from JSPS.

Notes and references

- (a) A. Yella, H.-W. Lee, H. N. Tsao, C. Yi, A. K. Chandiran, M. K. Nazeeruddin, E. W.-G. Diao, C.-Y. Yeh, S. M. Zakeeruddin and M. Grätzel, *Science*, 2011, **334**, 629–634; (b) T. Higashino and H. Imahori, *Dalton Trans.*, 2015, **44**, 448–463; (c) J. P. Hill, *Angew. Chem., Int. Ed.*, 2016, **55**, 2976–2978, and references cited therein.
- (a) R. Weissleder, *Nat. Biotechnol.*, 2001, **19**, 318–317; (b) A. M. Smith, M. C. Mancini and S. Nie, *Nat. Nanotechnol.*, 2009, **4**, 710–711; (c) G. Hong, S. Diao, A. L. Antaris and H. Dai, *Chem. Rev.*, 2015, **115**, 10816–10906; (d) A. L. Antaris, H. Chen, K. Cheng, Y. Sun, G. Hong, C. Qu, S. Diao, Z. Deng, X. Hu, B. Zhang, X. Zhang, O. K. Yaghi, Z. R. Alamparabli, X. Hong, Z. Cheng and H. Dai, *Nat. Mater.*, 2016, **15**, 235–242; (e) Q. Yang, Z. Ma, H. Wang, B. Zhou, S. Zhu, Y. Zhong, J. Wang, H. Wan, A. Antaris, R. Ma, S. Zhang, J. Yang, X. Zhang, H. Sun, W. Liu, Y. Liang and H. Dai, *Adv. Mater.*, 2017, 1605497; (f) G. Hong, A. L. Antaris and H. Dai, *Nature Biomedical Engineering*, 2017, **1**, 0010.
- (a) G. Qian, B. Dai, M. Luo, D. Yu, J. Zhan, Z. Zhang, D. Ma and Z. Y. Wang, *Chem. Mater.*, 2008, **20**, 6208–6216; (b) G. Qian, J. P. Gao and Z. Y. Wang, *Chem. Commun.*, 2012, **48**, 6426–6428.
- (a) S. Zhou, N. Jiang, K. Miura, S. Tanabe, M. Shimizu, M. Sakakura, Y. Shimotsuma, M. Nishi, J. Qiu and K. Hirao, *J. Am. Chem. Soc.*, 2010, **132**, 17945–17952; (b) S. Zhou, Q. Guo, H. Inoue, Q. Ye, A. Masuno, B. Zheng, Y. Yu and J. Qiu, *Adv. Mater.*, 2014, **26**, 7966–7972; (c) Y. Yu, Z. Fang, C. Ma, H. Inoue, G. Yang, S. Zheng, D. Chen, Z. Yang, A. Masuno, J. Orava, S. Zhou and J. Qiu, *NPG Asia Mater.*, 2016, **8**, e318.
- (a) M. Casalboni, F. De Matteis, P. Proposito, A. Quatela and F. Sarcinelli, *Chem. Phys. Lett.*, 2003, **373**, 372–378; (b) S. Hatami, C. Würth, M. Kaiser, S. Leubner, S. Gabriel, L. Bährig, V. Lesnyak, J. Pauli, N. Gaponik, A. Eychmüller and U. Resch-Genger, *Nanoscale*, 2015, **7**, 133–143.
- (a) T. V. Duncan, K. Susumu, L. E. Sinks and M. J. Therien, *J. Am. Chem. Soc.*, 2006, **128**, 9000–9001; (b) M. Pawlicki, M. Morisue, N. K. S. Davis, D. G. McLean, J. H. Haley, E. Beuerman, M. Drobizhev, A. Rebane, A. L. Thompson, S. I. Pascu, G. Accorsi, N. Armaroli and H. L. Anderson, *Chem. Sci.*, 2012, **3**, 1541–1547.
- (a) W. Siebrand and D. F. Williams, *J. Chem. Phys.*, 1968, **49**, 1860–1871; (b) R. Englman and J. Jortner, *Mol. Phys.*, 1970, **18**, 145–164.
- (a) V. S.-Y. Lin, S. G. DiMagno and M. J. Therien, *Science*, 1994, **264**, 1105–1111; (b) V. S.-Y. Lin and M. J. Therien, *Chem.–Eur. J.*, 1995, **1**, 645–651; (c) R. Kumble, S. Palese, V. S.-Y. Lin, S. G. DiMagno, M. J. Therien and R. M. Hochstrasser, *J. Am. Chem. Soc.*, 1998, **120**, 11489–11498.
- (a) H. L. Anderson, *Chem. Commun.*, 1999, 2323–2330; (b) M. U. Winters, J. Kärnbratt, M. Eng, C. J. Wilson, H. L. Anderson and B. Albinsson, *J. Phys. Chem. C*, 2007, **111**, 7192–7199; (c) M.-H. Chang, M. Hoffman, H. L. Anderson and L. M. Herz, *J. Am. Chem. Soc.*, 2008, **130**, 10171–10178.
- (a) M. Pawlicki, H. A. Collins, R. G. Dennig and H. L. Anderson, *Angew. Chem., Int. Ed.*, 2009, **48**, 3244–3266; (b) M. Drobizhev, Y. Stepanenko, Y. Dzenis, A. Karotki, A. Rebane, P. N. Taylor and H. L. Anderson, *J. Am. Chem. Soc.*, 2004, **126**, 15352–15353; (c) H. A. Collins, M. Khurana, E. H. Moriyama, A. Mariampillai, E. Dahlstedt, M. Balaz, M. K. Kuimova, M. Drobizhev, V. X. D. Yang, D. Phillips, A. Rebane, B. C. Wilson and H. L. Anderson, *Nat. Photonics*, 2008, **2**, 420–424.
- (a) J. C. Ostrowski, K. Susumu, M. R. Robinson, M. J. Therien and G. C. Bazan, *Adv. Mater.*, 2003, **15**, 1296–1300; (b) O. Fenwick, J. K. Sprafke, J. Binas, D. V. Kondratuk, F. Di



- Stasio, H. L. Anderson and F. Cacialli, *Nano Lett.*, 2011, **11**, 2451–2456.
- 12 (a) Y. Shirota, *J. Mater. Chem.*, 2000, **10**, 1–25; (b) Y. Shirota, *J. Mater. Chem.*, 2005, **15**, 75–93.
- 13 (a) A. Mishra and P. Bäuerle, *Angew. Chem., Int. Ed.*, 2012, **51**, 2020–2067; (b) M. Grucela-Zajac, K. Bijak, S. Kula, M. Filapek, M. Wiacek, H. Janeczek, L. Skorka, J. Gasiorowski, K. Higerl, N. S. Sariciftci, N. Nosidlak, G. Lewinska, J. Sanetra and E. Schab-Balcerzak, *J. Phys. Chem. C*, 2014, **118**, 13070–13086.
- 14 (a) M. Morisue, Y. Hoshino, K. Shimizu, M. Shimizu and Y. Kuroda, *Chem. Sci.*, 2015, **6**, 6199–6206; (b) M. Morisue, Y. Hoshino, M. Shimizu, S. Uemura and S. Sakurai, *Chem.–Eur. J.*, 2016, **22**, 13019–13022.
- 15 (a) M. R. Robinson, M. B. O'Regan and G. C. Bazan, *Chem. Commun.*, 2000, 1645–1655; (b) Y. Hirai, T. Nakanishi, Y. Kitagawa, K. Fushimi, T. Seki, H. Ito, H. Fueno, K. Tanaka, T. Satoh and Y. Hasegawa, *Inorg. Chem.*, 2015, **54**, 4364–4370.
- 16 (a) M. Ottmar, T. Ishisaka, L. R. Subramanian, M. Hanack and Y. Shirota, *Chem. Lett.*, 2001, 788–789; (b) A. Meunier and O. Lebel, *Org. Lett.*, 2010, **12**, 1896–1899.
- 17 T. Marszalek, M. Li and W. Pisula, *Chem. Commun.*, 2015, **52**, 10938.
- 18 (a) S. S. Babu, M. J. Hollamby, J. Aimi, H. Ozawa, A. Saeki, S. Seki, K. Kobayashi, K. Hagiwara, M. Yoshizawa, H. Möhwald and T. Nakanishi, *Nat. Commun.*, 2013, **4**, 1969; (b) H. Li, J. Choi and T. Nakanishi, *Langmuir*, 2013, **29**, 5394–5406.
- 19 (a) A. Nowak-Król, D. Gryko and D. T. Gryko, *Chem.–Asian J.*, 2010, **5**, 904–909; (b) S. Maruyama, K. Sato and H. Iwahashi, *Chem. Lett.*, 2010, **39**, 714–716.
- 20 (a) X. Zhou, S.-W. Kang, S. Kumar, R. R. Kulkarni, S. Z. D. Cheng and Q. Li, *Chem. Mater.*, 2008, **20**, 3551–3553; (b) T. Sakurai, K. Shi, H. Sato, K. Tashiro, A. Osuka, A. Saeki, S. Seki, S. Tagawa, S. Sasaki, H. Masunaga, K. Osaka, M. Takata and T. Aida, *J. Am. Chem. Soc.*, 2008, **130**, 13812–13813.
- 21 (a) K. Kishikawa, S. Furusawa, T. Tamaki, S. Kohmoto, M. Yamamoto and K. Yamaguchi, *J. Am. Chem. Soc.*, 2002, **124**, 1597–1605; (b) S. Ghosh, X.-Q. Li, V. Stepanenko and F. Würthner, *Chem.–Eur. J.*, 2008, **14**, 11343–11357; (c) F. Helmich, M. M. J. Smulders, C. C. Lee, P. H. J. Schenning and E. W. Meijer, *J. Am. Chem. Soc.*, 2011, **133**, 12238–12246.
- 22 (a) A. P. H. J. Schenning, M. Fransen and E. W. Meijer, *Macromol. Rapid Commun.*, 2002, **23**, 265–270; (b) V. Percec, E. Aquad, M. Peterca, J. G. Rudick, L. Lemon, J. C. Ronda, B. B. De, P. A. Heiney and E. W. Meijer, *J. Am. Chem. Soc.*, 2006, **128**, 16365–16367.
- 23 The spectral shape was reminiscent of the planar conformer similarly to the recent report: H. Doan, S. L. Raut, D. Yale, M. Balaz, S. V. Dzyuba and Z. Gryczynski, *Chem. Commun.*, 2016, **52**, 9510–9513.
- 24 (a) K. Cai, J. Xie and D. Zhao, *J. Am. Chem. Soc.*, 2013, **136**, 28–31; (b) M. Tanioka, S. Kamino, A. Muranaka, Y. Ooyama, H. Ota, Y. Shirasaki, J. Horigome, M. Ueda, M. Uchiyama, D. Sawada and S. Enomoto, *J. Am. Chem. Soc.*, 2015, **137**, 6436–6439.
- 25 D. Beljonne, G. E. O'Keefe, P. J. Hamer, R. H. Friend, H. L. Anderson and J. L. Brédas, *J. Chem. Phys.*, 1997, **106**, 9439–9460.
- 26 (a) M. H. Perrin, M. Gouterman and C. L. Perrin, *J. Chem. Phys.*, 1969, **50**, 4137–4150; (b) H. Kano, T. Saito and T. Kobayashi, *J. Phys. Chem. A*, 2002, **106**, 3445–3453.
- 27 (a) A. Huijser, B. M. J. M. Suijkerbuijk, R. J. M. K. Gebbink, T. J. Savenije and L. D. A. Siebbeles, *J. Am. Chem. Soc.*, 2008, **130**, 2485–2492; (b) X. Wang, G. Brisard, D. Fortin, P.-L. Karsenti and P. D. Harvey, *Macromolecules*, 2015, **48**, 7024–7038.
- 28 K. Rurack and M. Spieles, *Anal. Chem.*, 2011, **83**, 1232–1242.
- 29 M. Morisue, Y. Hoshino, M. Shimizu, T. Nakanishi, Y. Hasegawa, M. A. Hossain, S. Sakurai, S. Sasaki, S. Uemura and J. Matsui, *Macromolecules*, DOI: 10.1021/acs.macromol.7b00316.

