



Title	Muon-Spin Relaxation Study of Ir-Spin Fluctuations in Hole-Doped Pyrochlore Iridates (Y _{1-x-y} Cu _x Cay)2Ir2O7 [an abstract of entire text]
Author(s)	Julia, Angel
Citation	北海道大学. 博士(理学) 甲第13753号
Issue Date	2019-09-25
Doc URL	http://hdl.handle.net/2115/76119
Type	theses (doctoral - abstract of entire text)
Note	この博士論文全文の閲覧方法については、以下のサイトをご参照ください。
Note(URL)	https://www.lib.hokudai.ac.jp/dissertations/copy-guides/
File Information	Julia_Angel_summary.pdf



[Instructions for use](#)

Summary of Doctoral Dissertation

Degree requested Doctor of Science Applicant's name Julia Angel

Title of Doctoral Dissertation

Muon-Spin Relaxation Study of Ir-Spin Fluctuations in Hole-Doped Pyrochlore Iridates



(正孔ドーピングしたパイロクロア型イリジウム酸化物 $(Y_{1-x-y}Cu_xCa_y)_2Ir_2O_7$ における Ir スピン揺らぎ
のミュオンスピン緩和法による研究)

Recently, how the magnetic ordering of pyrochlore iridates $R_2Ir_2O_7$ changes in the boundary of metal-insulator transition (MIT) and eventually to be a possible spin liquid in $Pr_2Ir_2O_7$ remains unknown although those have been studied intensively over the past years. Magnetic properties of Ir moment are expected to play an essential role in various exotic states in $R_2Ir_2O_7$ such as Mott insulator, spin liquid, Weyl semimetal, axion insulator, and so on. Of the pyrochlore iridates, Mott insulator $Y_2Ir_2O_7$ (Y^{3+} : non-magnetic; Ir^{4+} : $5d^5$) serves as an ideal system to investigate the magnetic properties of Ir moment to clarify its origin. This is because the Y atom does not possess a local magnetic moment and larger spin-orbit interactions (no f moment/no d - f interaction). $Y_2Ir_2O_7$ is reported to involve antiferromagnet ordering of Ir moment with all-in-all-out (AIAO) arrangement below the metal-insulator transition temperature, T_{MI} of approximately 170 K. Further, the mechanism of MIT also should be studied by doping holes to the system. Since a critical issue on Mott insulator is the hole-doping effect, we, therefore, investigated the changes in the magnetic properties of $(Y_{1-x-y}Cu_xCa_y)_2Ir_2O_7$ ($x=0.05$) in which the hole concentration can be controlled by substituting Ca for Y. The existence of a so-called quantum critical point (QCP) where the electronic ground state is changed in the vicinity of the zero temperature and near the disappearance of antiferromagnet transition is also theoretically predicted by carrier doping.

In this study, we have initially studied the magnetic properties of $Y_2Ir_2O_7$ and its hole-doped, $(Y_{1-x-y}Cu_xCa_y)_2Ir_2O_7$ with $x = 0.05$ and $y = 0, 0.05, 0.08, 0.10, 0.20,$ and 0.25 by muon-spin relaxation (μ SR) measurement. The synthesis of these compounds is reported in the thesis. We also performed electrical resistivity, heat capacity, and magnetic susceptibility measurements. There is no sharp anomaly observed from results of heat capacity measurement. We then could determine T_{MI} and the magnetic transition temperature, T_N from the resistivity and μ SR measurements, respectively. Finally, the study has indicated that the substitution of Ca^{2+} for Y^{3+} in hole-doped $Y_2Ir_2O_7$ suppresses both T_N and T_{MI} . Moreover, both T_N and T_{MI} decreases with increasing value of y and seems to vanish at around $y = 0.15$ with $x = 0.05$, indicating the existence of QCP. Our μ SR results confirm the presence of an ordered magnetic state at below T_N . The AIAO spin-structure is confirmed from the density functional theory calculation to be the convinced model to explain our μ SR results. As far as we know, we have revealed the phase diagram of hole-doped $Y_2Ir_2O_7$ based on electrical transport and μ SR measurements for the first time.