



Title	Cationic polymerization of dibenzofulvene leading to a pi-stacked polymer
Author(s)	Nageh, Hassan; Wang, Yue; Nakano, Tamaki
Citation	Polymer, 144, 51-56 https://doi.org/10.1016/j.polymer.2018.04.042
Issue Date	2018-05-23
Doc URL	http://hdl.handle.net/2115/78208
Rights	© 2018. This manuscript version is made available under the CC-BY-NC-ND 4.0 license http://creativecommons.org/licenses/by-nc-nd/4.0/
Rights(URL)	http://creativecommons.org/licenses/by-nc-nd/4.0/
Type	article (author version)
Additional Information	There are other files related to this item in HUSCAP. Check the above URL.
File Information	Cationic_Polymn_of_DBF_SI_r3.pdf (Supporting information)



[Instructions for use](#)

Supporting Information to:

Cationic Polymerization of Dibenzofulvene Leading to a π -Stacked Polymer

Hassan Nageh, Yue Wang, Tamaki Nakano*

Institute for Catalysis (ICAT) and Graduate School of Chemical Sciences and Engineering,
Hokkaido University, N 21, W 10, Kita-ku, Sapporo 001-0021, Japan

E-mail: tamaki.nakano@cat.hokudai.ac.jp

Prof. T. Nakano




Fig. S1. IR spectra (full range) of poly(DBF)s prepared by anionic (a), radical (b), and cationic (c) polymerizations. [THF-insoluble polymers, KBr pellet]




Fig. S2. MALDI-TOF mass spectra of THF-soluble poly(DBF)s prepared using $\text{BF}_3\text{-Et}_2\text{O}$ (run 10 in Table 1) and (A) and using $\text{CH}_3\text{SO}_3\text{H}$ (run 11 in Table 1) (B). Samples were prepared by depositing 1 μL of poly(DBF) solution in CHCl_3 (7 mg/mL) onto pre-formed thin layer of dithranol matrix by drop-casting 1 μL of THF solution (10 mg/mL, 4.42×10^{-2} M) in a sample well.




Fig. S3. ¹H NMR spectra of poly(DBF) prepared using BF₃-Et₂O (run 10 in Table 1) before (a) and after heat treatment in CDCl₃ solution at 60°C for 0.5 h (b), 1 h (c), 3 h (d), and 6 h (e). [400 MHz, CDCl₃, 23°C]




Fig. S4. ^1H NMR spectra (aromatic region) of poly(DBF) samples prepared by cationic polymerization using $\text{BF}_3\text{-OEt}_2$ in CH_2Cl_2 at 0°C (run 3 in Table 1) and isolated by preparative SEC: Mn 1430 (a), 1000 (b), 920 (c), 820 (d), and 740 (e). [400 MHz, r.t., CDCl_3]




Fig. S5. Analytical SEC profiles of poly(DBF) samples prepared by cationic polymerization using $\text{BF}_3\text{-OEt}_2$ in CH_2Cl_2 at 0°C (run 3 in Table 1) and isolated by preparative SEC.
