Title	Self-assembled collagen fibrils from the swim bladder of Bester sturgeon enable alignment of MC3T3-E1 cells and enhance osteogenic differentiation
Author(s)	Moroi, Shoichi; Miura, Takayuki; Tamura, Takashi; Zhang, Xi; Ura, Kazuhiro; Takagi, Yasuaki
Citation	Materials Science and Engineering : C, 104, 109925 https://doi.org/10.1016/j.msec.2019.109925
Issue Date	2019-06-28
Doc URL	http://hdl.handle.net/2115/82063
Rights	© 2019. This manuscript version is made available under the CC-BY-NC-ND 4.0 license https://creativecommons.org/licenses/by-nc-nd/4.0/
Rights(URL)	https://creativecommons.org/licenses/by-nc-nd/4.0/
Type	article (author version)
File Information	msec_2019_109925.pdf

[Instructions for use](#)

Self-assembled collagen fibrils from the swim bladder of Bester sturgeon enable alignment of MC3T3-E1 cells and enhance osteogenic differentiation

Shoichi Moroi^a, Takayuki Miura^a, Takashi Tamura^a, Xi Zhang^{a,b}, Kazuhiro Ura^c, and Yasuaki Takagi^{c*}

^a Graduate School of Fisheries Sciences, Hokkaido University, 3-1-1 Minato-Cho, Hakodate, Hokkaido 041-8611, Japan

^b College of Fisheries, National Demonstration Center for Experimental Aquaculture Education, Hubei Provincial Engineering Laboratory for Pond Aquaculture, Huazhong Agricultural University, Wuhan 430070, China

^c Faculty of Fisheries Sciences, Hokkaido University, 3-1-1 Minato-Cho, Hakodate, Hokkaido 041-8611, Japan

E-mails: s.moroichi@gmail.com (S Moroi), s91153088m@frontier.hokudai.ac.jp (T Miura), t.mare.4124@gmail.com (T Tamura), oecanzhangxi@163.com (X Zhang), kazu@fish.hokudai.ac.jp (K Ura), takagi@fish.hokudai.ac.jp (Y Takagi)

*Corresponding author: Yasuaki Takagi (e-mail, takagi@fish.hokudai.ac.jp; TEL/FAX, +138-40-5550)

Abstract

Collagen is the most abundant protein in animals, and its polymer, collagen fibrils, regulate cellular proliferation, differentiation, and migration. Low antigenicity, biocompatibility, and biodegradability make collagen fibrils suitable functional scaffolds for tissue engineering. In a previous study, we found that the type I atelocollagen purified from the swim bladder of Bester sturgeon (swim bladder collagen, SBC) showed high fibril-forming ability, producing thicker fibrils faster than porcine collagen. In this study, we report a novel method to coat cell culture wells with highly aligned collagen fibrils using the SBC. Two types of fibrils with different thicknesses were prepared by changing the crosslinking treatment timing. The oriented, thick collagen fibrils induced pre-osteoblastic MC3T3-E1, pre-adipocytic 3T3-L1, pre-myocytic C2C12, and fibroblastic L929 cells to align in the same direction, whereas the oriented, fine fibrils made a cell network with their long pseudopods. Cellular proliferation was inhibited on both fibrils. Furthermore, both fibrils induced the early differentiation of MC3T3-E1 cells without differentiation stimuli. In contrast, the morphology of pre-chondrocytic ATDC5 cells on both fine and thick fibrils extended very short pseudopods and continued to maintain a spherical shape without stretching, suggesting a distinct effect by the fibrils. The newly developed fibril coatings are in the form of a thin film, thereby providing good visibility of the cell structure, including cell-cell and cell-ECM interactions, using a phase contrast microscope. The fibril coatings have high potential as a useful tool for tissue engineering research.

Keywords: sturgeon collagen, swim bladder collagen (SBC), self-assemble, cell culture, cell orientation

1. Introduction

Collagen is the main component of the extracellular matrix (ECM) in animals and it mechanically supports tissues [1]. Type I collagen, which is found in skin, bones, ligaments, and other tissues, is secreted extracellularly as a triple helical molecule, assembles into fibrils with a diameter of 10–300 nm, and functions as a scaffold for cells [2,3]. Collagen is an excellent biomaterial for artificial scaffolds owing to its high cell adhesiveness, biocompatibility, and biodegradability, and is mainly used in the form of a hydrogel or sponge [4–6]. Recent reports suggest that soluble signaling molecules, such as hormones and cytokines, and insoluble ECMs, such as collagen, also control cell proliferation, differentiation, and migration by transmitting various information [7–10]. Therefore, scaffold materials that control cellular functions have been getting more attention as "smart scaffolds" in tissue engineering [11]. Notably, scaffolds made of atelocollagen are of researchers' interest because they can be introduced into the human body for medical application, even if they have a heterologous origin, because of its low antigenicity [12]. The scaffold needs to have appropriate morphology [13], stiffness [14], and amino acid sequences for cellular attachment [15,16] to adjust cellular functions. For example, the RGD sequence functions to induce cell orientation on collagen fibrils [10].

For mimicking the oriented fibrous form of ECM, such as observed in ligaments, synthetic polymers (e.g., polylactic acid, polyimide) with superior processing have been used with various technologies, such as electrospinning [17,18] and surface micropatterning [19,20]. Recent reports demonstrated the effects of fibril thickness on cellular behavior; for example, 70–100 nm diameter fibrils

promote specific differentiation of human MSCs into osteoblasts [21]. Few reports have described the effects of fibers with diameters on the order of nanometers, as is collagen *in vivo*. Additionally, it is difficult to mimic aligned collagen fibrils *in vivo* owing to the low processing ability of collagen fibrils *in vitro*. Several strategies have been developed to build highly-aligned fibrillar collagen structures, including electrospinning [22], flow casting [23], and high magnetic field [24,25]. For example, control of the fibril alignment by a magnetic field can produce thin diameter fibrils close to natural collagen fibrils. However, the high cost of the process may hinder industrial production and the risk of denaturation of collagen molecules during processing must be considered [26].

In recent years, the most common sources of collagen for biomaterials and tissue engineering have been bovine skin and tendon, porcine skin, and rat tail [27]. However, the use of mammalian collagens has the risk of zoonoses such as bovine spongiform encephalopathy and foot-and-mouth disease. Religious beliefs also restrict the usage of porcine or bovine collagen. Marine collagen derived from aquatic animals has attracted attention as a smart alternative to mammalian collagen owing to their low risk of pathogen infections and low religious restrictions. We observed that the swim bladder of the Bester sturgeon, a hybrid of *Huso huso* × *Acipenser ruthenus*, contains a large amount of type I collagen [28]. Because the Bester sturgeon is a highly valued fish species especially famous for its caviar and is now widely aquacultured in China and Japan, the industrial-scale production of the SBC is possible. In addition, the SBC is characterized by low viscosity, high fibril-forming ability, and relatively high denaturation temperature [28]. However, atelocollagens from other tissues (scale, skin, muscle, digestive tract,

notochord, and snout cartilage) of the Bester sturgeon do not show such properties [28]. The special characteristics of the SBC enable the production of materials with a uniform orientation of fibrils using very easy and low-cost techniques [29,30]. We assumed that the especially high fibril-forming ability of SBC made it possible to align the fibrils with uniform orientation.

In this study, we developed an easy procedure to coat the bottom of cell culture wells with highly oriented fibrils using the SBC, and examined how oriented fibrils affected cell morphology, proliferation, and differentiation.

2. Material and Methods

2.1. Materials

Type I atelocollagen was extracted from the swim bladder of Bester sturgeon as described previously [28]. Porcine pepsin (EC 3.4.23.1, 1:10,000, Wako Pure Chemical Industries Ltd., Osaka, Japan) at a concentration of 0.1% was used for removing telopeptides of collagen molecules. For comparison, porcine skin type I collagen (Cellmatrix type I-C, Nitta Gelatin Inc., Osaka, Japan) was used. Cell culture media and penicillin/streptomycin (P/S) solution were obtained from Thermo Fisher Scientific (Waltham, MA). Hank's balanced salt was obtained from Sigma-Aldrich (St. Louis, MO). Other chemicals were obtained from Wako Pure Chemical Industries Ltd unless otherwise stated. Cell culture wares were from Corning, NY. Cells were obtained from RIKEN Cell Bank (Tsukuba, Japan) and Japanese Collection of Research Bioresources (Tokyo, Japan).

96

97 2.2. *Preparation of collagen-coated wells*

98 Lyophilized SBC was dissolved in an aqueous HCl solution (pH 3.0) at 1.0% (w/v), 4°C without stirring to
99 produce a homogenous solution. A 200 µl aliquot of the atelocollagen solution was poured into each well of
100 a 24-well cell culture plate, incubated for 30 minutes, and the solution was removed. The fibril formation
101 was induced by introducing a 0.1 M Na-phosphate buffer (PB, pH 7.6) into the wells for 24 hours at room
102 temperature (22°C). Crosslinking was performed using a 1 mM genipin in a 0.1 M PB for 24 hours to
103 prevent heat denaturation. Two ways of crosslinking were employed: crosslinking during fibril formation
104 and after fibril formation. In the former case, the PB containing genipin was used to induce fibril formation.
105 In the latter, wells were treated first with PB to induce fibril formation for 24 hours and then with PB
106 containing genipin for a subsequent 24 hours. After the crosslinking, wells were washed twice with cold
107 Hank's balanced salt solution (HBSS) containing 100 U/ml penicillin and 100 µg/ml streptomycin. For
108 comparison, wells were coated with porcine skin type I collagen following the instructions supplied by the
109 company. Briefly, collagen (0.03%, w/v) in an aqueous HCl solution was pipetted into the wells, incubated
110 for 30 minutes at room temperature (22°C), air-dried, crosslinked with PB containing 1 mM genipin for 24
111 hours, and rinsed twice with HBSS. SBC at a concentration of 0.03% was similarly coated. The genipin
112 crosslinking increases the thermal stability of the gels by the same degree as glutaraldehyde and is very low
113 toxicity [31]. 1 mM genipin was used for the crosslinking, under which no cell toxicity was observed [31].

114

2.3. Cell culture

MC3T3-E1, ATDC5, 3T3-L1, C2C12, and L929 cell lines, which showed pre-osteoblastic, pre-chondrocytic, pre-adipocytic, pre-myocytic, and fibroblastic features, respectively, were used to evaluate cellular response. To study the cellular morphology and proliferation, cells were maintained in their respective growth media: Minimum Essential Medium Eagle (MEM)-alpha supplemented with 10% fetal bovine serum (FBS) for the MC3T3-E1 cells, Dulbecco's Modified Eagles Medium/Nutrient Mixture F12 (DMEM/F12) supplemented with 10% FBS for the ATDC5 cells, DMEM supplemented with 10% FBS for the 3T3-L1 and C2C12 cells, and MEM supplemented with 10% FBS for the L929 cells. To study differentiation, MC3T3-E1 cells were seeded and maintained in the growth medium for one day and after that cultured in the osteogenic medium, growth medium supplemented with 10 mM β -glycerophosphate and 50 μ M ascorbic acid (Sigma-Aldrich). All cells were cultured in a humidified incubator at 37°C and 5% CO₂, and media was changed once every three days. All cultures were supplemented with 100 U/ml penicillin and 100 μ g/ml streptomycin.

The cell morphology was observed with a phase contrast microscope (DMI600B, Leica, Wetzlar, Germany) over the cell culture time.

2.4 Scanning electron microscopy

The microstructure of the bottom surface of the cell culture wells coated with the different collagens was studied under a scanning electron microscope (SEM; JSM6010LA, JEOL Ltd., Tokyo, Japan). PB

containing 2.5% (v/v) glutaraldehyde was poured into each well and incubated for 3 hours at room temperature for fixation. The samples were then rinsed twice with PB, dehydrated with ethanol, and the medium was changed to a t-butyl alcohol solution. The samples in t-butyl alcohol were then freeze-dried with a freeze-drying device (JFD-320; JEOL Ltd.), and the sidewalls of each well were cut off. The cell culture bottom was coated with gold-platinum using an auto fine coater (JFC-1600; JEOL Ltd.) and observed and digitally imaged by the SEM. 100 fibrils were randomly selected and their diameters were determined with ImageJ software.

2.5. Cell proliferation analysis

The relative cell number was determined by the measurement of DNA content in the well. At the cell cultures endpoints, the wells were emptied of media and rinsed once with PB containing 0.8% NaCl (PBS). The wells were stored at -30°C. To perform the assay, the well plates were thawed and digested in a cell lysate buffer (0.1 mg/ml Proteinase K with 0.01% SDS in PBS). The DNA content of the sample was measured after appropriate dilution with PBS using a fluorescent plate reader (ARVO X, PerkinElmer, Waltham, MA) (excitation, 355 nm; emission, 460 nm) with the addition of Hoechst 33258 (2 µg/ml). DNA from salmon sperm was used as a standard.

2.6 Differentiation of MC3T3-E1 cells

The osteoblastic differentiation of cultured MC3T3-E1 cells was assessed by quantifying alkaline

phosphatase (ALP) activity, which is synthesized primarily at an early stage of bone differentiation by osteoblasts [32]. The cells were washed with PBS and digested in 0.05% Triton X-100 (MP Biomedicals Inc., Santa Ana, CA). After centrifugation at 21,000g for 15 min (Hitachi Koki, Tokyo, Japan), the supernatants were collected, and the ALP activity was quantified using a LabAssay ALP kit (Wako) following the manufacturer's instructions. The color density was determined at 405 nm by a plate reader (infiniteF50R, Wako).

2.7. Statistics

Data was analyzed by ANOVA and a Tukey–Kramer post hoc test using Microsoft Excel add-in statistical software for multiple comparisons (SSRI, Tokyo, Japan). Values were expressed as the mean $\pm$ standard error. Statistical significance was accepted at $P < 0.05$.

3. Results

3.1. SEM images of collagen-coated wells

When the porcine collagen or SBC solution at a concentration of 0.03% (w/v) was coated on the bottom of the well, several aggregates of collagen molecules were observed, but no fibrils were confirmed (Figs. 1A, B). Thus, we concluded that the bottom was coated with collagen molecules. Hereafter, the coating method is called “molecular coating” and the coated wells “molecule-coated wells”. When the well was coated with a 1% SBC solution, aligned collagen fibrils appeared. By changing the timing of the crosslinking treatment

with genipin, two types of fibril-coated wells showing different fibril thickness were obtained (Figs. 1C, D). When fibrillogenesis and crosslinking were conducted simultaneously for 24 hours using the PB containing genipin, thin fibrils were aligned in the same direction on the well (Fig. 1C). In contrast, when fibrillogenesis for 24 hours and crosslinking for 24 hours were conducted sequentially, thick fibrils overlaid the thin fibrils (Fig. 1D). Both the thick and thin fibrils were aligned in the same direction, but the direction uniformity was greater in the thin fibrils. The diameter range of the simultaneously crosslinked fibrils was 51–192 nm with a mean diameter of 99.0 ± 2.8 nm, while the diameter range of the sequentially crosslinked fibrils was 53–520 nm with a mean diameter of 178.2 ± 8.1 nm (Fig. 2). Hereafter, we call the simultaneously and sequentially crosslinked coating methods as “fine-fibril coating” and “coarse-fibril coating”, respectively, and the coated wells as “fine-fibril-coated wells” and “coarse-fibril-coated wells”, respectively.

3.2. Cell morphology

The cell morphology was examined in the growth media appropriate to each cell type. All cells used in the present study showed good adhesion to all substrates. When the cells were well adhered, their morphologies were generally similar, except for the ATDC5 cells. This paper provides the morphologies of the MC3T3-E1 (Fig. 3) and ATDC5 (Fig. 4) cells as representative examples. The morphologies of 3T3-L1, C2C12, and L929 cells are supplied as Supplementary Materials (Suppl. Figs. 1-3).

The SBC molecule-coated wells render MC3T3-E1 cells faster adhesion and extension than the

porcine collagen-molecule-coated wells (Figs. 3A, D). Fast cell adhesion on the SBC-molecule-coated well was observed similarly with or without crosslinking with genipin (data not shown). A similar tendency was also observed in other cell types. The cells on the fibril collagen immediately adhered to the surfaces like on the SBC molecules (Figs. 3G, J). Before confluency, the MC3T3-E1 cells on the porcine skin collagen and SBC molecule-coated wells showed spindle or polygonal shapes, representing typical fibroblastic morphology (Figs. 3B, E). On the fine-fibril-coated well, the cell bodies were elongated but small compared with those on the molecule-coated wells (Figs. 3H). The cells extended their pseudopod to form a network (Fig. 3H). On the coarse-fibril-coated well, the shape of the cell bodies was similar to that of the fine-fibril-coated well, but the cell extensions were aligned in the same direction (Fig. 3K). When cells reached confluency, the cell shape became a spindle on the molecule-coated wells (Figs. 3C, F). Cells on the fine- and coarse-fibril-coated wells increased their numbers but did not reach confluency at seven days of culture (Figs. 3I, L).

ATDC5 pre-chondrocytes seeded on the porcine skin collagen and SBC molecule-coated wells showed spindle or polygonal shapes and reached confluency after seven days (Figs. 4-F). The morphology of ATDC5 cells on the fibril-coated wells was clearly different than the other cell types; they extended very short pseudopods on both fine- and coarse-fibril-coated wells one day after seeding (Figs. 4G, J) and continued to maintain a spherical shape without stretching until the end of the culture (seven days), although the cell density increased (Figs. 4H, I, K, L).

In this study, collagen fibrils of SBC were crosslinked with genipin for application to cell

cultures. Without genipin crosslinking, denaturation of collagen fibrils gradually occurred during cell culture, and the MC3T3-E1 cells on the coarse-fibril-coated well lost their orientation in association with the loss of collagen fibril orientation (Suppl. Fig. 4).

3.3. Cell proliferation

Cell proliferation was examined using growth media appropriate to each cell type. The MC3T3-E1 cells on both fine- and coarse-fibril-coated wells proliferated slowly compared with molecule-coated wells (Fig. 5A). The proliferation on the coarse-fibril-coated well was the slowest. Because no adverse effects of genipin crosslinking on the proliferation of cells on the molecule-coated wells were observed (data not shown), the slower cellular proliferation on the fine- and coarse-fibril-coated wells is due to the collagen fibrils. Similarly, in the ATDC5 cells, proliferation was slow on the fibril-coated wells (Fig. 5B). Fibrils commonly inhibited proliferation of all cell types used in this study (Suppl. Fig. 5).

3.4. Cell differentiation

The ALP activity was measured as an early marker for osteoblast differentiation. In this study, genipin treatment was not conducted on the molecule-coated wells. Cells were cultured in a growth medium for one day after seeding and then differentiation was stimulated. The assay was conducted just before stimulation of differentiation (Day 1), and two and six days after the stimulation (Days 3 and 7).

Cells on both porcine collagen and SBC molecule-coated wells had increased ALP activities on

Day 7 (Fig. 6). There were no significant differences between these two groups. In contrast, the ALP activities of cells on the fine- and coarse-fibril-coated wells showed the greatest values on Day 1 and decreased thereafter (Fig. 6). At all days, the ALP values of the cells on the fine-fibril-coated groups were the highest, followed by those of the coarse-fibril-coated groups, and the values of the porcine collagen and SBC molecule-coated groups were the lowest.

4. Discussion

In this study, we developed a novel method to coat aligned collagen fibrils on the bottom of cell culture wells. Techniques such as micropatterning are conventionally used to control the behavior of cells and to arrange the orientation of cell stretching. However, methods applicable to biomaterials such as collagen are very limited, and it is extremely difficult to industrially produce large quantities of materials made of aligned collagen fibrils. SBC produced highly-oriented collagen fibrils on the bottom of cell culture wells using a very simple process. By changing the timing of crosslinking treatment with genipin, two types of fibril-coated wells with different fibril thickness were obtained. The ECM topography [33], elasticity [34], and physical/gravitational stimulation caused by movement [35] are recently recognized as important cellular regulators. The ECM also regulates cell morphology: cells can recognize topography of the ECM and align along the fibers of an oriented fiber structure [19,20,36,37]. Therefore, fibrils oriented on a well must have regulatory cues for cell morphology and functions to reproduce an ECM environment closer to that of tissues in the animal body such as lamellar bones, tendons, and ligaments. Additionally, the newly

developed fibril-coatings are in the form of a thin film, thereby providing good visibility of the cell structure, including cell-cell and cell-ECM interactions, as observed by phase-contrast microscopy.

The present study showed that the SBC fibrils on the bottom of cell culture wells aligned in the same direction in the fibril coatings. We found that the orientation was similar to the flow direction of the PB that was introduced to the wells to force fibrillogenesis. The shear force occurred at the interface of the SBC and the PB when the PB is poured into the well is the possible mechanism for the alignment of fibrils into the same direction. This phenomenon may occur because the SBC rapidly make fibrils under the neutral pH since the introduction of the PB to the culture well took only several seconds. The similar alignment of the fibrils occurred when the 4% SBC solution was injected from a pipet to the buffer solution [30]. In addition, the low viscosity of the SBC solution is needed to conduct the coatings using a concentration of 1% SBC solution. Thus, the special properties of the SBC, such as fast fibril formation, high solubility, and low viscosity, make it possible to coat highly-oriented collagen fibrils. Additionally, our preliminary experiments using a transmission electron microscope (TEM) showed that the SBC fibrils formed in a test tube had the D-periodic pattern (data not shown); thus, the SBC fibrils formed *in vitro* retain the structure close to that of collagen fibrils *in vivo*. Although the TEM observation of the SBC fibrils coated on the bottom surface of the well has not conducted yet, it is possible that the coated SBC fibrils also retain the D-periodic structure.

In the preliminary experiments, we revealed that the bottom of the cell culture well was partially coated with fibrils when the concentration of the collagen solution is 0.5%, whereas, at 3%, the bottom was

thickly coated with fibrils (data not shown). Therefore, the concentration of the collagen solution is the regulatory key for the structure of the collagen on the bottom. At the concentration of 0.03% for the molecular coating, the collagen concentration is too low, and thus, the density of collagen molecules may be too low to form fibrils.

This study revealed that cells on the fine- and coarse-fibril-coated wells showed distinct morphologies: the cells on the fine fibrils made a network extending their pseudopods, whereas the cells on the coarse fibrils became aligned. Thus, one of the cues that fibrils give to the cells actually relates to cell morphology. We speculate that differences in the fibril thickness cause these morphological differences. Since the fibril diameter (ca. 99 nm) of the fine-fibril coating is close to the minimum fiber thickness for cell orientation [38], cells on the fine fibrils may not become aligned completely due to slight diameter variation. In other words, the thick fibrils of the coarse-fibril coating may be important for ensuring the orientation of the cells. Using the SEM, Zhang et al. [28] observed that a fusion of several thin fibrils made a thick fibril. In their experiment, no genipin crosslinking was conducted. Thus, under the condition making the fine-fibril coating, the genipin crosslinking that occurred simultaneously with the fibrillogenesis may inhibit the fusion of thin fibrils.

Cell morphology is an important factor for understanding cell properties and functions. The size of cell bodies on the fine- and coarse-fibril coatings tend to be smaller than those on molecular coatings, and thus, the cells changed their steric structure closer to that *in vivo*. In addition, the cells on the fine-fibril coating had extremely long pseudopods connecting each other, while the cells on the coarse-fibril coating

286 became aligned. The integrin-mediated cell adhesion to the scaffold with different topographical characters
287 may cause such morphological difference. Integrin is a transmembrane receptor that mediates cell
288 attachment to the ECM and activates focal adhesion kinase (FAK). Activation of the FAK affects cell
289 migration and cell proliferation in the presence of growth factor-related signals [39]. Integrin also regulates
290 the responsiveness of growth factor receptors and the apoptotic pathway of cells as a scaffold for adhesion-
291 dependent signal transduction [40]. Although the growth factors provide the trigger for cell proliferation, it
292 is the integrin-mediated cell adhesion that sustains the signal of the growth factors [41]. As described
293 below, distinct cell proliferation and differentiation patterns were observed when cells were cultured on the
294 fine- and coarse-fibril-coatings. Such responses would be induced by a consequence of the collaboration of
295 signals from growth factors and integrins.

296 The present study revealed the general suppression of cell proliferation of MC3T3-E1 and
297 ATDC5 cells on fine- and coarse-fibril-coated wells. Alternatively, the ALP activity of MC3T3-E1 cells
298 cultured on the fibril-coated wells showed very high values one day after culture in the growth medium.
299 This result indicates that osteogenic differentiation was promoted by SBC fibrils without any stimuli for
300 differentiation in the culture medium. The results corroborate past reports that osteogenic differentiation is
301 promoted by culturing cells on the fibrous structures [19,20,42,43].

302 The collagen fibril diameter of bone is 50–300 nm *in vivo* [44], and Watari et al. [20] reported
303 that oriented 200 nm diameter fibers most effectively induced osteogenic differentiation. In the present
304 study, the fine-fibril-coating (fibril diameter 51–192 nm) more effectively induced ALP activity than the

coarse-fibril-coating (fibril diameter 53–520 nm). Therefore, thicker fibrils of the coarse-fibril coating may inhibit osteoblastic differentiation compared with fine fibrils. It is also possible that the fibril diameter and other factors that are presently unknown might affect osteogenic differentiation on fibril coatings.

The activation of the ALP activity on the fibril coatings was, however, a transient phenomenon: it gradually decreased with prolonged culture in the osteogenic medium. This result implicates that the differentiation stage of the MC3T3-E1 cells proceeded with time because ALP is an early differentiation marker of osteoblasts. However, the precise mechanisms why ALP activity was transiently activated remain to be clarified. Similar transient activation of gene expressions short term after seeding was also reported in human fibroblasts on a nanoscale groove structure (width, 12.5 μm ; depth, 2 μm): the expression of genes involved in the cytoskeleton as well as signaling, transcription, and translation greatly increased at Day 1 and then decreased at Day 5 [33]. Although the authors suggested the possibility of the topographical structure for affecting the cellular transcription and translation, they do not describe the reason for the transient effects [33].

Unlike other cell types used in this study, ATDC5, a chondrogenic cell line, maintained its spherical shape on the fine- and coarse-fibril-coated wells for at least seven days during the culture. This morphology is seen in differentiated chondrocytes in animal, raising the possibility of promoted differentiation. Abagnale et al. [19] reported that both osteogenic and adipocytic differentiation, which are mutually exclusive, were promoted with submicroscale fibrous structures. Consequently, the fibril coatings may promote osteogenic differentiation and the differentiation of other cell types. It is necessary to clarify

whether the SBC fibrils promote the differentiation of stem cells into single or plural lineages.

Cells bind to collagen using integrins $\alpha_1\beta_1$, $\alpha_2\beta_1$, $\alpha_{10}\beta_1$, and $\alpha_{11}\beta_1$ [46]. The specific amino acid sequence, glycine-phenylalanine-hydroxyproline-glycine-glutamic acid-arginine (GFOGER), of collagen triple-helical molecule was reported as the binding site of integrins $\alpha_1\beta_1$, $\alpha_2\beta_1$, and $\alpha_{11}\beta_1$ [15, 46]. Thus, cells on the culture wells in this study use these integrins and bind to the GFOGER motifs of the SBC molecules, porcine collagen-molecules, and SBC fibrils. It is also possible that cells additionally use the general integrin-binding motif, an arginine-glycine-aspartic acid (RGD) sequence, of collagen. The present study revealed that the adhesion and extension of MC3T3-E1 cells on the SBC molecule-coated wells were faster than those on the porcine collagen-molecule-coated well. Also, the adhesion of the cells to SBC fibrils was fast. The precise mechanism of the better cellular adhesion and extension of the SBC is yet unknown, but we hypothesize that a greater number or accessibility of GFOGER and RGD motifs in SBC may determine better cellular adhesion and extension. However, mRNA sequences and deduced amino acid sequences of α -chains in sturgeon were only incompletely conducted; Zhang [47] and Zhang et al. [48] reported complete cDNA sequences of α_1 - and α_2 -chains of type I collagen from Amur sturgeon, but the sequence of a fish-specific α -chain (α_3) of the sturgeon were not determined. To prove the hypothesis, the priority of the future study is on the cDNA cloning of the α_3 -chain.

5. Conclusion

In tissue engineering research and application, biological scaffolds that control cell proliferation and differentiation have attracted attention [11]. Since ECM with collagen transmits various information to cells and regulates cell proliferation and differentiation [7,9,45], we established a unique method that produces two types of highly-aligned collagen fibrils on cell culture wells using SBC without any special technology, revealing that osteoblasts on the fibril coatings showed a low growth rate with accelerated osteogenic differentiation. The newly developed fibril coatings are in the form of a thin film, thereby providing good visibility of the cell structure, including cell-cell and cell-ECM interactions, under a phase-contrast microscope. Thus, the fibril coatings have high potential as a tool for tissue engineering research. Additionally, the coating will be applicable surface modifications of artificial scaffolds made of synthetic polymers to increase their cellular adhesiveness and biocompatibility.

Acknowledgments

This study was partly supported by the Regional Innovation Strategy Promotion Program, MEXT, Japan. Thanks are also due to Prof. S Adachi for supplying sturgeon swim bladders. We thank Ashleigh Cooper, PhD, from Edanz Group (www.edanzediting.com/ac) for editing a draft of this manuscript.

357 References

- 358 [1] J.C. Adams, F.M. Watt, Regulation of development and differentiation by the extracellular matrix,
359 Development. 117 (1993) 1183–1198.
- 360 [2] K.E. Kadler, D.F. Holmes, J.A. Trotter, J.A. Chapman, Collagen fibril formation, Biochem. J. 316
361 (Pt 1) (1996) 1–11.
- 362 [3] D.J. Prockop, Hulmes David J. S., Assembly of Collagen Fibrils, Elsevier Science, 1994.
- 363 [4] S.-A. Oh, H.-Y. Lee, J.H. Lee, T.-H. Kim, J.-H. Jang, H.-W. Kim, I. Wall, Collagen Three-
364 Dimensional Hydrogel Matrix Carrying Basic Fibroblast Growth Factor for the Cultivation of
365 Mesenchymal Stem Cells and Osteogenic Differentiation, Tissue Eng. Part A. 18 (2012) 1087–
366 1100.
- 367 [5] J. Glowacki, S. Mizuno, Collagen scaffolds for tissue engineering, Biopolymers. 89 (2008) 338–
368 344.
- 369 [6] B. V. Slaughter, S.S. Khurshid, O.Z. Fisher, A. Khademhosseini, N.A. Peppas, Hydrogels in
370 Regenerative Medicine, Adv. Mater. 21 (2009) 3307–3329.
- 371 [7] D. Gospodarowicz, D. Delgado, I. Vlodavsky, Permissive effect of the extracellular matrix on cell
372 proliferation in vitro, Proc. Natl. Acad. Sci. U. S. A. 77 (1980) 4094–8.
- 373 [8] H. Koyama, E.W. Raines, K.E. Bornfeldt, J.M. Roberts, R. Ross, Fibrillar Collagen Inhibits Arterial
374 Smooth Muscle Proliferation through Regulation of Cdk2 Inhibitors, Cell. 87 (1996) 1069–1078.
- 375 [9] M. Mizuno, R. Fujisawa, Y. Kuboki, Type I collagen-induced osteoblastic differentiation of bone-

376 marrow cells mediated by collagen- $\alpha 2\beta 1$ integrin interaction, *J. Cell. Physiol.* 184 (2000) 207–213.

377 [10] K. Poole, K. Khairy, J. Friedrichs, C. Franz, D.A. Cisneros, J. Howard, D. Mueller, Molecular-scale
378 Topographic Cues Induce the Orientation and Directional Movement of Fibroblasts on Two-
379 dimensional Collagen Surfaces, *J. Mol. Biol.* 349 (2005) 380–386.

380 [11] D.G. Anderson, J.A. Burdick, R. Langer, Smart biomaterials, *Science*. 305 (2004) 1923–4.

381 [12] B. Pontz, W. Meigel, J. Rauterberg, K. Kuhn, Localization of Two Species Specific Antigenic
382 Determinants on the Peptide Chains of Calf Skin Collagen, *Eur. J. Biochem.* 16 (1970) 50–54.

383 [13] G.T. Christopherson, H. Song, H.-Q. Mao, The influence of fiber diameter of electrospun substrates
384 on neural stem cell differentiation and proliferation, *Biomaterials*. 30 (2009) 556–564.

385 [14] M. Levy-Mishali, J. Zoldan, S. Levenberg, Effect of Scaffold Stiffness on Myoblast Differentiation,
386 *Tissue Eng. Part A*. 15 (2009) 935–944.

387 [15] C.G. Knight, L.F. Morton, A.R. Peachey, D.S. Tuckwell, R.W. Farndale, M.J. Barnes, The
388 collagen-binding A-domains of integrins $\alpha 1\beta 1$ and $\alpha 2\beta 1$ recognize the same specific amino acid
389 sequence, GFOGER, in native (triple-helical) collagens, *J. Biol. Chem.* 275 (2000) 35–40.

390 [16] H. Shin, S. Jo, A.G. Mikos, Biomimetic materials for tissue engineering, *Biomaterials*. 24 (2003)
391 4353–4364.

392 [17] R.D. Cardwell, L.A. Dahlgren, A.S. Goldstein, Electrospun fibre diameter, not alignment, affects
393 mesenchymal stem cell differentiation into the tendon/ligament lineage, *J. Tissue Eng. Regen. Med.*
394 8 (2014) 937–945.

- 395 [18] F. Yang, R. Murugan, S. Wang, S. Ramakrishna, Electrospinning of nano/micro scale poly(l-lactic
396 acid) aligned fibers and their potential in neural tissue engineering, *Biomaterials*. 26 (2005) 2603–
397 2610.
- 398 [19] G. Abagnale, M. Steger, V.H. Nguyen, N. Hersch, A. Sechi, S. Joussen, B. Denecke, R. Merkel, B.
399 Hoffmann, A. Dreser, U. Schnakenberg, A. Gillner, W. Wagner, Surface topography enhances
400 differentiation of mesenchymal stem cells towards osteogenic and adipogenic lineages,
401 *Biomaterials*. 61 (2015) 316–326.
- 402 [20] S. Watari, K. Hayashi, J.A. Wood, P. Russell, P.F. Nealey, C.J. Murphy, D.C. Genetos, Modulation
403 of osteogenic differentiation in hMSCs cells by submicron topographically-patterned ridges and
404 grooves, *Biomaterials*. 33 (2012) 128–136.
- 405 [21] S. Oh, K.S. Brammer, Y.S.J. Li, D. Teng, A.J. Engler, S. Chien, S. Jin, Stem cell fate dictated
406 solely by altered nanotube dimension, *Proc. Natl. Acad. Sci. U. S. A.* 106 (2009) 2130–5.
- 407 [22] J.A. Matthews, G.E. Wnek, D.G. Simpson, G.L. Bowlin, Electrospinning of collagen nanofibers,
408 *Biomacromolecules*. 3 (2002) 232–238.
- 409 [23] Y. Tanaka, K. Baba, T.J. Duncan, A. Kubota, T. Asahi, A.J. Quantock, M. Yamato, T. Okano, K.
410 Nishida, Transparent, tough collagen laminates prepared by oriented flow casting, multi-cyclic
411 vitrification and chemical cross-linking, *Biomaterials*. 32 (2011) 3358–3366.
- 412 [24] N. Builles, H. Janin-Manificat, M. Malbouyres, V. Justin, M.-R. Rovère, G. Pellegrini, J. Torbet,
413 D.J.S. Hulmes, C. Burillon, O. Damour, F. Ruggiero, Use of magnetically oriented orthogonal

414 collagen scaffolds for hemi-corneal reconstruction and regeneration, *Biomaterials*. 31 (2010) 8313–
 415 8322.

416 [25] S. Chen, N. Hirota, M. Okuda, M. Takeguchi, H. Kobayashi, N. Hanagata, T. Ikoma,
 417 Microstructures and rheological properties of tilapia fish-scale collagen hydrogels with aligned
 418 fibrils fabricated under magnetic fields, *Acta Biomater*. 7 (2011) 644–652.

419 [26] D.I. Zeugolis, S.T. Khew, E.S.Y. Yew, A.K. Ekaputra, Y.W. Tong, L.-Y.L. Yung, D.W.
 420 Hutmacher, C. Sheppard, M. Raghunath, Electro-spinning of pure collagen nano-fibres – Just an
 421 expensive way to make gelatin?, *Biomaterials*. 29 (2008) 2293–2305.

422 [27] R. Parenteau-Bareil, R. Gauvin, F. Berthod, Collagen-Based Biomaterials for Tissue Engineering
 423 Applications, *Materials*. 3 (2010) 1863–1887.

424 [28] X. Zhang, M. Ookawa, Y. Tan, K. Ura, S. Adachi, Y. Takagi, Biochemical characterisation and
 425 assessment of fibril-forming ability of collagens extracted from Bester sturgeon *Huso*
 426 *huso* × *Acipenser ruthenus*, *Food Chem*. 160 (2014) 305–312.

427 [29] M.T.I. Mredha, X. Zhang, T. Nonoyama, T. Nakajima, T. Kurokawa, Y. Takagi, J.P. Gong, Swim
 428 bladder collagen forms hydrogel with macroscopic superstructure by diffusion induced fast
 429 gelation, *J. Mater. Chem. B*. 3 (2015) 7658–7666.

430 [30] M.T.I. Mredha, N. Kitamura, T. Nonoyama, S. Wada, K. Goto, X. Zhang, T. Nakajima, T.
 431 Kurokawa, Y. Takagi, K. Yasuda, J.P. Gong, Anisotropic tough double network hydrogel from fish
 432 collagen and its spontaneous *in vivo* bonding to bone, *Biomaterials*. 132 (2017) 85–95.

- 433 [31] H.G. Sundararaghavan, G.A. Monteiro, N.A. Lapin, Y.J. Chabal, J.R. Miksan, D.I. Shreiber,
434 Genipin-induced changes in collagen gels: Correlation of mechanical properties to fluorescence, J.
435 Biomed. Mater. Res. Part A. 87A (2008) 308–320.
- 436 [32] G.R. Beck, E.C. Sullivan, E. Moran, B. Zerler, Relationship between alkaline phosphatase levels,
437 osteopontin expression, and mineralization in differentiating MC3T3-E1 osteoblasts, J. Cell.
438 Biochem. 68 (1998) 269–280.
- 439 [33] M.J. Dalby, M.O. Riehle, S.J. Yarwood, C.D.W. Wilkinson, A.S.G. Curtis, Nucleus alignment and
440 cell signaling in fibroblasts: Response to a micro-grooved topography, Exp. Cell Res. 284 (2003)
441 274–282.
- 442 [34] A.J. Engler, S. Sen, H.L. Sweeney, D.E. Discher, Matrix Elasticity Directs Stem Cell Lineage
443 Specification, Cell. 126 (2006) 677–689.
- 444 [35] R. Tatsumi, S.M. Sheehan, H. Iwasaki, A. Hattori, R.E. Allen, Mechanical Stretch Induces
445 Activation of Skeletal Muscle Satellite Cells in Vitro, Exp. Cell Res. 267 (2001) 107–114.
- 446 [36] B.K.K. Teo, S.T. Wong, C.K. Lim, T.Y.S. Kung, C.H. Yap, Y. Ramagopal, L.H. Romer, E.K.F.
447 Yim, Nanotopography Modulates Mechanotransduction of Stem Cells and Induces Differentiation
448 through Focal Adhesion Kinase, ACS Nano. 7 (2013) 4785–4798.
- 449 [37] Y. Yang, K. Wang, X. Gu, K.W. Leong, Biophysical Regulation of Cell Behavior—Cross Talk
450 between Substrate Stiffness and Nanotopography, Engineering. 3 (2017) 36–54.
- 451 [38] W.A. Loesberg, J. te Riet, F.C.M.J.M. van Delft, P. Schön, C.G. Figdor, S. Speller, J.J.W.A. van

452 Loon, X.F. Walboomers, J.A. Jansen, The threshold at which substrate nanogroove dimensions may
 453 influence fibroblast alignment and adhesion, *Biomaterials*. 28 (2007) 3944–3951.

454 [39] A.P. Gilmore, L.H. Romer, Inhibition of focal adhesion kinase (FAK) signaling in focal adhesions
 455 decreases cell motility and proliferation., *Mol. Biol. Cell*. 7 (1996) 1209–1224.

456 [40] A.P. Gilmore, Anoikis, *Cell Death Differ.* 12 (2005) 1473–1477.

457 [41] R.K. Assoian, M.A. Schwartz, Coordinate signaling by integrins and receptor tyrosine kinases in
 458 the regulation of G1 phase cell-cycle progression, *Curr. Opin. Genet. Dev.* 11 (2001) 48–53.

459 [42] R. Matsumoto, T. Uemura, Z. Xu, I. Yamaguchi, T. Ikoma, J. Tanaka, Rapid oriented fibril
 460 formation of fish scale collagen facilitates early osteoblastic differentiation of human mesenchymal
 461 stem cells, *J. Biomed. Mater. Res. Part A*. 103 (2015) 2531–2539.

462 [43] K. Sisson, C. Zhang, M.C. Farach-Carson, D.B. Chase, J.F. Rabolt, Fiber diameters control
 463 osteoblastic cell migration and differentiation in electrospun gelatin, *J. Biomed. Mater. Res. Part A*.
 464 94A (2010) 1312–1320.

465 [44] K. Hoshi, S. Kemmotsu, Y. Takeuchi, N. Amizuka, H. Ozawa, The Primary Calcification in Bones
 466 Follows Removal of Decorin and Fusion of Collagen Fibrils, *J. Bone Miner. Res.* 14 (1999) 273–
 467 280.

468 [45] J. Richards, D. Pasco, J. Yang, R. Guzman, S. Nandi, Comparison of the growth of normal and
 469 neoplastic mouse mammary cells on plastic, on collagen gels and in collagen gels, *Exp. Cell Res.*
 470 146 (1983) 1–14.

471 [46] W.-M. Zhang, J. armo Käpylä, J. S. Puranen, C. G. Knight, C.-F. Tiger, O. T. Pentikäinen, M. S.
472 Johnson, R. W. Farndale, J. Heino, D. Gullberg, $\alpha 1 \beta 1$ integrin recognizes the GFOGER sequence
473 in interstitial collagens, J. Biol. Chem. 278 (2003) 7270–7277.

474 [47] X. Zhang, Studies on the properties of sturgeon collagen as potential biomaterials, Doctoral thesis,
475 Hokkaido University (2015) pp.123.

476 [48] X. Zhang, N. Azuma, S. Hagihara, S. Adachi, K. Ura, Y. Takagi, Characterization of type I and II
477 procollagen $\alpha 1$ chain in Amur sturgeon (*Acipenser schrenckii*) and comparison of their gene
478 expression, Gene 579 (2016) 8–16.

479

480

Figure captions

Fig. 1. Scanning electron microscope images of the bottom surfaces of the cell culture wells coated with collagen. In (A), the well was coated with a porcine skin type I atelocollagen solution (0.03%) and washed with 0.1 M Na-phosphate buffer (PB, pH 7.6) (porcine collagen-molecule-coated well). In (B), the well was coated with a Bester sturgeon swim bladder type I atelocollagen (SBC) solution (0.03%) and washed with PB (SBC-molecule-coated well). In (C), the well was coated with an SBC solution (1.0%) and fibril formation and cross-linking were simultaneously induced by the PB containing 1 mM genipin (fine-fibril-coated well). In (D), the well was coated with an SBC solution (1.0%), fibril formation was induced by a PB, and cross-linking was induced sequentially by the PB containing 1 mM genipin (coarse-fibril-coated well). Scale bars, 5 μ m.

Fig. 2. Distribution of the collagen fibril diameter of the fine-fibril-coated well (white columns) and the coarse-fibril-coated well (black columns).

Fig. 3. Phase contrast microscope images of MC3T3-E1 cells cultured for 1 hour (A, D, G, J), one day (B, E, H, K), and seven days (C, F, I, L) on the porcine collagen molecule-coated well (A-C), the SBC molecule-coated well (D-F), the fine-fibril-coated well (G-I), and the coarse-fibril-coated well (J-L). Scale bars, 75 μ m.

Fig. 4. Phase contrast microscope images of ATDC5 cells cultured for 3 hours (A, D, G, J), one day (B, E, H, K), and seven days (C, F, I, L) on the porcine collagen molecule-coated well (A-C), the SBC molecule-coated well (D-F), the fine-fibril-coated well (G-I), and the coarse-fibril-coated well (J-L). Scale bars, 75 μm .

Fig. 5. Proliferation of MC3T3-E1 cells (A) and ATDC5 cells (B) on the porcine collagen molecule-coated well (white column), the SBC molecule-coated well (black column), on the fine-fibril-coated well (hatched column), and the coarse-fibril-coated well (dotted column). Columns and bars indicate means and standard errors. Different letters in the same day indicate significant differences ($p < 0.05$ by Tukey-Kramer test).

Fig. 6. ALP activities of MC3T3-E1 cells cultured on the porcine collagen molecule-coated well (white column), the SBC molecule-coated well (black column), the fine-fibril-coated well (hatched column), and the coarse-fibril-coated well (dotted column). Columns and bars indicate means and standard errors. Different letters in the same day indicate significant differences ($p < 0.01$ by Tukey-Kramer test).

Fig. 1

Fig. 2

Fig. 3

Fig. 4

Fig. 5

Fig. 6

Supplementary Fig. 1. Phase contrast microscopy images of 3T3-L1 cells cultured for 1 day on the porcine collagen molecule-coated well (A), the SBC molecule-coated well (B), the fine-fibril-coated well (C), and the coarse-fibril-coated well (D).

Supplementary Fig. 2. Phase contrast microscopy images of C2C12 cells cultured for 1 day on the porcine collagen molecule-coated well (A), the SBC molecule-coated well (B), the fine-fibril-coated well (C), and the coarse-fibril-coated well (D).

Supplementary Fig. 3. Phase contrast microscopy images of L929 cells cultured for 1 day on the porcine collagen molecule-coated well (A), the SBC molecule-coated well (B), the fine-fibril-coated well (C), and the coarse-fibril-coated well (D).

Supplementary Fig. 4. Scanning electron microscope images of the bottom surfaces of the cell culture wells coated with collagen fibrils. A 200 μ l aliquot of the atelocollagen solution (1%) was poured into each well of the 24-well cell-culture plate, incubated for 30 minutes, and removed from each well. The fibril formation was induced by introducing a 0.1 M Na-phosphate buffer (PB, pH 7.6) into the wells for 24 hours. MC3T3-E1 cells were cultured after crosslinking with the PB containing genipin for subsequent 24 hours (A) or without cross linking (B). After culture for 1 day, the morphology of the crosslinked fibrils were the same as that before the culture (see Fig. 1D in the manuscript). Without the genipin crosslinking, randomly aligned collagen fibrils were observed. Arrows indicate cells.

Supplementary Fig. 5. Proliferation of 3T3-L1 (A), C2C12 (B), and L929 cells (C) on the porcine collagen molecule-coated well (white column), the SBC molecule-coated well (black column), the fine-fibril-coated well (hatched column), and the coarse-fibril-coated well (dotted column). Columns and bars indicate means and standard errors. Different letters in the same day indicate significant differences ($p < 0.05$ by Tukey-Kramer test).

Highlights

- Atelocollagen from the swim bladder of sturgeon forms oriented fibrils
- Two types of fibrils were coated on cell culture dishes
- Thick collagen fibrils induced cells to align in the same direction
- Cellular proliferation was inhibited on both thin and thick fibrils
- Both fibrils stimulated the early differentiation of MC3T3-E1 cells

Graphical abstract

Processing

Fillet, Caviar

By-products

Extraction

Purified collagen

Coating

Highly-oriented collagen fibrils on the dish
Cells aligned along the fibrils

Cell proliferation
ALP activity (MC3T3-E1)