



Title	Crack Tip Field of a Double-Network Gel: Visualization of Covalent Bond Scission through Mechanoradical Polymerization
Author(s)	Matsuda, Takahiro; Kawakami, Runa; Nakajima, Tasuku; Gong, Jian Ping
Citation	Macromolecules, 53(20), 8787-8795 <a href="https://doi.org/10.1021/acs.macromol.0c01485">https://doi.org/10.1021/acs.macromol.0c01485</a>
Issue Date	2020
Doc URL	<a href="http://hdl.handle.net/2115/82839">http://hdl.handle.net/2115/82839</a>
Rights	This document is the Accepted Manuscript version of a Published Work that appeared in final form in Macromolecules, copyright © American Chemical Society after peer review and technical editing by the publisher. To access the final edited and published work see <a href="https://dx.doi.org/10.1021/acs.macromol.0c01485">https://dx.doi.org/10.1021/acs.macromol.0c01485</a> .
Type	article (author version)
Additional Information	There are other files related to this item in HUSCAP. Check the above URL.
File Information	Supporting Information.pdf



[Instructions for use](#)

Supporting Information for

## Crack Tip Field of a Double-Network Gel:

### Visualization of Covalent Bond Scission through Mechanoradical Polymerization

Takahiro Matsuda<sup>\*,‡,‡,#</sup>, Runa Kawakami<sup>†,#</sup>, Tasuku Nakajima<sup>‡,§,¶</sup> and Jian Ping Gong<sup>\*,‡,§,¶</sup>

<sup>‡</sup>Faculty of Advanced Life Science, <sup>†</sup>Graduate School of Life Science, <sup>§</sup>Soft Matter GI-CoRE and <sup>¶</sup>Institute for Chemical Reaction Design and Discovery (WPI-ICReDD); Hokkaido University, Japan.

<sup>#</sup>These authors contributed equally.

\*To whom correspondence should be addressed.

Phone and Fax: +81-11-706-9011. Email: tkhr.matsuda@gmail.com; gong@sci.hokudai.ac.jp

Address: N21W11, Kita-ku, Sapporo 001-0021, Japan.

#### Contents

Supporting Methods .....	2
Supporting Figures .....	4
References for Supporting Information .....	8


## Supporting Methods

**Chemicals.** 2-Acrylamido-2-methylpropane sulfonic acid sodium salt (NaAMPS, 49.8 wt.% aqueous solution) was provided by Toagosei. *N,N'*-Methylenebis(acrylamide) (MBAA), 2-oxoglutaric acid, and *N*-isopropylacrylamide (NIPAAm) were purchased from FUJIFILM Wako Pure Chemical Corporation. Acrylamide (AAm) was purchased from Junsei Chemical. 8-Anilino-1-naphthalenesulfonic acid (ANS) was purchased from Tokyo Chemical Industry. Acetone was purchased from Kanto Chemical. All materials except for AAm were used as received, and AAm was recrystallized from acetone once before use.

**Synthesis of DN gels.** Double-network hydrogels were synthesized following a previously reported procedure.<sup>S1,S2</sup> First, poly(2-acrylamido-2-methylpropane sulfonic acid sodium salt) (PNaAMPS) single-network gels were synthesized as the first network. An aqueous solution of 1.0 M NaAMPS, 3.0–3.5 mol% MBAA, and 1 mol% 2-oxoglutaric acid was prepared, where the concentration denoted as mol% was the molar percentage with respect to the monomer. For quantitative discussion of the comparison between tearing test and tensile test (Figures 7, 8, S3, and S4), the MBAA concentration was fixed as  $x_1 = 3.0$  mol%. The solution was poured into a glass mold made of two flat glass plates separated using a silicone rubber spacer (1.0 mm thick) in an argon glove box. The solution in the mold was irradiated with UV light (365 nm, 4 mW cm<sup>-2</sup>) for 8 h in a glove box to allow for radical polymerization, resulting in a PNaAMPS single-network gel sheet. Afterwards, the PNaAMPS gel was immersed in a second network precursor solution for more than 1 day at 10 °C to swell the gel and introduce the second-network monomers to the gel. The second-network precursor aqueous solution comprises 2.0–4.0 AAm, 0.01–0.02 mol% MBAA, and 0.01 mol% 2-oxoglutaric acid. For quantitative discussion of the comparison between tearing test and tensile test (Figures 7, 8, S3, and S4), AAm and MBAA concentrations were fixed at  $C_2 = 4.0$  M and  $x_2 = 0.02$  mol%, respectively. The swollen gel was sandwiched between two flat glass plates, moved to an argon glove box, and then irradiated with UV light for 9 h in a glove box to synthesize the second PAAm network in the presence of the first PNaAMPS network. The synthesized DN gel was immersed in a large volume of deionized water for at least 1 day to remove unreacted reagents and make the gel equilibrium-swollen state in water.


**Tensile test for mechanical characterization.** To characterize the tensile mechanical properties of a DN gel, we conducted uniaxial and uniaxial cyclic tensile tests in air. In the uniaxial tensile test, dumbbell-shaped DN gels (standardized to JIS-K 6251-7; 12 mm gauge length, 2 mm width, and 3.1 mm thickness) were uniaxially stretched using a tensile tester (INSTRON 5965, Instron Co.) at a cross-head velocity of 100 mm min<sup>-1</sup> (nominal strain rate of ~0.1 s<sup>-1</sup>).<sup>S3</sup> The stress  $\sigma$  was characterized as the nominal stress, which is the measured force divided by original cross-sectional area. The strain  $\epsilon$  was measured using a non-contacting video extensometer (AVE, Instron Co.). Under the same experimental conditions, cyclic tensile tests with incremental imposed strains were also performed to characterize the dissipated mechanical energy density  $U_{\text{diss}}$  as a function of strain  $\epsilon$  from mechanical hysteresis (see Figure S3).<sup>S3</sup>

## Supporting Figures




\*Standard deviation from three individual measurements. \*\*Standard deviation obtained by the law of propagation error.


**Figure S1.** Characterization of monomer conversion of mechanoradical NIPAAm polymerization in a typical case. We characterized the monomer conversion from weight analysis as described in this Figure. First, the weight fraction of the first and second network in an unstretched DN gel fed with NIPAAm (sample A) was characterized as  $W_A'/W_A$ . The weight fraction of the networks in the unstretched gel (sample A) was identical to that in a stretched gel (sample B) because of the stretching resulted in no weight change. Second, the weight fraction of the solid (sum of the networks and fed NIPAAm monomer) in the unstretched sample was characterized as  $W_A''/W_A$ . Third, the weight fraction of the polymer (sum of the networks and mechanically-synthesized PNIPAAm polymer; excluding residual unreacted NIPAAm monomer that can be washed out by immersing the gel in water) was characterized as  $W_B'/W_B$ , assuming that PNIPAAm polymer cannot be extracted from the gel by immersing the gel in water because it should be tethered to the ruptured end of the first network. Based on these three results, the monomer conversion was characterized as the synthesized PNIPAAm polymer weight fraction divided by the fed NIPAAm monomer weight fraction; that is,  $(W_B'/W_B - W_A'/W_A) / (W_A''/W_A - W_A'/W_A)$ . For a DN sample stretched at a strain of  $\sim 4$ , the NIPAAm monomer conversion was estimated as  $40.7 \pm 8.6\%$ . The feed formulation in the synthesis of the DN gel was NaAMPS 1.0 M and MBAA 3.0 mol% for the first network, and AAm 4.0 M and MBAA 0.01 mol% for the second network. To extract NIPAAm monomer from a gel, the gel was immersed in large volume of water for three days. To remove water from a gel, the gel was dried at 120 °C in a vacuum for 6 h.



**Figure S2.** A typical (a) full view and (b) expanded view of fluorescence intensity profiles and transmitted light profile around the fractured surface of a DN gel. Because the raw fluorescence intensity profile (blue curve) contains relatively strong noise, we used the moving-average over 9 raw-data points in the main text and the moving-average intensity values are plotted against the  $z$ -position of the center point of the 9 points (red curve). As the raw data was sampled at a  $6.2 \mu\text{m}$  interval in the  $z$ -position, the 9-point moving-average gives an average over  $\sim 50 \mu\text{m}$ . The fluorescence intensity was measured by excitation of the 402.5 nm laser light. To determine the position of the gel, the transmitted light was also observed. The profile of the transmitted light (gray curve) clearly indicates the fractured surface (boundary of air and the gel) so that this profile was used to determine the fractured surface at point  $z = 0$ . In (b), the fluorescence intensity of raw data steeply increased at the surface, while that of moving-averaged data was blunted due to the moving-averaging processing.



**Figure S3.** A typical result of the cyclic tensile test of a DN gel. **(a)** Schematic of the mechanical input of the cyclic tensile test. Only the loading curves were recorded because with respect to DN gels, an unloading curve overlaps with the subsequent loading curve. **(b)** Cyclic stress–strain loading curves of the DN gel. **(c)** Dissipated mechanical energy density  $U_{\text{diss}}$  as a function of imposed strain  $\epsilon_{\text{max}}$ . Following the reported procedure,<sup>S3</sup>  $U_{\text{diss}}$  for each maximum strain  $\epsilon_{\text{max}_n}$  (corresponding cycle number  $n$ ) was characterized from the accumulation of the mechanical hysteresis:  $U_{\text{diss}_n} = \sum_{i=1}^n \Delta U_{\text{diss}_i}$ , where  $\Delta U_{\text{diss}_n} = \int_0^{\epsilon_{\text{max}_n}} \sigma_n(\epsilon) d\epsilon - \int_0^{\epsilon_{\text{max}_n}} \sigma_{n+1}(\epsilon) d\epsilon$  is the hysteresis area of each sequential step ( $n^{\text{th}}$  and  $(n+1)^{\text{th}}$  stress–strain curves with the stress  $\sigma_n(\epsilon)$  and  $\sigma_{n+1}(\epsilon)$ , respectively) in the strain range  $0 < \epsilon < \epsilon_{\text{max}_n}$ . The data of  $U_{\text{diss}}-\epsilon_{\text{max}}$  plot (Figure 7c in the main text) were obtained from four individual tests of this DN gel to collect the multiple data points.



**Figure S4.** Supporting figure describing the protocol in order to obtain the maximum stress profile  $\sigma_{\max}(z)$  shown in Figure 8b (main text). The profile of the maximum stress imposed as a function of the distance  $z$  from the fractured surface,  $\sigma_{\max}(z)$ , was obtained from the maximum strain profile  $\varepsilon_{\max}(z)$  (Figure S4a) and the uniaxial stress–strain curve (Figure S4b) which are identical as shown in Figures 8a and 7a in the main text, respectively. To convert each  $\varepsilon_{\max}$  value in the  $\varepsilon_{\max}(z)$  plot into the corresponding  $\sigma_{\max}$  value, we used a polynomial fitting curve for the stress–strain curve in Figure S4b. Because the  $\varepsilon_{\max}$  characterized in Figure S4a is no more than 2.0, we used the fitting curve within the range of  $0 < \varepsilon < 2$  ( $\sigma = 0.1026 \varepsilon^6 - 0.7004 \varepsilon^5 + 1.8683 \varepsilon^4 - 2.4113 \varepsilon^3 + 1.3615 \varepsilon^2 + 0.0888 \varepsilon$ ) as shown in Figure S4b. The resulting  $\sigma_{\max}(z)$  is shown in Figure 8b in the main text.

### References for Supporting Information

- (S1) Ahmed, S.; Nakajima, T.; Kurokawa, T.; Anamul Haque, M.; Gong, J. P. Brittle–ductile transition of double network hydrogels: Mechanical balance of two networks as the key factor. *Polymer* **2014**, *55* (3), 914–923.
- (S2) Matsuda, T.; Kawakami, R.; Namba, R.; Nakajima, T.; Gong, J. P. Mechanoresponsive self-growing hydrogels inspired by muscle training. *Science* **2019**, *363*, 504–508.
- (S3) Nakajima, T.; Kurokawa, T.; Ahmed, S.; Wu, W.-L.; Gong, J. P. Characterization of internal fracture process of double network hydrogels under uniaxial elongation. *Soft Matter* **2013**, *9*, 1955–1966.