

HOKKAIDO UNIVERSITY

Title	Rheological characteristics of epoxy asphalt binders and engineering properties of epoxy asphalt mixtures - state-of-the- art	
Author(s)	Jamshidi, Ali; White, Greg; Kurumisawa, Kiyofumi	
Citation	Road Materials and Pavement Design, 23(9), 1957-1980 https://doi.org/10.1080/14680629.2021.1963814	
Issue Date	2022-09	
Doc URL	http://hdl.handle.net/2115/86566	
Rights	" This is an Accepted Manuscript of an article published by Taylor & Francis in Road Materials and Pavement Design on [date of publication], available online: http://www.tandfonline.com/10.1080/14680629.2021.1963814.	
Туре	article (author version)	
File Information	Final Version (full author details and affiliations).pdf	

Sector Se

Rheological Characteristics of Epoxy Asphalt Binders and Engineering Properties of Epoxy Asphalt Mixtures- State-of-the-Art

5	
4	Ali Jamshidi ¹ , Greg White ² , and Kiyofumi Kurumisawa ³
5	¹ University of Sunshine Coast, Sippy Downs, Queensland, Australia, Tell: +61-754-56-5435
6	Email: <u>alij_ep@yahoo.com</u> and ajamshidi@usc.edu.au
7	² University of Sunshine Coast, Sippy Downs, Queensland, Australia,
8	Tell: +61 7 5456 5418, Email: gwhite2@usc.edu.au
9	³ Hokkaido University, Kita 13, Nishi 8, Kita-ku, Sapporo, Hokkaido, 060-8628, Japan
10	Tell: +81- 11-706-6319, Email: kurumi@eng.hokudai.ac.jp

11 Abstract

З

12 The asphalt industry is aiming to produce high quality materials and efficient technologies for pavement construction. One such technology that attracts attention is epoxy asphalt. This paper 13 discussed the concepts, theories, and engineering properties of epoxy asphalt technology and products. 14 As the initial step, the chemical structure of epoxy materials was explained. Then principles of epoxy 15 asphalt technology were discussed. Subsequently, the rheological characteristics of epoxy asphalt 16 binder (EAB) were characterized. Engineering properties of an epoxy asphalt mixture (EAM) were 17 then evaluated. The results indicated that EAB has better rheological properties than the traditional 18 modified and net asphalts. Moreover, the results showed that superior structural performance of EAM 19 20 compared with the traditional hot and warm mixtures. However, recyclability, initial strength, and 21 total cost of the pavement construction remain matters of concern.

22 **1.Introduction**

The asphalt manufacturing industry is currently faced with two challenges. The first one being the preference of oil refineries to produce high value-added products as opposed to low quality materials used as asphalt binders. A reasonable explanation may be related to the lack of oil pressure in the oil fields. Therefore, the production of binders is not the main priority for many refineries. As the main source of industrial fuel in the plants and raw material of asphalt binder, a lack of crude oil results in an increase in asphalt mix production costs.

29 The second challenge is that asphalt binder consumption is dramatically increasing due to the rapid 30 development of transportation infrastructure worldwide. Therefore, various types of binders are required to meet all the requirements of utility conditions. At first glance, the higher demand for 31 32 asphalt binders is an opportunity for the asphalt industry, but the production of many high quality binders using the limited sources of bitumen and carbon-based energy carriers are bottlenecks of the 33 34 asphalt manufacturing industry. It is necessary to develop various technologies, additives, and 35 recycling methods to cater the asphalt mix to paving projects to address the challenge. For example, various types of polymers are used to modify binders. These polymers can be divided into two main 36 37 groups: elastomers and plastomers (Polacco et al. 2005, Sengoz et al. 2009). The elastomers, such as styrene-butadiene-styrene (SBS) and styrene-isoprenestyrene, modified binder produces asphalt 38 39 mixtures with good elastic performance, enhanced cracking resistance, and improved complex 40 modulus (Yildirim 2007).

- 41 The plastomers (e.g., polyethylene, polypropylene, and ethylene-vinyl acetate copolymer (EVA)) used
- 42 for binder modification produce asphalt mixtures with higher stiffness and good rutting performance
- 43 (Sureshkumar *et al.* 2010, Fuentes-Auden *et al.* 2008). Although the plastomer- or elastomer-modified
- 44 asphalt mixes meet many structural requirements of pavements, there are still some drawbacks, such
- 45 as limited improvement in elasticity, storage stability, and high thermal sensitivity (Lu and Isacsson
- 46 2001, Zhu *et al.* 2013).

The asphalt pavement technologists have also tried to find sources of asphalt rejuvenators for the extension of asphalt surface life, such as microalgae, bio-oil, swine manure, wood lignin, and waste cooking oil (Airey *et al.* 2008, Fini *et al.* 2011, Cao *et al.* 2019). Such developments have provided great progress in asphalt pavement technology; however, the quality of asphalt binders is still a significant concern for flexible pavement technology.

52 To meet the increasing demand for high-quality asphalt and reduce crude oil-based asphalt binder consumption, production of synthetic binders represents a potential new strategy. Molecular structures 53 of such binders can be modified by synthetic methods to produce binders with appropriate properties 54 55 in various temperature ranges and pavement ages. For instance, Airev et. al (2008) showed that the rheological characteristics of synthetic binders are comparable to those of traditional asphalt. 56 However, the high cost of synthetic binders, and the lack of infrastructure to produce these products 57 58 on a large scale have limited their application to date. Therefore, it is necessary to develop a new generation of asphalt binders that not only have better rheological characteristics than traditional and 59 60 modified binders, but can also be produced and tested using current technologies. Epoxy asphalt technology can fulfill these requirements. There are different types of epoxy glues with a wide variety 61 of applications from repairing shoes to machine manufacturing, construction materials, shipbuilding, 62 electronic, electrical, and the aircraft industry. The binding property of epoxy together with asphalt 63 can make a durable material to adhere to aggregate particles in the asphalt mixture because both are 64 glues. Epoxy asphalt binder (EAB) as a multi-phase material is one of the reactive polymer-modified 65 66 binders, in which thermosetting epoxy resin is mixed with a thermoplastic asphalt binder. Since there are many types of epoxy, different binders with the required properties can be produced. It is 67 68 necessary to understand the rheological characteristics of EAB as well as the laboratory and field 69 performance of the epoxy asphalt mix (EAM). This state-of-the-art study attempts to promote 70 understanding of the epoxy asphalt binder rheology and analysis of mixture laboratory performance, which will support the development and wider application of the technology in academic research and 71 72 industry practice. Field and functional performance of EAM were out of scope of this study.

73 2. Chemical Structure of Epoxy Resin

74 The most common used epoxy resins are products of epichlorohydrin polycondensation with phenols (diglycidylether of bisphenol A) (Vyrozhemskyi et al. 2017). Adding sodium hydoxside (Na(oH)2 75 catalyses the formation of hydrochloride intermediates which performs as dehydrohalogens to 76 neutralize the hydrochloric acid (HCl) (Xiang and Xiao 2020). This chemical reaction happens when 77 78 the temperature is 110°C over 16 h. The final organic matters are separated, dried with sodium sulfate 79 (NaSO4), and then slightly distilled in a vacuum environment (Hsieh et al. 2020, Raquez et al. 2010). 80 The common chemical structure of the epoxy resin can be expressed as linear polyether with epoxy groups and the hydroxyl groups in Figure 1. Table 1 shows 6 main typical types of epoxy resin 81 categorized by ASTM D1763. 82



Figure 1: The typically chemical structure of epoxy resin (Osumi 1987).

Every engineering property can be attributed to the chemical structure that exists in the epoxy resin ofthe as follows (Osumi 1987, Petrie 2005):

- Reactivity: this property can be characterized by hydroxyl and epoxy groups at the middle
 and ends of main chain respectively.
 - 2. Flexibility and chemical resistance: they are related to inclusion of bonds in the main chain.
- 89 3. Thermal stability: this parameter depends on benzene rings.
- 904. Adhesion: this depends upon secondary hydroxyl groups which are located along the main91chain.
- 92 93

88

83

Table 1: Typical types of epoxy resin based on ASTM D1763 (2013)

Types	Name
Ι	Bisphenol A and epichlorohydrin
II	Reaction product of phenol and formaldehyde (novolacresin) and epichlorohydrin
III	Cycloaliphatic and peracid epoxies
IV	Glycidyl esters
V	Reaction product of epichlorohydrin and paminophenol
VI	Reaction product of epichlorohydrin and glyoxal tetraphenol

94

95 In order to cure epoxy resin, a substance called curing agents reacts with the epoxy or hydroxyl 96 groups. The process of curing usually takes place through two different mechanisms: opening- ring 97 and/or polymerization. It should be noted that catalysts can begin the photopolymerization reaction 98 within the epoxy resin. The selection of curing agent depends on many variables, including epoxy 99 type, application, viscosity, pot life, curing temperature and method, shear strength and toughness 100 (Collyer 2012, Sancaktar 1990). Table 2 lists typical curing agents and their benefits and drawback in 101 more details.

- 102
- 103

Table 2: Various types of curing agent and properties (Meath 1990, Cranley 1994, Collyer 2012,

Xiang and Xiao 2020).

Туре	benefit	drawback	
Aliphatic amines	Easy to use Low viscosity Normal cure at room temperature but rapid cure at the high temperatures Moderate chemical resistance	Critical mix ratios Relatively short life cycle High potential for skin irritant Rigid, poor peel and impact effects Relatively weak bond strength above 80°C High vapor pressure	
Aromatic amines	Moderate thermal and chemical stability	Solid state at the room temperature Slow cure at the high temperature ranges	
Anhydrides	High thermal and chemical stability	Critical mix ratios Rigid Slow cure at high temperature	
Polyamids	Easy to use Low toxicity High bond strength and flexibility Normal curing at the room temperature	High formulation cost High viscosity Weak thermal and chemical resistance Slow curing at the elevated	

	High peel and impact resistance	temperatures
		Odor
Polysulfides and	High moisture resistance	Weak tensile strength
mercaptans	Flexible	Weak stability at the elevated
-		temperatures
	Quick setting time	Low speed curing at the elevated
Catalytic and	High heat resistance	temperatures
latent hardeners	Long pot life	Weak moisture resistance
	Catalytic action	Rigid

105 In the next section curing in the epoxy asphalt binder is explained in detail. It should be noted that the 106 epoxy resin and curing agent can be produced through petrochemical processes and synthetic chemical reactions. In addition, resin and curing agents can be produced using renewable natural 107 108 resources which increases the sustainability in the epoxy industry. For example, epoxy resin can be made from vegetables, soybean, cellulose, camellia sinensis, and lignin (Kumar et al. 2018). Also, the 109 bio-based curing agent can be derived from citric acid, cashew nutshell, rosin, corncobs, and gallic 110 acid (Kumar et al. 2018). This may indicate that the source biomaterials can influence the final epoxy 111 resin and curing process (Cranley 1994, Mohan 2013). 112

3.Epoxy Asphalt Technology

114 3.1. Phase 1: EAB Production

115 Three different materials are required for the production of EAB: (1) epoxy material, (2) curing agent, and (3) an asphalt binder. EAB has a two-phase chemical-based system. The first phase is 116 117 thermosetting epoxy resin or continuous phase (component A), and the second phase is the petroleumbased asphalt binder or disperses phase. For the production of EAB, the curing agent and asphalt 118 binder are blended together (component B), refer to EAB production in Table 3. Subsequently, 119 120 component A is mixed with component B. The blend of components is cured, which results in a set of irreversible chemical reactions. The reaction product is the three-dimensional, continuous spatial 121 122 network of epoxy in the EAB structure. The asphalt binder spheres are dispersed among the resin 123 (disperse phase) (Yu et al. 2009a, Huang et al. 2010, Cong et al. 2010).

124 125

Table 3: Different methods of EAB pro	oduction (Xiang and Xiao 2020)
---------------------------------------	--------------------------------

Source	Component	Condition of production
Chemcosystem	A: epoxy resin B: base asphalt, curing agents and other additives	Step 1: Preheat the component A to 87 ± 5 °C; Step 2: Preheat the component B to 128 ± 5 °C; Step 3: Blend the components A and B to achieve a homogeneous mix
Tough (TAF)	A: base asphalt B: epoxy resin C: curing agent	Step 1: Preheat the component A to 150 °C Step 2: Preheat the component B and Part C 60 °C Step 3: Blend the components B and C first, Step 4: Blend the components B and C with the component A until it is homogeneous

126

127 For EAB production based on TAF, the curing agent is a separate component called component C. In

this production method, the components A and B are asphalt binder and epoxy resin respectively. In contrast to the previous method, the component B and C are blended together first. Then the blend is mixed with the asphalt (refer to Table 2 for more details)

130 mixed with the asphalt (refer to Table 3 for more details).

Additionally, chemical reactions begin after mixing components. These reactions eventually lead to a cross-linked polymer structure throughout the binder structure. The final EAB is a rubber-like

elastomeric asphalt binder with a built-up polymer structure. Additionally, EAB can be treated as a

heterogeneous blend of an asphalt binder and epoxy resin. More details about the curing reaction are explained in the following section.

136 3.2. Phase 2: Curing Process of EAB

Curing plays a pivotal role in the toughening or hardening of EAB. The mechanism of curing is 137 complex and depends on several variables such as temperature, time, and the chemical components of 138 the curing agent, asphalt binder properties, and aggregate gradation. Curing begins when the epoxy 139 (component A) and blend of the asphalt binder and the curing agent (component B) are mixed 140 together. The particle size of the asphalt binder increases as the chemicals cure. Consequently, a 141 142 stable cross-linking network is formed between the asphalt binder and the epoxy resin (Yu et al. 2009a, Cong et al. 2010, 2019, Huang et al. 2010). The epoxy network structure can improve various 143 properties of the binder (Dong and Li 2015). The epoxy resin forms a three-dimensional network that 144 145 wraps around the asphalt particles (Ai et al. 2016). This network constrains the flow of the binder particles at elevated temperatures and makes the EAB flexible. The molecular structure obtained after 146 curing is of a linear and straight-chain type. However, its rigidity and recovery can be compared to 147 148 that of the resins (Takahashi et al. 2010). Both the epoxy material and asphalt are glues, and when the two are blended together, they can bind the particles and become stronger over time as well as absorb 149 heat (thermosetting characteristics). Therefore, the thermosetting nature of epoxy improves the 150 stability of EAB against high temperature deformation, thermal cracking, moisture, and resistance to 151 solvents such as fuel (Alabaster et al. 2008, Chen, 2009, Cong et al. 2011, Mo et al. 2012, Sun et al. 152 153 2021).

Epoxy resins and most curing agents, such as anhydrides and aliphatic and aromatic amines, are 154 petroleum-based products. Some of these products are toxic, which limits their application due to 155 environmental concerns (Fuhaid et al. 2018). To decrease effects of temperature variation on the 156 curing, different types of the agents are produced. There are primarily four kinds of curing agents: 157 158 low-temperature curing agent (Kim et al. 2000); room-temperature curing (Koji et al. 2015); 159 Moderate temperature curing agent (Chen et al. 2007) and High-temperature curing agent (Guo 2014). 160 The curing method also plays a pivotal role in the quality and performance of EAB. Without the proper curing process, epoxy resin materials may lose the ability to continue the chemical reaction, 161 162 which results in a lack of stability (Miller and Bellinger 2003).

The size of asphalt granules in EAB depends on the asphalt content, and the time, rate, temperature, 163 and method of curing. For example, Ai et al. (2016) reported that the asphalt particles cured by 164 microwave were bigger than those in EAB cured by the conventional method. The extent of curing 165 has been evaluated using various tests. As an example, the trend of curing can be characterized 166 through the evaluation of changes in the peak of the area of the 917 cm⁻¹ epoxy band using Fourier-167 transform infrared spectroscopy (FTIR) (Herrington, 2010, Cong et al. 2019). Additionally, empirical 168 tests, such as softening point, viscosity and Marshall Stability, can be useful to study the trend of 169 170 curing (Cao et al. 2011, Ei Rahman et al. 2012, Qian et al. 2012).

Curing is a dynamic phenomenon and an endothermal reaction that requires time. Mixing the hot 171 aggregate and EAB accounts for 50% of curing in EAM (Cao et al. 2011). The rest of the curing 172 occurs after the construction of the pavement. For example, Chen et al. (2018a) recommended that the 173 epoxy pavement be opened to traffic after 12 h of paving due to initial curing. Also, A field study of 174 175 curing showed that the modulus of epoxy porous EAM increases by 78% after 13 days (Herrington 176 and Alabaster 2008). Analysis of curing by FTIR showed that at 60 °C (as upper surface pavement temperature), the curing reaction, consisting of an epoxy ring, is completed after 7 days, while it cures 177 178 after 58 days at 20 °C, which is consistent with results of the evaluation of full curing in the field by

179 Widyatomoko et al. (2006). However, Takahashi et al. (2010) reported that the final strength of EAM

- 180 was obtained at 1, 2, and 4 weeks at of curing at 55 °C, 40 °C, and 30 °C, respectively, which means
- 181 the higher ambient temperature decreases curing time (Zhu 2013). In a similar study, the curing rate
- increased 10-fold if the pavement temperature increases from 30 °C to 60 °C (Cao et al. 2011). In

- another study, Xu *et al.* (2021a) reported that the open traffic time from 21 h decreases to 6 h when
- 184 the ambient temperature raised from 25 $^{\circ}$ C to 35 $^{\circ}$ C. It means that the waiting time to open the
- pavement to the traffic decreased by approximately 70% when the ambient temperature increased by
- 40%. It should be noted that aggregate packing plays key role in curing (Min *et al.* 2020).
 Additionally, other environmental factors influence curing in the field. For example, when the wind
- 187 Additionally, other environmental factors influence curing in the field. For example, when the wind 188 speed is higher than 10 m/s, the air is foggy, or there is dew, or relative humidity is more than 90%,
- 188 speed is inglief than 10 m/s, the air is loggy, of there is dew, of relative humdridy is more than 90%,
 189 laying EAM is not permitted (Zhu 2013). The reason is that that the EAB is a thermosetting material,
 - any type of moisture, due to humidity, fog and dew, can absorb thermal energy of EAB which results
- in reduction of temperature. Any temperature loss delays curing which results in lack of stiffness.
- To simulate curing in the laboratory, the samples were cured for 50 min at 120 °C prior compaction, and then the samples were cured for an additional 5 h at 120 °C after compaction (Qian *et al.* 2013,
- 194 Chen *et al.* 2018b). The EAM supplier recommended 121 °C as the mixing and compaction 195 temperature (Luo *et al.* 2015). Additionally, Chen *et al.* (2012a) recommended 5 hours at 130 °C as 196 the optimum laboratory curing conditioning of EAM.
- When the surface is paved with EAM, the mix temperature drops to the ambient temperature. This can 197 result in a delay in curing. Therefore, it is better to pave the surface during the hot season because 198 EAM has the heat-storing capacity. For example, the heat-storing capacity of EAM used in the 199 pavement of the 2nd and 3rd bridge of the Yangtze river was 45 days in the summer (Zhang 2007, Liu 200 et al. 2010). Furthermore, curing of epoxy depends on the base or chemical compounds of the agent 201 (Zhou et al. 2017). As an example, to quickly open the pavement to traffic using an acid-based EAM 202 203 in cold temperatures in DaGuang Ming, China, 3000 sheets of electric blankets were applied for 13 204 days, called in-situ curing technique (Yan et al. 2013, Apostolidis et al. 2019a). To overcome such shortcomings, amine-based curing agents are often recommended (Liu et al. 2010, Yin et al. 2014, 205 206 Kang et al. 2016). Amine-curing agents are more expensive than acid-curing agents, which increases 207 the total price of EAM (Song et al. 2017). Therefore, the best approach to achieve a satisfying curing is selection of appropriate curing agent based on environmental factors and chemical characteristics of 208 epoxy resin. 209
- If EAB as a three-component system (unmodified binder, epoxy resin, and curing agent) is compared 210 with traditional polymer-modified binder (PMB), as a two-component system (unmodified binder + 211 reactive copolymers such as polyurethanes and unmodified binder + reactive elastomeric terpolymer 212 213 (RET)), role of curing agent is the same as accelerators and activator exist in the polymers and reactive copolymers. In other words, catalyst in EAB production is a separate material added in the 214 215 production, while the catalysts and reactive substance are incorporated in the chemical structure of polymer materials. Furthermore, the catalyst can be added in the binder during modification process. 216 For example, polyphosphoric acid is added in the binder containing RET pills which leads to 217 218 crosslinking in the binder. As polyphosphoric acid is used in the bitumen-polymer mixture, the amount of polymer needed for the modification is reduced (Jasso et al. 2015, Polacco et al. 2015). 219 220 Interaction between the catalyst and polymer improves binder rheological and chemical properties. 221 Selection of appropriate reactive polymer in PMB or curing agent in EAB is an effective approach to add functional groups for obtaining specific functions of the resultant binder (Functionalization). It 222 should be noted that functionalization can improve rheological characteristics and chemical properties 223 of the binder (Zhu et al. 2014). Obviously, the rheological properties and quality of the base binder 224 225 play pivotal in the rheological properties of the PMB and EAB.

4. Rheological Characteristics of EAB

Rheological properties are one of the key indicators for the analysis of deformation and flow of a binder. Effects of any modification in the binder structures can affect rheological characteristics. Since asphalt binders are a multi-phase material, it is necessary to analyze binder performance at various temperatures through different indicators. The rheological tests for asphalt binders can be grouped into two main groups: empirical and advanced tests. The empirical tests, such as softening,

penetration or ignition, and ring and ball softening point, provide basic information which can beuseful for contractors and consultants.

Advanced tests, using a dynamic shear rheometer, rotational viscometer, and bending beam rheometer,

and testing direct tensile strength not only provide more information about the structural response of

- binder at various temperature ranges but is also useful for asphalt producers, material technologists,
- and researchers for the evaluation of mix performance. Both empirical and advanced tests of EAB are
- helpful. In this section, results of both the tests are evaluated. Figure 2(a) shows that the softening
- 239 point of EAB decreases as the epoxy content increases, which is consistent with results yielded by Yu
- et al. (2009b), Huang and Huang (2011), and EI Rahman et al. (2012). Additionally, the penetration
- 241 (Figure 2(a)) and ductility (Figure 2(b)) of EAB increase as the epoxy content increases.



(a) Softeningpoint versus epoxy content

(b) Ductility versus epoxy content

Figure 2: Basic properties of EAB as a function of epoxy content; plotted based data reported by Dong and Li (2015).

Two other parameters affecting the rheological characteristics of EMB are curing time and 242 243 temperature. Higher curing time and temperature increase the tensile strength, complex modulus, and ductility of EAB. For example, Figure 3(a) illustrates the tensile trend of EAB as a function of curing 244 time. From the figure, the tensile strength increases with the increase in curing time for both curing 245 temperatures. Additionally, the epoxy type and method of preparation can influence the rheological 246 247 properties of the resultant EAB. Figure 3(b) shows that the EAB prepared using epoxy Type A has a higher complex shear modulus (G*) compared to that of Type B. The complex shear modulus of 248 Type A is 962 MPa at 10 °C, which is twice that of Type B. Therefore, the stiffness of Type A is 249 250 higher than of Type B. As a result, the design of EAB means the selection of the appropriate epoxy 251 material, content, curing temperature, and curing time. Fuhaid *et al.* (2018) also reported that $G^*/\sin \delta$ of EAB containing a bio-based epoxy was more than 4 times higher than the value for the neat binder, 252 253 indicating that the bio-based EAM is less prone to temperature susceptibility. Moreover, EAB has a higher storage modulus (G') compared with the moduli of other asphalt binders (Cong et al. 2015). 254 255 The reason is that the elastic property of EAB is dominant at high temperatures (Xiao et al. 2013), because EAB retains its physical state at the high temperatures, while the conventional binders and 256 257 polymer-modified binders become viscous (Kang et al. 2015). As an example, the storage modulus of EAM is much higher than the loss modulus in the high-temperature ranges (Cong et al. 2015), 258 meaning higher elastic properties. In contrast, the loss modulus of conventional binders was higher 259 260 than their storage modulus, indicating the viscous nature of the binders. Consequently, the high elastic characteristic of EAB decreases the creep compliance (Xiao et al. 2011, Kang et al. 2015, Holleran et 261 al. 2017) thereby increasing the recovery rate of the binder. However, it is recommended to 262

characterize the effects of various epoxy types and curing agents on the viscoelastic characteristics of
 EAB through master curves, black and Cole-Cole diagrams. As an instance, Huang *et al.* (2019)
 developed some master curves for characterization of creep compliance of epoxy asphalt.

The optimum rheological design of EAB depends on the appropriate selection of curing time, asphalt 266 type, and epoxy type and content, and also, the optimum epoxy content depends on temperature and 267 268 the frequency test (Dong and Li 2015). Therefore, pavement service conditions, including the environmental ambient temperature and frequency of traffic loading, should be well understood for an 269 optimum design of EAB. The curing method can affect the rheological characteristics of EAB. Figure 270 4 shows the difference in elongation and tensile strength due to curing methods. From the figure, it is 271 272 observed that the elongation and tensile strength of microwave-cured EAB is 7.6% higher than the conventionally cured EAB. The tensile strength of microwave-cured EAB is also observed to be lower 273 274 than its conventionally cured counterparts (Figure 4(b)). In addition, use of modifier may change curing rate and mechanism. To find optimized conditions for curing, more chemical and 275 276 microstructural tests are essential (Li et al. 2021).



281



(a): Tensile strength versus curing time

(b) G* versus temperature

Figure 3: Trends of tensile strength and G*; plotted based on data reported by Xiao *et al.* (2011).





(a) Elongation percent (b) Tensile strength Figure 4: Effect of different curing methods on the engineering properties of EAB; plotted based on data reported by Ai *et al.* (2016).

284

Figure 5 shows the rotational viscosity of EAB containing various epoxies at various curing times at 285 160 °C. The viscosity of pure epoxy (100%) is less than the viscosity of EAB immediately after the 286 materials are mixed (Figure 5a). However, the viscosity increases significantly after 2.5 h after mixing 287 (Figure 5b), indicating that curing increases the viscosity, which is consistent with the results reported 288 by Fuhaid et al. (2018) and Zhang et al. (2021). The incremental epoxy molecular weight results in 289 290 higher viscosity due to curing (Liu et al. 2017a). For example, Wang et al. (2021) showed that the 291 viscosity of the EAM increases at the higher temperatures due to the continuous cross-linking reaction occurs during curing. 292 EAM is typically mixed at approximately 110 °C to 120 °C that allows 57 to 94 min of hauling (Lu 293 and Bors 2015). Furthermore, Cong et al. (2011) recommended 2,000 to 3,000 mPa.s as the optimal 294

viscosity range of EAB for compaction (Figure 5 (b)), which is consistent with ranges recommended 295 296 by Gallagher and Vermillion (1997) and Chen et al. (2012a). From Figure 5(b), the viscosities of the binders containing 45%, 50%, and 55% epoxy are 1,234; 1,473; and 1,360 mPa.s, respectively, which 297 298 are much lower values than the recommended 2,000 mPa.s. Additionally, the time to reach 2,000 mPa.s at the curing temperature of 110 to 130 °C varies from 48 min to 70 min (Yu et al. 2009b). In 299 another similar study, Li et al. (2014) recommended that the viscosity should be equal to or less than 300 301 1,000 m.Pa.s 50 min after mixing. Therefore, by knowing the target viscosity for compaction, a combination of curing time and epoxy content can be selected. The time until the epoxy reaches 1,000 302 303 mPa.s is an indicator of haul time and operational window or reserve time. Beyond that amount of time, the workability of mix decreases, which may result in poor EAM. For example, Takahashi et al. 304 (2010) found that the degree of compaction of EAM proportionally decreases over time. 305



(a) Immediately after mixing (0 h)
 (b) 2.5 h after mixing
 Figure 5: Viscosity of EAB containing various epoxy; plotted based on data reported by Yin *et al.* (2015).

307

308 The use of any additives or modifiers can influence the allowable construction time. For example, Figure 6 shows the effects of mineral fiber size on the construction time. The fiber size is an effective 309 variable that affects viscosity. From the figure, two different trends can be observed. The first trend is 310 that the allowable construction time decreases as the mineral fiber size increases because the bigger 311 size increases EAB viscosity, thereby decreasing the workability of the mix. Therefore, determining 312 the optimum size of the mineral fiber is a key factor. The second trend is that the increase in fiber 313 content decreases the allowable construction time. To compare the effect of fiber content on the 314 reduction of allowable time, refer to the set Equation (1). 315

The slope of the equation shows the reduction of allowable time per 1% fiber content. For instance, the slope of the equation for 8 mm fiber is 2.1 min, which indicates the allowable time decreases 2.1 min as 1% of 8 mm-fiber is added, which is 41% and 54% larger than those related to 2-mm and 5mm fiber, respectively. Consequently, the lower fiber content responds to a lower extension of allowable time of EAM construction.

321 In another study, Liu et al. (2017b) reported that the incorporation of ethylene vinyl acetate (EVA) 322 copolymer in EAM decreases the construction time from 56 min (for the control EAM or 0% EVA) to 323 38 min (for 4% by weight of EVA). To extend the operational window, different methodologies can be used. For example, the use of a natural fibrous nanoclay, namely attapulgite (chemical formula 324 325 Si8O20Mg5(Al)(OH)2(H2O)4·4H2O with a 2:1 phyllosilicate structure) (Bradley 1940), in EAB 326 decreases the viscosity because of the hindrance impact of fibrous nanoclays on the molecular 327 movement of epoxy monomers, curing agents, and asphalt binder particles (Esmizadeh et al. 2016). 328 The analysis by a rotational viscometer of different percentages of attapulgite, from 0% (control) to 5%, shows that the viscosity decreases with the increased percentage (Sun et al. 2015, 2018). 329 330 Therefore, the higher percentages of attapulgite extend the paving window, and the attapulgite performance as a viscosity-reducing agent can be compared with the warm-mix additives. 331 Consequently, the characteristics of modifiers play a key role in the trend of EAB viscosity. For 332 333 instance, the incorporation of mineral fibers increases the EAB viscosity, depending on fiber content 334 and length of the fibers (Xue and Qian, 2016).



 $T = \begin{cases} -0.93F + 61.12 & \text{for } 2 \text{ mm fiber} \\ -1.23F + 61.80 & \text{for } 5 \text{ mm fiber} \\ -2.10F + 58.00 & \text{for } 8 \text{ mm fiber} \end{cases}$ (1)

Figure 6: Effect of the mineral fiber size and content on the allowable construction time; plotted based on data reported by Xue and Qian (2016).

where T is allowable time; F is fiber content ($R^2=94\%$)

336

A useful technology to extend the paving window is the foaming process. The binder foaming 337 phenomenon increases the surface area of the system, resulting in lower viscosity. Afterward, the 338 339 lower viscosity of EAM enhances the workability of the mixture, prolonging the allowable time of EAM construction. In this regard, Yu et al. (2016) found that the construction time, based on the 340 341 target viscosity of 1,000 mPa.s, of 64 min for the non-foamed EAB extended to 108, 101, and 97 min as 1%, 2%, and 3% water was added, respectively concluding that 1% is the optimum foaming-water 342 percentage in the study. Beyond 1%, the viscosity of foamed EAM increased because of the deeper 343 degree of the chemical reaction between the epoxy resins and the curing agent, resulting in a higher 344 viscosity and less workability. The optimum percentage may vary depending on the curing agent and 345 binder type. In another study, Huang et al. (2017) recommended 2% as the optimum content of 346 foaming water. Also, the higher percentage of water may deaccelerate the curing process between the 347 epoxy and curing agent. The higher percentage of water results in an inferior rutting resistance of the 348 349 mixture due to a lack of structural consistency. Therefore, the foaming water content should not 350 exceed the optimum value. However, morphological analysis shows that the higher percentages of foaming water results in smaller size epoxy granules with a more uniform distribution in the EAM 351 microstructure. Additionally, there is a new EAM technology that can be mixed at 160 °C to 180 °C, 352 which increases the hauling time from 60 to 150 min (Liu and Zhang, 2010). The use of warm 353 mixture asphalt (WMA) additives also decreases the viscosity of EAB, increasing the hauling time of 354 EAM. For example, Gong et al. (2021) showed that the elongation, tensile strength, and toughness of 355 EAB modified with 1% Sasobit[®] (as a common WMA additive) were 12%, 8%, and 15% higher than 356 neat EAM (without Sasobit[®]), respectively. Therefore, the crystalline network due to the 357 incorporation of Sasobit[®], together with the higher stiffness of the epoxy materials, increased the 358 elongation and toughness of EAB. The optimum additive content depends on the additive type. Thus, 359 360 different additives have different effects on the rheological properties of EAM. The optimum additive content or modifier depends on the target rheological characteristics because of various mechanisms. 361 For example, the optimum content of SBS-modified binder for EAB was 40% (by weight), based on 362 363 toughness and tensile strength of the binder, while the results of the elongation test showed the 60% (by weight) is the optimum content (Liu et al. 2018). Therefore, it is necessary to choose the critical 364 rheological property or properties to be targeted for modification. 365

Additionally, the complex interaction between the epoxy resin, binder, modifiers, and additives increases the uncertainty of the conventional thermo-rheological constitute models, such as the fractional linear solid (FLS) model and the Huet-Sayegh (HS) model (Wu *et al.* 2018). The uncertainty is due to the complicated synergistic effects of the resin, binder, additive, temperature, and intermolecular forces. Consequently, there are no highly accepted models to predict the rheological properties of EAB. Thus, it is recommended that the rheological behaviors of EAB are modeled by a set of micromodels valid for a specific temperature and frequency range.

Additionally, it is necessary for the compatibility between the asphalt binder and the epoxy resin to be evaluated. Compatibility is an essential indicator for selection of binder type and epoxy material (Min 2011). Although the higher toughness of EAB reduces temperature susceptibility, it can lead to low temperature cracking. To improve the compatibility and toughness of EAM at a low temperature, three different methods are proposed:

- 378
- To add natural rubber, SBS, styrene isoprene styrene block copolymers (SIS), or other elastic materials, which effectively improve the toughness of EAB (Jiang *et al.* 2018, Cong *et al.* 2016, Yin *et al.* 2014, Kang *et al.* 2010). However, the shortcoming is that the viscosity of the modified EAB increases substantially. The lack of compatibility between the modifier and the epoxy can be problematic.
- To use cis-butenedioic anhydride and maleic acid as an asphalt modifier (Herrington *et al.* 1999). Although cis-butenedioic anhydride improves the viscoelastic properties of asphalt binder, the higher viscosity and cost limit its application in epoxy asphalt technology (Zher'akova and Kochkan'an 1990).
- To use curing agents with a long-chain fatty acid or anhydride that have a high compatibility with both the asphalt binder and epoxy material (Li *et al.* 2014, Zhang *et al.* 2010, Araki *et al.* 2008). This method can be consistent with epoxy asphalt technology.
- To use polyethylene glycol (PEG) in EAM. The PEG with number-average molecular weight (Mn) of 400-800 g/mol could improve the toughness of epoxy asphalt (Min *et al.* 2021a). As
 the Mn of PEG increases, the low-temperature resistance, toughness, and hydrophilicity of asphalt binder improve. However, PEG chains may slightly decrease high temperature signature characteristics of the asphalt.
- 396

5. Engineering Properties of EAM

398 5.1. Marshall Stability and Flow

Marshall Stability and Flow are common conventional asphalt mix tests to determine the optimum 399 binder content (OBC). This test set is relatively inexpensive and very user-friendly. Therefore, the 400 required test equipment can be found in many laboratories. Figure 7 shows the Marshall Stability of 401 EAM. It can be seen that the increase in epoxy has no significant effect on the Marshall Stability but 402 increases the flow. Therefore, the epoxy resin has no effect on the binder content in terms of the 403 404 Marshall Stability. This trend was similar to the other trends reported by Fuhaid et al. (2018). Additionally, they reported that the air-void percentage of EAM and the control mixture was almost 405 identical. However, Ei-Rahman et al. (2012) reported that more epoxy materials increased the 406 Marshall Stability. Consequently, different resin types may result in various effects on the volumetric 407 408 properties of the mix and the Marshall properties. Also, the interlocking of aggregate particles plays a 409 pivotal role in the initial Marshall Stability of EAM (Huang et al. 2011). Further investigations are 410 required to characterize the effect of the epoxy resin content, type, and their interaction with aggregate particles. In addition, the method of EAM production can affect the Marshall stability, flow and the 411 other mix properties. For example, Cong (2009) evaluated the effect of different blending methods of 412

components for EAM production (Table 4). The effect of aggregate and filler properties should be
considered in analysis of Marshall Stability of EAM. In this regard, Xu *et al.*, (2021b) evaluated effect
of two types of filler on the Marshal Stability of EAM. The results showed that the Marshall Stability
of EAM containing filler dust was 73% higher than the mixtures with mineral filler.

417



Figure 7: Marshall Stability and flow as a function of epoxy content; plotted based on data reported by Yin *et al.* (2015).

production			
Blending		Blending	
Method	Description	Time	
		(sec)	
	Blending aggregate		
Ι	particles with 120		
	components A and B		
	Step 1: Blending		
	aggregate particles	30	
	with part B		
II	Step 2: Adding		
	component B to the		
	blend prepared in the	90	
	step 1		
	Step 1: Mixing		
III	aggregate particles	30	
	with Component B		
	Step 2: Adding		
	component A to the		
	blend prepared in the	90	
	step 1		

Table 4: Different blending methods in	EAM
production	

418

419

Figure 8 illustrates the effect of different blending methods on the Marshall stabilities and volumetric properties of EAM. From the Figure, the maximum Marshall Stability can be achieved from the method I, while the air void and voids in the mineral aggregate (VMA) of EAM in all the methods are almost identical. As a result, selection of the blending method may play a key role to quality control and mix design of EAM. It should be noted that every epoxy material supplier will provide instructions and guidelines to blends of the components and aggregate that should be followed carefully.

EAM can also be produced with other waste materials and binder modifiers (Figure 9). For example,
Figure 9(a) shows that the Marshall stability of the EAM samples is much higher than the PMB,
indicating the higher structural performance. Furthermore, the Marshall stability of the PMB samples
decrease as the glass content increases, but the Marshall Stability of the EAM samples do not change.
The trend of the flow for both mixes are also similar; however, the flow of EAM are higher than those
of PMB. The Marshall Stability of EAM is consequently less sensitive to the glass content.

- 432 of PMB. The 3433
- 434
- 435
- 436
- 437
- 438
- 439
- 440
- 441
- 442



Figure 8: Effect of different blending methods on the Marshall Stability and volumetric properties of EAM, plotted based on data reported by Cong (2009).



Figure 9: Marshall Stability and flow of EAM.

Figure 9(b) also shows that the Marshall Stability of EAM modified by mineral fibers increases. The 445 reason is that the fiber increases the binder viscosity and bridge the microcracks formed in the mix 446 447 during the loading. Consequently, the structural performance of EAM can be improved by adding waste glass and mineral fiber. However, the OBC may be different because of the absorption of the 448 449 modifiers or additives. For example, the waste glass particles do not absorb the binder because of their hydrophobic nature, while the mineral fibers are hydrophilic materials. Therefore, it is expected that 450 the OBC in EAM increases by adding higher percentages of fiber. Moreover, the compatibility of 451 452 EAM and fiber or any modifiers/alternative materials needs further investigation. It should be noted 453 that adding fiber requires facilities in the production line of EAM which incurs initial costs. In addition, workability of EAM containing fiber is matter of concern. Also, the long-term performance 454 of the fiber-modified EAM in terms of field aging and durability should be addressed in the life cycle 455 of mixture. As a result, all the uncertainty and risks in the performance EAB should be analyzed. 456

457 Other industrial by-products that can be used as an asphalt modifier are sulfur or sulfur-derived 458 polymers, resulting from the bulk polymerization reaction between sulfur and dicyclopentadiene 459 above the melting point of sulfur (Salman *et al.* 2016, Adam *et al.* 2003). Additionally, the melting

443

460 point of the polymerized sulfur decreases with the increase in the amount of the dicyclopentadiene. Kwon et al. (2017) showed that the melting point of the polymerized sulfur decreases to as low as 461 room temperature when 60% dicyclopentadiene is blended. Therefore, a cold mix of EAM can be 462 produced using a liquid sulfur polymer. The results show that the Marshall Stability test of the liquid 463 sulfur polymer EAM is 1.5 to 2.3 times higher than those of neat binders. The reason is a more stable 464 465 polymer network formed in the presence of sulfur and the curing of epoxy materials. It should be noted that the samples should be tested after curing because the Marshall stability of samples without 466 enough curing does not represent structural consistency of EAM. The lack of curing results in less 467 stiffness which results in low Marshall stability. In addition, plastic deformation increases because of 468 469 the low stiffness in EAB.

Use of alternative aggregate is another approach to improve engineering properties of EAM. In a laboratory study, Min *et al.* (2021b) studied the effect of ceramsite as an aggregate alternative on the Marshall Stability. The results indicated that EAM samples could meet the Marshall Stability requirement for all the ceramsite contents under heavy and light compaction, while SBS-EAM could only meet the requirement at lower percents. The higher strength was achieved under light compaction of EAM because of less aggregate degradation. As a result, Min *et al.* (2021b) recommended the light compaction for EAM containing ceramsite.

477 5.2. Rutting

EAM is characterized by a high modulus and high resistance to the rutting (Burns 1964, Dinnen 1981).
In this regard, Nakanishi *et al.* (2000) reported that the dynamic modulus of EAM was higher than the
stone matrix asphalt (SMA) and gussasphalt. EAM is also less prone to premature rutting owing to a
low initial dynamic stability (Ishibashi *et al.* 1990). The possible reason is that the higher stiffness in
EAM increases the dynamic modulus owing to a relatively higher complex Poisson's ratio of EAM
(Wang *et al.* 2021, Bocci *et al.* 2015, Mayama 1978a, b).

Figure 10 illustrates the trend of rutting with EAM compared with that with the control sample 484 (traditional asphalt mix) at different instances in a laboratory study for different curing days. From the 485 486 figure, the rutting depth of EAM after 14 days of construction is equal to that of the traditional asphalt mix (1-day mix or control mix). Subsequently, rutting decreases significantly over time with EAM, 487 and the rate of rutting depth varies. To characterize the effect of time, Equation 2 is proposed, which 488 corresponds to Figure 10. The slopes of the aforementioned equation show the rate of rutting depth 489 development over 1,000 cycles of loading. For example, the rutting rate of control mix (1-day control 490 mix) is 0.1, which means 0.1 mm per 1,000 cycles of loading while the corresponding value is 0.04 491 for 42-day EAM. The effect of curing on the structural response of EAM can be characterized by the 492 493 reduction in rutting using the slopes of Equation 2.



 $RD = \begin{cases} 0.10L + 1.87 & R^2 = 95\% \text{ control mixture} \\ 0.10L + 1.71 & R^2 = 94\% & 14 - day \text{ EAM} \\ 0.08L + 1.42 & R^2 = 93\% & 28 - day \text{ EAM} \\ 0.64L + 1.11 & R^2 = 94\% & 36 - day \text{ EAM} \\ 0.04L + 0.49 & R^2 = 94\% & 42 - day \text{ EAM} \end{cases}$ (2)

where RD is rut depth; L is the number of load cycles.

Figure 10: Trend of rutting as a function of time at 45 °C; plotted based on data reported by Vyrozhemskyi *et al.* (2017). Note: 1-day rutting results for the control asphalt mix, but the other samples are EAM.

495

Although the stiffness of EAM is relatively much higher, the behavior of EAB is still assumed to be
viscoelastic. Therefore, the dynamic modulus test of EAM should be in the range of linear
viscoelasticity, which is lower or equal to 150 microstrains (Yao *et al.* 2013a). This linear
viscoelastic limit of EAB is much higher than that of the conventional and modified asphalt binders,
that are 20 and 100 micro-strain, respectively (Airey *et al.* 2004).

Furthermore, the incorporation of modifiers and additives improves rutting resistance and the dynamic stability of EAM. For example, mineral fibers decrease the rut depth of EAM because the fiber increases the stiffness of the EAB (Figure 11). From the figure, the rut depth decreases, and the dynamic stability increases when the mineral fiber content increases. Additionally, the maximum dynamic stability and minimum rut depth (maximum structural capacity regarding rutting) are for 6% fiber.

Rutting, together with other failures, can accelerate failures in the asphalt pavement. Therefore, it is better to evaluate the interaction between rutting and other failures. To characterize the effect, Zhong *et al.* (2017) analyzed the performance of EAM using the Hamburg wheel tracking test. The result showed that no yield point after 20,000 loading cycles at 60 °C indicating superior performance. The yield point indicates that rutting depth development transfers from rutting to moisture damage (i.e., moisture damage is a dominant factor in the development of rutting beyond the yield point). The excellent rutting performance of EAM prevents rapid failures due to moisture because of the high

514 bonding between the aggregate and EAM. Furthermore, moisture sensitivity of EAM increases due to

the binder and aggregates adhesion as well as increasing the wettability of the aggregate particles 146

- 516 surface with binder (Bahmani *et al.* 2021).517 As discussed earlier, the cured samples should be tested
- As discussed earlier, the cured samples should be tested because EAMs without sufficient curing
 show misleading results. The samples with poor curing show the higher rut depth owing to lack of
 stiffness.

Although laboratory tests, such as Hamburg wheel tracking or traditional wheel tracking test and asphalt pavement analyzer, may provide satisfying results of rutting and the other propertied, it is necessary to develop new test protocols, procedures, and setups to better simulate the realistic

- 523 conditions in the field.
- 524



Figure 11: Effect of fiber content on the rut depth and dynamic stability of EAM; plotted based on results reported by Xue and Qian (2016).

525 5.3. Crack Resistance

Indirect tensile strength (ITS) is a parameter used to evaluate the potential of cracking in asphalt 526 concrete mixtures. Laboratory results showed that EAM has a higher stiffness in terms of ITS 527 compared with the other modified mixtures (Zhu et al. 2004, Apostolidis et al. 2019b) because of the 528 high stiffness of EAB (Chen et al. 2018a, Wang et al. 2013). Additionally, oxidative aging of samples 529 530 increased the ITS of EAM. For example, Herrington and Alabaster (2008) showed that the ITS of porous EAM are higher than for the traditional asphalt regardless of oxidation time. Furthermore, they 531 532 found that the ITS increases linearly up to 120 h for both pavements. At 186 h, there is an inflection point, and then the ITS increases in EAM. The same inflection point is observed for the porous 533 control mix. The change in the trend can be related to the stiffening effects of the binders. Although 534 535 both pavements display the same trend, the values are different. It should be noted that aggregate type, gradation, epoxy content and binder performance grade play pivotal role in crack resistance of EAM 536 537 (Bahmani et al. 2021).

538 Fatigue cracking is another mode of structural failures in the pavement. Cong et al. (2015) and Nguyen and Tran (2021) carried out research on the fatigue behavior of EAM. As role of thumb, the 539 outputs indicated that the effect of temperature on the fatigue life of EAM significantly depends on 540 541 the stress level and epoxy content. The fatigue life of a mixture increases at the lower stress level and temperature due to the high elastic property (storage modulus) of EAB. The elastic strain recovers 542 543 after unloading, which results in the dominant action of the elastic behavior in fatigue. At elevated temperatures, the EAB may have insufficient elasticity to recover. Therefore, the plastic behavior 544 becomes the dominant action, which results in micro-cracks. The rates of crack initiation and 545 propagation are different, which depend on aggregate gradation and particle distribution. The analysis 546 of crack initiation and propagation based on the results of three-point bending beam samples clearly 547 showed that crack propagation is stopped when the coarse aggregate particles are in the process of 548 cracking (Chen et al. 2014), but the crack propagation continues due to cumulative stress and strain 549 until the pavement fails. However, the performance of EAM is superior to traditional mix in terms of 550 fatigue life (Yin et al. 2015, Huang 2015). 551

Additionally, the high ductility of EAB (Figure 2(b)) results in the higher flexural strength in the EAM (Figure 12). The flexural strength of EAM is almost three times higher than those of PMBmixtures, which is consistent with results reported by Zhao *et al.* (2019). The similar trend was observed in flexural strength of EAM compared to SBS-modified mixtures (Wang *et al.* 2021). Also, Xu *et al.* (2019a) found that fatigue life of EAM is two to three times higher than SMA and 557 gussasphalt. Furthermore, type of filler has significant effect on the fatigue life of EAM. As an 558 instance, Xu *et al.* (2021a) reported that the EAM samples containing filler composed of dust from 559 aggregate had a significantly longer fatigue life than that of the samples containing filler composed of 560 mineral powder.

The flexural strength of PMB is much higher than for mixes produced using the neat or unmodified binders. The higher flexural stiffness and strain result in a high structural capacity under traffic loading. Therefore, the thickness of the pavement layer decreases due to use of EAM. Consequently, the use of EAM can result in lesser consumption of raw material due to lower pavement thickness.

565 Similarly, the superior performance of EAM in fatigue leads to less maintenance and rehabilitation, 566 especially for pavements subjected to heavy traffic loads.

Some field investigations showed significant fatigue failures of EAM (Changjiang *et al.* 2007, Xiaohua *et al.* 2010), which is inconsistent with laboratory results. The reason for these failures includes the concept of fatigue endurance in the field compared to the laboratory samples.

- 570 If the EAM is subjected to stress or strain lower than the fatigue endurance, the fatigue failures do not 571 appear. Once the cumulative stress/strain reaches the fatigue endurance, the fatigue failures appear
- quickly. Consequently, the analysis of fatigue endurance is recommended as a criterion for the EAM
- 573 mix design and evaluation (Wang and Zhang 2019). A lack of knowledge of the fatigue response of FAA and to the angle following response to dia different studies (2011, 2011, 2011).
- EAM can lead to the early failures reported in different studies (Seim 1973, Cheng *et al.* 2011, Chen
 et al. 2011). Furthermore, the structural performance of substrate layers plays important roles in the
- fatigue life of the pavement system. Thus, it is necessary to evaluate the surface and the substrate
 layers together to understand the combined EAM fatigue properties better.

578 Moreover, there are different methodologies for the selection of fatigue endurance, which may result 579 in different fatigue life prediction. For example, Bhattacharjee *et al.* (2009) used the visco-elastic 580 theory to find fatigue endurance, while Brown *et al.* (2006) proposed the Weibull function to find the 581 fatigue failure criteria. Carpenter *et al.* (2003) and Schapery (1984) used the concepts of dissipated 582 energy and work potential theory for the determination of fatigue endurance, respectively.

The potential performance of EAM in terms of fatigue stiffness can be improved using fiber. The fiberimproves the structural performance of asphalt concrete via two different mechanisms:

585 586

587 588

589

590

591 592

- The fiber dispersed throughout the mixture forms a network that resists crack propagation and prevents aggregate material from sliding to the pavement surface. Furthermore, the fiber can evenly distribute stress and strain throughout the matrix of the mix, reducing local micro-failures. Furthermore, the fiber bridges the cracks, which results in fewer openings. Also, load transferring does not develop into micro-cracks due to the fibers. Therefore, fiber decelerates the propagation of cracking, which results in higher fracture strength.
- The fiber performs as a stabilizer in the asphalt binder which decreases asphalt drain down or
 binder creep due to the higher viscosity of the asphalt binder. This property is particularly
 important for the porous asphalt mix or open-graded friction courses or mixes constructed for
 high-temperature service condition.
- 597

There are various types of fiber materials used in asphalt mixtures. Depending on the fiber type, the optimum content based on fatigue life is chosen. For example, Wang *et al.* (2019) showed that the flexural strength of EAM increased as the fiber glass content increased. It was also shown that the maximum fatigue life was for the EAM containing 6% and 9% fiber glass. Beyond 9%, the fatigue life decreased because of the poor dispersion of fibers in the EAM. In another study, 9% mineral fiber increased the fatigue life by 55% (Xue and Qian 2016). Therefore, it is expected that 9% fiber is the optimum fiber content for EAM.



(a) Flexural strength (b) Flexural Strength at the failure point Figure 12: Comparison between EAM and mixture using PMB; plotted based data reported by Min *et al.* (2019).

606

607 **6.** Conclusion

A new generation of asphalt binders could be produced using a thermosetting epoxy technology instead of a thermoplastic process relied on by traditional asphalt materials. A network formed by the curing of epoxy materials in the structure of EAB, improving rheological characteristics. EAB can be produced using various binder types and additives, but the compatibility should be evaluated for quality assurance.

Due to the thermosetting nature of epoxy, it cannot be remelted by heat. Therefore, any extra curing 613 614 decreases the workability of the mix significantly. As a result, there is a limited time for transportation of EAM because curing drastically decreases workability. WMA additives, foam technology, and 615 some nanomaterials can be used to extend the time of paying. However, the optimum content of 616 617 WMA additives, water for foam production, and nanomaterials depends on curing type, epoxy content, chemical properties of the base binder. Additionally, optimum epoxy content, type, and any modifier 618 can be determined based on results of rheological characteristics of EAM and utility service of 619 pavement. A well-designed EAB is not prone phase separation, which significantly reduces the 620 durability of the modified asphalts. 621

Laboratory structural performance of EAM has been evaluated in terms of Marshall properties, ITS, rutting, and fatigue. The results clearly indicated that the structural performance of EAM is much higher than the conventional HMA and WMA due to strong binding of aggregate particles and binders, as well as high stiffness of EAB. Additionally, the structural performance of EAM can be improved using waste materials and additives. Epoxy asphalt technology is therefore compatible with many waste materials available on the market. However, the mixing time must be carefully controlled so that it is long enough to give a uniform coating of EAB to the aggregate particles and short enough to delay EAB during construction.

629 delay EAB during630

631 **References:**

Adam, W., Bargon, R. M., and Schenk, W. A. (2003). Direct epiossification of alkenes and allenes
with elemental sulfur and thiiranes as sulfur sources, catalyzed by molybdenum oxo complexes. *American Chemical Society*, 125(13), 3871-3876.

- Ai, T., Xiang, S., and Wang, Z. (2016). Effects of microwave curing on the chemical and physical
 properties of epoxy asphalt. *Materials in Civil Engineering (ASCE)*, 28(11), 06016013.
- Airey, G. D., Mohammed, M. H., and Fichter, C. (2008). Rheological characteristics of synthetic road
- Alrey, G. D., Monammed, M. H., and Fichter, C. (2008). Rheological characteristics of synthetic roa
- 638 binders. *Fuel*, 87(10-11), 1763-1775.

- Airey GD, Rahimzadeh B, Collop AC. (2004). Linear rheological behavior of bituminous paving
 materials. *Materials in Civil Engineering (ASCE)*,16(3):212–20.
- 641 Alabaster D, Herrington P.R, Waters J.C. (2008). Long life open-graded porous asphalt. In: Third
- 642 International Conference on Accelerated Pavement Testing, APT 2008, Madrid, Spain.
- Apostolidis, P., Liu, X., van de Ven, M., Erkens, S., and Scarpas, T. (2019a). Control the crosslinking
- of epoxy-asphalt via induction heating. *International Journal of Pavement Engineering*, 1-10.
 Apostolidis, P., Liu, X., van de Ven, M., Erkens, S., and Scarpas, T. (2019b). Kinetic viscoelasticity
- Apostolidis, P., Liu, X., van de Ven, M., Erkens, S., and Scarpas, T. (2019b). Kinetic viscoelasticity
 of crosslinking epoxy asphalt. *Transportation Research Record*, 2673(3), 551-560.
- Araki, W., Wada, S., and Adachi, T. (2008). Viscoelasticity of epoxy resin/silica hybrid materials
 with an acid anhydride curing agent. *Applied Polymer Science*, 108(4), 2421-2427.
- ASTM D 1763. (2013). Standard specification for epoxy resins. West Conshohocken, Pennsylvania,USA.
- Bahmani, H., Sanij, H. K., & Peiravian, F. (2021). Estimating Moisture Resistance of asphalt mixture
 containing epoxy resin using Surface Free Energy Method and Modified Lottman test. *International*
- 653 *Journal of Pavement Engineering*, 1-13.
- 654 Bhattacharjee, S., Swamy, A. K., and Daniel, J. S. (2009). Application of elastic-Viscoelastic
- correspondence principle to determine fatigue endurance limit of hot-mix asphalt. *Transportation Research Record*, 2126(1), 12-18.
- Bocci, E., Graziani, A., and Canestrari, F. (2015). Mechanical 3D characterization of epoxy asphalt
 concrete for pavement layers of orthotropic steel decks. *Construction and Building Materials*, 79,
 145-152.
- 660 Bradley, W. (1940). The structural scheme of attapulgite. Am Miner, 25:405–10.
- Brown., E.R. (2006). Methods for determining the endurance limit using beam fatigue tests.
 International Conference on Perpetual Pavement, 13-15.
- Burns C.D. (1964). Laboratory and field study of epoxy-asphalt concrete, Technical Report 3-368, US
 Army Engineer Waterways Experiment Station, US Corps of Engineers, USA.
- 665 Cao, X. J., Lei, Y. B., Wang, W., and Tang, B. M. (2011). A curing model for epoxy asphalt concrete
- and its implementation for construction. International Journal of Pavement Research and Technology,
- 667 4(3), 140-146.
- 668 Cao, W., Wang, Y., and Wang, C. (2019). Fatigue characterization of bio-modified asphalt binders 669 under various laboratory aging conditions. *Construction and Building Materials*, 208, 686-696.
- 670 Carpenter, S. H., Ghuzlan, K. A., and Shen, S. (2003). Fatigue endurance limit for highway and 671 airport pavements. *Transportation Research Record*, 1832(1), 131-138.
- 672 Changjiang, H., Zhendong, Q., Jianwei, W., and Guangyi, H. (2007). Research on failures treatment
- technique of epoxy asphalt concrete steel deck bridge surfacing. *Transportation Science and Technology*, 5.
- 675 Chen, L.X., Tian, H., Liu, Q.W., and Wang. J. (2007). Curing reaction kinetics of epoxy resin using
- dicyandiamide modified by aromatic amines, *Wuhan University Journal of Natural Science*. 12 (6),
 1105–1108.
- 678 Chen X. (2009). On the fracture properties of epoxy asphalt mixture with SCB test. Taylor & Francis
 679 Group, ISBN 978-0-415-55854-9, London, UK, 531–540.
- Chen., LL., Qian., Z.D., Luo., S. (2011). Assessment of crack sealing materials and techniques for
 epoxy asphalt pavement on steel bridges decks. Transportation Research Board of the National
 Academies, Washington, D.C. USA.
- 683 Chen, L. L., Qian, Z. D., and Jiang, C. L. (2012a). Research on strength developing procedure of
- epoxy asphalt mixture. In Ninth Asia Pacific Transportation Development Conference, American
 Society of Civil Engineers and International Chinese Transportation Professionals Association T. Y.
- Society of Civil Engineers and International Chinese Transportation Professionals Association T. Y.
 Chen, L., Qian, Z., and Lu, Q. (2014). Crack initiation and propagation in epoxy asphalt concrete in
- the three-point bending test. *Road Materials and Pavement Design*, 15(3), 507-520.

- 688 Chen, C., Eisenhut, W. O., Lau, K., Buss, A., and Bors, J. (2018a). Performance characteristics of 689 epoxy asphalt paving material for thin orthotropic steel plate decks. *International Journal of* 690 *Pavement Engineering*, 1-11.
- 691 Chen, C., Eisenhut, W. O., Lau, K., Ingram, A., and Bors, J. (2018b). Stiffening thin orthotropic deck
- 692 structures with thermoset epoxy asphalt for improved fatigue resistance. In Civil Infrastructures
- 693 Confronting Severe Weathers and Climate Changes Conference, Springer Publisher, Heidelberg,694 Germany, 32-43.
- 695 Collyer, A. A. (Ed.). (2012). Rubber toughened engineering plastics. Springer Science & Business
 696 Media.
- 697 Cong, P., Jianying, Y., and Shuanfa, C. (2010). Effects of epoxy resin contents on the rheological 698 properties of epoxy-asphalt blends. *Applied Polymer Science*, 118(6), 3678-3684.
- Cong, P., Chen, S., and Yu, J. (2011). Investigation of the properties of epoxy resin-modified asphalt
 mixtures for application to orthotropic bridge decks. *Applied Polymer Science*, 121(4), 2310-2316.
- Cong, P., Liu, N., Shang, H., and Zhao, H. (2015). Rheological and fatigue properties of epoxy
 asphalt binder. *International Journal of Pavement Research and Technology*, 8(5), 370-376.
- Cong, P., Tian, Y., Liu, N., and Xu, P. (2016). Investigation of epoxy resin modified asphalt
 binder. *Applied Polymer Science*, 133(21).
- Cong, P., Luo, W., Xu, P., and Zhang, Y. (2019). Chemical and physical properties of hot mixing
- epoxy asphalt binders. *Construction and Building Materials*, 198, 1-9.
- 707 Cranley, P.E. Paint and Coatings Industry, 1994.
- Cubuk, M., Gürü, M., and Çubuk, M. K. (2009). Improvement of bitumen performance with epoxyresin. *Fuel*, 88(7), 1324-1328.
- 710 Dinnen, A. (1981). Epoxy Bitumen for Critical Road Conditions, Proceedings of the 2nd Eurobitume
- 711 Symposium, Cannes, France, Vol. 2, p. 294-296.
- 712 Dong, Z., and Li, L. P. (2015). Study on dynamic mechanical properties and microstructure of epoxy
- 713 asphalt. In 2015 International Conference on Applied Science and Engineering Innovation. Atlantis714 Press.
- 715 Dubowik DA, Ross GC. (2001). A novel waterborne epoxy resin for zero-void, two component
- 716 coating. In: 2000, International Waterborne High-Solids and Powder Coatings Symposium, New
- 717 Orleans, USA.
- El Rahman, A. A., El-Shafie, M., and El Kholy, S. A. (2012). Modification of local asphalt with
 epoxy resin to be used in pavement. *Egyptian Journal of Petroleum*, 21(2), 139-147.
- Esmizadeh E, Naderi G, Yousefi AA, Milone C. (2016). Investigation of curing kinetics of epoxy
 resin/novel nanoclay–carbon nanotube hybrids by non-isothermal differential scanning calorimetry.
- *Thermal Analysis and Calorimetry*,126:771–84.
- 723 Fini, E. H., Kalberer, E. W., Shahbazi, A., Basti, M., You, Z., Ozer, H., and Aurangzeb, Q. (2011).
- Chemical characterization of biobinder from swine manure: Sustainable modifier for asphalt binder.
 Materials in Civil Engineering (ASCE), 23(11), 1506-1513.
- Fuentes-Auden, C., Andres Sandoval, J., Jerez, A., Navarro, F.J., Martinez-Boza, F.J., Partal, P., C.
- and Gallegos, C. (2008). Evaluation of thermal and mechanical properties of recycled polyethylene
- modified bitumen. *Polymer Testing*, 25 (8): 1005-1012.
- Fuhaid, A. A., Lu, Q., and Luo, S. (2018). Laboratory Evaluation of biobased epoxy asphalt binder for
 asphalt pavement. *Materials in Civil Engineering (ASCE)*, 30(7),1-8.
- Gallagher, K.P and Vermillion, D.R. (1997). Thermosetting asphalt having continuous phase polymer,
 U.S. Pat: 5604274. Lin International Group Chongqing Urban Planning Bureau.
- 733 Gong, J., Liu, Y., Jiang, Y., Wang, Q., Xi, Z., Cai, J., and Xie, H. (2021). Performance of epoxy
- asphalt binder containing warm-mix asphalt additive. *International Journal of Pavement Engineering*,
 1-10.
- 736 Guo. X. (2014). Epoxy resin adhesives with high-temperature and study its curing reaction kinetics,
- 737 Donghua University, Shanghai, China.

- Herrington, P. R., Wu, Y., and Forbes, M. C. (1999). Rheological modification of bitumen with
 maleic anhydride and dicarboxylic acids. *Fuel*, 78(1), 101-110.
- Herrington, P.R, and Alabaster, D. (2008). Epoxy modified open-graded porous asphalt. *Road Materials and Pavement Design*, 9(3), 481-498.
- Holleran, G., Holleran, I., Bearsley, S., Dubois, C. J., and Wilson, D. (2017). Epoxy asphalt for
- 743 durability of open graded mixes: part 1 performance approaches. In 17th AAPA International
- 744 *Flexible Pavements Conference*, Australian Asphalt Paving Association, Melbourne, Australia, 13-16.
- Hsieh, T. H., Kinloch, A. J., Masania, K., Lee, J. S., Taylor, A. C., & Sprenger, S. (2010). The
- toughness of epoxy polymers and fibre composites modified with rubber microparticles and silica
 nanoparticles. *Materials Science*, 45(5), 1193-1210.
- Huang, K., Xia, J. L., and Ding, H. Y. (2010). Properties of thermosetting epoxy asphalt materials
 prepared from modified epoxy resin. *Thermosetting Resin*, 25(1), 35-39.
- Huang, M., and Huang, W. (2011). Analyses of viscosity variation in solidifying procedure of epoxy
- asphalt. In Third International Conference on Transportation Engineering (ICTE) American Society
 of Civil Engineers China Communications and Transportation Association.
- Huang, W., Li, X., Qian, Z., and Li, Z. (2011). Analysis on mechanical mechanism of thermosetting
- epoxy asphalt concrete using mesomechanics approach. In 11th International Conference of Chinese
- 755 Transportation Professionals (ICCTP) American Society of Civil Engineers, National Natural Science
- 756 Foundation of China, Nanjing, China.
- Huang, W. (2015). Integrated design procedure for epoxy asphalt concrete–based wearing surface on
 long-span orthotropic steel deck bridges. *Materials in Civil Engineering (ASCE)*, 28(5), 04015189.
- Huang, m., Wen, X., and Wang, L. (2017). Influence of foaming effect, operation time and health
- preserving properties of foam epoxy asphalt mixtures. *Construction and Building Materials*, 151, 931-938.
- Huang, M., and Wen, X. (2019). Experimental study on photocatalytic effect of nano TiO2 epoxy
 emulsified asphalt mixture. *Applied Sciences*, 9(12), 2464.
- Ishibashi, et al. (1990). Prefabricated orthotropic steel deck paving, pavement, Vol. 25, No. 9. Japan
- Road Association, 2007. Waterproofing Handbook for Highway Bridge Slabs, Tokyo, Japan.
- Jasso, M., Hampl, R., Vacin, O., Bakos, D., Stastna, J., & Zanzotto, L. (2015). Rheology of
 conventional asphalt modified with SBS, Elvaloy and polyphosphoric acid. *Fuel Processing Technology*, 140, 172-179.
- Jiang, Y., Liu, Y., Gong, J., Li, C., Xi, Z., Cai, J., and Xie, H. (2018). Microstructures, thermal and
 mechanical properties of epoxy asphalt binder modified by SBS containing various styrene-butadiene
- structures. *Materials and Structures*, 51(4), 86.
- Kang, Y., Chen, Z., Jiao, Z., and Huang, W. (2010). Rubber-like thermosetting epoxy asphalt
 composites exhibiting atypical yielding behaviors. *Applied Polymer Science*, 116(3), 1678-1685.
- Kang, Y., Song, M., Pu, L., and Liu, T. (2015). Rheological behaviors of epoxy asphalt binder in
 comparison of base asphalt binder and SBS modified asphalt binder. *Construction and Building Materials*, 76, 343-350.
- Kang, Y., Wu, Q., Jin, R., Yu, P., and Cheng, J. (2016). Rubber-like Quasi-thermosetting
 polyetheramine-cured epoxy asphalt composites capable of being opened to traffic immediately.
 Scientific Reports, 6, 18882.
- Kim, J.S., Chin, I.J., Lee, B.S. (2000). Curing of DGEBA epoxy with modified low- temperature
 curing agents, Environmental Sciences and Pollution Management, Seoul, Korea.
- Koji, A., Sawako, K. kenji, K., and Masahiro, F. (2015). Imidazole derivatives as latent curing agents
 for epoxy thermosetting resins, *Material Letters*, 161, 408–410.
- Kumar, S., Samal, S. K., Mohanty, S., & Nayak, S. K. (2018). Recent development of biobased epoxy
 resins: a review. *Polymer-Plastics Technology and Engineering*, 57(3), 133-155.
- 786 Kwon, H., Lee, A. S., Lee, J. H., Park, N. K., Kim, G. D., Cho, B., and Yu, S. (2017).
- 787 Characterization of liquid state sulfur polymer/epoxy blend as asphalt pavement materials. Industrial
- *and Engineering Chemistry*, 53, 386-391.

- Liu, X.W. and Zhang, X.N. (2010). Application of Japanese TAF epoxy asphalt concrete in deck
 pavement bridge tunnel machinery construction. *Technology*, 1, 69-71. (in Chinese)
- Liu Y, Xi Z, Cai J, Xie H. (2017a). Laboratory investigation of the properties of epoxy asphalt.
 Materials and Structure, 50:219.
- Teiu, Y., Zhang, J., Chen, R., Cai, J., Xi, Z., and Xie, H. (2017b). Ethylene vinyl acetate copolymer
- modified epoxy asphalt binders: phase separation evolution and mechanical properties. *Construction and Building Materials*, 137, 55-65.
- Liu, Y., Zhang, J., Jiang, Y., Li, C., Xi, Z., Jun Cai, J., and Xie, H. (2018). Investigation of secondary
- phase separation and mechanical properties of epoxy SBS-modified asphalts. *Construction and Building Materials*, 165, 163-172.
- Li, S., Huang, K., Yang, X., Li, M., and Xia, J. (2014). Design, preparation and characterization of
 novel toughened epoxy asphalt based on a vegetable oil derivative for bridge deck paving. RSC
 Advances, 4(84), 44741-44749.
- Li, Y., Cao, D., Zhang, Y., & Jia, X. (2021). Performance of a dry-method-epoxy modifier and a modified epoxy-asphalt mixture. *Construction and Building Materials*, 266, 120229.
- Luo, S., Lu, Q., and Qian, Z. (2015). Performance evaluation of epoxy modified open-graded porous asphalt concrete. *Construction and Building Materials*, 76, 97-102.
- Lu, X.H., and Isacsson, U. (2001). Modification of road bitumens with thermoplastic polymers.
 Polymer Testing, 20 (1), 77–86.
- Mayama, M. (1978a). Mechanical Properties of Epoxy Asphalt Mixtures. *The Japan Petroleum Institute*, 21(1), 68-76 (In Japanese).
- 810 Mayama, M. (1987b). Vibrating and Mechanical Properties of Ferrite-Epoxy Mixtures. *Doboku*
- 811 *Gakkai Ronbunshu*, (385), 59-68. (In Japanese)
- 812 Meath, A.R. Handbook of Adhesives, New York, 1990.
- 813 Miller, J. S., and Bellinger, W. Y. (2003). Distress identification manual for the long-term pavement
- performance program. Rep. No. FHWARD- 03-031, Federal Highway Administration, Washington,
 DC, USA.
- Min, Z., Zhou, L., Wang, Q., and Zhang, Y. (2019). Performance Evaluation of epoxy-asphalt mixture
 blended with glass aggregate. *Materials in Civil Engineering (ASCE)*, 31(6), 04019083.
- 818 Min, Z., Sun, L., Wang, Q., and Yu, Z. (2020). Influence of aggregate packing on the performance of
- uncured and cured epoxy asphalt mixtures. *Materials in Civil Engineering (ASCE)*, 32(5), 04020103.
- Min, Z., Wang, Q., Xie, Y., Xie, J., & Zhang, B. (2021a). Influence of polyethylene glycol (PEG)
 chain on the performance of epoxy asphalt binder and mixture. *Construction and Building Materials*,
 272, 121614.
- Min, Z., Yu, Z., & Wang, Q. (2021). Behaviours of incorporating ceramsite into epoxy asphalt mixture as thermal resistance aggregates. *International Journal of Pavement Engineering*, 1-15.
- Mo, L. T., Fang, X., Yan, D. P., Huurman, M., & Wu, S. P. (2012). Investigation of mechanical
 properties of thin epoxy polymer overlay materials upon orthotropic steel bridge decks. *Construction and Building Materials*, 33, 41-47.
- Mohan, P. (2013). A critical review: the modification, properties, and applications of epoxy resins. *Polymer-Plastics Technology and Engineering*, 52(2), 107-125.
- 830 Nakanishi, H., Okochi, T., and Goto., K. (2000). The structural evaluation for an asphalt pavement on
- a steel plate deck. In World of Asphalt Pavements, International Conference, 1st, 2000, Sydney, New
 South Wales, Australia.
- 833 Nguyen, Q. T., & Tran, T. C. H. (2021). Experimental investigation of fatigue behavior for polymer
- 834 modified asphalt and epoxy asphalt mixtures. In Proceedings of the 3rd International Conference on 835 Sustainability in Civil Engineering, Springer, Singapore, 161-166.
- 836 Osumi, Y. (1987). One-Part Epoxy Resin. Three Bond Technical News, 19(1), 1-10.
- 837 Petrie, E. M. (2005). Epoxy adhesive formulations. McGraw Hill Professional, New York, USA.
- 838 Polacco, G., Berlincioni, S., Biondi, D., Stastna, J., and Zanzotto, L. (2005). Asphalt modification
- 839 with different polyethylene-based polymers. *European Polymer Journal*, 41 (12), 2831–2844.

- 840 Polacco, G., Filippi, S., Merusi, F., and Stastna, G. (2015). A review of the fundamentals of polymer-
- modified asphalts: Asphalt/polymer interactions and principles of compatibility. *Advances in colloid and Interface Science*, 224, 72-112.
- Qian, Z., Chen, L., Wang, Y., and Shen, J. (2012). Curing reaction model of epoxy asphalt binder.
 Journal of Wuhan University of Technology, *Material Science*, 27(4), 763-767.
- Qian, Z., Chen, C., Jiang, C., and de Fortier Smit, A. (2013). Development of a lightweight epoxy
 asphalt mixture for bridge decks. *Construction and Building Materials*, 48, 516-520.
- 847 Qian, Z. D., Liu, Y., Liu, C. B., and Zheng, D. (2016). Design and skid resistance evaluation of
- skeleton-dense epoxy asphalt mixture for steel bridge deck pavement. *Construction and Building Materials*, 114, 851-863.
- Raquez, J. M., Deléglise, M., Lacrampe, M. F., & Krawczak, P. (2010). Thermosetting (bio) materials
 derived from renewable resources: a critical review. *Progress in Polymer Science*, 35(4), 487-509.
- Salman, M. K., Karabay, B., Karabay, L. C., and Cihaner, A. (2016). Elemental sulfur based
 polymeric materials: Synthesis and characterization. *Applied Polymer Science*, 133(28).
- 854 Sancaktar, E. (1990). Engineered Materials Handbook, Vol. 3: Adhesives and Sealants.
- Schapery, R. A. (1984). Correspondence principles and a generalized integral for large deformation and fracture analysis of viscoelastic media. *International Journal of Fracture*, 25(3), 195-223.
- 857 Seim., C. (1973). Skid resistance of epoxy asphalt pavements on California Toll bridges. In Skid
- 858 Resistance of Highway Pavements. West Conshohocken, Pennsylvania, USA, 41-59.
- Sengoz, B., Topal, A., and Isikyakar, G. (2009). Morphology and image analysis of polymer-modified
 bitumens, *Construction and Building Materials*, 23 (5),1986–1992.
- Song, M., Liang, R., Deng, J., and Kang, Y. (2017). Sealed accelerants facilitate epoxy asphalt
 concretes opening to traffic quickly. *Construction and Building Materials*, 147, 1-8.
- Sun, Y., Zhang, Y., Xu, K., Xu, W., Yu, D., Zhu, L. (2015). Thermal, mechanical properties, and
 low-temperature performance of fibrous nanoclay-reinforced epoxy asphalt composites and their
 concretes. *Applied Polymer Science*,132(12), 41694(1-9).
- 866 Sun, Y., Liua, Y., Jianga, Y., Xua, K., Xib, Z., and Xie, H. (2018). Thermal and mechanical properties
- of natural fibrous nanoclay reinforced epoxy asphalt adhesives. *International Journal of Adhesion and Adhesives*, 85: 308-314.
- Sun, Y., Liu, Y., Gong, J., Han, X., Xi, Z., Zhang, J., ... & Xie, H. (2021). Thermal and bonding
 properties of epoxy asphalt bond coats. *Journal of Thermal Analysis and Calorimetry*, 1-13.
- 871 Sureshkumar, M.S., Filippi, S., Polacco, G., Kazatchkov, I., Stastna, J., and Zanzotto, L. (2010).
 872 Internal structure and linear viscoelastic properties of EVA/asphalt nanocomposites. *European*
- 873 *Polymer Journal*, 46 (4), 621–633.
- 874 Takahashi, M., and Shimazaki, M., and Aoki, M. (2010). Applicability of bright-colored epoxy
- asphalt mixture for repair of concrete pavements in tunnels, 11th International Symposium of Asphalt
 Pavements (ISAP), Nagoya, Japan.
- 877 Vyrozhemskyi, V., Kopynets, I., Kischynski, S., and Bidnenko, N. (2017). Epoxy asphalt concrete is
- 878 a perspective material for the construction of roads, IOP Conference Series: Materials Science and
- 879 Engineering. Building up Efficient and Sustainable Transport Infrastructure (BESTInfra2017), Prague,
 880 Czech Republic.
- Wang, Y., Ye, J., Liu, Y., Qiang, X., and Feng, L. (2013). Influence of freeze thaw cycles on
 properties of asphalt-modified epoxy repair materials. *Construction and Building Materials*. 41, 580585.
- Wang, X., Wu, R., and Zhang, L. (2019). Development and performance evaluation of epoxy asphalt
 concrete modified with glass fibre. *Road Materials and Pavement Design*, 20(3), 715-726.
- Wang, X., Ma, B., Chen, S., Wei, K., & Kang, X. (2021). Properties of epoxy-resin binders and
 feasibility of their application in pavement mixtures. *Construction and Building Materials*. 295,
- 888 123531.

- 889 Widyatmoko, I., Zhao, B., Elliot, R. C., and Lloyd, W. G. (2006). *Curing characteristics and the* 890 *performance and durability of epoxy asphalts. In Proceedings of the 10th Conference on Asphalt*
- 890 *performance and durability of epoxy asphalt*891 *Pavements*, Quebec, Canada, 12-17.
- Wu, Q., Wanga, C., Liang, R., Liu, Y., Cheng, J., and Kang, Y. (2018). Fractional linear viscoelastic
 constitutive relations of anhydride-cured thermosetting rubber-like epoxy asphalt binders.
- 894 *Construction and Building Materials*, 170, 582-590.
- Xiang, Q., and Xiao, F. (2020). Applications of epoxy materials in pavement engineering.
 Construction and Building Materials, 235, 117529.
- Xiaohua Zhou, Zong Hai, Yihe and Tong, Yuli. (2010). The diseases analysis of steel bridge deck
 pavement of Epoxy Asphalt concrete highway. *Traffic Science and Technology*, 26 (8), pp. 105-107.
- Xiao, Y., Van de ven, M.F.C., Molennar, A.A.A., and Zandvoort, F. (2011). Characteristics of twocomponents epoxy modified bitumen. *Materials and Structures*, (44): 611-622.
- 901 Xiao, Y., Van de Ven, M. F. C., Molenaar, A. A. A., Su, Z., and Chang, K. (2013). Design approach
- for epoxy modified bitumen to be used in antiskid surfaces on asphalt pavement. *Construction and Building Materials*, 41, 516-525.
- Xue, Y., and Qian, Z. (2016). Development and performance evaluation of epoxy asphalt concrete
 modified with mineral fiber. *Construction and Building Materials*, 102, 378-383.
- Xu, X., Yang, X., Huang, W., Xiang, H., and Yang, W. (2019). New damage evolution law for steel–
 asphalt concrete composite pavement considering wheel load and temperature
 variation. *Materials*, 12(22), 3723.
- Xu, J., Ma, B., Mao, W., & Wang, X. (2021a). Strength characteristics and prediction of epoxy resin
 pavement mixture. *Construction and Building Materials*, 283, 122682.
- Xu, W., Wei, J., Chen, Z., Wang, F., & Zhao, J. (2021b). Evaluation of the effects of filler fineness on
 the properties of an epoxy asphalt mixture. *Materials*, 14(8), 2003.
- 913 Yan, C.X., Li, Z.G., and Cao, S.C. (2013). Epoxy asphalt pavements in Chinese cold regions low
 914 temperature. *Architecture Technology*, 6, 18-20.
- 915 Yao, B., Cheng, G., Wang, X., Cheng, C., and Liu, S. (2013a). Linear viscoelastic behaviour of
- 916 thermosetting epoxy asphalt concrete experiments and modelling. *Construction and Building* 917 *Materials*, 48, 540-547.
- 918 Yildirim, Y. (2007). Polymer modified asphalt binders. *Construction and Building Materials*, 21(1),
 919 66-72.
- Yin, H., Jin, H., Wang, C., Sun, Y., Yuan, Z., Xie, H., ... and Cheng, R. (2014). Thermal, damping,
 and mechanical properties of thermosetting epoxy-modified asphalts. *Thermal Analysis and*
- 922 *Calorimetry*, 115(2), 1073-1080.
- Yin, H., Zhang, Y., Sun, Y., Xu, W., Yu, D., Xie, H., and Cheng, R. (2015). Performance of hot mix
 epoxy asphalt binder and its concrete. *Materials and Structures*, 48(11), 3825-3835.
- Yu, J., Cong, P., Wu, S., and Cheng, S. (2009a). Curing behaviour of epoxy asphalt. *Wuhan University of Technology-Material Science Edition*, 24(3), 462-465.
- Yu, J., Cong, P., and Wu, S. (2009b). Laboratory investigation of the properties of asphalt modified
 with epoxy resin. *Applied Polymer Science*, 113(6), 3557-3563.
- Yu, X., Dong, F., Ding, G., Liu, S., and Shen, S. (2016). Rheological and microstructural properties of
 foamed epoxy asphalt. *Construction and Building Materials*, 114, 215-222.
- P31 Zhang, D.J. (2007). Epoxy asphalt concrete pavement of Nanjing Changjiang 3rd Bridge, Highways 9,
 P32 21–25.
- Zhang, X.L., Zhang, W.N., Liu, J., and Chen., Y.R. (2010). Application of hyperbranched polyesters
 in modification of epoxy resins, *Chemical Adhesion*, 32 (3): 51–55.
- 935 Zhang, J., Su, W., Liu, Y., Gong, J., Xi, Z., Zhang, J., ... & Xie, H. (2021). Laboratory investigation
- 936 on the microstructure and performance of SBS modified epoxy asphalt binder. Construction and
- **937** *Building Materials*, 270, 121378.

- Zhao, Y., Jiang, J., Ni, F., and Zhou, L. (2019). Fatigue cracking resistance of engineered
 cementitious composites (ecc) under working condition of orthotropic steel bridge decks pavement.
- 940 *Applied Sciences*, 9(17), 3577.
- 241 Zher'akova, G., and Kochkan'an, R. (1990). Reactivity and structure investigation of coals in reaction with dispersive First = 0.01
- 942 with dienophiles. *Fuel*, 69(7), 898-901.
- 243 Zhong, K., Yang, X., and Wei, X. (2017). Investigation on surface characteristics of epoxy asphalt
 244 concrete pavement. *International Journal of Pavement Research and Technology*, 10(6), 545-552.
- 245 Zhou, W., Xia, Y., Tsai, F. C., Jiang, T., Zhao, H., and Wen, J. (2017). Effects of compound curing
- agent on the thermo-mechanical properties and structure of epoxy asphalt. International Journal of
- 947 *Pavement Engineering*, 18(10), 928-936.
- Zhu, J., Chen, Z, Min, Z., Huang, W., and Wang, J. (2004). Study on epoxy resin modified asphalt
 materials for highway. *South East University (Natural Science Edition)*, 515-517 (In Chinese).
- 950 Zhu, C. (2013). Japan TAF epoxy asphalt concrete design and steel bridge deck pavement
- 951 construction technology. In Applied Mechanics and Materials. Transportation Technical Publications,
- 952 Genev, Switzerland, 330, 905-910.
- 953 Zhu, J., Birgisson, B., and Kringos, N. (2014). Polymer modification of bitumen: Advances and
- 954 challenges. *European Polymer Journal*, 54, 18-38.