



Title	The effect of dentine surface preparation and reduced application time of adhesive on bond strength
Author(s)	Saikaew, Pipop
Citation	北海道大学. 博士(歯学) 甲第13045号
Issue Date	2018-03-22
DOI	10.14943/doctoral.k13045
Doc URL	http://hdl.handle.net/2115/89188
Type	theses (doctoral)
Note	共著 : A.F.M. Almas Chowdhury, Mai Fukuyama, Shinichi Kakuda, Ricardo M. Carvalho, Hidehiko Sano
File Information	Saikaew_Pipop.pdf



[Instructions for use](#)

博士論文

The effect of dentine surface preparation and reduced application
time of adhesive on bond strength
(切削方法の違いと接着材処理時間の短縮が象牙質の接着強さに与える影響
についての検討)

平成30年3月申請

北海道大学
大学院歯学研究科口腔医学専攻

Pi pop Sai kaew



The effect of dentine surface preparation and reduced application time of adhesive on bonding strength



Pipop Saikaew^{a,*}, A.F.M. Almas Chowdhury^a, Mai Fukuyama^a, Shinichi Kakuda^a, Ricardo M. Carvalho^{a,b}, Hidehiko Sano^a

^a Department of Restorative Dentistry, Division of Oral Health Science, Hokkaido University Graduate School of Dental Medicine, Kita 13, Nishi 7, Kita-ku, Sapporo 060-8586, Japan

^b Department of Oral Biological and Medical Sciences, Division of Biomaterials, University of British Columbia, Faculty of Dentistry, 2199 Wesbrook Mall, Vancouver, BC V6T 1Z3, Canada

ARTICLE INFO

Article history:

Received 20 November 2015

Received in revised form 29 January 2016

Accepted 2 February 2016

Keywords:

Universal adhesives
Microtensile bond strength
Bonding application time
Surface preparation
SEM

ABSTRACT

Objective: This study evaluated the effects of surface preparation and the application time of adhesives on the resin–dentine bond strengths with universal adhesives.

Methods: Sixty molars were cut to exposed mid-coronal dentine and divided into 12 groups ($n=5$) based on three factors; (1) adhesive: G-Premio Bond (GP, GC Corp., Tokyo, Japan), Clearfil Universal Bond (CU, Kuraray Noritake Dental Inc., Okayama, Japan) and Scotchbond Universal Adhesive (SB, 3M ESPE, St. Paul, MN, USA); (2) smear layer preparation: SiC paper ground dentine or bur-cut dentine; (3) application time: shortened time or as manufacturer's instruction. Fifteen resin–dentine sticks per group were processed for microtensile bond strength test (μ TBS) according to non-trimming technique (1 mm^2) after storage in distilled water (37°C) for 24 h. Data were analyzed by three-way ANOVA and Dunnett T3 tests ($\alpha=0.05$). Fractured surfaces were observed under scanning electron microscope (SEM). Another 12 teeth were prepared and cut into slices for SEM examination of bonded interfaces.

Results: μ TBS were higher when bonded to SiC-ground dentine according to manufacturer's instruction. Bonding to bur-cut dentine resulted in significantly lower μ TBS ($p<0.000$). Shortening the application time resulted in significantly lower bond strength for CU on SiC and GP on bur-cut dentine. SEM of fractured surfaces revealed areas with a large amount of porosities at the adhesive resin interface. This was more pronounced when adhesives were bonded with a reduced application time and on bur cut dentine.

Clinical significance: The performance of universal adhesives can be compromised on bur cut dentine and when applied with a reduced application time.

© 2016 Elsevier Ltd. All rights reserved.

1. Introduction

All-in-one self-etching adhesives have become popular in dentistry because of their advantages such as less technique sensitivity and user-friendliness [1]. However, there are still concerns about the effectiveness of 1-step adhesives when bonding to uncut enamel [2,3], to different smear layer preparation [4,5] and their long-term durability [1].

Recently, universal adhesives have been introduced to the market. They are principle 1-step self-etching adhesives that can be applied in either self-etching mode or etch-and-rinse mode [6–8]. Similar to the mildly acidic self-etching adhesives, there are concerns regarding the effect of smear layer on their bonding performance [5,9,10]. Most of the studies that have evaluated the effect of smear layer preparation on the bond strength of adhesives used only different SiC-paper grits, which can be regarded as not clinically relevant [9–16]. Furthermore, the study from Oliveira et al. [9] reported that the loosely organized smear layer produced by SiC papers was easier for self-etching primer to penetrate when compared to those of diamond burs.

* Corresponding author. Tel.: +81 11 706 4261; fax: +81 11 706 4878.
E-mail addresses: pipop045@den.hokudai.ac.th, pipop045@gmail.com (P. Saikaew).

Table 1
Adhesive system (batch number), composition and application procedures.

Adhesive (batch number)	pH ^a	Composition	Manufacturers' instruction
Clearfil Universal Bond (000002)	2.3	10-MDP, Bis-GMA, HEMA, ethanol, hydrophilic aliphatic dimethacrylate, colloidal silica, dl-camphorquinone, silane coupling agent and water	1. Apply the adhesive to the dentine surface with the applicator brush and rub it in for 10 s 2. Dry the dentine surface sufficiently by blowing mild air for more than 5 s until the adhesive does not move 3. Light cure for 10 s
G-Premio Bond ^b (1411061G)	1.5	10-MDP, 4-META, 10-methacryloyloxydecyl dihydrogen thiophosphate, methacrylate adic ester, distilled water, acetone, photo initiators, silica fine powder	1. Apply using a microbrush 2. Leave undisturbed for 10 s after application 3. Dry thoroughly for 5 s with oil free air under maximum air pressure 4. Light cure for 10 s
Scotchbond Universal (572054)	2.7	10-MDP, HEMA, silane, dimethacrylate resins, Vitrebond TM copolymer, filler, ethanol, water, initiators	1. Apply the adhesive on the surface and rub it in for 20 s 2. Gently air-dry the adhesive for approximately 5 s for the solvent to evaporate 3. Light cure for 10 s

10-MDP: 10-methacryloyloxydecyl dihydrogen phosphate; Bis-GMA: bisphenol A diglycidyl methacrylate; HEMA: 2-hydroxyethyl methacrylate; 4-META: 4-methacryloyloxyethyl trimellitate anhydride.

^a The pH for SB and CU was obtained from Ref. [6]. For GP it was informed by the manufacturer.

^b The shortened application time is an optional application mode suggested by the manufacturer.

To overcome the infiltration-impairing effect of smear layer, prolonged application time has been suggested as an option to increase bond strength [11]. Although, the bond strength improvement might be system-specific [12]. However, contrary to the suggestive findings referred above, the newly developed product from GC Corp., G-Premio Bond claims that high bond strength can be achieved even when applied with shortened application time (optional manufacturer's instructions). Although shorter application time may be clinically appealing, the procedure may carry negative consequences to adhesive infiltration and solvent evaporation. Since one product has adopted such optional reduced application time, it becomes interesting to test if such approach can also be applied to other adhesives; and whether the type of smear layer plays a role on the adhesive effectiveness at different application times.

Therefore, the aim of this study was to evaluate the effects of adhesive application time and dentine surface preparation on resin–dentine microtensile bond strength (μ TBS) of three universal adhesives. The null hypotheses tested were that (1) there is no effect of application time and, (2) there is no effect of surface preparation on the bond strength.

2. Materials and methods

2.1. Tooth selection and preparation

Seventy-two extracted non-carious human third molars were used in this study. They were stored in an aqueous solution of

0.5% chloramine-T at 4°C and used within 6 months after extraction. The teeth were collected under a protocol reviewed and approved by the university ethical committee (#2013-7). The teeth were abraded to expose mid-coronal dentine with a gypsum model trimmer under water coolant. A light microscope was used to confirm that no enamel remained on the dentine surface.

2.2. Adhesives and bonding procedures

The teeth were randomly assigned into 12 experimental conditions ($n = 5$ to μ TBS; $n = 1$ to interfacial structure observation) according to: dentine surface preparation (SiC-prepared dentine vs bur-cut dentine) and adhesive application time (manufacturer's instruction vs shortened). These variables were tested for three adhesive systems: G-Premio Bond [GP, GC Corp., Tokyo, Japan], Clearfil Universal Bond [CU, Kuraray Noritake Dental Inc., Okayama, Japan], and Scotchbond Universal Adhesive [SB, 3M ESPE, St. Paul, MN, USA]. Details of the variables and products can be found in Table 1.

Occlusal dentine surfaces were prepared by using either 600-grit SiC paper (Sankyo-Rikagaku Co., Saitama, Japan) or tapered regular grit diamond bur (diamond point FG, #103R, Shofu, Kyoto, Japan). For SiC paper preparation, the surfaces were manually polished for 60 s under running water using a 600-grit SiC paper. In case of diamond bur, dentine surfaces were ground with the bur in a high-speed handpiece with copious water spray for 5 light-pressure strokes per tooth in order to make a uniform surface. For

Table 2
Bond strength of adhesives according to surface preparation and application time. Values are MPa (SD).

Adhesive	SiC		bur	
	Shortened application time (S)	Manufacturer's instruction (MI)	Shortened application time (S)	Manufacturer's instruction (MI)
Clearfil Universal Bond	48.6(11.8) ^{b,c,d}	66.3(10.4) ^a	14.7(4.8) ^f	19.6(6.3) ^f
G-Premio Bond	61.6(7.9) ^{a,b}	63.3(12.1) ^a	28.7(6.7) ^e	46.4(7.9) ^c
Scotchbond Universal Adhesive	68.6(11.1) ^a	68.9(10.6) ^a	29.1(6.7) ^e	35.1(7.4) ^{d,e}

Different superscript letters indicate statistically significant differences ($p < 0.05$).

each surface preparation, half of the teeth received the adhesives applied according to manufacturer’s instruction, and the other half received the adhesives applied under the shortened time. Each adhesive was dropped directly from the bottle on dentine, air dried immediately and then light cured. Two 2mm-thick layers of resin composite (Clearfil AP-X, Kuraray Noritake Dental Inc., Tokyo, Japan) were built-up on the bonded surface. Each layer was light cured for 20 s operating using a light curing device (Optilux 401, Demetron/Kerr, Orange, CA, USA) at ≥ 550 mW/cm².

2.3. Microtensile bond strength (μ TBS) test

After storage in 37 °C water for 24 h, each bonded tooth was sectioned into beams (cross-sectional area approximately 1 mm²) using an Isomet diamond saw (Isomet 1000, Buehler, Lake Bluff, Illinois, USA). For each tooth (n=5), three beams from the central area were randomly selected for μ TBS, therefore resulting in a total of 15 beams to be tested. The remainder of the beams was stored for longer-term testing. The beams were fixed to a Ciucchi’s jig with cyanoacrylate glue (Model Repair 2 Blue, Dentsply-Sankin, Otahara, Japan) and subjected to a tensile force at a crosshead speed of 1 mm/min in a desktop testing apparatus (EZ test, Shimadzu, Kyoto, Japan). μ TBS was expressed in MPa, and data were analyzed by three-way ANOVA and Dunnett T3 tests ($\alpha = 0.05$).

2.4. Fracture mode analysis

The fractured specimens were mounted on an aluminum stub, then coated with Pt-Pd for 150 s. The fracture modes were determined using a scanning electron microscope (SEM, S-4000, Hitachi, Tokyo, Japan) at an accelerating voltage of 10 kV. Surfaces were examined at lower magnification to categorize the mode of fractured and specific features were further examined at 3000 \times and 10,000 \times . Fracture mode categories were classified into four groups [13]: A, adhesive failure; CD, cohesive failure within dentine; CC, cohesive failure within composite resin; or M, mixed failure.

2.5. Interfacial structure observation

One tooth per group was bonded in the same way as described for μ TBS test. The teeth were cut parallel to the long axis into slabs. Two slabs from central part were selected and prepared for SEM observation by following a protocol described by Ting et al. [14]. All slabs were serially polished with the series of SiC papers and diamond pastes. After that, treated with 5% HCl for 30s followed by NaOCl for 5 min. Then, the slabs were left to air dry for 24 h. Finally, they were sputter-coated with Pt-Pd for 150 s and then examined at 3000 \times magnification.

3. Results

3.1. μ TBS

There were no pre-test failures in this study. Our results indicated that there were significant effects between adhesive vs surface preparation ($F = 12.02$; $p < 0.000$), and adhesive vs application time ($F = 3.5$; $p = 0.032$). There was no direct effect of surface preparation vs application time ($F = 1.17$; $p = 0.280$). The interaction of factors was significant ($F = 10.006$; $p < 0.000$).

Bond strengths were always significantly higher when the adhesives were bonded to 600-grit SiC paper-prepared surfaces than when bonded to bur-cut dentine, regardless of the application time (Table 2). The influence of application time was only observed for CU and GP and was dependent on the surface preparation. CU presented significantly lower bond strengths when bonded using a shortened application time on SiC paper prepared dentine; and GP resulted in significantly lower bond strengths when used with the short application mode on the bur-cut dentine (Table 2).

3.2. Fracture modes

In general, the fracture modes were mainly categorized as mixed failure and adhesive failure. There was a clear tendency that




Fig. 1. Fracture modes of the three adhesives bonded to SiC prepared dentine and bur-cut dentine, with reduced application time and as manufacturers’ instruction.




Fig. 2. Representative SEM images of failure mode in bur-cut dentine group at high magnification (10,000 \times and 3000 \times (inserts)). Pores of a variety of sizes can be observed on the fractured surfaces. CU at shortened time (a) and CU at manufacturers' instruction time (b): submicron size voids (0.3–1 μm) were generally seen on the surface. GP at shortened time (c) and GP at manufacturers' instruction time (d): submicron size combined with bigger size pores (more than 1 μm) could be detected. SB at shortened time (e): very small pores (0.1–0.3 μm) could be detected. SB at manufacturers' instruction time (f): the fewest and smallest amounts of pores were observed for this group. (Additional images available online).

more cohesive failures occurred with SiC prepared dentine (Fig. 1). The SEM examination of the fracture modes revealed unusual features on the fractured surfaces. When adhesive failure areas were examined at higher magnifications (10,000 \times and 3000 \times (inserts)), a high concentration of porosity was observed for both CU and GP adhesives, and at a lower degree for SB adhesive. More porosity and bigger pores appeared to be associated with the groups that were bonded with shortened application time and on bur-cut dentine (Fig. 2, additional images of SiC prepared dentine are available online). The pores were predominantly round having a submicron sized diameter. Only those in GP were above 1–2 μm . They were uniformly distributed on the entire surface of the

adhesive failure beams with some areas presenting a concentration of larger pores.

3.3. Interfacial structure observation

The representative of SEM images are shown in Figs. 3–5. A general observation for all groups was the fact that the hybrid layer was not distinct from the SEM images (Fig. 3–5). Resin tags detected were short, sparsely distributed and only more distinct on surfaces prepared with SiC paper and preferably when the adhesive was applied according to the manufacturer's




Fig. 3. SEM images of the interfacial structure of CU ($\times 3000$) according to surface preparation and application time. (a) With shortened application time on SiC-ground dentine, no resin tags were observed. (b) Short resin tags (arrow) were observed when CU was applied according to manufacturers' instruction time on SiC-ground surface. (c, d) Few short resin tags (arrow) were formed in bur-cut dentine.

directions (Figs. 3–5b). Resin tags were either absent or appeared as very short projections and scarcely distributed along the observed area when the adhesives were bonded to bur-cut dentine, regardless of the application time (Fig. 3–5c,d). Round voids were sometimes encountered within the adhesive layer of GP applied to bur-cut dentine and under the shortened time (Fig. 4c). In some areas, GP adhesive layer appeared to have two distinct layers (visible by different contrast in the images) separated by a jagged line with some round shape features (Fig. 4a).

4. Discussion

According to the results, the type of surface preparation and the adhesive application time both had a significant effect on the bond strengths. Therefore, both of the anticipated null hypotheses were rejected. Many laboratory studies evaluate adhesive systems with bond strength testing. Most of them prepared dentine surface by using SiC paper to reproduce the smear layer in clinical situation [15–17]. However, it is expected that the characteristics of the smear layer will vary according to the preparation variables [9,10]. Moreover, it is expected that the resultant smear layer will have an impact on the performance of the adhesive system, particularly on the so-called mild self-etch

category [1,18]. It has been demonstrated that smear layers prepared with a diamond bur were more compact than those prepared by SiC paper when examined under SEM [9,10] and TEM [5]. Therefore, in the case of self-etch adhesives, it is possible that the denser smear layer might hinder the acidic monomer infiltration, hence compromising the bond strength. The results of present study also supported this hypothesis. Bonding to bur-cut dentine always resulted in significantly lower μ TBS, regardless of the adhesive or application time. According to the interfacial analysis, it appeared that resin tags were more evident and apparently better formed when the adhesives were bonded to surfaces prepared by SiC paper following the manufacturer's recommended application time (compare Fig. 3b vs a,c,d; Fig. 4b vs a,c,d; Fig. 5b vs a,c,d).

Without phosphoric acid etching, acidic monomers of self-etch adhesives do not remove the smear layer. Rather, the smear layer is partially demineralized and incorporated into the hybrid layer. Recently, Mine et al. [5] demonstrated that there are two zones of hybridized layers when ultra-mild one-step self-etch adhesives are used. The upper portion is called “resin smear complex”, which is the result of resin infiltration into the residual surface smear. The lower, thinner portion is the “true hybrid layer”. From their observation, the adhesive resin was able to penetrate the SiC ground smear layer more effectively than the bur-cut smear layer.




Fig. 4. SEM images of the interfacial structure of GP ($\times 3000$) according to surface preparation and application time. (a) With shortened application time on SiC-ground dentine, short resin tags were found (arrow). Note jagged line apparently separating the adhesive layer into two distinct zones (black arrowhead) (b) Longer resin tags (arrow) were observed in the group that was applied according to manufacturers' application time. (c, d) The resin tags were rarely seen in bur-cut group (arrow). Note the resin composite filling the round pore at the top of the adhesive layer (large arrow) (c).

When the acidic monomers from self-etch adhesives attempt to infiltrate across the smear layer, they are simultaneously buffered by the minerals present within the smear layer and, therefore, gradually lose their acidity and capacity to self-infiltrate. In thicker, more compact bur-cut smear layer, the acidic monomers of the adhesives might not have been able to penetrate uniformly across the smear layer to form the true hybrid layer with the underlying dentine. This possibility supports the lower bond strengths and the fracture modes that were mainly mixed and adhesive failure on bur-cut dentine. In our study, the type of smear layer had the most significant impact on the bond strength. Significant reductions in bond strengths were always observed for bur-cut dentine, regardless of the adhesive type used or mode of application. This finding has profound clinical implications since bur-cut dentine is usually the type of dentine clinicians encounter in daily practice. Therefore, significantly lower bond strengths should be expected when bonding clinically with the adhesives evaluated in this study.

In this study, multiple functional monomers containing adhesives were tested (4-MET, 10-MDP, and MDTP in GP; polyalkynoic acid copolymer and 10-MDP in SB). These multiple functional monomers might improve the bonding performance by interacting to the compact bur-cut smear layer. This could explain the higher μ TBS of GP and SB on bur-cut dentine.

Some studies have recommended a prolonged application time to increase the bond strengths of self-etch adhesives [11,12,19]. As the application time is extended, the increase in monomer infiltration might be expected [19,20]. However, prolonged application times might not be practical in clinics. On the contrary, clinicians in general would desire to reduce the application time. In this study, in order to understand the effect of the application time on the bond strength, the application time was experimentally minimized by blowing the adhesive immediately after directly dropping the adhesive from the bottle on the dentine surface. The overall results demonstrated that adhesive application according to manufacturer's instruction (longer) provided higher μ TBS. However, statistically significant differences were observed only in case of CU on SiC and GP on bur-cut dentine. For SB, reduction in application time has no influence on μ TBS regardless of prepared surface. However, pores on fractured surface were less pronounced when SB was applied according to manufacturers' instruction (Fig. 2f). Furthermore, resin tags were better formed compared to shortened application time (Fig. 5a–d). These might be caused by the longer application time (20 s) associated with rubbing motion according to the manufacturers' instruction (Table 1). This is also reported by Amsler et al. [21] that reduced application time had no effect on bonding performance of SB.




Fig. 5. SEM images of the interfacial structure of SB ($\times 3000$) according to surface preparation and application time. (a) Poorly formed resin tags were observed with shortened application time group on SiC. (b) Longer and more tags (arrow) were observed when SB was applied according to manufacturers' instruction. (c) Only short resin tags were found on bur-cut dentine at shortened time. (d) More resin tags were detected when SB was applied according to manufacturers' instruction.

As discussed above, the infiltration of the self-etch adhesive across the smear layer is a time dependent process, which is also hindered by the buffering action of the smear layer [4]. It is expected, therefore, that the shorter application time might have not been sufficient for the acidic monomer to infiltrate across the smear layer and form a strong bond with underlying dentine. Residual solvent and water entrapped within the adhesive layer may have also played a role on the results. With shortened application time, solvent evaporation might have not been sufficient. Therefore, the residual solvent could have compromised the adhesive polymerization [22,23] and, therefore, the resultant bond strength. Erhardt et al. [12] stated that the effect of prolonged application time was system dependent. Extended application time cannot improve solvent evaporation when water is added as a solvent into ethanol solvated monomer. Both water and ethanol can hydrogen bond to each other and also to monomers. Thus, their evaporation rate is reduced [24]. In current study, the examination of adhesive failures that occurred at the interface between the adhesive and the resin revealed a large concentration of submicron-size pores (Fig. 2). These features were highly evident in the groups that were applied with a shortened time (Fig. 2a,c,e). We believe these pores represent entrapped solvent and water that could not evaporate due to the limited amount time allowed. Similar features have been reported on interfaces examined by

TEM. The authors suggested that such round pores are a result of droplets caused by phase separation of the adhesive that rendered entrapped within the adhesive layer. Furthermore, they suggested that the shorter application time was not enough for droplet evaporation [25].

Although the presence of this large amount of voids at the interface between the resin and the adhesive has reduced the bonded surface area dramatically, it is surprising that the bond strengths did not fall significantly, except for 2 groups (Table 2). The presence of the voids, however, appears to have driven the failures to occur at that interface. While no remarkable compromising effect was observed because of the presence of the voids, however, a crucial effect on the long-term adhesion could be expected.

The results of this study have important clinical implications. To purposely reduce the application time of the adhesives used in this study is not a recommended practice. Quick application time increase the risk of entrapment of solvents within the adhesive that might have profound consequences for the degradation of the bonded assembly after water sorption. The risk of compromised bonding with reduced application time increases when dentine is prepared by bur, which is almost always the case in a clinical setting.

5. Conclusions

Within the limitation of this study, it may be concluded that

1. Dentine surface preparation had an influence on the μ TBS. Smear layer form bur-cut dentine had an undesirable effect on all the three universal adhesives used in this study.
2. Application time had an impact on the adhesive performance. The shortened application time resulted in insufficient solvent evaporation and bonding mechanism which leads to lower bond strength for two out of three adhesives tested, depending on the type of surface preparation.

Acknowledgements

All materials in this study were supported by Kuraray Noritake Dental Inc., GC Corp., and 3M ESPE

Appendix A. Supplementary data

Supplementary data associated with this article can be found, in the online version, at <http://dx.doi.org/10.1016/j.jdent.2016.02.001>.

References

- [1] B. Van Meerbeek, K. Yoshihara, Y. Yoshida, A. Mine, J. De Munck, K.L. Van Landuyt, State of the art of self-etch adhesives, *Dent. Mater.* 27 (2011) 17–28.
- [2] D.H. Pashley, F.R. Tay, Aggressiveness of contemporary self-etching adhesives. Part II: etching effects on unground enamel, *Dent. Mater.* 17 (2001) 430–444.
- [3] R. Yamada, T. Hayakawa, K. Kasai, Effect of using self-etching primer for bonding orthodontic brackets, *Angle Orthod.* 72 (2002) 558–564.
- [4] F.R. Tay, D.H. Pashley, Aggressiveness of contemporary self-etching systems. I: depth of penetration beyond dentin smear layers, *Dent. Mater.* 17 (2001) 296–308.
- [5] A. Mine, J. De Munck, M.V. Cardoso, K.L. Van Landuyt, A. Poitevin, A. Van Ende, et al., Dentin-smear remains at self-etch adhesive interface, *Dent. Mater.* 30 (2014) 1147–1153.
- [6] C. Chen, L.N. Niu, H. Xie, Z.Y. Zhang, L.Q. Zhou, K. Jiao, et al., Bonding of universal adhesives to dentine—old wine in new bottles? *J. Dent.* 43 (2015) 525–536.
- [7] G. Marchesi, A. Frassetto, A. Mazzoni, F. Apolonio, M. Diolosà, M. Cadenaro, et al., Adhesive performance of a multi-mode adhesive system: 1-year in vitro study, *J. Dent.* 42 (2014) 603–612.
- [8] A. Wagner, M. Wendler, A. Petschelt, R. Belli, U. Lohbauer, Bonding performance of universal adhesives in different etching modes, *J. Dent.* 42 (2014) 800–807.
- [9] S.S.A. Oliveira, M.K. Pugach, J.F. Hilton, L.G. Watanabe, S.J. Marshall, G.W. Marshall Jr., The influence of the dentin smear layer on adhesion: a self-etching primer vs. a total-etch system, *Dent. Mater.* 19 (2003) 758–767.
- [10] V. Sattabanasuk, V. Vachiramon, F. Qian, S.R. Armstrong, Resin–dentin bond strength as related to different surface preparation methods, *J. Dent.* 35 (2007) 467–475.
- [11] M. Toledano, J.P. Proença, M.C.G. Erhardt, E. Osorio, F.S. Aguilera, R. Osorio, et al., Increases in dentin-bond strength if doubling application time of an acetone-containing one-step adhesive, *Oper. Dent.* 32 (2007) 133–137.
- [12] M.C. Erhardt, R. Osorio, J. Pisani-Proença, F.S. Aguilera, E. Osorio, L. Breschi, et al., Effect of double layering and prolonged application time on MTBS of water/ethanol-based self-etch adhesives to dentin, *Oper. Dent.* 34 (2009) 571–577.
- [13] A. Cova, L. Breschi, F. Nato, A. Ruggeri, M. Carrilho, L. Tjäderhane, et al., Effect of UVA-activated riboflavin on dentin bonding, *J. Dent. Res.* 90 (2011) 1439–1445.
- [14] S. Ting, A.F.M.A. Chowdhury, F. Pan, J. Fu, J. Sun, S. Kakuda, et al., Effect of remaining dentin thickness on microtensile bond strength of current adhesive systems, *Dent. Mater. J.* 34 (2015) 181–188.
- [15] C. Tani, W.J. Finger, Effect of smear layer thickness on bond strength mediated by three all-in-one self-etching priming adhesives, *J. Adhes. Dent.* 4 (2002) 283–289.
- [16] A. Reis, V. Grandi, L. Carlotto, G. Bortoli, R. Patzlaff, L.Mde A. Rodrigues, et al., Effect of smear layer thickness and acidity of self-etching solutions on early and long-term bond strength to dentin, *J. Dent.* 33 (2005) 549–559.
- [17] S. Kenshima, A. Reis, N. Uceda-Gomez, Lde L. Tancredo, L.E. Filho, F.N. Nogueira, et al., Effect of smear layer thickness and pH of self-etching adhesive systems on the bond strength and gap formation to dentin, *J. Adhes. Dent.* 7 (2005) 117–126.
- [18] R.B. Ermis, J. De Munck, M.V. Cardoso, E. Coutinho, K.L. Van Landuyt, A. Poitevin, et al., Bond strength of self-etch adhesives to dentin prepared with three different diamond burs, *Dent. Mater.* 24 (2008) 978–985.
- [19] A.D. Cardoso PdC. Loguercio, L.C.C. Vieira, L.N. Baratieri, A. Reis, Effect of prolonged application times on resin-dentin bond strengths, *J. Adhes. Dent.* 7 (2005) 143–149.
- [20] N. Nakabayashi, Y. Saimi, Bonding to intact dentin, *J. Dent. Res.* 75 (1996) 1706–1715.
- [21] F. Amsler, A. Peutzfeldt, A. Lussi, S. Flury, Bond strength of resin composite to dentin with different adhesive systems: influence of relative humidity and application time, *J. Adhes. Dent.* 17 (2015) 249–256.
- [22] B.H. Cho, S.H. Dickens, Effects of the acetone content of single solution dentin bonding agents on the adhesive layer thickness and the microtensile bond strength, *Dent. Mater.* 20 (2004) 107–115.
- [23] M. Cadenaro, L. Breschi, F.A. Rueggeberg, M. Suchko, E. Grodin, K. Agee, et al., Effects of residual ethanol on the rate and degree of conversion of five experimental resins, *Dent. Mater.* 25 (2009) 621–628.
- [24] C.K.Y. Yiu, E.L. Pashley, N. Hiraishi, N.M. King, C. Goracci, M. Ferrari, et al., Solvent and water retention in dental adhesive blends after evaporation, *Biomaterials* 26 (2005) 6863–6872.
- [25] K.L. Van Landuyt, J. De Munck, J. Snauwaert, E. Coutinho, A. Poitevin, Y. Yoshida, et al., Monomer-solvent phase separation in one-step self-etch adhesives, *J. Dent. Res.* 84 (2005) 183–188.