

HOKKAIDO UNIVERSITY

Title	Evaluation of climate effect on resilient modulus of granular subgrade material
Author(s)	Lin, Tianshu; Ishikawa, Tatsuya; Yang, Jiaqiang; Tokoro, Tetsuya
Citation	Cold Regions Science and Technology, 194, 103452 https://doi.org/10.1016/j.coldregions.2021.103452
Issue Date	2022-02
Doc URL	http://hdl.handle.net/2115/90810
Rights	© <2021>. This manuscript version is made available under the CC-BY-NC-ND 4.0 license http://creativecommons.org/licenses/by-nc-nd/4.0/
Rights(URL)	http://creativecommons.org/licenses/by-nc-nd/4.0/
Туре	article (author version)
File Information	revised Manuscript ver2.pdf



Hokkaido University Collection of Scholarly and Academic Papers : HUSCAP

- 1 Evaluation of climate effect on resilient modulus of granular subgrade material
- 2

3 Tianshu Lin^a, Tatsuya Ishikawa^{b,*}, Jiaqiang Yang^a, Tetsuya Tokoro^c

⁴ ^a Graduate School of Engineering, Hokkaido University, Kita 13, Nishi 8, Kita-Ku, Sapporo 060-

5 8628, Japan

6 ^b Faculty of Engineering, Hokkaido University, Kita 13, Nishi 8, Kita-Ku, Sapporo 060-8628, Japan

7 [°] Faculty of Engineering, Hokkai-Gakuen University, 1-1, Minami 26 Nishi 11, Chuo-ku, Sapporo

8 064-0926, Japan

9 Keywords

10 Resilient modulus, Unsaturated soil, Freeze-thaw action, Subgrade material, Laboratory element test

11 Abstract

12 This study examines the effects of freeze-thaw actions and the concurrent seasonal fluctuations in water content, named as climate effect in this study, on the resilient modulus of subgrade materials to evaluate 13 14 their mechanical behavior in cold regions. A series of suction-controlled resilient modulus tests on sub-15 grade materials with variant freeze-thaw, wheel loads, and water contents conditions were conducted 16 using a newly developed test apparatus. Test results were used to construct a simple model to estimate 17 the climate effect on the resilient modulus by considering the synergistic effects between water content 18 and freeze-thaw. Besides, this study calculated the fatigue life of eight local flexible pavement projects 19 with variant subgrade layer moduli considering climate effect by combining the newly proposed model 20 and long-term in-situ measured data. Results proved that climate-related degradation of the subgrade 21 materials decreases the fatigue life of asphalt pavements in cold regions.

22 **1. Introduction**

^{*} Corresponding author. Email address: t-ishika@eng.hokudai.ac.jp

23 In snowy cold regions such as Hokkaido, a northern island in Japan, pavement structures suffer annually freeze-thaw cycles as the 0°C isotherm may penetrate deep into the pavement. Freeze-thaw action de-24 25 teriorates pavement structures in two ways as frost-heave and thaw-weakening. The swelling of soil 26 during freezing conditions caused by an increasing presence of ice lens finally leads to cracking in the 27 asphalt-mixture layer (hereafter referred to as the "As layer"). Thaw-weakening means a drop of base 28 and subgrade layer strength and stiffness caused by suddenly rising water content, which comes from 29 the inflow of snowmelt water or the thawing of ice lenses, and deteriorates uniformity of particle skel-30 eton structure after freeze-thaw action (Jong et al., 1998; Simonsen and Isacsson, 1999).

31 A detailed understanding of the mechanical behavior of the base/subgrade materials during freeze-thaw 32 is essential to develop a mathematical model of the mechanical response of the base/subgrade layer in 33 cold regions and incorporate it into the theoretical design method for pavement structures. To achieve 34 such understanding, it is necessary to quantitatively capture the deformation-strength characteristics of 35 unbound granular base course and subgrade materials subjected to cyclic freeze-thaw actions under 36 various compaction conditions and water contents through laboratory element tests with high-precision 37 under sufficiently controlled experimental conditions. As the result, a significant loss of stiffness from 38 frozen to thawed and an increase in the recovery period are observed in both in-situ bearing capacity 39 test for frozen and thawed pavement structure and laboratory element test for frozen, thawed, and re-40 covered base/subgrade material (Berg et al., 1996; Cole et al., 1981; Johnson et al., 1978; Simonsen et al., 2002; Simonsen and Isacsson, 2001). However, partly due to the apparatus limitation and different 41 42 research topics, the synergistic effects between water content and freeze-thaw on the resilient modulus 43 (M_r) , which is the key factor of base/subgrade layer as it associates with the elastic modulus (E) used in 44 the design calculation for pavement structures applying the multi-layer elastic theory or finite element 45 method, have not yet been quantitatively evaluated and modeled in these tests. In this study, the syner-46 gistic effects between freeze-thaw actions and concurrent seasonal fluctuations in water content, named 47 as climate effect, will be examined.

48 Ishikawa et al. (2019a) examine the climate effect on the resilient deformation characteristics of base 49 course materials through a series of resilient modulus tests on base course materials under various water 50 contents. As a complementary and further research, this study examines and evaluates the climate effect on M_r of subgrade material through a series of suction-controlled resilient modulus tests (hereafter referred to as the "MR test") with variant freeze-thaw, wheel loads, and water contents conditions. This study names the unsaturated condition and freeze-thaw action applied in the MR test as climate process. Besides, this study attempts to develop a simple mathematical model of the mechanical response of subgrade materials subjected to climate effect, in order to establish a method for evaluating the longterm performance of the granular subgrade layer at pavement structures in cold regions.

57 2. Conventional Models

58 2.1 Universal model and Ng model

Mechanistic-Empirical Pavement Design Guide (MEPDG) (AASHTO, 2008) proposed a universal
model to predict the resilient modulus with stress variables as shown in Eq. (1).

61
$$M_r = k_1 p_a \left(\frac{\theta}{p_a}\right)^{k_2} \left(\frac{\tau_{oct}}{p_a} + 1\right)^{k_3}$$
 (1)

62 where k_1, k_2, k_3 are regression constants; p_a is atmospheric pressure and set as 101 kPa in this study; θ is 63 bulk stress (kPa); τ_{oct} is octahedral stress (kPa).

However, this model cannot reflect the effect of moisture content. To overcome this shortcoming, several models (Cary and Zapata, 2011; Liang et al., 2008; Ng et al., 2013) are proposed based on the universal model. Within these models, the Ng model shown in Eq. (2) adds an independent stress state variable that incorporates matric suction effects. It shows good applicability on predicting resilient modulus of unsaturated unbound granular materials through the relatively higher coefficient of determination (\mathbb{R}^2) value than other models (Han and Vanapalli, 2016).

70
$$M_r = k_1 p_a \left(\frac{\theta}{p_a}\right)^{k_2} \left(\frac{\tau_{oct}}{p_a} + 1\right)^{k_3} \left(\frac{\psi}{\sigma_{net}} + 1\right)^{k_4}$$
 (2)

71 where k_1, k_2, k_3, k_4 are regression constants; p_a is atmospheric pressure; θ is bulk stress; τ_{oct} is octahedral 72 stress; σ_{net} is net mean stress (kPa), defined as $[\theta/3-u_a]$; ψ is matric suction (kPa).

73 2.2 Enhanced Integrated Climatic Model

74 MEPDG also suggests a model, named as EICM (Enhanced Integrated Climatic Model) (NCHRP,

75 2004), to capture the freeze-thaw effect on M_r as shown in Eq. (3). This model adds a new factor,

76 F_{env} , on the universal model (Eq. (1)) to represent the reduction of M_r due to freeze-thaw. F_{env} is a 77 reduction factor defined by the ratio of M_r for freeze-thawed soil divided by M_r for unfrozen soil.

78
$$M_r = F_{env} \cdot k_1 p_a \left(\frac{\theta}{p_a}\right)^{k_2} \left(\frac{\tau_{oct}}{p_a} + 1\right)^{k_3}$$
(3)

79 **3. Test Apparatus and Material**

80 *3.1 Freeze-thaw triaxial apparatus*

Fig. 1 illustrates the schematic diagram of the apparatus used in this study, which consists of a cyclic triaxial test apparatus that can apply cyclic axial loads, and three low-temperature baths which could circulate low-temperature fluids (antifreeze) in the cap, pedestal, and inner cell to control the temperature separately. The size of the specimen is 170 mm in height and 70 mm in diameter. The apparatus can apply the matric suction (ψ) by controlling pore-water pressure (u_w) from the pedestal end and poreair pressure (u_a) from the cap end (Fig. 1 (b) and (c)). Details about the test apparatus could be found in the previous study (Lin et al., 2019a).



Fig. 1. Freeze-thaw triaxial apparatus.

88

90 *3.2 Toyoura sand*

Toyoura sand is a type of Japanese standard sand, employed as the test material in this study and laboratory element tests by many other researchers. As a non-frost-susceptible material, it is classified as a poorly graded sand (SP) according to ASTM classification. Specimens were prepared by air pluviation method and the degree of compaction is 96% and dry density (ρ_d) is 1.58 g/cm³ to satisfy the pavement subgrade layer standard provided by Japanese Ministry of Land, Infrastructure, Transport and Tourism (Japan Road Association, 2006).

97 Fig. 2 shows the soil-water characteristic curve (SWCC) of Toyoura sand obtained from this apparatus 98 (Lin et al., 2019b). The SWCC of this soil is S-shaped with an inflection point where the matric suction 99 increased as the volumetric water content decreased, and the shape qualitatively matches the results of 100 previous studies (Ishikawa et al., 2014). Besides, the difference in SWCCs between a freeze-thawed 101 specimen and an unfrozen specimen can hardly be recognized. This phenomenon is originated in no 102 particle breakage due to freeze-thaw action, which led to little change in the water retentivity and per-103 meability before and after freeze-thawing (Ishikawa et al. (2016)). The fitting curve for unfrozen spec-104 imen through Fredlund and Xing model (1994) is also displayed in the figure.



105

Fig. 2. Soil-water characteristic curves of Toyoura sand (after Lin et al., 2019b).

106

107 **4. Laboratory Testing Program**

108 *4.1 MR test*

109 Resilient modulus is especially important in mechanistic pavement design procedure and considerable 110 researches had been conducted since Seed et al. (1955) proposed the concept of resilient modulus as the 111 ratio of the amplitude of cyclic deviator stress to the amplitude of the resultant recoverable axial strain. 112 In this study, MR test is performed according to AASHTO test standard T307-99 (AASHTO, 2003). 113 Due to the limitation of the apparatus, this study applied a loading pulse with a frequency of 0.2 Hz 114 (Fig.3 (a)), which is different from the AASHTO standard haversine-shaped loading pulse with a fre-115 quency of 10 Hz (Fig.3 (b)). According to the measured loading data, it is recognized that haversine-116 shaped load was almost reproduced though the frequency is much lower than the recommended value 117 in AASHTO standard. Examination of this limited loading frequency would be discussed in the latter 118 part.





Fig. 3. Loading wave in (a) this study, (b) AASHTO standard.

AASHTO standard has 11 loading steps from MR-0 to MR-10. According to the AASHTO standard, MR-0 aims to make sure the cap completely reaches the top end of the specimen. For this reason, this study prolonged the loading number from 1000 cycles to 2000 cycles to ensure a stable residual strain after MR-0. Besides, the vertical stress in stages MR-4, 5, 9, and 10 are significantly larger than the stress measured at the actual situation in Japan (Kishikawa et al., 2017). The overstress in MR-4, 5 increased the relative density, and the results of MR- 6, 7, 8 cannot be evaluated accurately (Aoki et al., 2018). To sustain the relative density, this study skipped MR-4, 5, 9, and 10 and inserted MR-1.5, 2.5, 128 6.5, and 7.5 to keep the total test step as 11. Table 1 lists details of applied stress, like confining pressure (σ_c) , maximum deviator stress (q_{max}) , constant deviator stress to keep positive contact between the cap and 129 the specimen (q_{cont}) , cyclic deviator stress (q_{cyclic}) , and the loading number (N_c) . Fig. 3 illustrates the 130 131 definitions of q_{max} , q_{cont} , and q_{cyclic} in one loading cycle. In the MR tests, water can freely drain in or out 132 during the loading process due to the test standard T307-99 (AASHTO, 2003). Within past studies, 133 some undrained resilient modulus tests were conducted under saturated conditions (Guo et al., 2013; 134 Lin et al., 2019). The buildup of pore-water pressure was overestimated as the in-situ base/subgrade 135 layer rarely to be saturated. Some other undrained resilient modulus tests for unsaturated specimens did 136 not use a suction-controlled method to prepare specimen (Chen et al., 2018; Fall et al., 1997; Khoury 137 and Zaman, 2004; Yang et al., 2005) and the precise suction value during the test could not be measured. 138 Based on the axis-translation technique, a suction-controlled undrained resilient modulus test method 139 is proposed for saturated and unsaturated specimen (Cary and Zapata, 2016; Yang et al., 2008). How-140 ever, an undrained condition is still not fully reproduced in these laboratory element tests as the water 141 path is closed during loading while the pore-air pressure path is open to control it as a constant to keep 142 a constant effective confining pressure, named as Constant Water content (CW) test (Fredlund and 143 Rahardjo, 1993). A Consolidated Undrained (CU) resilient modulus test for unsaturated specimens with 144 controlled suction still lacks investigation. Therefore, this study only focuses on the drained condition. 145 It is noted that the pore water in the subgrades shall be excited under traffic loading and it may take a long time to dissipate. Hence, subgrade layers under traffic loading are likely under undrained condi-146 147 tions. The buildup of pore-water pressure during cyclic loading in undrained conditions seriously dete-148 riorates the mechanical properties and engineering performance of subgrade material. A suction-con-149 trolled consolidated undrained MR test method is under investigation to improve the understanding of 150 how pore-water pressure develops under cyclic loading.

151 Table 1. Loading conditions of MR tests.

Name	σ_c (kPa)	q_{max} (kPa)	q_{cont} (kPa)	q _{cyclic} (kPa)	Nc
MR-0	41.4	27.6	2.76	24.84	2000
MR-1	41.4	13.8	1.38	12.42	100

MR-1.5	41.4	20.7	2.07	18.63	100
MR-2	41.4	27.6	2.76	24.84	100
MR-2.5	41.4	34.5	3.45	31.05	100
MR-3	41.4	41.4	4.14	37.26	100
MR-6	27.6	13.8	1.38	12.42	100
MR-6.5	27.6	20.7	2.07	18.63	100
MR-7	27.6	27.6	2.76	24.84	100
MR-7.5	27.6	34.5	3.45	31.05	100
MR-8	27.6	41.4	4.14	37.26	100

152 *4.2 Test sequence*

This study designed five types of MR test named as Unfrozen test (hereafter referred to as the "U test"), 153 154 Unfrozen-Wheel loads test (hereafter referred to as the "UW test"), Freeze-Thaw test (hereafter referred 155 to as the "FT test"), Freeze-Thaw-Wheel loads test (hereafter referred to as the "FTW test"), and Freeze-156 Wheel loads-Thaw test (hereafter referred to as the "FWT test"). Each test was conducted under satu-157 rated and unsaturated conditions. U tests measure M_r of subgrade material at unfrozen status which 158 simulates normal season. UW tests condition aims to simulate subgrade material suffered wheel loads 159 at the normal season. FT tests, by applying one-dimensional freeze-thaw action on specimen before MR 160 test, aim to detect the resilient modulus just after freeze-thaw action. FTW tests, by applying an addi-161 tional wheel loads process after freeze-thaw action, could simulate a subgrade material that suffered 162 wheel loads at thawing season. FWT tests, by applying additional wheel loads process between freeze-163 thaw action, could simulate a subgrade material suffered wheel loads at the freezing season. All tests 164 start with a fully saturated specimen, by confirming the pore pressure coefficient is 0.96 or more. In this 165 study, a fully saturated specimen for test under saturated condition is prepared as follows: (1) Supplying CO_2 to replace the air in the specimen. (2) Supplying de-aired water through the specimen. As this study 166 167 uses the filter method and axis translation technique to prepare an unsaturated specimen from a saturated 168 condition, CO_2 could not be supplied in the specimen. The saturation process for test under unsaturated 169 conditions is prepared as follows: (1) Supplying de-aired water through the specimen. (2) Applying back

pressure of 200 kPa step by step. The u_w , u_a , and σ_c are 200, 200, and 220 kPa at the end. Table 2 sum-170 171 marizes the sequence of each test. For example, the most complicated test, FWT test in unsaturated condition, is performed as follows: (1) Applying consolidation process. Within this process, 172 predetermined consolidation stress of 41.4 kPa, which is the same as the highest confining pressure in 173 174 the MR test (AASHTO, 2003), is applied to the specimen. The u_w , u_a , and σ_c are set as 200, 200, and 241.4 kPa according to the 200 kPa back pressure. (2) Applying suction process to obtain an unsaturated 175 176 specimen. This process is carried out by decreasing u_w while keeping u_a and σ_c constant. (3) Applying 177 freezing process by lowering specimen temperature. (4) Applying wheel loads process with predeter-178 mined cyclic deviator stress. (5) Applying thawing process by raising specimen temperature. (6) Per-179 forming MR test. More details like test technique for unsaturated specimen preparation, stress state 180 during wheel loads process, and temperature conditions applied during the freeze-thaw process are ex-181 plained in the next section. It is noted that suction process is applied prior to freezing process in FT, 182 FTW, and FWT tests under unsaturated conditions as shown in Table 2. This sequence means matric 183 suction is under control during the whole freeze-thaw action, which involves a high level of experi-184 mental skill. Another simpler test sequence applies freeze-thaw action on a saturated specimen and 185 controls matric suction after freeze-thaw action, which is far from the actual situation as the subgrade 186 layer hardly to be saturated in winter. Lin et al. (2019b) compared performance of specimens prepared 187 by these two test sequences and found that more water drains out and axial displacement is larger during 188 the freeze-thaw process when freeze-thaw action is applied on a saturated specimen. Consequently, this 189 study applied suction process prior to freezing process as it better reproduces the actual situation that 190 subgrade material meets during the freezing season.

191 Table 2. Test sequence for U, UW, FT, FTW, and FWT test.

Test		Test sequence												
name	Consolidation process			SuctionFreezingprocessprocess			I	Wheel load process	Thawing process		Wheel loads process		MR test	
U	\rightarrow	0	\rightarrow	⊖/×	\rightarrow	×	\rightarrow	×	\rightarrow	×	\rightarrow	×	\rightarrow	\bigcirc
UW	\rightarrow	\bigcirc	\rightarrow)/x	\rightarrow	×	\rightarrow	×	\rightarrow	×	\rightarrow	\bigcirc	\rightarrow	\bigcirc

FT	\rightarrow	\bigcirc	\rightarrow	⊖/×	\rightarrow	\bigcirc	\rightarrow	×	\rightarrow	\bigcirc	\rightarrow	×	\rightarrow	\bigcirc
FTW	\rightarrow	\bigcirc	\rightarrow	⊖/×	\rightarrow	\bigcirc	\rightarrow	×	\rightarrow	\bigcirc	\rightarrow	\bigcirc	\rightarrow	\bigcirc
FWT	\rightarrow	\bigcirc	\rightarrow)/×	\rightarrow	\bigcirc	\rightarrow	\bigcirc	\rightarrow	\bigcirc	\rightarrow	×	\rightarrow	\bigcirc

192

Note: Omeans Applied this progress; × means Skipped this progress.

193 *4.3 Climate and wheel loading conditions*

194 4.3.1 Suction process

195 As mentioned in the Introduction part, to examine and evaluate the climate effect on M_r of subgrade 196 material, a series of suction-controlled MR tests with two kinds of water content, saturated and unsatu-197 rated, under variant freeze-thaw history and wheel loads condition are performed. The unsaturated spec-198 imen used in this study has a 40% degree of saturation, equals to 16% volumetric water content, as the 199 long-term field measurement data (Ishikawa et al., 2012) of the volumetric water content of a subgrade 200 layer in Hokkaido is about 16%. According to SWCC of Toyoura sand (Fig. 2), the matric suction (ψ) 201 is set as 3.75 kPa by axis translation technique (Fredlund and Morgenstern, 1977) to obtain this unsatu-202 rated specimen. Suction process starts from the fully saturated and isotropic consolidated condition by 203 decreasing pore-water pressure in steps while keeping both confining pressure and pore-air pressure constant. A decrease of pore-water pressure means an increase of matric suction, which causes the 204 205 drainage of pore-water from the specimen. Upon attaining an equilibrium condition, the drainage is 206 stopped. The above-described procedure is then repeated for a higher value of matric suction, ψ , until 207 3.75 kPa to finally obtain an unsaturated specimen. It is noted that, stress condition in Table 1 is used in the saturated condition, based on a total stress approach in which the triaxial system measures the 208 209 mechanical response of the material subjected to different combinations of cyclic deviator stress (q_{cyclic}) 210 and confining pressures (σ_c). From the unsaturated soil mechanics perspective, the air phase becomes 211 important in the measurement and control of matric suction and the total stress is replaced by the net 212 normal stress (Cary and Zapata, 2011), which is the difference between the total stress and the pore-air 213 pressure (σ -u_a). By using the axis translation technique, the confining pressure becomes the net confin-214 ing pressure (σ_c - u_a) and the axial stress, σ_a , becomes the net axial stress (σ_a - u_a). This approach does not affect the way the deviator stress is defined since the air pressure will affect σ_a and σ_c in the same 215

- 216 proportion. Consequently, the stress value in Table 1 is the same for an unsaturated test when the con-
- 217 fining pressure becomes the net confining pressure.
- 218 4.3.2 Freezing and thawing process

219 Temperatures of cap and pedestal during freeze-thaw process are shown in Fig. 4. One-dimensional 220 freeze-thaw action is achieved in the following steps. The initial temperature of cap and pedestal were 221 set and kept to 0 °C and 16.8 °C respectively and a frost heave cell (see Fig. 1) is mounted to restrict the radial deformation during freeze-thaw process. The thermal shock is applied at the top end of the 222 specimen prior to freezing to avoid supercooling. Then, temperatures of cap and pedestal are lowered 223 to -18.9 °C and -2.1 °C respectively with a constant cooling rate of 1.67 °C/hr. Similar to the previous 224 225 research (Aoki et al., 2018), a constant cooling rate of 1.67 °C/hr is used in this study to avoid the 226 supercooled state, caused by too large rates, or excessive test time, caused by too small rates. Next, 227 temperatures of cap and pedestal are kept for 5 hours to ensure the uniformity of unfrozen water. The thawed status is achieved by raising temperatures of cap and pedestal to 5 °C and 16.8 °C with a heating 228 229 rate of 1.67 °C/hr. Open-system freeze-thaw process is used in this test by opening the pedestal water 230 plumbing path during the freeze-thaw process, which means the specimen could drain in or out water 231 freely. Referring to JGS 0172-2009 (Japanese Geotechnical Society, 2009), applied axial stress during 232 the freeze-thaw process is set as 10 kPa. More details of freeze-thaw action and specimen performance 233 like drainage volume and axial displacement could be found in previous research (Lin et al., 2019b).





235

Fig. 4. Temperature of cap and pedestal during freeze-thaw process.

4.3.3 Wheel loads process

237 The wheel loads in this study could be classified into three types: loads on the unfrozen specimen (UW test), loads on the frozen specimen (FWT test), and loads on the thawed specimen (FTW test). Loading 238 239 cycles of wheel loads in UW, FTW, and FWT tests are 1000 times. Loading frequency and pulse shape 240 are the same as those in MR test loading (Fig. 3 (a)). Constant deviator stress (q_{cont}) and cyclic deviator 241 stress (q_{cyclic}) during wheel loads process should be determined through an appropriate method to simu-242 late actual stress state of the subgrade layer during normal or freezing seasons. General Analysis of Multi-layered Elastic Systems (GAMES) (Maina and Matsui, 2004) is used to determine the qcont and 243 q_{cyclic} on the subgrade layer caused by a 49-kN wheel load on a typical pavement structure in the Japa-244 245 nese design guide. Fig. 5 illustrates the pavement structure and parameters like Young's modulus, E, 246 and Poisson's ratio, v, used in this study. These values come from the Japanese design guide recom-247 mended value (Japan Road Association, 2006). It is noted that these moduli are roughly estimated val-248 ues, which may have a large difference with in-situ measured data. Besides, the design guide sets moduli 249 of base, subbase, and subgrade layers as constant, which implies a necessity of modification. A modi-250 fication with variant E caused by climate effect will be realized and introduced in the latter part. Ac-251 cording to GAMES calculation results, the q_{cont} and q_{cyclic} of wheel loads process in UW and FTW,

which simulate wheel loads in normal and thawing season, are set as 9.6 and 26.2 kPa. The q_{cont} and q_{cyclic} of wheel loads process in FWT, which simulate wheel loads in freezing season, are set as 9.6 and 24.5 kPa. In FWT test, removing frost heave cell before applying wheel loads process is necessary as it restricts the specimen in a radial direction. Then, a copper pipe, which could circulate antifreeze, is installed around the specimen to keep the frozen status during the whole wheel loads process. When the wheel loads process is finished, the copper pipe is removed, and the thawing period is started.



Fig. 5. Pavement structure and E, v used in GAMES.

258 259

260 5. Test Results and Discussions

261 5.1 Effects of loading frequency

262 Examining the influence of loading frequency is necessary to check the reliability of test results, and 263 the usefulness and generality of the proposed testing method, as the loading frequency used in AASHTO 264 standard is 10 Hz. Toyoura sand specimens with three water content (40%, 70%, and 100% degree of 265 saturation, matric suction for such degree of saturation is 3.75kPa, 3 kPa, and 0 kPa respectively) are 266 prepared to perform MR test with two different apparatus, freeze-thaw triaxial apparatus and medium-267 size triaxial apparatus. Medium-size triaxial apparatus could apply loading frequencies of 10 Hz. Details 268 of medium-size triaxial apparatus could be checked in previous research (Ishikawa et al., 2014). Fig. 6 269 plots the average resilient modulus ratio between M_r of MR-1 to MR-8 with high frequency and low 270 frequency under different matric suction conditions. The fitting curve shown in Fig. 6 is obtained 271 through Eqs. (5) and (6) and will be explained later. First of all, all ratios are higher than 1, which means 272 that higher loading frequency always leads to a higher modulus regardless of the degree of saturation. 273 Fig. 6 also illustrates that matric suction influences the average resilient modulus ratio between different 274 loading frequencies. To be precise, the average resilient modulus ratio increases with ψ , which also 275 implies that the frequency effect is more significant for a specimen with higher matric suction.



276

Fig. 6. Average resilient modulus ratio under different matric suction conditions.

277

Eq. (4) was proposed to quantitively describe the frequency effect on the resilient modulus (Kim et al.,

280
$$\frac{E(f)}{E(0.5 Hz)} = 1 + F(\psi) * Log(f)$$
 (4)

where *f* is loading frequency; E(0.5 Hz) is resilient modulus obtained at *f*=0.5 Hz; E(f) is predicted resilient modulus at any frequency, *f*; $F(\psi)$ is referred as the frequency effect, which is affected by matric suction, ψ .

Based on Eq. (4), the average resilient modulus ratio between 10 Hz and 0.2 Hz could be expressed asfollows:

$$286 \qquad \frac{E(10 \ Hz)}{E(0.2 \ Hz)} = \frac{\frac{E(10 \ Hz)}{E(0.5 \ Hz)}}{\int_{-\infty}^{\infty} \frac{E(0.2 \ Hz)}{E(0.5 \ Hz)}} = \frac{1 + F(\psi) * Log(10)}{1 + F(\psi) * Log(0.2)} = \frac{1 + F(\psi)}{1 - 0.6989 F(\psi)} \tag{5}$$

Based on Eq. (5) and measured average resilient modulus ratio, the value of $F(\psi)$ under three matric suction values could be determined as shown in Fig. 7.





290

Fig. 7. Frequency effect under different matric suction conditions.

A nonlinear equation $(F(\psi)=a-b^*c^{\psi})$ is chosen as the fitting model because it would not meet such question that $F(\psi)$ increases to an unrealistic level when the ψ is extremely large. Besides, parameters in this nonlinear equation have a clearer physical meaning. When ψ goes to an infinite value or zero, $F(\psi)$ equals to *a* or *a-b*. As a result, *a* means upper limit of $F(\psi)$ and *a-b* means $F(\psi)$ when the specimen is fully saturated. Substituting fitted frequency effect, $F(\psi)$, into Eq. (5), predicted average resilient modulus ratio with high accuracy could be obtained (see the black line in Fig. 6).

297 Consequently, M_r obtained through freeze-thaw triaxial apparatus with limited loading frequency could 298 be converted to general AASHTO standard M_r through Eqs. (5) and (6). Since limited unsaturated con-299 dition and soil type are used to investigate the effect of loading frequency, this conversion should only 300 be used here to overcome frequency effect. Besides, different loading frequencies may lead to some 301 unclear changes in pore water pressure, pore air pressure, and so on. More study on the frequency effect 302 is necessary to improve understanding of resilient modulus.

303
$$F(\psi) = 0.06153 - 0.02043 * 0.68826^{\psi}$$
 (6)

304 *5.2 Effects of matric suction on resilient modulus*

305 Aiming to quantitively analyze the effect of stress state, freeze-thaw action, matric suction on the M_r , 306 this study performs regression analysis with Ng model to obtain the value of k_1 , k_2 , k_3 , k_4 from a series 307 of MR tests and investigate how freeze-thaw action and fluctuating water content affect these values. 308 Figs. 8 to 12 illustrate M_r of U, UW, FT, FTW, and FWT test respectively. The red dot is measured M_r 309 and the fitting surface is obtained through Ng model (Eq. (2)). It is noted that these results are converted 310 data through Eqs. (5) and (6) and seen as general AASHTO standard resilient modulus. Table 3 lists 311 regression analysis results through Ng model. Regression analysis here is performed regardless of the 312 degree of saturation. In other words, saturated and unsaturated U tests are treated as one group to per-313 form regression analysis. UW, FT, FTW, and FWT tests are regression analyzed in the same method. 314 High R² values validate the applicability of Ng model.

It is well known that M_r highly relates to stress variables. To be specific, M_r increases with lower deviator stress (q) or higher confining pressure (σ_c) and matric suction (ψ). This is because a higher σ_c leads to increasing of frictional force, which helps resist soil deformation. This trend could be found during all test results as shown in Fig. 6 to 10. As shown in Figs. 8 to 12, all unsaturated tests have a higher M_r than saturated tests regardless of freeze-thaw and wheel loads history. Additionally, M_r obtained from unsaturated specimen through all tests has a more slanting surface, in other words, q and σ_c have a more significant influence on the M_r when the specimen is unsaturated. Consequently, suddenly rising water 322 content, induced by the inflow of snowmelt water and the thawing of ice lenses at thawing season or



heavy rainfall at summertime, greatly degrades the subgrade layer stiffness.



Fig. 8. Resilient modulus of U test under saturated and unsaturated condition.





327

Fig. 9. Resilient modulus of UW test under saturated and unsaturated condition.





Fig. 10. Resilient modulus of FT test under saturated and unsaturated condition.





331

Fig. 11. Resilient modulus of FTW test under saturated and unsaturated condition.



332

333

Fig. 12. Resilient modulus of FWT test under saturated and unsaturated condition.

Test name	k_1	k_2	k_3	k_4	\mathbb{R}^2
U	2.103	1.065	-4.843	2.740	0.949
UW	1.750	1.088	-4.916	3.639	0.905
FT	1.873	0.844	-4.111	2.474	0.910
FTW	2.328	0.823	-4.967	0.845	0.803
FWT	2.011	0.538	-3.382	1.766	0.805

Table 3. Regression analysis results through Ng model.

335 5.3 Effects of freeze-thaw action

336 Freeze-thaw action decreases the M_r when other test conditions are the same as revealed by the com-

337 parison between U and FT tests or UW and FTW tests no matter under saturated or unsaturated

338 conditions. Another phenomenon worth to pointing out is all M_r surfaces in the freeze-thawed test are 339 lower and flatter compared with those surfaces in the unfrozen test. This observation through geometry view could be described as when the σ_c increases the same amount in both unfrozen tests (U or UW) 340 and freeze-thawed tests (FT or FTW), the M_r of the unfrozen specimen would increase more signifi-341 342 cantly. Besides, when q increases the same amount in both unfrozen tests (U or UW) and freeze-thawed 343 tests (FT or FTW), the M_r of the unfrozen specimen would decrease more significantly. In other words, 344 freeze-thaw also lowers the sensitivity of M_r to stress variables like q or σ_c . These findings indicate that 345 only attribute that weakening to suddenly rising water content is not sufficient for modeling the M_r . 346 Even without rising water content, freeze-thaw action could also degrade the stiffness of subgrade ma-347 terial. Thaw weakening is more like a synergistic effect between freeze-thaw and fluctuating water 348 content. Past research (Lin et al., 2019b) observed that specimen height would increase, and the water 349 would drain out of the specimen when water is transforming to ice in the freezing process due to the 9% 350 volumetric expansion. Accordingly, with the melting of ice in thawing process, specimen height would 351 decrease, and water would drain into the specimen. With the expansion and settled down of specimen, 352 the soil particle skeleton structure is rearranged. It is reasonable to assume that the freeze-thaw process 353 deteriorates the uniformity of particle skeleton structure and finally leads to worse mechanical proper-354 ties. In fact, changes in soil structure of clay due to freeze-thaw has been investigated by some researchers. By X-ray μ CT scanning, Starkloff et al. (2017) determined a reduction in macroporosity (>140 μ m 355 pore diameter), pore thickness, and their specific surface area for a silty clay loam and especially for a 356 loamy sand after several feeeze-thaw cycles. Wang et al. (2018) observed close correlations between 357 358 the physical property changes and the CTI, variation in CT image intensity, for clay before and after freeze-thaw cycles. Leuther and Schlüter (2021) found that frost action induced a consolidation of re-359 360 packed soil clods, resulting in a systematic reduction in pore sizes and macropore connectivity by X-361 ray μ CT. It is noted that a more detailed and explicit study on soil structure of sand before and after 362 freeze-thaw or track of water migration during freeze-thaw process is necessary to support this assump-363 tion.

365 For unfrozen specimen, the wheel loads reduce M_r , as indicated in Figs. 8 and 9 (U test and UW test), 366 partly due to the disturbance of soil particle skeleton structure uniformity caused by wheel loads. 367 Whereas, the wheel loads after the freeze-thaw process elevate M_r a little, as illustrated in Figs. 10 and 368 11 (FT test and FTW test). In this case, the role of wheel loads for freeze-thawed soil is some kind of 369 consolidation to help the specimen regain the uniformity of particle skeleton structure. On the other 370 hand, wheel loads applied on a frozen specimen do not affect M_r greatly, as shown through the compar-371 ison between results from FT test and FWT test (see Figs. 10 and 12). A reasonable explanation for this 372 phenomenon is that a frozen specimen has a much higher stiffness than a thawed specimen. Figs. 13 373 and 14 demonstrate the relationship between the loading number, N_c , and axial strain, ε_a , and Secant 374 Young's modulus, E_s, during wheel loads process in FWT test and FTW test separately. It is noted that the Secant Young's modulus (E_s) in this study is defined as the ratio of cyclic deviator stress to the 375 maximum axial strain, $(\varepsilon_a)_{max}$, during one loading cycle, which consists of recoverable axial strain, $(\varepsilon_a)_r$, 376 377 and permanent axial strain, $(\varepsilon_a)_p$. The smallest axial strain during one loading cycle is defined as $(\varepsilon_a)_p$. It is obvious that a frozen specimen has a larger modulus than an unfrozen specimen when the degree 378 379 of saturation is the same. To be specific, the stiffness of frozen saturated or unsaturated specimens is 6 or 3 times that of the thawed specimen. Within all frozen specimens, though saturated one has a much 380 381 larger stiffness than unsaturated one as more ice is formed in the saturated specimen, axial strains in 382 these two specimens are both at a very low level. Despite frost-susceptibility of the soil, freezing action 383 significantly amplifies the stiffness of the specimen since ice has a much larger stiffness as compared with soils. Consequently, the axial strain of frozen specimen, no matter maximum axial strain, $(\varepsilon_a)_{max}$, 384 or permanent axial strain, $(\varepsilon_a)_p$, will be a very small value compared with those of thawed specimen. An 385 extremely low ε_a for saturated frozen specimen causes the variation in measured stiffness as the axial 386 387 displacement transducer fluctuates when measuring such low value. Besides, by comparing Fig. 14 (a) 388 and (b), the unsaturated specimen shows a larger E_s and smaller ε_a than those of the saturated specimen, 389 which implies that matric suction strengthens the mechanical properties of a thawed specimen.





391

Fig. 13. Axial strain and Secant Young's modulus during wheel loads process in FWT test.



Fig. 14. Axial strain and Secant Young's modulus during wheel loads process in FTW test.

6. Proposal of a modified climate model

395 6.1 Applicability of EICM

396 As above mentioned, both freeze-thaw and rising water content have a negative influence on the resili-397 ent modulus. In general, these two factors both contribute to the thaw weakening illustrated by compar-398 ing M_r of unsaturated unfrozen (Fig. 8 (b)) and saturated freeze-thawed test (Fig. 10 (a)). This syner-399 gistic effects of water content and freeze-thaw on M_r has a more complicated mechanism. By comparing 400 Fig. 8 and 10, decreasing amount of M_r is more significant in a saturated condition, which implies that 401 a decrease in M_r caused by freeze-thaw is strongly related to the water content before freezing. More 402 water contents exist in a specimen when the freeze-thaw action is applied, the M_r decreases more sig-403 nificantly after a freeze-thaw action. It is reasonable to assume that the amount of ice formed during the

404 freezing period has a positive relationship with the change of particle skeleton structure and the de-405 creasing amount of M_r .

406 Ng model uses the regression constants k_2 , k_3 , and k_4 to reflect the influence of bulk stress, θ , octahe-407 dral shear stress, τ_{oct} , and matric suction, ψ , on M_r separately. Since M_r increases with larger θ and ψ , 408 k_2 and k_4 are positive values. Besides, as M_r decreases with larger τ_{oct} , k_3 is a negative value. As a 409 result, a larger absolute value of k_2 , k_3 , and k_4 means a higher effect of θ , τ_{oct} , and ψ on M_r . As shown 410 in Table 3, k_2 , k_3 , and k_4 of the FT test have smaller absolute values comparing with them in the U test, which is consistent with observations that freeze-thaw weakens the influence of θ , τ_{oct} , and ψ . 411 Regression analysis for FT and FTW tests through EICM is performed to check its applicability and 412 413 validity. To extend this model into unsaturated conditions, F_{env} in Eq. (3) is added on the Ng model 414 (Eq. (2)) in a similar way as shown in Eq. (7). As mentioned before, EICM estimates the reduction 415 of M_r caused by freeze-thaw action with an adjustment factor, F_{env} . To examine whether this param-416 eter could fully capture the climate effect, regression analysis is conducted with one variable, F_{env} , 417 and four fixed parameters, k_1 , k_2 , k_3 , and k_4 . k_1 to k_4 are determined by regression analysis results of 418 U and UW tests obtained by Ng model (Eq. (2)).

419
$$M_r = F_{env} \cdot k_1 p_a \left(\frac{\theta}{p_a}\right)^{k_2} \left(\frac{\tau_{oct}}{p_a} + 1\right)^{k_3} \left(\frac{\psi}{\sigma_{net}} + 1\right)^{k_4}$$
(7)

Table 4 lists the regression analysis results of FT and FTW tests through EICM model (Eq. (7)). A decreasing R^2 value compared with R^2 shown in Table 3 implies the conventional model cannot fully capture the climate effect. Structure in Eq. (7) indicates that k_2 , k_3 , and k_4 are not influenced by F_{env} , as EICM assumes the climate effect only raises or lowers the M_r surface but does not change the surface shape. However, as shown in Figs. 8 to 12, it is so obvious that this assumption is not consistent with test results in this study, that is climate effect not only raise or lower the M_r surface but also change the surface shape.

427 Table 4. Applicability of EICM and modified Ng models.

Test name k_1 k_2 k_3 k_4 F_{env} F_{clim} \mathbf{R}^2

U test	2.103	1.065	-4.843	2.740	—	_	0.949
FT test (EICM)	2.103	1.065	-4.843	2.740	0.897	_	0.872
FT test (Modified)	2.103	1.065	-4.843	2.740	—	0.885	0.901
UW test	1.750	1.088	-4.916	3.640	—	_	0.905
FTW test (EICM)	1.750	1.088	-4.916	3.640	0.680	—	0.506
FTW test (Modified)	1.750	1.088	-4.916	3.640	—	0.668	0.619

428 6.2 Modified Ng model

To overcome this drawback, this study assumes the climate effect could be expressed by an adjusting factor that decreases k_1 , k_2 , k_3 , and k_4 with the same ratio. This assumption is quite reasonable as k_1 , k_2 , k_3 , and k_4 all have a smaller absolute value by a similar degree when the specimen is subjected to freeze-thaw action, indicated by regression analysis results of U test and FT test in Table 3. Based on this assumption, Ng model (Eq. (2)) is modified by adding a new parameter, F_{clim} , into all regression parameters (k_1 , k_2 , k_3 , and k_4), as shown in Eq. (8). Same as before, it is noted that only F_{clim} is variable and k_1 to k_4 are fixed as the value obtained through regression analysis results of U or UW test.

436
$$M_r = F_{clim} \cdot k_1 p_a \left(\frac{\theta}{p_a}\right)^{F_{clim} \cdot k_2} \left(\frac{\tau_{oct}}{p_a} + 1\right)^{F_{clim} \cdot k_3} \left(\frac{\psi}{\sigma_{net}} + 1\right)^{F_{clim} \cdot k_4}$$
(8)

Regression analysis results of FT and FTW tests shown in Table 4 proved that modified Ng model 437 438 has a better performance and accuracy compared with EICM. Fig. 15 illustrates the fitting surface for 439 FT test results through EICM and modified Ng model. It is obvious that fitting surface through mod-440 ified Ng model better matches test results compared with fitting surface through EICM. Consequently, 441 the assumption is validated that freeze-thaw action lowers the influence of stress variables like bulk stress, octahedral shear stress, and matric suction and decreases k_1 , k_2 , k_3 , and k_4 with the same ratio. It 442 is noted that R² value of tests with wheel loads process, UW and FTW tests, are all lower than R² of 443 444 tests without wheel loads process, U and FT tests. As discussed before, wheel loads process presents a complicated effect on the mechanical properties of specimen when it is applied on a frozen, thawed, or 445 unfrozen specimen. Such a complicated effect decreases the accuracy of all models. A further and com-446 447 prehensive study on wheel loads, especially how does it affect pavement fatigue life, is necessary.

448 Furthermore, principal stress axis rotation induced by wheel loads also needs to be considered as it





451 Fig. 15. Fitting surfaces of FT test results through (a) EICM (b) modified Ng model.

452 7. Application to Japanese Pavement Design Guide

453 7.1 Fatigue life analysis of asphalt pavement

450

454 To evaluate the climate effect on the degradation of subgrade layer, this chapter discusses the fatigue 455 life of the asphalt pavement in cold regions. Japanese design guide provides fatigue failure criteria to 456 calculate allowable number of equivalent 49-kN wheel loads against rutting (N_{β}) and fatigue cracking 457 (N_{fa}) , which are calculated by a theoretical design method (Asphalt Institute, 1982) using a simplified three-layers model which consists of As layer, base layer, and subgrade layer as shown in Fig. 16. In 458 459 general, the Japanese pavement design guide assumes the elastic moduli of base layer (E_2) and subgrade 460 layers (E_3) are constant throughout a whole year. However, Ishikawa et al. (2019a) discussed the influ-461 ences of the seasonality in E_2 on the fatigue life of the asphalt pavement in cold regions by considering freeze-thaw action and seasonal fluctuation in water content through combining in-situ measured stiff-462 463 ness and laboratory tested stiffness data. In this study, to capture the seasonality of the E_3 and its effect 464 on pavement fatigue life, E_2 is kept as a constant and E_3 varies considering freeze-thaw action and the 465 associated seasonal fluctuation in water content. Moreover, since E_3 does not have a significant effect on the N_{fa} calculation model employed in the Japanese pavement design guide, only N_{fs} is calculated in 466 467 this study using Eq. (9) (Japan Road Association, 2006).

It is noted that the three-layers model shown in Fig. 16 is simplified from the five-layers model shown in Fig. 5 by combining asphalt and stabilization into As layer and base and subbase into base layer. Such simplification is recommended since this study focuses on the effect of the seasonality of the E_3 on pavement fatigue life, N_{fs} . Clear distinguishing between asphalt and stabilization or base and subbase does not greatly affect the calculated N_{fs} with changing E_3 . Besides, three-layers model helps achieve consistency when performing case study since only asphalt, base, and subgrade layer are essential in actual flexible pavement structure while stabilization and subbase layer are not always set (Fig. 17).

475
$$N_{fs} = \beta_{s1} \cdot \{ 1.365 \times 10^{-9} \cdot \varepsilon_a^{-4.477 \cdot \beta_{s2}} \}$$
 (9)

476 where $\beta_{s1}=2134$ and $\beta_{s2}=0.819$ are the compensation coefficients for Asphalt Institute model based on 477 the actual situation of Japanese pavement; ε_a is the compressive strain on the top surface of the subgrade 478 layer under a design wheel load of 49 kN, which is greatly affected by E_3 .



 M_p : Monthly mean temperature of As layer.

479

480

Fig. 16. Cross section used in GAMES.





Fig. 17. Pavement structure models.

This study performed fatigue-life analysis against eight test pavement structures located at Hokkaido, 483 484 Japan. Civil Engineering Research Institute for Cold Region (CERI) designed and constructed eight test pavements (Maruyama et al., 2006). Fig. 17 illustrates the structures and length of each test pavement. 485 486 All eight pavement structures consist of asphalt mixture, base layer, and subgrade layer with multiple 487 materials and thicknesses. Four types of asphalt mixtures are used in test pavement. Fine-graded asphalt mixture has a 0 - 13 mm gradation distribution. Middle-graded asphalt mixture has the same range of 488 489 gradation distribution but more coarse aggregate. Coarse-graded and stabilized asphalt mixture have a 490 0 - 20 mm and 0 - 30 mm gradation distribution separately. Two types of base layer material are used 491 as C-40, crusher-run with maximum 40 mm gradation distribution, and C-80, anti-frost crusher-run with 492 maximum 80 mm gradation distribution. The asphalt mixtures, crusher-run materials, and subgrade soil 493 in one section are simplified into the As layer, base layer, and subgrade layer separately in GAMES 494 analysis (Fig. 16). Consequently, all eight sections could be simplified into three layers models with 495 different layer thicknesses to estimate ε_a through GAMES analysis. Then, monthly fatigue life against 496 rutting, $N_{fs,i}$, is calculated with monthly representative layer moduli. The total fatigue life against rutting, 497 $N_{fs.d}$, is calculated through Eq. (10).

498
$$N_{fs,d} = \frac{12}{\sum_{i=1}^{12} \frac{1}{N_{fs,i}}}$$
 (10)

499 Stiffness of asphalt mixture (E_1) is determined through the following equations (Japan Road Association, 500 2006; Maruyama et al., 2008).

$$501 E_1 = -278.4M_p + 10930 (11)$$

502
$$M_p = M_a \left[1 + \frac{2.54}{h+10.16} \right] - \frac{25.4}{9(h+10.16)} + \frac{10}{3}$$
 (12)

where M_p is the monthly mean temperature of asphalt mixture at depth of h (°C); M_a is monthly mean air temperature (°C); h is the depth equals to one-third of the height of asphalt mixture (cm).

505 Constant stiffness of base layer (E_2) through the year is set as 265MPa referring to previous research 506 (Maruyama et al., 2008).

507 When considering the climate effect, freeze-thaw action and seasonal fluctuation in water content, on the stiffness of subgrade layer, the monthly representative elastic moduli were divided into three types 508 509 of seasonal E_3 values (E_3 for freezing season, thawing season, and regular season except for freezing 510 and thawing seasons) for the simplicity of the fatigue life analysis. The E_3 value for freezing season is 511 set as 200 MPa, according to the back analysis of FWD test results (Ishikawa et al., 2019a). Though 512 Young's modulus of freezing unsaturated specimen is detected around 600 MPa as shown in Fig. 11, 513 this test result was obtained under fully frozen status, which may be different from the in-situ condition 514 that only top of subgrade layer is frozen during winter season. Consequently, a 200 MPa modulus from 515 in-situ FWD test is treated as a more suitable value for the E_3 to represent whole subgrade layer during 516 freezing season. In addition, this study assumes that when the average frost-penetration depth for the 517 month gets into the subgrade layer regardless of deep or shallow, the E_3 increases due to freezing. Here, 518 the average frost-penetration depth (z) was calculated by substituting the freezing index calculated from 519 the daily mean air temperatures measured by AMeDAS (Automated Meteorological Data Acquisition 520 System) into the modified Berggren formula (Aldrich Jr, 1956) shown below:

521
$$z = \alpha \sqrt{\frac{172800F}{(L/\lambda)_{eff}}}$$
(12)

522 where α is a correction coefficient; *F* is a freezing index which is the average air temperature during 523 freezing season multiplied by its duration in days; $(L/\lambda)_{eff}$ is an effective ratio of *L* to λ ; *L* is the latent 524 heat of soil; λ is a thermal conductivity of the soil.

The E_3 value for the regular season is estimated by substituting the value of k_1 , k_2 , k_3 , and k_4 into Ng model as shown in Eq. (13). The principal stress ratio is equal to 4 under 5 kPa confining pressure to determine bulk stress and octahedral shear stress. It is noted that this stress condition was selected so that M_r at normal season matches layer stiffness determined in previous research (Maruyama et al., 2008).

530
$$M_r = 2.103 \cdot p_a \left(\frac{\theta}{p_a}\right)^{1.065} \left(\frac{\tau_{oct}}{p_a} + 1\right)^{-4.843} \left(\frac{\psi}{\sigma_{net}} + 1\right)^{2.74}$$
(13)

531 The matric suction in subgrade layer is also necessary to estimate E_3 . Ishikawa et al. (2012) performed 532 long-term field measurements of frost-penetration depth, daily precipitation, and degree of saturation 533 in each layer of the pavement. Fig. 18 illustrates the long-term field measured degree of saturation, S_r , of subgrade layer through a year. The subgrade material is a sandy soil, named Tomakomai soil, com-534 535 posed of 8% clay, 13% silt, 51% sand, 28% gravel. This study uses Toyoura sand to represent the subgrade layer since the mechanical and hydraulic properties of Tomakomai soil are under investigation. 536 It is assumed that effective degree of saturation, S_e , would be same in Toyoura sand subgrade and 537 538 Tomakomai soil subgrade under same climate condition. S_e of subgrade layer illustrated in Fig. 18 was 539 calculated by using a residual degree of saturation (S_{rr}) of 25.67%, which was determined through the 540 SWCC estimated with grain-size distribution of Tomakomai soil (Fredlund et al., 2002). Consequently, 541 monthly average S_e is selected to determine matric suction of subgrade layer in each month through 542 SWCC of Toyoura sand (Fig. 2), and monthly representative M_r is calculated by Eq. (13).





544

Fig. 18. Long-term field measured S_r of subgrade layer.

The E_3 value for thawing season is estimated by modified Ng model with considering climate effect, F_{clim} . By substituting F_{clim} and the value of k_1 , k_2 , k_3 , and k_4 into Eq. (8), the M_r of the thawed season could be estimated as shown in Eq. (14) and (15). It is noted that matric suction used here corresponds to the highest water content during thawing season. In other words, E_3 value for thawing season stands for the worst situation, and the recovering period from thawing season to regular season is not considered in this paper. A furthermore comprehensive model is under developing to capture the recovering period.

552
$$M_r = F_{clim} \cdot 2.103 \cdot p_a \left(\frac{\theta}{p_a}\right)^{F_{clim} \cdot 1.065} \left(\frac{\tau_{oct}}{p_a} + 1\right)^{F_{clim} \cdot -4.843} \left(\frac{\psi}{\sigma_{net}} + 1\right)^{F_{clim} \cdot 2.74}$$
(14)

553
$$F_{clim} = 0.885$$

Table 5. Monthly representative elastic moduli of subgrade layer, E_3 .

		Jan	Feb	Mar	Apr	May	Jun	Jul	Aug	Sep	Oct	Nov	Dec
Original design guide		76	76	76	76	76	76	76	76	76	76	76	76
Water content	10 Hz	77	75	61	76	76	71	69	76	76	76	76	75
fluctuation	0.2 Hz	71	69	55	70	70	65	63	70	70	70	70	69
Climate effect	10 Hz	77	200	50	76	76	71	69	76	76	76	76	75

(15)

0.2 Hz	71	200	45	70	70	65	63	70	70	70	70	69
--------	----	-----	----	----	----	----	----	----	----	----	----	----

Consequently, Table 5 lists the estimated monthly representative E_3 through a year with consideration 555 556 of climate effect under different loading frequencies. E_3 (f=0.2 Hz) are estimated with original MR test 557 data, while E_3 (f=10 Hz) are estimated with converted MR test data through Eqs. (5) and (6). As the climate effect is a synergistic effect between water content fluctuation and freeze-thaw action, it is 558 559 essential to check climate effect step by step. For this reason, monthly representative E_3 only consider-560 ing water content fluctuation under different loading frequencies are also calculated through Eq. (13) 561 and shown in Table 5. Besides, referring to previous research (Maruyama et al., 2008), a constant E_3 562 through the year is set as 76MPa and applied in the original design guide condition. Poisson's ratio of 563 As layer, base layer, and subgrade layer are set as 0.35, 0.35, and 0.4 separately, which come from the design guide recommend value. 564

From Table 5, it is recognized that compared with the original design guide condition, E_3 drops at early spring (Mar) and summertime (Jun and Jul) when the water content fluctuation is considered since snowmelt water and the thawing of ice lenses at thawing season and heavy rainfall at summertime increases the water content in subgrade layer and finally decreases the stiffness. When freeze-thaw action is also considered, E_3 drops furthermore at Mar due to the thaw weakening and increases to 200 MPa at Feb due to the freezing action. Besides, moduli decrease with loading frequency.

571 7.2 Loading frequency effect on fatigue life of the pavement

To discuss the influence of loading frequency on fatigue life against rutting, E_3 (f=0.2 Hz) and E_3 (f=10 572 573 Hz) listed in Table 5 are used to calculate N_{fs} in all eight test pavement structures. Fig. 19 displays the N_{fs} with variant E_3 considering water content fluctuation (named as " N_{fs} -Water content fluctuation") 574 575 and climate effect (named as " N_{ls} -Climate effect") under different loading frequencies. It is obvious that 576 N_{fs} (f=10Hz) are always larger than N_{fs} (f=0.2Hz) no matter only consider water content fluctuation or 577 synergistic climate effect on E_3 . To clearly discuss the loading frequency effect on the fatigue life, the ratio of $N_{fs}(R_{Nf})$ for different pavement structures are also plotted in Fig. 18. The R_{Nf} considering loading 578 frequency with water content fluctuation or climate effect is determined through dividing the N_{fs} 579 580 (f=0.2Hz) by the N_{fs} (f=10Hz) when considering water content fluctuation or synergistic climate effect 581 on E_3 . R_{Nf} in all pavement structures are around 0.861, which implies that fatigue life decreases about 582 13.9% when loading frequency lowers from 10Hz to 0.2Hz. Conclusively, converting E_3 (*f*=0.2Hz) to 583 E_3 (*f*=10Hz) is necessary as loading frequency effect could not be ignored.



584

585

Fig. 19. Loading frequency effect on fatigue life against rutting.

586 7.3 Climate effect on fatigue life of the pavement

To discuss the climate effect, Fig. 20 displays the N_{fs} -Water content fluctuation and N_{fs} -Climate effect 587 under 10Hz loading frequency. N_{fs} with constant E₃ of 76 MPa (named as "N_{fs}-Original") is also shown 588 589 here. It is obvious that N_{fs} -Water content fluctuation is smaller than N_{fs} -Original but larger than N_{fs} -590 Climate effect, implies that reduced E_3 caused by sudden increasing water content decreases N_{fs} and 591 freeze-thaw action decreases N_{fs} further as the reduced E_3 during thawing season has a stronger influ-592 ence on the N_{fs} than the increasing E_3 during the freezing season. To clearly discuss the influence of 593 water content fluctuation, freeze-thaw action, and climate effect on the fatigue life, R_{Nf} for different 594 structures are also plotted in Fig. 20. The R_{Nf} considering water content fluctuation or climate effect are 595 determined through dividing the N_{fs} -Water content fluctuation or N_{fs} -Climate effect by the N_{fs} -Original,

while the R_{Nf} considering freeze-thaw action is determined through dividing the N_{fs} -Climate effect by the N_{fs} -Water content fluctuation. All ratios are lower than 1, indicates that influence of water content fluctuation, freeze-thaw action, and climate effect on E_3 all decrease the fatigue life. R_{Nf} caused by water content, freeze-thaw action, and climate effect are around 0.938, 0.965, and 0.905 separately. In other words, the N_{fs} decreases 6.2% when changing E_3 caused by water content fluctuation is considered and it would further decrease 3.5% when effect of freeze-thaw action on E_3 is also considered. A synergistic climate effect on E_3 decreases N_{fs} about 9.5%.

These results suggest that for improving the applicability and validity of the current Japanese design standard, the introduction of the theoretical design method for pavement structures, which can take account of the effects of the freeze-thaw actions and the concurrent seasonal fluctuation in water content on the subgrade layer stiffness, is effective in the asphalt pavements for cold regions.



607

608

Fig. 20. Climate effect on fatigue life against rutting.

609 8. Conclusions

610 The following findings can be mainly obtained:

• Through performing a series of suction-controlled resilient modulus tests for a subgrade material with variant freeze-thaw, wheel loads, and water contents conditions, the effects of freezethaw actions and the concurrent seasonal fluctuations in water content (named as climate effect in this study) are examined and evaluated. As a consequence, climate effect degrades the resilient deformation characteristics of subgrade materials.

616 Climate effect not only reduces the resilient modulus, but also weakens the influences of stress • 617 variables like bulk stress, octahedral shear stress, and matric suction on resilient modulus. Besides, the decreasing amount of resilient modulus caused by climate effect is more significant 618 619 in a saturated condition, which implies that a synergistic effect of water content and freeze-620 thaw on the resilient modulus. The degradation in resilient modulus caused by freeze-thaw relates to the water content before the specimen is frozen. It is reasonable to assume that the 621 amount of ice formed during the frozen period has a positive relationship with the change of 622 623 particle skeleton structure uniformity and degradation of the mechanical properties of subgrade 624 materials.

• A new parameter representing the climate effect, F_{clim} , is added into Ng model to quantitatively evaluate resilient modulus for the subgrade material under complex freeze-thaw, fluctuating water content, and variant stress states. Better performance compared with EICM proved the applicability and reliability of newly proposed modified Ng model.

To modify current Japanese design guide by replacing constant subgrade layer moduli with a 629 630 variant relating to water content fluctuation and freeze-thaw history, newly proposed modified 631 Ng model, long-term measured in-situ subgrade layer water content, and laboratory obtained 632 SWCC are used. Calculated fatigue life against rutting proves that both water content fluctua-633 tion and freeze-thaw action degrade stiffness of subgrade layer and finally decrease the fatigue 634 life of asphalt pavements in cold regions. Accordingly, when developing a design method with high prediction accuracy for the asphalt pavements in cold regions, it is important to consider 635 the change in the stiffness of subgrade layer caused by the climate conditions. 636

These findings indicate that a detailed understanding of the mechanical behavior of the subgrade during freeze-thaw is essential to develop a mathematical model for the mechanical response of the subgrade layer in cold regions and incorporate it into the theoretical design method for pavement structures. Further and more comprehensive studies including more unbound granular materials with various water contents are recommended to examine the validity, limitation of application, and so forth as these findings are obtained through limited experimental conditions.

643 Acknowledgements

This research was supported in part by Grant-in-Aid for Scientific Research (B) (20360206), (C) (15K06214), and (A) (16H02360) from Japan Society for the Promotion of Science (JSPS) KA-KENHI. The authors gratefully acknowledge research supports and invaluable comments come from Dr. Kimio Maruyama and the Civil Engineering Research Institute for Cold Region. The authors would also acknowledge the effort of Mr Ryosuke Aoki, former master student of Hokkaido University, who helped performed part of laboratory element tests. Support from China Scholarship Council is also highly acknowledged.

651 References

- AASHTO, 2008. Mechanistic-empirical pavement design guide: a manual of practice, 2nd ed. Ameri-
- 653 can Association of State Highway and Transportation Officials (AASHTO), Washington DC.
- AASHTO, 2003. Standard method of test for determining the resilient modulus of soils and aggregate
- materials: AASHTO designation T 307-99. American Association of State Highway and Trans portation Officials, Washington D.C.
- Aldrich Jr, H.P., 1956. Frost penetration below highway and airfield pavements. Highw. Res. Board
 Bull. 135, 124-149.
- Aoki, R., Ishikawa, T., Tokoro, T., Lin, T., 2018. Evaluation method for resilient modulus of sub-
- 660 grade materials in cold regions. 58th Technical Report of the Annual Meeting of the JGS Hok-

661 kaido Branch, Sapporo; p. 23–30. [in Japanese]

662 Asphalt Institute, 1982. Research and Development of Asphalt Institute's Thickness Design Manual,

- 663 9th ed. Asphalt Institute, College Park Md.
- Berg, R.L., Bigl, S.R., Stark, J.A., Durell, G.D., 1996. Resilient modulus testing of materials from
 Mn/Road: phase 1. https://doi.org/10.21949/1404573
- 666 Cary, C.E., Zapata, C.E., 2011. Resilient modulus for unsaturated unbound materials. Road Mater.
- 667 Pavement Des. 12 (3), 615–638. https://doi.org/10.1080/14680629.2011.9695263
- 668 Cary, C.E., Zapata, C.E., 2016. Pore water pressure response of soil subjected to dynamic loading un-
- der saturated and unsaturated conditions. Int. J. Geomech. 16.
- 670 https://doi.org/10.1061/(ASCE)GM.1943-5622.0000642
- 671 Chen, C., Zhou, Z., Kong, L., Zhang, X., Yin, S., 2018. Undrained dynamic behaviour of peaty or-
- 672 ganic soil under long-term cyclic loading, Part I: Experimental investigation. Soil Dyn. Earthq.
- 673 Eng. 107, 279–291. https://doi.org/10.1016/j.soildyn.2018.01.012
- 674 Cole, D.M., Irwin, L.H., Johnson, T.C., 1981. Effect of Freezing and Thawing on Resilient Modulus
- of a Granular Soil Exhibiting Nonlinear Behavior. Transp. Res. Rec. J. Transp. Res. Board 809,
 19–26.
- 677 Fall, M., Tisot, J.P., Cisse, I.K., 1997. Undrained behaviour of compacted gravel lateritic soils from
- 678 western Senegal under monotonic and cyclic triaxial loading. Eng. Geol. 47, 71–87.
- 679 https://doi.org/10.1016/s0013-7952(96)00124-x
- Fredlund, D.G., Morgenstern, N.R., 1977. Stress State Variables for Unsaturated Soils. J Geotech. Geonviron. 103 (5), 447–466.
- 682 Fredlund, D.G., Rahardjo, H., 1993. Soil Mechanics for Unsaturated Soils, Soil Mechanics for Un-

683 saturated Soils. John Wiley & Sons, Inc., Hoboken, NJ, USA.

- 684 https://doi.org/10.1002/9780470172759
- Fredlund, D.G., Xing, A., 1994. Equations for the soil-water characteristic curve. Can. Geotech. J. 31
- 686 (4), 521–532. https://doi.org/10.1139/t94-061
- 687 Fredlund, M.D., Wilson, G.W., Fredlund, D.G., 2002. Use of the grain-size distribution for estimation
- of the soil-water characteristic curve. Can. Geotech. J. 39 (5), 1103–1117.
- 689 https://doi.org/10.1139/t02-049
- 690 Guo, L., Wang, J., Cai, Y., Liu, H., Gao, Y., Sun, H., 2013. Undrained deformation behavior of

- 691 saturated soft clay under long-term cyclic loading. Soil Dyn. Earthq. Eng. 50, 28–37.
- 692 https://doi.org/10.1016/j.soildyn.2013.01.029
- Han, Z., Vanapalli, S.K., 2016. State-of-the-art: Prediction of resilient modulus of unsaturated sub-
- 694 grade soils. Int. J. Geomech. 16 (4), 04015104. https://doi.org/10.1061/(ASCE)GM.1943-
- 695
 5622.0000631
- 696 Ishikawa, T., Lin, T., Kawabata, S., Kameyama, S., Tokoro, T., 2019a. Effect evaluation of freeze-
- thaw on resilient modulus of unsaturated granular base course material in pavement. Transp. Geotech. 21, 100284. https://doi.org/10.1016/j.trgeo.2019.100284
- Ishikawa, T., Lin, T., Yang, J., Tokoro, T., Tutumluer, E., 2019b. Application of the UIUC model for
- 700 predicting ballast settlement to unsaturated ballasts under moving wheel loads. Transp. Geotech.
- 701 18, 149-162. https://doi.org/10.1016/j.trgeo.2018.12.003
- Ishikawa, T., Tokoro, T., Miura, S., 2016. Influence of freeze–thaw action on hydraulic behavior of
 unsaturated volcanic coarse-grained soils. Soils Found. 56 (5), 790–804.
- 704 https://doi.org/10.1016/j.sandf.2016.08.005
- Ishikawa, T., Zhang, Y., Tokoro, T., Miura, S., 2014. Medium-size triaxial apparatus for unsaturated
- 706 granular subbase course materials. Soils Found. 54 (1), 67–80.
- 707 https://doi.org/10.1016/j.sandf.2013.12.007
- Ishikawa, T., Kawabata, S., Kameyama, S., Abe, R., Ono, T., 2012. Effects of freeze-thawing on me-
- chanical behavior of granular base in cold regions. 10-12 September 2012. In: I Miura, H Yo-
- 510 shida, Abe, editors. Advances in transportation geotechnics II, Proc intern conf, Sapporo; p.
- 711 118–124.
- Japan Road Association, 2006. Pavement design manual, Japan Road Association, Tokyo. [in Japa nese]
- Japanese Geotechnical Society, 2009. Test Method for frost susceptibility of soils (JGS 0172-2003),
- Standards of Japanese Geotechnical Society for Laboratory Soil Testing Methods; 2009. p. 45–
 50. [in Japanese]
- Johnson, T.C., Cole, D.M., Chamberlain, E.J., 1978. Influence of freezing and thawing on the resilient
- 718 properties of a silt soil beneath an asphalt concrete pavement. U.S. Cold Regions Research and

- 719 Engineering Laboratory, CRREL Report 78–23. http://hdl.handle.net/11681/9380
- Jong, D.T., Bosscher, P.J., Benson, C.H., 1998. Field Assessment of Changes in Pavement Moduli
- Caused by Freezing and Thawing. Transp. Res. Rec. J. Transp. Res. Board 1615 (1), 41–48.
 https://doi.org/10.3141/1615-06
- 723 Kim, D.S., Kweon, G.-C., Lee, K.-H., 1997. Alternative Method of Determining Resilient Modulus of
- 724 Compacted Subgrade Soils Using Free-Free Resonant Column Test. Transp. Res. Rec. J. Transp.
- 725 Res. Board 1577 (1), 62–69. https://doi.org/10.3141/1577-08
- 726 Kishikawa, T., Otgonjargal, D., Kawaguchi, T., Nakamura, D., Yamashita, S., 2017. Influence of
- freeze-thaw on stress propagation in the ground. Proc., 57th Technical Report of the Annual
- 728 Meeting of the JGS Hokkaido Branch, Kitami; p. 27–34. [in Japanese]
- 729 Khoury, N.N., Zaman, M.M., 2004. Correlation Between Resilient Modulus, Moisture Variation, and
- 730 Soil Suction for Subgrade Soils. Transp. Res. Rec. J. Transp. Res. Board 1874, 99–107.
- 731 https://doi.org/10.3141/1874-11
- Leuther, F., Schlüter, S., 2021. Impact of freeze-thaw cycles on soil structure and soil hydraulic properties. Soil 7, 179-191. https://doi.org/10.5194/soil-7-179-2021
- Liang, R.Y., Rabab'ah, S., Khasawneh, M., 2008. Predicting Moisture-Dependent Resilient Modulus
- of Cohesive Soils Using Soil Suction Concept. J. Transp. Eng. 134 (1), 34–40.
- 736 https://doi.org/10.1061/(ASCE)0733-947X(2008)134:1(34)
- 737 Lin, B., Zhang, F., Feng, D., 2019. Long-term resilient behaviour of thawed saturated silty clay under
- repeated cyclic loading: experimental evidence and evolution model. Road Mater. Pavement

739 Des. 20, 608–622. https://doi.org/10.1080/14680629.2017.1407819

- Lin, T., Ishikawa, T., Aoki, R., 2019a. Resilient properties of unbound granular materials subjected to
- 741 freeze-thaw and wheel loads. Proc of 16th Asian Regional Conference on Soil Mechanics and
- 742 Geotechnical Engineering, Taipei.
- Lin, T., Ishikawa, T., Tokoro, T., 2019b. Testing method for resilient properties of unsaturated un-
- bound granular materials subjected to freeze-thaw action. Japanese Geotech. Soc. Spec. Publ. 7
- 745 (2), 576–581. https://doi.org/10.3208/jgssp.v07.089
- Lin, T., Ishikawa, T., Luo, B., 2019c. Applicability of Modified University of Illinois at Urbana-

747 Champaign Model for Unbound Aggregate Material with Different Water Content, Transp. Res.

```
748 Rec. 2673 (3), 439-449. https://doi.org/10.1177/0361198119827530
```

- 749 Maina, J.W., Matsui, K., 2004. Developing Software for Elastic Analysis of Pavement Structure Re-
- 750 sponses to Vertical and Horizontal Surface Loadings. Transp. Res. Rec. J. Transp. Res. Board

751 1896 (1), 107–118. https://doi.org/10.3141/1896-11

- 752 Maruyama, K., Tako, J., Kasahara, A., 2008. Fatigue failure life prediction method of asphalt pave-
- 753 ment. J. JSCE. E 64 (3), 416–426. [in Japanese] https://doi.org/10.2208/jsceje.64.416
- 754 Maruyama, K., Tako, J., Kasahara, A., 2006. Long-term performance of asphalt pavements at bibi
- 755 new test road. J. JSCE. E 62 (3), 519–530. [in Japanese] https://doi.org/10.2208/jsceje.62.519
- NCHRP, 2004. Guide for mechanistic-empirical design of new and rehabilitated pavement structures.
- 757 National Cooperative Highway Research Program 1-37 A.
- Ng, C.W.W., Zhou, C., Yuan, Q., Xu, J., 2013. Resilient modulus of unsaturated subgrade soil: exper-
- imental and theoretical investigations. Can. Geotech. J. 50 (2), 223–232.
- 760 https://doi.org/10.1139/cgj-2012-0052
- 761 Seed, H.B., CHAN, C.K., Monismith, C.L., 1955. Effects of repeated loading on the strength and de-

formation of compacted clay. Highw. Res. Board Proc. 34, 541-558.

- 763 Simonsen, E., Isacsson, U., 2001. Soil behavior during freezing and thawing using variable and con-
- stant confining pressure triaxial tests. Can. Geotech. J. 38 (4), 863–875.
- 765 https://doi.org/10.1139/t01-007
- Simonsen, E., Isacsson, U., 1999. Thaw weakening of pavement structures in cold regions. Cold Reg.
 Sci. Technol. 29 (2), 135–151. https://doi.org/10.1016/S0165-232X(99)00020-8
- 768 Simonsen, E., Janoo, V.C., Isacsson, U., 2002. Resilient Properties of Unbound Road Materials dur-
- 769 ing Seasonal Frost Conditions. J. Cold Reg. Eng. 16 (1), 28–50.
- 770 <u>https://doi.org/10.1061/(ASCE)0887-381X(2002)16:1(28)</u>
- 771 Starkloff, T., Larsbo, M., Stolte, J., Hessel, R., and Ritsema, C., 2017. Quantifying the impact of a
- succession of freezing-thawing cycles on the pore network of a silty clay loam and a loamy sand
- topsoil using X-ray tomography. Catena, 156, 365–374. <u>https://doi.org/10.1016/j.ca-</u>
- 774 tena.2017.04.026

- Wang, S., Yang, P., Yang, Z., 2018. Characterization of freeze-thaw effects within clay by 3D X-ray
 Computed Tomography. Cold Reg. Sci. Technol. 148, 13-21. https://doi.org/10.1016/j.coldregions.2018.01.001
- 778 Yang, S.-R., Huang, W.-H., Tai, Y.-T., 2005. Variation of Resilient Modulus with Soil Suction for
- 779 Compacted Subgrade Soils. Transp. Res. Rec. J. Transp. Res. Board 1913, 99–106.
- 780 https://doi.org/10.1177/0361198105191300110