



Title	An effective medium of H <sub>2</sub> O and low-pressure CO <sub>2</sub> for the selective hydrogenation of aromatic nitro compounds to anilines
Author(s)	Meng, Xiangchun; Cheng, Haiyang; Fujita, Shin-ichiro et al.
Citation	Green Chemistry, 13(3), 570-572 <a href="https://doi.org/10.1039/c0gc00246a">https://doi.org/10.1039/c0gc00246a</a>
Issue Date	2011-03
Doc URL	<a href="https://hdl.handle.net/2115/47798">https://hdl.handle.net/2115/47798</a>
Rights	Green Chem., 2011, 13, 570-572 - Reproduced by permission of The Royal Society of Chemistry (RSC)
Type	journal article
File Information	GC13-3_570-572.pdf



# An Effective Medium of H<sub>2</sub>O and Low-pressure CO<sub>2</sub> for the Selective Hydrogenation of Aromatic Nitro Compounds to Anilines

Xiangchun Meng,<sup>a</sup> Haiyang Cheng,<sup>b</sup> Shin-ichiro Fujita,<sup>a</sup> Yancun Yu,<sup>b</sup> Fengyu Zhao<sup>\*b</sup> and Masahiko Arai<sup>\*a</sup>


Received (in XXX, XXX) Xth XXXXXXXXXX 200X, Accepted Xth XXXXXXXXXX 200X

First published on the web Xth XXXXXXXXXX 200X

DOI: 10.1039/b000000x

**Chemoselective hydrogenation of water-insoluble aromatic nitro compounds can be achieved over Ni catalysts in a H<sub>2</sub>O-compressed CO<sub>2</sub> system at 35–50°C without using any environmentally harmful solvent. The effective CO<sub>2</sub> pressure is much lower than the critical pressure of CO<sub>2</sub>. The hydrogenation of nitro group should be the rate-determining step.**

The selective hydrogenation of aromatic nitro compounds to the corresponding anilines is an industrially important reaction.<sup>1</sup> The proposed reaction pathways (Scheme 1) include direct (I–II–III and IV–III) and indirect (VI–VII–VIII–IX) routes.<sup>2</sup> The reduction of PHA to AN is the common rate-determining step in the direct route.<sup>2</sup> The authors studied the hydrogenation of nitrobenzene (NB) and chloronitrobenzene (CNB) over supported Ni catalysts in compressed CO<sub>2</sub>.<sup>3</sup> The use of compressed CO<sub>2</sub> and supported Ni catalysts is effective for producing the aniline compounds with almost 100% selectivity in the whole range of conversion. The rate of hydrogenation depends on CO<sub>2</sub> pressure and is maximized at high pressures of ca. 9–12 MPa.<sup>3</sup> Here, we report that the combination of H<sub>2</sub>O and CO<sub>2</sub> is more beneficial for these selective hydrogenation reactions and the effectiveness of CO<sub>2</sub> pressurization can appear at a lower pressure of 0.8 MPa. The rate-determining step is the transformation of NB in the present reaction instead of the hydrogenation of PHA.




**Scheme 1** Possible reaction pathways for the reduction of nitrobenzene.

NB: nitrobenzene, NSB: nitrosobenzene, PHA: *N*-phenylhydroxylamine, AN: aniline, AOB: azoxybenzene, AB: azobenzene, HAB: hydrazobenzene.

Fig. 1 gives the results of NB hydrogenation in different reaction media using a 41 wt-% Ni/Al<sub>2</sub>O<sub>3</sub> catalyst (the details of catalyst preparation and hydrogenation run are given in ESI). The influence of CO<sub>2</sub> pressure on the conversion of NB depends on the medium used (Fig. 1a). In the absence of CO<sub>2</sub>, the conversion was larger in ethanol and *n*-hexane (66% and

29%) than that in H<sub>2</sub>O and solvent-less NB (6% and 3%). However, the conversion was significantly enhanced when the H<sub>2</sub>O–NB mixture was compressed by CO<sub>2</sub> at a low pressure such as 0.8 MPa; the conversion was comparable to that obtained in the supercritical 12 MPa CO<sub>2</sub>–NB mixture. For the H<sub>2</sub>O–NB, the conversion gradually increased with CO<sub>2</sub> pressure up to 17 MPa. The pressurization with CO<sub>2</sub> had a drastically negative impact and a slightly positive effect on the conversion of NB in ethanol and *n*-hexane, respectively. Note that the selectivity to AN was almost 100% in the whole range of conversion for the reactions in scCO<sub>2</sub>, CO<sub>2</sub>–*n*-hexane, and CO<sub>2</sub>–H<sub>2</sub>O systems. In ethanol and *n*-hexane, undesired PHA and AOB were formed in large quantities, resulting in small yields of the desired product of AN (Fig. 1b and Fig. S1 in ESI). Hence, the combination of H<sub>2</sub>O–CO<sub>2</sub> medium and Ni catalyst is a better reaction system for the selective hydrogenation of NB to AN under mild conditions (low temperature and CO<sub>2</sub> pressure) without any organic solvent.



**Fig. 1** (a) Influence of CO<sub>2</sub> pressure on the conversion of NB after 30 min reaction and (b) the yield of AN against the conversion of NB in different reaction systems. (Ni/Al<sub>2</sub>O<sub>3</sub> 0.1 g, NB 19.5 mmol, H<sub>2</sub> 6 MPa, 50°C)


To examine the features of our H<sub>2</sub>O–CO<sub>2</sub> reaction media, hydrogenation runs were conducted with NB, NSB, and PHA in H<sub>2</sub>O and H<sub>2</sub>O–CO<sub>2</sub> systems (Table 1). In both systems, the rate of hydrogenation followed the order PHA > NB > NSB. For NB hydrogenation in pure H<sub>2</sub>O, the selectivity to AN was ca. 62% and NSB and AOB were the main byproducts (entry 1). In the H<sub>2</sub>O–CO<sub>2</sub> system, however, the selectivity to AN was 95%; NSB and AOB were little formed in the hydrogenation of NB (entry 4) although the conversion of NSB was very slow (entry 5). It is likely, therefore, that in this H<sub>2</sub>O–CO<sub>2</sub> system the NB transforms directly to PHA and this step is the rate-determining one. The coupling of NSB and PHA should be suppressed due to their low concentrations. In pure H<sub>2</sub>O, in contrast, the NB should also change to PHA via NSB in addition to the direct transformation to PHA. The coupling reaction between NSB and PHA is also possible to occur.

**Table 1** Hydrogenation of NB, NSB, and PHA<sup>a</sup>

Entry	Medium	Substrate	Conv. (%)	Selectivity (%) <sup>b</sup>		
				AN	NSB	PHA
1	H <sub>2</sub> O	NB	21	61.9	9.0	1.9
2		NSB <sup>c</sup>	8	20.4		- <sup>d</sup>
3		PHA	100 <sup>‡</sup>	94.6	- <sup>d</sup>	
4	H <sub>2</sub> O–CO <sub>2</sub> (3 MPa)	NB	55	95.1	2.4	2.4
5		NSB	13	36.9		- <sup>d</sup>
6		PHA	100 <sup>‡</sup>	95.3	- <sup>d</sup>	

<sup>a</sup> Conditions: H<sub>2</sub>O 10 cm<sup>3</sup>, Ni/Al<sub>2</sub>O<sub>3</sub> 0.1 g, substrate 9.75 mmol, H<sub>2</sub> 6 MPa, 50°C, 10 min. <sup>b</sup> The other byproduct was AOB. <sup>c</sup> 30 min. <sup>d</sup> Not detected.

The molecular interactions of H<sub>2</sub>O with a hydrophilic intermediate of PHA were examined by FTIR (experimental details are in ESI). Fig. 2 shows a slight red-shift of ν(NO) in the H<sub>2</sub>O compared to that in the gas phase. The N–O bond of PHA is weakened through interactions with H<sub>2</sub>O, possibly via OH...O and OH...N bonding.<sup>4</sup> Several authors reported the promotion effects of H<sub>2</sub>O on the hydrogenation of aromatic nitro compounds in organic solvents, but the reasons are still unclear.<sup>5</sup> Now, the results of Table 1 and Figure 2 allow us to propose that H<sub>2</sub>O can promote the reaction step III accepted as the rate-determining step in organic solvents, enhancing the reaction rate and the selectivity to aniline.



**Fig. 2** FTIR spectra of PHA in the ν(NO) region.

To further inspect the features of the present H<sub>2</sub>O–CO<sub>2</sub>


system, NB was hydrogenated in a H<sub>2</sub>O–compressed N<sub>2</sub> (7 MPa) medium, but no positive effects on the conversion and the selectivity to AN were observed. It is known that CO may be formed via the reverse water gas shift reaction during hydrogenation reactions in the presence of H<sub>2</sub> and CO<sub>2</sub>.<sup>6</sup> Although no CO was detected for the gas phase by GC analysis in our reaction, an attempt was made to add 0.2 MPa 9.9% CO/He into the reaction mixture of NB–H<sub>2</sub>O–CO<sub>2</sub> (3 MPa). This was found to cause a significant decrease in the conversion from 62% to 15%. Thus, in the present hydrogenation reactions, the formation of CO was unlikely.

The enhancement of NB conversion in NB–H<sub>2</sub>O–CO<sub>2</sub> system can be explained by a few different factors. CO<sub>2</sub> is soluble in H<sub>2</sub>O, its mole fraction being 0.25% and 2.0% at 0.8 and 9.4 MPa, respectively, at 50°C.<sup>7</sup> The dissolution of CO<sub>2</sub> enhances the solubility of a gaseous reactant H<sub>2</sub> in the H<sub>2</sub>O and NB phases. The H<sub>2</sub>O phase of H<sub>2</sub>O–CO<sub>2</sub> mixture was acidic (ca. pH 3<sup>8</sup>). A reaction run was also conducted in a 0.8 mol dm<sup>-3</sup> NaHCO<sub>3</sub> buffered H<sub>2</sub>O solution at 3 MPa CO<sub>2</sub> (pH > 6<sup>8b</sup>); the conversion (48%) was slightly lower than that in the unbuffered system (62%), while the high selectivity to AN did not change. NaHCO<sub>3</sub> can also be hydrogenated to NaHCO<sub>2</sub> with Ru complex or supported Pd catalyst;<sup>9</sup> but supported Ni catalysts do not give significant NaHCO<sub>2</sub> concentrations.<sup>9a</sup> When the concentration of NaHCO<sub>3</sub> was changed from 0.8 to 0.2 mol dm<sup>-3</sup>, the hydrogenation of NB gave the same conversion, indicating that the influence of NaHCO<sub>3</sub> hydrogenation on the reaction of NB is marginal in our systems. Thus, the acidic nature of the H<sub>2</sub>O phase might be one of positive factors, but its effect is small. Our previous *in situ* FTIR show that compressed CO<sub>2</sub> interacts with the reacting species, NB, NSB, and PHA, decreasing the reactivity of NB but increasing the reactivity of NSB and PHA.<sup>3</sup> These molecular interactions should also be important in the H<sub>2</sub>O–CO<sub>2</sub>–NB reaction system. In addition, the solid catalyst granules were well dispersed in the H<sub>2</sub>O phase but not in the NB phase, due to hydrophilic nature of the oxide support materials (Fig. S2 in ESI). NB is sparingly soluble (ca. 17 mmol dm<sup>-3</sup> at 25°C) and PHA is soluble in H<sub>2</sub>O (ca. 82 mmol dm<sup>-3</sup> in saturated salt solution at 0°C<sup>10</sup>). Therefore, the hydrogenation of NB and PHA is likely to occur at the NB–H<sub>2</sub>O interfacial layer and in the H<sub>2</sub>O phase. In the H<sub>2</sub>O–CO<sub>2</sub> system, the rate of AN formation is controlled by the conversion of NB into PHA. Interfacial H<sub>2</sub>O and NB molecules form hydrogen bonding, OH...ONO,<sup>11</sup> which may weaken the N–O bond of NB. Previously, a striking rate increase was observed in some reactions on water and this was ascribed to the H bonds between interfacial water molecules and reactants or transition state.<sup>12</sup> In addition, da Rocha et al. studied the molecular structure of the H<sub>2</sub>O–compressed CO<sub>2</sub> interface and observed excess accumulation of the fluids on both sides of the interface.<sup>13</sup> The local density enhancements can have a large impact on the chemical reactions.<sup>14</sup>

After the reaction, the H<sub>2</sub>O phase was easily separated from the organic product phase. This H<sub>2</sub>O phase containing 0.35 mol dm<sup>-3</sup> AN was further used for the second reaction, giving the same results as that using pure H<sub>2</sub>O. Hence, the H<sub>2</sub>O phase can be recyclable without any post-purification, which is of

practical significance.

Furthermore, the potential of the H<sub>2</sub>O–CO<sub>2</sub> medium was examined for the hydrogenation of chloronitrobenzene (CNB) at 35°C, which is less soluble in H<sub>2</sub>O than NB. A 9 wt-% or 16 wt-% Ni/TiO<sub>2</sub> catalyst was used since the selectivity to chloroaniline (CAN) was slightly better than that obtained with the Ni/Al<sub>2</sub>O<sub>3</sub> (Table S1 in ESI). Fig. 3a shows the conversion of *o*-CNB over 9 wt-% Ni/TiO<sub>2</sub> as a function of CO<sub>2</sub> pressure for the reaction mixtures in the presence and absence of H<sub>2</sub>O. One can see again that the H<sub>2</sub>O significantly promoted the hydrogenation of *o*-CNB similar to NB but the conversion increased with CO<sub>2</sub> pressure through to 13 MPa. The positive effect of H<sub>2</sub>O was also observed in the hydrogenation of *m*- and *p*-CNB over 16 wt-% Ni/TiO<sub>2</sub>. In Fig. 3b the yield of CAN is plotted against the total conversion of *o*-, *m*-, and *p*-CNB substrates (the change of conversion and selectivity with reaction time is shown in ESI Fig. S3). For all the isomers, no dehalogenation and coupling occurred and so the selectivity to CAN was almost 100% at any conversion, confirming the effectiveness of the present reaction system including H<sub>2</sub>O and low-pressure CO<sub>2</sub> for the selective hydrogenation of aromatic nitro compounds to anilines.



**Fig. 3** (a) Influence of CO<sub>2</sub> pressure on the conversion of *o*-CNB over 9 wt-% Ni/TiO<sub>2</sub> after 50 min of hydrogenation in the systems of H<sub>2</sub>O–CO<sub>2</sub> and compressed CO<sub>2</sub> alone; (b) CAN yield against CNB conversion during the hydrogenation of CNB isomers in the H<sub>2</sub>O–CO<sub>2</sub> (6 MPa) system. (CNB 9.52 mmol, Ni/TiO<sub>2</sub> 0.15 g, H<sub>2</sub> 4 MPa, 35°C)

In conclusion, the interactions of CO<sub>2</sub> and H<sub>2</sub>O with the reacting species, the *in situ* formed acidity, and the better dispersion of Ni catalyst in the H<sub>2</sub>O phase are responsible for the fast and selective hydrogenation of NB in the H<sub>2</sub>O–CO<sub>2</sub> system, in which the conversion of NB into PHA may be the rate-determining step.

## Acknowledgments

We thank the financial support from the One Hundred Talent Program of CAS, NSFC 20873139, KJCX2, YW.H16, Japan Society for the Promotion of Science with Grant-in-Aid for Scientific Research (B) 18360378, and the CAS-JSPS international joint project GJHZ05.

## Notes and references

<sup>a</sup> Division of Chemical Process Engineering, Faculty of Engineering, Hokkaido University, Sapporo 060-8628, Japan. Fax: +81 11 706 6594; Tel: +81 11 706 6594; E-mail: marai@eng.hokudai.ac.jp  
<sup>b</sup> State Key Laboratory of Electroanalytical Chemistry, Changchun Institute of Applied Chemistry, Chinese Academy of Sciences, Changchun 130022, China. Fax: +86 431 8526 2410; Tel: +86 431 8526 2410; E-mail: zhaofy@ciac.jl.cn  
X. Meng is currently with School of Chemical Engineering, Changchun University of Technology, Changchun 130012, China.  
† Electronic Supplementary Information (ESI) available: Experimental procedures, phase behavior observations, and hydrogenation data. See DOI: 10.1039/b000000x/  
‡ PHA decomposed partly into NSB, AN, and AOB during GC analysis (Fig. S4 in ESI). Both PHA and NSB were not detected during GC analysis of the product, indicating PHA is consumed completely after 10 min of reaction. The total pressure in the reactor dropped to a constant value in 6–8 min, further confirming the complete conversion of PHA.

- 1 A. S. Travis, in *The Chemistry of Anilines*, ed. Z. Rappoport, John Wiley & Sons, Ltd, Chichester, England, 2007, pp. 715–782.
- 2 (a) F. Haber, *Z. Elektrochem.*, 1898, **22**, 506; (b) H. U. Blaser, *Science*, 2006, **313**, 312–313; (c) A. Corma, P. Concepcion and P. Serna, *Angew. Chem., Int. Ed.*, 2007, **46**, 7266–7269.
- 3 (a) X. Meng, H. Cheng, Y. Akiyama, Y. Hao, W. Qiao, Y. Yu, F. Zhao, S. Fujita and M. Arai, *J. Catal.*, 2009, **264**, 1–10; (b) X. Meng, H. Cheng, S. Fujita, Y. Hao, Y. Shang, Y. Yu, S. Cai, F. Zhao and M. Arai, *J. Catal.*, 2010, **269**, 131–139.
- 4 (a) G. A. Yeo and T. A. Ford, *J. Mol. Struct.: Theochem*, 1991, **235**, 123–136; (b) P. Politzer, J. S. Murray and M. C. Concha, *J. Phys. Org. Chem.*, 2008, **21**, 155–162.
- 5 (a) S. Nishimura, *Handbook of Heterogeneous Catalytic Hydrogenation for Organic Synthesis*, John Wiley & Sons, New York, 2001, pp. 334, 336; (b) J. Ning, J. Xu, J. Liu, H. Miao, H. Ma, C. Chen, X. Li, L. Zhou and W. Yu, *Catal. Commun.*, 2007, **8**, 1763–1766; (c) P. Maity, S. Basu, S. Bhaduri and G. K. Lahiri, *Adv. Synth. Catal.*, 2007, **349**, 1955–1962.
- 6 M. Burgener, D. Ferri, J.-D. Grunwaldt, T. Mallat and A. Baiker, *J. Phys. Chem. B*, 2005, **109**, 16794–16800.
- 7 L. W. Diamond and N. N. Akinfiev, *Fluid Phase Equilib.*, 2003, **208**, 265–290.
- 8 (a) K. L. Toews, R. M. Shroll, C. M. Wai and N. G. Smart, *Anal. Chem.*, 1995, **67**, 4040–4043; (b) C. Roosen, M. Ansoerge-Schumacher, T. Mang, W. Leitner and L. Greiner, *Green Chem.*, 2007, **9**, 455–458.
- 9 (a) C. J. Stalder, S. Chao, D. P. Summers and M. S. Wrighton, *J. Am. Chem. Soc.*, 1983, **105**, 6318–6320; (b) J. Elek, L. Nadasdi, G. Papp, G. Laurenczy and F. Joó, *Appl. Catal. A*, 2003, **255**, 59–67.
- 10 O. Kamm and C. S. Marvel, *Org. Synth.*, 1925, **4**, 57–59.
- 11 M. Jorge and M. Natália D. S. Cordeiro, *J. Phys. Chem. C*, 2007, **111**, 17612–17626.
- 12 Y. S. Jung and R. A. Marcus, *J. Am. Chem. Soc.*, 2007, **129**, 5492–5502.
- 13 S. R. P. da Rocha, K. P. Johnston, R. E. Westacott and P. J. Rossky, *J. Phys. Chem. B*, 2001, **105**, 12092–12104.
- 14 I. Benjamin, *Acc. Chem. Res.*, 1995, **28**, 233–239.