



HOKKAIDO UNIVERSITY

Title	Ammonia borane-metal alanate composites : hydrogen desorption properties and decomposition processes
Author(s)	Nakagawa, Yuki; Ikarashi, Yudai; Isobe, Shigehito et al.
Citation	RSC Advances, 4(40), 20626-20631 https://doi.org/10.1039/c4ra02476a
Issue Date	2014
Doc URL	https://hdl.handle.net/2115/58504
Type	journal article
File Information	RSCAdv_4_20626.pdf



ARTICLE

Ammonia Borane - Metal Alanate composites: hydrogen desorption properties and decomposition processes

Cite this: DOI: 10.1039/x0xx00000x

Received 00th January 2012,
Accepted 00th January 2012

DOI: 10.1039/x0xx00000x

www.rsc.org/

Yuki Nakagawa,^{*a} Yudai Ikarashi,^a Shigehito Isobe,^{*ab} Satoshi Hino^a and Somei Ohnuki^a

Hydrogen desorption properties and decomposition processes of $\text{NH}_3\text{BH}_3\text{-MAlH}_4$ ($\text{M} = \text{Na}, \text{Li}$) composites were investigated by using thermogravimetry-differential thermal analysis (TG-DTA-MS), powder X-ray diffraction (XRD) and Fourier transform infrared spectroscopy (FTIR) analyses. We prepared the composites by ball-milling and the mixtures by hand-milling. The ball-milled composites desorbed 4-5 wt% hydrogen at three exothermic steps below 260 °C. The emissions of by-product gases, NH_3 , B_2H_6 and $\text{B}_3\text{H}_6\text{N}_3$, were effectively suppressed. From XRD and FTIR analyses, the formation of mixed-metal ($\text{Na}(\text{Li}), \text{Al}$) amidoborane phase was suggested. Very different results were obtained using hand-milling. They showed only one exothermic reaction at 80-90 °C. The emission of by-product gases was not suppressed. By comparing the differences between ball-milled composites and hand-milled mixtures, the importance of mixed-metal amidoborane in this system was proposed.

1. Introduction

Ammonia borane (NH_3BH_3 , AB) is considered as one of the most promising hydrogen storage materials because of its high hydrogen capacity (19.6 wt%, 0.145 kg L^{-1}) and relatively low dehydrogenation temperature.¹ Nevertheless, sluggish kinetics below 100 °C, poor recyclability, and emission of by-product gases during heating (e.g., ammonia (NH_3), diborane (B_2H_6) and borazine ($\text{B}_3\text{H}_6\text{N}_3$)) are disadvantages for practical applications.²⁻⁴ For instance, release of ammonia causes damage to the fuel cell performance even at trace levels.⁵ Also, NH_3 and B_2H_6 are toxic materials for living things.^{6, 7}

To overcome these disadvantages, several approaches have been developed, such as infusion of AB in nanoscaffolds,⁸ doping with transition metals as catalysts,⁹ size and catalytic effects from graphitic carbon nitride,¹⁰ and chemical modification of AB by replacing one of H atoms with an alkali or alkaline earth metal to form metal amidoboranes.¹¹ In previous reports, many kinds of AB-MH (Metal Hydride) composites, such as AB-LiH,¹¹⁻¹⁶ AB-NaH,^{11-13,17,18} AB-KH,^{12,13,19} AB-MgH₂,^{20,21} AB-CaH₂,²⁰ AB-LiNH₂,²² AB-LiBH₄,²³ and AB-Li₃AlH₆,²⁴ were synthesized and their dehydrogenation properties were investigated. Recently, we experimentally verified that AB-MAlH₄ ($\text{M} = \text{Na}, \text{Li}$) composites, which were prepared based on the indicator we proposed, can suppress the emission of NH_3 , B_2H_6 and $\text{B}_3\text{H}_6\text{N}_3$.²⁵ However, their decomposition processes have not been clarified yet.

In this study, we investigated the decomposition processes of AB-MAlH₄ ($\text{M} = \text{Na}, \text{Li}$) composites. We prepared the composites by ball-milling and the mixtures by hand-milling. We analysed the hydrogen desorption properties by thermogravimetry-differential thermal analysis-mass spectrometry (TG-DTA-MS) and performed

phase identification by powder X-ray diffraction (XRD) and Fourier transform infrared (FTIR) spectroscopy. By comparing the ball-milled composites and hand-milled mixtures, the decomposition processes were proposed.

2. Experimental

The starting materials NH_3BH_3 , NaAlH_4 , LiAlH_4 (purity 97 %, 90 %, 95 %, respectively) were purchased from Sigma Aldrich Co. Ltd. These materials were used as-received without any purification. All samples were handled in an argon-filled glovebox to prevent sample oxidation. AB-MAlH₄ ($\text{M} = \text{Na}, \text{Li}$) composites were prepared by ball-milling of AB and MAlH₄ ($\text{M} = \text{Na}, \text{Li}$) with a molar ratio of 1 : 1 under a 1.0 MPa H_2 atmosphere with 300 rpm for 5 min. Ball-milling was performed by using a planetary ball-mill apparatus (Fritsch Pulverisette 7) with 20 stainless steel balls (7 mm in diameter) and 300 mg samples (ball : powder ratio = 70 : 1, by mass). We also prepared the mixtures by hand-milling. Hand-milled mixtures were prepared by mixing AB and MAlH₄ ($\text{M} = \text{Na}, \text{Li}$) in an agate mortar in the glove box for 90 seconds. Hand-milling over 120 seconds is dangerous because it often causes gas eruptions. The hydrogen desorption properties were examined by thermal desorption mass spectrometry measurements (TDMS, ULVAC, BGM-102) combined with thermogravimetry and differential thermal analysis (TG-DTA, Bruker, 2000SA). The heating rate was 5 °C min^{-1} and the helium gas flow rate was 300 mL min^{-1} . Powder X-ray diffraction (XRD, PANalytical, X'Pert Pro with Cu K α radiation) measurements were performed to observe the phases of composites. The samples used for XRD measurements were




Fig. 1 TG-DTA-MS profiles of ball-milled AB-MAIH₄ composites; (a) AB-NaAlH₄ composite, (b) AB-LiAlH₄ composite. The heating rate was 5 °C min⁻¹.

placed on a greased glass plate in an argon-filled glovebox and then sealed with a polyimide sheet (Kapton, The Nilaco Co. Ltd.) to avoid oxidation during measurement. Fourier transform infrared spectrometry (FT-IR, Spectrum One, Perkin-Elmer) measurements were performed using a diffuse reflection cell to investigate chemical bonds in the composites. All the samples were diluted with KBr to a mass ratio of 5 : 95 (sample : KBr).

3. Results and Discussion

3.1 Hydrogen desorption properties of ball-milled composites

TG-DTA-MS results of ball-milled AB-MAIH₄ (M = Na, Li) composites are shown in Fig. 1. As shown in Fig. 1 (a), exothermic peaks were observed at 66, 127, and 164 °C in DTA profile of AB-NaAlH₄ composite. These peaks correspond to H₂ desorption peaks in mass spectra. The composite did not desorb NH₃, B₂H₆, and B₃H₆N₃ at all within the accuracy of our apparatus. From TG profile, the amount of desorbed H₂ was estimated at 5 wt%. AB-LiAlH₄ composite showed similar H₂ desorption properties as those of AB-NaAlH₄ composite. Three exothermic peaks (53, 117 and 131 °C) were observed in DTA profile. The composite did not desorb NH₃, B₂H₆ and B₃H₆N₃. The suppression of by-product gas emission was also found in AB-Li₃AlH₆ composite.²⁴ The amount of desorbed H₂ was about 4 wt% for AB-LiAlH₄ composite. These results were quite different from the TG-DTA-MS results of AB² or MAIH₄²⁶ (M = Na, Li) itself, suggesting the reactions between AB and MAIH₄ during milling and heating. Each exothermic peak of AB-LiAlH₄ composite was lower than the corresponding peak of AB-NaAlH₄ composite. This would be correlated with the lower thermal stability of LiAlH₄ than that of NaAlH₄.²⁷

3.2 Structure and phase analyses of ball-milled composites

The pressure increase due to H₂ desorption was observed during ball-milling, which suggested the mixed-metal amidoborane formed by the reaction between NaAlH₄ and AB. NH₃, B₂H₆, and B₃H₆N₃ desorption was not observed during ball-milling. One of the driving forces for the reaction would be the affinity of H^{δ-} in NaAlH₄ and H^{δ+} in NH₃ of AB. Fig. 2 shows the XRD profiles of ball-milled AB-MAIH₄ (M = Na, Li) composites after heating to each temperature. Broad diffraction peaks at around 20° and 27° in all profiles originate from the polyimide film and grease to prevent sample oxidation. In AB-NaAlH₄ composite, both AB and NaAlH₄ phases were observed at room temperature (RT). Besides, small unknown peaks appeared in the range of 15 – 30°. These peaks doesn't match with any diffraction pattern of decomposition products of starting materials or mono-metal amidoborane, suggesting the formation of mixed-metal (Na, Al) amidoborane phase during ball-milling. After heating to 80 °C, the peak intensities of mixed-metal amidoborane became stronger compared to RT. The reaction between AB and NaAlH₄ proceeded further to form the mixed-metal amidoborane, resulting in the H₂ desorption at 66 °C as shown in Fig. 1 (a). After heating to 140 °C, the mixed-metal amidoborane phase disappeared, indicating its decomposition. It is interesting that NaBH₄ phase appeared at 140 °C. After heating to 170 °C, strong peak intensities of NaBH₄ were observed, while most of NaAlH₄ phase disappeared. The formation process of NaBH₄ will be described in Section 3.3. Furthermore, a new set of peaks were observed in the range of 10 – 25°. This could be another mixed-metal amidoborane formed by the reaction between Na₃AlH₆ and AB. After heating to 260 °C, this unknown phase decomposed and only NaBH₄ and Al phases were observed. In case of AB-LiAlH₄ composite, similar results were obtained as AB-NaAlH₄ composite. At RT, unknown peaks, which were considered as mixed-metal (Li, Al) amidoborane, were




Fig. 2 XRD profiles of ball-milled AB-MAIH₄ composites after heating to each temperature; (a) AB-NaAlH₄ composite, (b) AB-LiAlH₄ composite.

observed in the range of 10 – 25°. After heating to 170 °C, further new peaks were observed in the range of 10 – 40°. The peak positions of AB-Li₃AlH₆ composite reported by Xia *et al.* were also shown as reference in Fig. 2 (b).²⁴ The positions of observed peaks were similar to the reference, suggesting the formation of mixed-metal (Li, Al) amidoborane. Though borohydride phase was not observed in the XRD profiles of AB-LiAlH₄ composite, the FTIR spectra showed the strong B-H stretching. This indicated that the amorphous LiBH₄ formed during heating.

Fig. 3 shows the *in-situ* FTIR spectra of ball-milled AB-MAIH₄ (M = Na, Li) composites during heating. The spectra of AB and MAIH₄ (M = Na, Li) at RT were also shown as references. In AB-MAIH₄ (M = Na, Li) composites, peak intensities corresponding to N-H stretching between 3150 and 3500 cm⁻¹ decreased as temperature increased, whereas peaks corresponding to B-H stretching between 2200 and 2400 cm⁻¹ were remained after heating to 260 °C in both composites. This phenomenon was also observed in other metal amidoboranes.^{17,20,21,23,24} From this result, the formation of metal amidoborane phase was also suggested.




Fig. 3 *In-situ* FTIR spectra of ball-milled AB-MAIH₄ composites at each temperature; (a) AB-NaAlH₄ composite, (b) AB-LiAlH₄ composite. AB and MAIH₄ (M = Na, Li) spectra was presented for comparison. The heating rate was 5 °C min⁻¹.




Fig. 4 TG-DTA-MS profiles of hand-milled AB-MAIH₄ mixtures; (a) AB-NaAlH₄ mixture, (b) AB-LiAlH₄ mixture. The heating rate was 5 °C min⁻¹.




Fig. 5 XRD profiles of hand-milled AB-MAIH₄ mixtures at RT and after heating to 260 °C; (a) AB-NaAlH₄ mixture, (b) AB-LiAlH₄ mixture.

3.3 Comparison with hand-milled mixtures

To clarify the reaction process in detail, we prepared the mixtures by hand-milling and investigated their H₂ desorption properties and phases. Interestingly, results were quite different from the ball-milled composites. Fig. 4 shows TG-DTA-MS results of hand-milled AB-MAIH₄ (M = Na, Li) mixtures. Sharp exothermic peaks were observed at 90 °C (AB-NaAlH₄) and 84 °C (AB-LiAlH₄) in DTA profiles. The weight losses of about 30 wt% (AB-NaAlH₄) and 50 wt% (AB-LiAlH₄) were also observed. From the mass spectra, H₂, NH₃, B₂H₆ and B₃H₆N₃ peaks were observed in both mixtures. Except this exothermic reaction, any reactions were not observed up to 260 °C.

Fig. 5 shows the XRD profiles of hand-milled AB-MAIH₄ (M = Na, Li) mixtures before and after heating to 260 °C. Before heating, AB and MAIH₄ (M = Na, Li) were observed. Unknown peaks were not observed in the range of 10 – 30°,

which was different from the results of ball-milled composites. After heat treatment, NaBH₄ was observed in the AB-NaAlH₄ mixture, which was similar to the results of ball-milled composites.

The reaction observed in the hand-milled mixture was quite similar to the solid state reaction of MAIH₄ (M = Na, Li) with NH₄Cl. In this reaction, MCl and [H₄Al·NH₄] is formed and soon [H₄Al·NH₄] decomposes to [HAlNH] and H₂, accompanied by a large exothermic heat.²⁸ The previous study showed diammoniate of diborane (DADB), [(NH₃)₂BH₂]⁺[BH₄]⁻, an ionic isomer of AB, is formed during the induction period before H₂ desorption occurs.²⁹ MAIH₄ was also confirmed to be an ionic compound, consisting of M⁺ cation and AlH₄⁻ anion.³⁰ Considering the reaction between DADB and NaAlH₄, the reaction between BH₄⁻ anion and Na⁺ cation would cause the formation of NaBH₄. On the one hand, the reaction between [(NH₃)₂BH₂]⁺ and AlH₄⁻ would cause the H₂ and by-product gas emissions. However, the ball-milled

composites showed the different results from the hand-milled mixtures. This would be attributed to the formation of mixed-metal amidoborane. Though this phase was not observed in the hand-milled mixtures, it was observed in the ball-milled composites at not only RT but also other temperatures (e.g., 170 °C). The interaction between metal amidoborane and AB like $\text{LiNH}_2\text{BH}_3\cdot\text{NH}_3\text{BH}_3$ showed the significantly low H_2 desorption temperature.^{15,16} Similarly, the interaction between mixed-metal amidoborane and AB could occur in the ball-milled composites. Mixed-metal amidoborane would stabilize the reaction between Al-H bonds and N-H bonds, resulting in the suppression of by-product gases. Thus, it is suggested that mixed-metal amidoborane plays an important role in suppressing the emission of by-product gases.

4. Conclusions

AB-MAIH₄ (M = Na, Li) composites were successfully synthesized by ball-milling and their hydrogen desorption properties and decomposition processes were investigated. The composites desorbed 4-5 wt% hydrogen below 260 °C, accompanied by H_2 desorption. They did not desorb NH_3 , B_2H_6 , and $\text{B}_3\text{H}_6\text{N}_3$ at all. They showed three exothermic reactions below 260 °C, accompanied by H_2 desorption. The first reaction is ascribed to the formation of mixed-metal amidoborane phase. The second reaction is ascribed to the decomposition of mixed-metal amidoborane. In the last, the reactions described as below occurred. One is the reaction between AB and MAIH₄ (M = Na, Li), which result in the formation of MBH₄ (M = Na, Li). The other is the reaction between M₃AlH₆ (M = Na, Li) and AB, which result in the formation of another mixed-metal amidoborane. The hand-milled mixtures showed quite different results from the ball-milled composites. They showed only one exothermic reaction at 80-90 °C. The emission of by-product gases was not suppressed. By comparing the results of the ball-milled composites with those of the hand-milled mixtures, the importance of the mixed-metal amidoborane as a barrier against by-product gas emission in this system was proposed. These results would be helpful for clarifying reaction mechanisms of AB-MH composites.

Notes and References

^a Graduate School of Engineering, Hokkaido University, N-13, W-8, Sapporo 060-8278, Japan. E-mail: isobe@eng.hokudai.ac.jp (S. Isobe), y-nakagawa@eng.hokudai.ac.jp (Y. Nakagawa); Tel: +81-11-706-6771; FAX: +81-11-706-6772

^b Creative Research Institution, Hokkaido University, N-21, W-10, Sapporo 001-0021, Japan

- 1 F. H. Stephens, V. Pons and R. T. Baker, *Dalton Trans.*, 2007, **25**, 2613-2626.
- 2 G. Wolf, J. Baumann, F. Baitalow and F. P. Hoffmann, *Thermochim. Acta*, 2000, **343**, 19-25.
- 3 F. Baitalow, J. Baumann, G. Wolf, K. J. Röbber and G. Leitner, *Thermochim. Acta*, 2002, **391**, 159-168.
- 4 J. Baumann, F. Baitalow and G. Wolf, *Thermochim. Acta*, 2005, **430**, 9-14.
- 5 N. Rajalakshmi, T. T. Jayanth and K. S. Dhathathreyan, *Fuel Cells*, 2004, **3**, 177-180.
- 6 International Chemical Safety Cards, ICSC number: 0414.
- 7 International Chemical Safety Cards, ICSC number: 0432.
- 8 A. Gutowska, L. Li, Y. Shin, C. M. Wang, X. S. Li, J. C. Linehan, R. S. Smith, B. D. Kay, B. Schmid, W. Shaw, M. Gutowski and T. Autrey, *Angew. Chem. Int. Ed.*, 2005, **44**, 3578-3582.
- 9 B. L. Conley, D. Guess and T. J. Williams, *J. Am. Chem. Soc.*, 2011, **133**, 14212-14215.
- 10 Z. Tang, X. Chen, H. Chen, L. Wu and X. Yu, *Angew. Chem. Int. Ed.*, 2013, **52**, 5832-5835.
- 11 Z. Xiong, C. K. Yong, G. Wu, P. Chen, W. Shaw, A. Karkamkar, T. Autrey, M. O. Jones, S. R. Johnson, P. P. Edwards and W. I. F. David, *Nat. Mater.*, 2008, **7**, 138-141.
- 12 A. T. Luedtke and T. Autrey, *Inorg. Chem.*, 2010, **49**, 3905-3910.
- 13 Y. Zhang and C. Wolverton, *J. Phys. Chem. C*, 2012, **116**, 14662-14664.
- 14 K. Shimoda, K. Doi, T. Nakagawa, Y. Zhang, H. Miyaoka, T. Ichikawa, M. Tansho, T. Shimizu, A. K. Burrell and Y. Kojima, *J. Phys. Chem. C*, 2012, **116**, 5957-5964.
- 15 C. Wu, G. Wu, Z. Xiong, W. I. F. David, K. R. Ryan, M. O. Jones, P. P. Edwards, H. Chu and P. Chen, *Inorg. Chem.*, 2010, **49**, 4319-4323.
- 16 C. Wu, G. Wu, Z. Xiong, X. Han, H. Chu, T. He and P. Chen, *Chem. Mater.*, 2010, **22**, 3-5.
- 17 K. J. Fijałkowski and W. Grochala, *J. Mater. Chem.*, 2009, **19**, 2043-2050.
- 18 K. Shimoda, Y. Zhang, T. Ichikawa, H. Miyaoka and Y. Kojima, *J. Mater. Chem.*, 2011, **21**, 2609-2615.
- 19 H. V. K. Diyabalanage, T. Nakagawa, R. P. Shrestha, T. A. Semelsberger, B. L. Davis, B. L. Scott, A. K. Burrell, W. I. F. David, K. R. Ryan, M. O. Jones and P. P. Edwards, *J. Am. Chem. Soc.*, 2010, **132**, 11836-11837.
- 20 Y. Zhang, K. Shimoda, H. Miyaoka, T. Ichikawa and Y. Kojima, *Int. J. Hydrogen Energy*, 2010, **35**, 12405-12409.
- 21 X. Kang, L. Ma, Z. Fang, L. Gao, J. Luo, S. Wang and P. Wang, *Phys. Chem. Chem. Phys.*, 2009, **11**, 2507-2513.
- 22 K. R. Graham, T. Kemmitt and M. E. Bowden, *Energy Environ. Sci.*, 2009, **2**, 706-710.
- 23 J. Luo, H. Wu, W. Zhou, X. Kang, Z. Fang and P. Wang, *Int. J. Hydrogen Energy*, 2012, **37**, 10750-10757.
- 24 G. Xia, Y. Tan, X. Chen, Z. Guo, H. Liu, and X. Yu, *J. Mater. Chem. A*, 2013, **1**, 1810-1820.
- 25 Y. Nakagawa, S. Isobe, Y. Ikarashi and S. Ohnuki, *J. Mater. Chem. A*, 2014, **2**, 3926-3931.
- 26 T. Zhang, S. Isobe, Y. Wang, H. Oka, N. Hashimoto and S. Ohnuki, *J. Mater. Chem. A*, 2014, **2**, 4361-4365.
- 27 T. Matsunaga, F. Buchter, K. Miwa, S. Towata, S. Orimo and A. Züttel, *Renewable Energy*, 2008, **33**, 193-196.
- 28 H. Zhang, Y. S. Loo, H. Geerlings, J. Lin and W. S. Chin, *Int. J. Hydrogen Energy*, 2010, **35**, 176-180.
- 29 A. C. Stowe, W. J. Shaw, J. C. Linehan, B. Schmid and T. Autrey, *Phys. Chem. Chem. Phys.*, 2007, **9**, 1831-1836.
- 30 H. W. Brinks and B. C. Hauback, *J. Alloys Compd.*, 2003, **354**, 143-147.