



# HOKKAIDO UNIVERSITY

Title	Improvement of Biomass Fuel Properties for Rice Straw Pellets Using Torrefaction and Mixing with Wood Chips
Author(s)	Kizuka, Ryosuke; Ishii, Kazuei; Ochiai, Satoru et al.
Citation	Waste and Biomass Valorization, 12(6), 3417-3429 <a href="https://doi.org/10.1007/s12649-020-01234-8">https://doi.org/10.1007/s12649-020-01234-8</a>
Issue Date	2021-06
Doc URL	<a href="https://hdl.handle.net/2115/84433">https://hdl.handle.net/2115/84433</a>
Rights	This is a post-peer-review, pre-copyedit version of an article published in Waste and Biomass Valorization. The final authenticated version is available online at: <a href="http://dx.doi.org/10.1007/s12649-020-01234-8">http://dx.doi.org/10.1007/s12649-020-01234-8</a>
Type	journal article
File Information	Ishii-body-revised3.pdf



# Improvement of Biomass Fuel Properties for Rice Straw Pellets Using Torrefaction and Mixing with Wood Chips


Ryosuke Kizuka, Kazuei Ishii, Satoru Ochiai, Masahiro Sato, Atsushi Yamada and Koei Nishimiya

## Abstract

Utilization of rice pellets as biomass fuel has many challenges compared with wood pellets, including low heating value, low bulk density, and high ash content, that cause high logistic costs and clinker formation. To solve these problems, this study focused on upgrading the quality of rice straw pellets to improve logistic efficiency by torrefaction and mixing with wood chips. Torrefaction and mixing with wood chips was effective to improve the energy density, the mechanical durability and the contents of fixed carbon, nitrogen, sulfur and ash, leading to the improvement of both logistic efficiency and combustion behavior. The burning test showed that increases in the fixed carbon content and the mechanical durability contributed to stable increases in the temperature inside the furnace during starting up and reduced the amount of ash in the exhaust gas during stable combustion.

**Keywords:** rice straw pellets, torrefaction, mixing with wood chips, supply chain, combustion behavior

## Graphical abstract



26 **Statement of Novelty**

27 Rice straw has difficulty for biomass fuels because of high supply chain costs caused by  
28 low heating value, low bulk density, high moisture content, low grindability, and high  
29 ash content. This study attempted to overcome the difficulty by torrefaction and mixing  
30 with wood chips to produce rice straw pellets. Pellets of torrefied rice straw mixed with  
31 wood chips (PTRSW) improved the energy density and mechanical durability  
32 significantly to mitigate the problems on storage and transportation. Since the fixed  
33 carbon content and mechanical durability in PTRSW was improved, in the combustion  
34 test using a real biomass boiler, PTRSW achieved smooth starting up of the boiler and  
35 low emissions of particle matters compared to pellets only from rice straw.

36  
37  
38

39 **1. Introduction**

40 The promotion of renewable energy utilization is required to reduce greenhouse gas  
41 (GHG) emissions and to enhance energy independence within each region. The European  
42 Union (EU) determined to reduce GHG emissions and provide secure, affordable, and  
43 sustainable energy for its citizens. The ambitious targets for 2030 for GHG emissions  
44 reduction and renewable energy share were set to -40% and at least 32%, considering  
45 the electricity, heating/cooling, and transportation sectors [1]. According to the 5<sup>th</sup>  
46 Strategic Energy plan in Japan [2], the target for the share of renewable electricity is  
47 22–24% by 2030. However, no targets for the heating/cooling or transportation sectors  
48 have been set. In Japan, which has low energy independence in the primary energy  
49 supply, biomass should be used for heating, particularly in cold regions, such as  
50 Hokkaido.

51

52 As the potential of wood biomass for energy production is limited globally [3], higher  
53 quantities of alternative agricultural fuels may be used in the near future [4]. In Japan,  
54 a number of power generation plants using wood biomass, such as wood chips from forest  
55 residue, have been started up, and are operated with a feed-in-tariff benefit. As of the  
56 end of March 2017, there were 491 large-scale biomass wood power plants with a certified  
57 power generation capacity of 12 million kW [5]. Some plants import palm kernel shell  
58 from other countries to obtain cheaper biomass because presently the wood biomass  
59 industry in Japan is competitive and the palm kernel shell is 40% cheaper than wood  
60 chips in Japan [6]. To increase the share of renewable heat sources, agricultural residue  
61 in a region will need to be used in small-scale biomass boilers within the same region,

62 even if the fuel quality is less than that of wood biomass.

63

64 There is an abundance of agricultural residues, such as rice straw in Japan. However,  
65 most of the agricultural residue is just returned into the soil as organic matter to enrich  
66 the soil [7], which means that the utilization ratio of agricultural residue is only 30% [8].  
67 Ishii et al. [9] showed that rice straw pellets could be economically competitive with wood  
68 pellets and other fossil fuels when the investment subsidy was 50% and other conditions,  
69 such as collection and storage methods, were established. However, rice straw has many  
70 shortcomings, such as high moisture content, low bulk density, low heating value, high  
71 ash content, hygroscopic nature, low energy density, and poor grindability [10, 11]. These  
72 shortcomings make the logistics of using rice straw as biomass fuel uneconomical, such  
73 as in the making of rice straw pellets. In addition, high ash content causes a clinker  
74 problem that inhibits combustion in boilers.

75

76 Our approach to overcoming this shortcoming is “torrefaction of rice straw” and “mixing  
77 with wood chips” to produce composite pellets [12], which are defined as pellets of  
78 torrefied rice straw mixed with wood chips (PTRSW) in this study. Torrefaction of rice  
79 straw as pretreatment before pelletization, and the production of pellets using both wood  
80 and torrefied rice straw would contribute to the wider use of lignocellulosic biomass in  
81 other countries.

82

83 The torrefaction process is a thermal treatment process in an inert atmosphere and in  
84 the low temperature range of 200–300°C [13]. The torrefied product retains 61–98% of  
85 its original energy content, while losing 3–58% of its original mass in case of willow at  
86 torrefaction temperature of 210°C to 300°C [14], which is due to a partial loss of the  
87 moisture, and volatile matter contained in the biomass. As the temperature increases  
88 during the torrefaction process, the initial mass loss occurs after 100°C because of  
89 vaporization of the moisture, and then decomposition begins in the order of  
90 hemicelluloses, lignin, and cellulose [15]. The removal of oxygen is also the key to weight  
91 loss and quality improvement of biomass fuels, such as a decrease in the O/C ratio [16,  
92 17], thereby producing a hydrophobic solid product with an increased energy density on  
93 a mass basis. This torrefaction temperature of 200–300°C partially decomposes the  
94 hemicellulose in the biomass fiber [18], resulting in much less energy required to grind  
95 the torrefied biomass [13, 19]. According to IEA Bioenergy [20], torrefaction stands out  
96 as a very promising technological option to convert and modify different sources of solid  
97 biomass into a bioenergy feedstock similar to coal. Torrefaction requires a lot of energy,

98 but torrefaction gas, including CO, can be used for the torrefaction process. The efficiency  
99 was 72–89%, which is defined by the energy content of torrefied wood divided by the sum  
100 of the energy content of original wood before torrefaction and supplied energy [21, 22,  
101 23].

102

103 According to Chen et al. [24], the number of studies on torrefaction of biomass has  
104 increased since 2008. The studies have comprehensively reviewed torrefaction processes  
105 and properties of torrefied biomass, such as moisture content, volatile matter, fixed  
106 carbon and elemental contents, solid yield, energy density and yield, and grindability for  
107 various kinds of biomass (bagasse, bamboo, rice husk, sawdust, spruce, willow, and  
108 wheat straw). Tumuluru and Hess [25] summarized the following research findings on  
109 the effectiveness of torrefaction: Improved storability, flowability, energy value, reduced  
110 logistic and preprocessing costs, variability, and storage off-gas.

111

112 Kizuka et al. [12] torrefied rice straw and revealed that the torrefaction temperature of  
113 280°C increased the lower heating value (LHV) from 14.9 MJ/kg to 19.5 MJ/kg with a  
114 remaining heat content of 80% and that the torrefaction temperatures of 220°C and  
115 250°C increased the LHV to 15.6 MJ/kg and 17.3 MJ/kg with remaining heat contents of  
116 96.9% and 92.7%, respectively, suggesting that the torrefaction temperature should be  
117 selected depending on priority in making biomass fuels: e.g., when long-distance  
118 transportation is needed, 280°C might be selected because of its high energy density.  
119 However, for PTRSW, the other fundamental indexes related to supply chain, such as  
120 bulk and energy density and mechanical durability have not yet been evaluated to verify  
121 our approach.

122

123 In addition, the torrefaction process increases ash content because only the volatile  
124 matter is decreased. The clinker problem should be solved by means of other methods.  
125 With regard to the ash melting behavior of biomass fuels causing a clinker problem, the  
126 main influencing parameters are the mass fractions of calcium (Ca) and magnesium (Mg)  
127 in the biomass. Both elements raise the ash melting temperature. The mass fraction of  
128 potassium (K) in combination with silicon (Si) lowers the melting temperature, which  
129 enhances clinker formation [26]. Mack et al. [4] showed that wheat straw pellets caused  
130 a boiler shutdown because of heavy slagging caused by the high degree of sintering  
131 indicated by the high molar ratio of  $(\text{Si}+\text{P}+\text{K})/(\text{Ca}+\text{Mg}+\text{Al})$  for the fuel.

132

133 Mack et al. [4] pointed out that the combustion behavior of agricultural fuels in boilers

134 might be improved by adapting the combustion unit itself through primary or secondary  
135 measures, or by improving fuel properties, and suggested that blending of agricultural  
136 fuels with soft wood might be effective. The town of Nanporo in Hokkaido, Japan started  
137 a business to use rice straw pellets. To mitigate the clinker problem, Nanporo introduced  
138 a co-combustion process of rice straw and wood pellets at a ratio of 1:1 [27]. Actually, the  
139 activities in Nanporo town were the starting point of our approach to produce PTRWS.  
140 Kizuka et al. [12] showed that an increase in the mixing ratio of torrefied rice straw to  
141 wood decreased the basicity, which is one of the indicators of clinker formation, to  
142 mitigate the clinker problem. As pointed out by Mack et al. [4], adaptation of the  
143 combustion unit itself is needed for low-quality biomass fuels. Particularly, for a small-  
144 scale biomass boiler, not only clinker problems, but also emissions of particle matter in  
145 flue gas are problems [28]. In order to solve these problems, a combustion test should be  
146 conducted using actual boilers and PTRWS to verify continuous burning without clinker  
147 and particle matter problems.

148

149 Therefore, the objectives of this study were:

- 150 1) to clarify the characteristics of PTRSW, such as LHV, bulk density, energy density,  
151 mechanical durability, and ash content, which are related to supply chain and  
152 combustion behavior, and
- 153 2) to clarify the combustion behavior of PTRSW, such as clinker formation and the  
154 emission of particle matter, through combustion tests using a small-scale boiler.

155

156

## 157 **2. Materials and methods**

### 158 **2.1 Rice straw and wood samples**

159 The rice straw (cut to a length of 15 cm) used in this study was collected in November  
160 2016 from Nanporo in Hokkaido, Japan. The wood chip samples (length of 2–3 cm and  
161 from the needle-leaved tree, *Abies sachalinensis*) were provided from the wood  
162 processing industry that produces wood pellets. The collected rice straw and wood  
163 samples were stored at a room temperature of 20–25°C, in the laboratory of Hokkaido  
164 University. Our experiments were conducted in 2018. The moisture contents of the rice  
165 straw and wood samples were about 10.2% and 7.7%, respectively, and their ash content  
166 was about 8.9–12.1% and 0.2–0.4%, respectively. No pretreatment, such as drying, was  
167 conducted for rice straw and wood chips.

168

### 169 **2.2 Torrefaction method**

### 170 **2.2.1 Torrefaction of rice straw**

171 Next, 3–5 kg of rice straw was put into the stainless reactor (450 mm H × 550 mm W ×  
172 470mm L), and the reactor was sealed tightly. The reactor was placed into an electric  
173 drying oven (FS-605, Advantec Co., Ltd., in Japan). The reactor was heated up to the  
174 designated temperature (200°C or 250°C) in a non-oxygen environment achieved by  
175 flowing nitrogen gas into the reactor (about 50 L/min). According to the results in Kizuka  
176 et al. [12], when considering setting the torrefaction temperature to 220°C, 250°C, or  
177 280°C as described above, 250°C was selected considering that both the LHV and  
178 remaining heat content were better compared with the other temperatures. The  
179 torrefaction temperature of 200°C was also selected to for comparison with the other  
180 torrefaction method, which will be described in the next section. To make the inside  
181 atmosphere as homogeneous as possible, the nitrogen flow outlet tube was located into  
182 the center of the reactor. The temperature inside the reactor was increased by 1°C /min.  
183 After the temperature reached the designated value (i.e., the torrefaction temperature),  
184 it was maintained for 1 h. The reactor was then cooled down naturally to room  
185 temperature. The only rice straw torrefied homogeneously was used, and another,  
186 torrefied heterogeneously, was removed.

187

### 188 **2.2.2 Torrefaction of rice straw pellets**

189 The rice straw pellets were produced using a pelletizer (EF-BM-370, Earth Engineering  
190 Co., Ltd. capacity: 200 kg/h, diameter of die: 6 mm) [27], which is called pelletizer A in  
191 this study. The rice straw pellets were torrefied using a screw continuous reactor (Figure  
192 1), owned by the Forest Products Research Institute, Hokkaido Research Organization  
193 because of the better flowability of rice straw pellets compared with rice straw that is  
194 not pelletized. The temperature inside the reactor was set to 200°C and the retention  
195 time was about 45 min, which was shorter than the 1 h described in the previous section.  
196 As described below, this did not affect the results.

197

### 198 **2.3 Pelletization**

199 Eight types of pellets were produced to clarify the effectiveness of torrefaction of rice  
200 straw, as shown in Table 1. All pellets were produced with an initial water content of  
201 15% just before pelletization. Using another pelletizer (EF-BS-055; Earth Engineering  
202 Co., Ltd. in Japan; capacity: 20 kg/h, diameter of die: 6 mm) [12], which is called  
203 pelletizer B, five types of pellets were produced. The performances of pelletizers A and B  
204 were almost the same in terms of the mechanical durability. Only rice straw was  
205 pelletized (RSP1). The rice straw torrefied at a temperature of 200°C was pelletized

206 (TP200°C–100%) and PTRSW was produced at a mixture ratio of 1:1 (TP200°C–50%).  
207 The rice straw torrefied at a temperature 250°C was pelletized (TP250°C–100%) and  
208 PTRSW was produced at a mixture ratio of 1:1 (TP250°C–50%).

209

210 To clarify which step was better to apply the torrefaction process, before or after  
211 pelletization, pellets of rice straw were torrefied. Actually, the rice straw pellets (RSP2),  
212 which were produced using pelletizer A as described above, were torrefied using the  
213 screw continuous reactor (PT200°C). The rice straws used for RSP2 and RSP1 were  
214 collected from different fields but the same region. The quality of the rice straw was  
215 almost the same. For reference purposes, the wood chips were also pelletized (WP) using  
216 pelletizer B.

217

## 218 **2.4 Analysis of pellets**

### 219 **2.4.1 Proximate and ultimate analysis**

220 All analytical methods were conducted in accordance with standard methods in Japan.  
221 Three samples were chosen to determine the water content, ash content, volatile portion  
222 and fixed carbon content. The volatile portion was measured by loss on ignition at 600°C  
223 and the ash content was measured by heating at 815°C, according to Japanese Industrial  
224 Standards, and in particular, standard JIS M 8812 [29]. The fixed carbon content was  
225 calculated by subtracting the moisture content, the ash content, and the volatile portion  
226 from the weight of the sample.

227

228 In accordance with JIS M 8819 [30], an automatic elemental analyzer (vario EL cube:  
229 Elementar Analysensysteme GmbH, Germany) was used to analyze the content of  
230 carbon, nitrogen, hydrogen and sulfur. Four samples were analyzed. It is noted that the  
231 content of oxygen was calculated by subtracting the water, ash, carbon, nitrogen,  
232 hydrogen, and sulfur contents from the weight of the sample.

233

### 234 **2.4.2 Lower heating values (LVHs)**

235 In accordance with JIS M 8814 [31], the higher heating values (HHVs) of the samples  
236 were measured using a bomb calorimeter (C7000: IKA, Germany). One mass of  
237 approximately 0.5 g of shredded samples was analyzed; this was repeated four times.  
238 The LVHs were calculated from their HHVs and the hydrogen content by using Eq. (1).

239

$$240 \text{LHV} = \text{HHV} - r \times (\text{U} + 9\text{H}), \quad (1)$$

241

242 where, LHV and HHV are the lower and higher heating values (MJ/kg), respectively,  $r$   
243 is the evaporative latent heat (2512 kJ/kg),  $U$  is the moisture content (kg/kg) and  $H$  is  
244 the hydrogen content (kg/kg).

245

### 246 **2.4.3 Bulk density and energy density**

247 After drying a container with known volume, it was filled with samples, and then  
248 dropped naturally three times from a height of 15 cm to densify the samples. The adding  
249 of more samples to the container and natural dropping were repeated to fill the container  
250 with samples. The weights of the empty container and container with samples were  
251 measured, and the bulk density of the samples was calculated by using Eq. (2).

252

$$253 \quad BD = (m_1 - m_0)/V \times 1000, \quad (2)$$

254

255 where,  $BD$  is the bulk density (kg/m<sup>3</sup>),  $m_0$  is the weight of empty container (g),  $m_1$  is the  
256 weight of the container filled with samples (g), and  $V$  is the volume of the container (cm<sup>3</sup>).

257

258 The energy density (ED) was calculated by using Eq. (3).

259

$$260 \quad ED = LHV \times BD \quad (3)$$

261

### 262 **2.4.4 Mechanical durability**

263 Mechanical durability is an important criterion for the storage and transportation of  
264 pellets. The mechanical durability was measured by the following procedure in  
265 accordance with quality standards for wood pellets [32]. Pellets were sieved to remove  
266 loose residues using a 3.15 mm sieve. To test the mechanical durability, a rotary box (300  
267 mm L × 125 mm W × 300 mm H), in which a baffle plate (230 mm L × 50 mm W) was  
268 fixed, was used [27]. The rotary box was operated at 50 rpm for 10 min to make the  
269 pellets collide together after sieving to break them up. Afterwards, the broken samples  
270 from the rotary box were sieved again and the weight of pellets remaining on the sieve  
271 was measured. The mechanical durability was defined as the ratio of the weight of pellets  
272 after collisions to the weight of pellets before collisions.

273

### 274 **2.4.5 Thermogravimetry and differential thermal analysis (TG–DTA)**

275 TG–DTA was conducted for the rice straw, rice straw torrefied at the temperatures of  
276 200°C and 250°C, and wood chips by using TG–DTA equipment (STA7300; Hitachi High-  
277 Tech Science Corporation Corp.). All samples were heated to 605°C at the increase rate

278 of 10°C/min.

279

## 280 **2.5 Combustion test**

### 281 **2.5.1 Small-scale rotary kiln biomass pellet boiler**

282 This study applied a commercially available small-scale rotary kiln biomass boiler (TKD-  
283 SBU02; Takeda Tekko-Sho Co., Ltd.), as shown in Figure 2. It was developed for heating  
284 greenhouses in agriculture. The specifications of the boiler are given in Table 2. This  
285 boiler was developed for heating greenhouses in agriculture. Even when a biomass with  
286 high ash content is burned, a rotary kiln performs smooth ash removal. Intermittent  
287 rotation of the kiln prevents ash or clinker from stagnating inside the furnace to mitigate  
288 clinker growth. Two air injection systems, such as direct aeration to biomass and  
289 aeration for rotational flow, ensure stable combustion, even if agricultural residues with  
290 heating values lower than woody biomass are used as fuels.

291

### 292 **2.5.2 Procedure**

293 Three kinds of pellets were used in this combustion test: TP200°C–50%, PT200°C, and  
294 RSP2. The period of the combustion test was 3 h for each pellet type.

295

296 The boiler was started automatically, according to the procedure shown in Figure 3. The  
297 electric heater ignited the pellets 1 min after the feeding of the pellets started. The  
298 feeding of pellets was stopped at 3.5 min. The air flow was started at 4 min to grow  
299 flaming. At 7.5 min, the feeding of pellets was restarted, and at 10 min, the rotation of  
300 kiln was started. At 13 min, the electric heater ignited again and the rotational flow was  
301 started for stable operation.

302

303 The rotary valve intermittently fed the pellets to the furnace. The valve was opened for  
304 3 s and closed. The period of the valve closing was adjusted so that the feed rate of pellets  
305 would be adjusted to 360–400 MJ/h. The rotary kiln was turned by about 14.4° after  
306 every seven feeding times at furnace temperatures less than 300°C, and every three  
307 feeding times at furnace temperatures more than 300°C.

308

### 309 **2.5.3 Measurement**

310 The amounts of supplied pellets and ash were measured, from which the ash in the  
311 exhaust gas was estimated based on mass balance. The points for the measurement of  
312 temperature and flow rate are shown in Figure 3. The temperatures at the inside of the  
313 furnace, the outlet of the furnace, the outside air, the warm current air, and the exhaust

314 gas were measured. The flow rate of the warm current air and the exhaust gas were also  
315 measured. Analyzing the exhaust gas, such as particle matter, CO, NO<sub>x</sub>, and SO<sub>x</sub>, is  
316 important, but this was not measured in this study.

317

318

### 319 **3. Results and Discussion**

#### 320 **3.1 Effectiveness of torrefaction in logistics**

##### 321 **3.1.1 Proximate and ultimate analysis**

322 Table 3 shows the result of the proximate analysis for each pellet type. Since all pellets  
323 were produced after adjusting the water content to about 15%, the water contents were  
324 8–10% except for PT200°C, which was torrefied after pelletization. Mixing with wood  
325 chips and rice straw (TP200°C–50% and TP250°C–50%) decreased the ash content in  
326 rice straw from 9.16–9.74% to 4.70–5.12%, which can mitigate clinker problems.  
327 Torrefaction increased the fixed carbon contents in TP200°C–100% and TP250°C–100%  
328 to 15.93% and 16.80%, respectively, which were higher than that for RSP1 (15.67%).  
329 Comparing RSP2 with PT200°C, the fixed carbon content, as well as the water content,  
330 were improved by torrefaction after pelletization.

331

332 To clarify the effectiveness of torrefaction, the content of volatile, fixed carbon, and ash  
333 were recalculated without the water content. The increase in the torrefaction  
334 temperature from 200°C to 250°C decreased the volatile portion from 72.66% (TP200°C-  
335 100%) to 71.33% (TP250°C-100%) and from 78.14% (TP200°C-50%) to 77.41% (TP250°C-  
336 50%). The thermal stability of the major biomass constituents during torrefaction is  
337 cellulose > lignin > hemicelluloses [15]. Chen and Kuo [33] conducted torrefaction of  
338 hemicelluloses, cellulose, and lignin individually at torrefaction temperature of 230°C,  
339 260°C, and 290°C, and found that hemicelluloses were decomposed, but cellulose and  
340 lignin were only slightly decomposed at 230°C. In this experiment, hemicelluloses  
341 contributed to decrease in the volatile portion. Comparing RSP1 and TP200°C-100%, the  
342 torrefaction temperature of 200°C did not change the volatile portion, but comparing  
343 RSP2 with PT200°C, the volatile portion decreased. Chen et al. [34] also suggested that  
344 the volatile portion changed little at temperatures of 200°C and 230°C. The torrefaction  
345 temperature in the screw continuous reactor might be higher than our setting of 200°C,  
346 even if the retention time was shorter than 1 h (45 min). This result was reflected by the  
347 sensitive temperature range for the decomposition of hemicellulose.

348

349 As shown in Table 3, the ultimate analysis showed that increases in the torrefaction

350 temperature removed oxygen from 40.77% (TP200°C-100%) to 36.99% (TP250°C-100%)  
351 and 42.98% (TP200°C-50%) to 40.8% (TP250°C-50%). This result is supported by existing  
352 studies [17, 35, 36]. In addition, the nitrogen content was increased by torrefaction from  
353 0.560% (RSP1) to 0.753% (TP200°C–100%) and 0.766% (TP250°C–100%), but that the  
354 sulfur content was decreased from 0.08% (RSP1) to 0.063% (TP200°C–100%) and  
355 0.0057% (TP250°C-100%). Knudsen et al. [37] and Saleh et al. [38] reported that  
356 torrefaction removed sulfur from wheat straw. In addition, PTRSW decreased both  
357 nitrogen and sulfur content in the pellets by mixing with wood chips. These properties  
358 can mitigate emissions of nitrogen oxides and sulfur oxides during burning of the pellets.  
359

360

### 361 **3.1.2 Lower heating value (LHV)**

362 In general, the LHV of rice straw is lower than that of wood. This study produced the  
363 same tendency, as shown in Table 3: 14.80 MJ/kg and 15.42 MJ/kg for RSP1 and RSP2,  
364 respectively, and 17.6 MJ/kg for WP. Torrefaction increased the LHV of pellets with rice  
365 straw, to 15.56 MJ/kg, 16.09 MJ/kg, and 15.74 MJ/kg in TP200°C–100%, TP250°C–100%,  
366 and PT200°C, respectively, leading to improvements of 2% to 9% in the LHV. The  
367 increase in the LHV of rice straw during torrefaction was comparable with that reported  
368 in other studies for agricultural residues [17, 34, 35]. In addition, mixing with wood chips  
369 improved the LHV further to 16.56 MJ/kg and 16.80 MJ/kg in TP200°C–50% and  
370 TP250°C–50%, respectively.

371

### 372 **3.1.3 Bulk density and energy density**

373 Table 3 also shows that torrefaction increased the bulk density to 1.2–1.4 times that for  
374 RSP1. Particularly, the torrefaction temperature of 250°C increased to more than that  
375 in WP. Torrefaction improves grindability to decrease particle size [12, 39], resulting in  
376 an increase in bulk density during the pelletization process. However, torrefaction of the  
377 rice straw pellets (PT200°C) did not change the bulk density compared with normal rice  
378 straw pellets (RSP2) because rice straw pellets themselves were just torrefied (PT200°C).  
379 The small portion of volatiles seemed to be decomposed without any change in the  
380 structure of the pellets, which decreased the bulk density.

381

382 Finally, the energy density was calculated using the LHV and bulk density to evaluate  
383 the effectiveness of torrefaction on the transportation of pellets, as shown in Table 3.  
384 Torrefaction increased the energy density to 1.3–1.5 times that for RSP1. In addition,  
385 PTRSW increased 1.4–1.5 times that for RSP1. However, torrefaction of rice straw pellets

386 (PT200°C) did not change the energy density compared with that for RSP2. Torrefaction  
387 after pelletization had no advantages in terms of energy density. Thus, torrefaction of  
388 rice straw before pelletization mixing with wood chips was effective to improve the  
389 energy density of rice straw pellets.

390

#### 391 **3.1.4 Mechanical durability**

392 Figure 4 shows the relationship between mechanical durability and bulk density. The  
393 mechanical durability of rice straw pellets (RSP1 and RSP2) was about 86%, meaning  
394 the pelletizers A and B performed similarly in regard to mechanical durability. Although  
395 torrefaction of rice straw pellets at the torrefaction temperature of 200°C (PT200°C) did  
396 not change the mechanical durability, the pelletization of torrefied rice straw (TP200°C-  
397 100% and TP200°C-50%) increased it to the same level as that for WP. As described above,  
398 this is because torrefaction improved grindability, and the small particles were pelletized  
399 effectively with high density. Torrefaction at the temperature of 250°C did not increase  
400 the mechanical durability compared with that of 200°C because the high torrefaction  
401 temperature was assumed to have changed the chemical properties of the rice straw,  
402 leading to changes in the pelletizing properties. Stelte et al. [40] also pointed out that  
403 torrefaction increased the friction in the press channel while pellet strength decreased  
404 with an increase in torrefaction temperature. However, PTRSW improved the  
405 mechanical durability (TP250°C–50%). Wood chips play the role of binder for torrefied  
406 rice straw. Although mechanical durability is an important indicator for the  
407 transportation of pellets, high mechanical durability can help good combustion of pellets,  
408 such as reduction of fly ash in the exhaust gas [41].

409

#### 410 **3.1.5 TG/DTA**

411 Figure 5 shows the results for TG, derivative TG (DTG), and DTA for rice straw, wood  
412 chips, and rice straw torrefied at the temperatures of 200°C and 250°C, respectively, in  
413 which peak time, temperature and DTG/DTA values are also shown.

414

415 Since all samples were dried up before the TG/DTA analysis, no changes in TG for water  
416 evaporation were seen. The order in the residual mass was torrefied rice straw (250°C),  
417 torrefied rice straw (200°C), and rice straw, because the volatile portion, mainly  
418 hemicelluloses, was already removed during the torrefaction process. A higher  
419 torrefaction temperature resulted in a higher residual mass [42].

420

421 In DTG and DTA, there were two peaks except for the rice straw. As described above, the

422 thermal stability of major biomass constituents during torrefaction is cellulose > lignin  
423 > hemicelluloses [15]. Hemicellulose in each sample were thermally decomposed and  
424 volatilized around the first peak, and then cellulose and lignin were decomposed until  
425 the second peak. Around the second peak, char combustion was also observed. The first  
426 peak in the rice straw that was torrefied at the temperature of 250°C was lower than the  
427 others because portions of hemicellulose were already decomposed by torrefaction [42].  
428 The fact that there was smaller second peak in raw rice straw compared with the others  
429 indicates that the volatile portion was mainly burned during the broad first peak.

430

431 In the wood chips, both first and second peaks were observed, but the second peak  
432 showed a continuous exothermal reaction. There were sharp second peaks in both the  
433 torrefied rice straw samples because torrefaction increased the fixed carbon content.  
434 During the char combustion around the second peak, the torrefied rice straw samples  
435 showed longer tails than that of wood chips in DTA. Although the materials and  
436 conditions were different from those in this study, Ma et al. [42] showed that bamboo  
437 torrefied at 300°C had longer tails than raw samples and samples torrefied at 200 and  
438 250°C.

439

440

## 441 **3.2 Combustion characteristics**

### 442 **3.2.1 Fuel feeding**

443 Table 4 summarizes the feed rate for each pellet. The feed rate in RSP2 was the highest  
444 on the basis of energy, followed by PT200°C and TP200°C–50%. The feed rate in volume  
445 is an important indicator because it determines the capacity of storage for pellets. The  
446 feed rate required for the same feed rate in energy base as RSP2 was calculated. The  
447 feed rate in TP200°C–50% was the smallest among the three pellets, meaning about 30%  
448 can be saved in the capacity of a storage tank compared with that for RSP2.

449

### 450 **3.2.2 Temperature**

451 In all conditions, continuous combustion was achieved without clinker problems.  
452 Particularly, the combustion was stable for operation times from 1 h to 3 h. Table 5 shows  
453 the average temperature at the measurement points during stable combustion. The  
454 temperature at the inside of the furnace was 726–818°C. The temperature at the outlet  
455 of the burner reached to 855–898°C. As a result, the difference in the temperature of  
456 warm current air and outside air was 40.3–43.3°C. Although the feed rate in TP200°C–  
457 50% was the smallest among the three pellets, as shown in Table 4, the temperature at

458 the outlet of the burner was 897°C which was almost the same as that for RSP2 because  
459 the temperature at the inside of the furnace in TP200°C–50% was relatively higher than  
460 that in RSP2, with no char combustion.

461

462 There were differences in temperature change until 1 h (during starting up) among the  
463 three pellets. Figures 6 and 7 show the temperature changes inside the furnace and at  
464 the outlet of the burner, respectively. All pellets were ignited 3 min after the initial  
465 ignition, and the temperature inside the furnace increased to 300°C. In the case of  
466 TP200°C–50%, the temperature continued to rise up to 800°C. For PT200°C and RSP2,  
467 the temperatures decreased once, and in particular, the temperature in RSP2 dropped  
468 significantly. Rice straw pellets (RSP2) fed from 0 min to 3.5 min were burned completely  
469 around 300°C because rice straw does not have char combustion, as described above.  
470 However, in the case of TP200°C–50%, the temperature rose continuously because char  
471 combustion of torrefied rice straw and wood chip occurred.

472

### 473 **3.2.3 Clinker formation**

474 Clinkers were collected from the furnace after the combustion test. As shown in Table 6,  
475 the total weight of clinker varied from 104 to 123 g, where it was the smallest in the case  
476 of PT200°C. The maximum size of clinker varied from 8 × 8 cm to 8 × 15 cm. In all pellets,  
477 there was no combustion inhibition by clinker formation for the combustion test period  
478 of 3 h. Further continuous combustion seems to be possible without clinker problems.  
479 This is because the ratio of clinker to fuel was only from 0.19% to 0.21%. Although direct  
480 comparison of this result is impossible, in the combustion tests conducted by Regueiro et  
481 al. [43], using a small-scale combustor with underfeed fixed bed and grass-based types  
482 of pellets with ash content of about 6%, the ratio of clinker to fuel was 3.67 to 5.78%. The  
483 rotary kiln biomass boiler used in this study was effective for smooth discharge of ash  
484 from the furnace.

485

486 Clinker formation depends on the elemental composition of the ash and the temperature  
487 inside the furnace. Table 6 shows the elemental composition of the ash and the clinker.  
488 The main components were SiO<sub>2</sub>, K<sub>2</sub>O, CaO, Fe<sub>2</sub>O<sub>3</sub>, and Mn<sub>2</sub>O<sub>3</sub>, accounting for more than  
489 95% of the contents. In particular, SiO<sub>2</sub> accounted for 60–70% for the ash, and for 75–  
490 77% for the clinker. Na and K decrease the melting point [44], which encourages clinker  
491 formation during combustion. Jenkins et al. [45] made the binary phase diagram  
492 between Na<sub>2</sub>O and K<sub>2</sub>O for alkali oxide under SiO<sub>2</sub>, where the melting point for K<sub>2</sub>O was  
493 less than 800°C when the SiO<sub>2</sub> content was 80%. As the temperature inside the furnace

494 varied from 726°C to 818°C and the SiO<sub>2</sub> content in the clinker was 75–77%, the melting  
495 of K<sub>2</sub>O contributed to the clinker formation. It was expected that the clinker formation  
496 would be significant in PT200°C and RSP2 because of their higher ash content than that  
497 of TP200°C–50%. However, the tendency in clinker formation was the same among the  
498 three pellets. This was because the rotary kiln was effective in its smooth ash removal  
499 to prevent clinker growth.

500

### 501 **3.2.4 Ash in the exhaust gas**

502 Mass balance was calculated during stable combustion, as is shown in Figure 8, to  
503 evaluate the amount of ash in the exhaust gas. The amount of ash in the exhaust gas  
504 was estimated by subtraction of the volatile matter and moisture and the ash discharged  
505 from the furnace from the amount of pellet input. The amount of ash in the exhaust gas  
506 in TP200°C–50% was the lowest, at less than 1.0%. This was because the ash content for  
507 TP200°C–50% was the lowest and its mechanical durability was the highest of the three  
508 pellet types. Regueiro et al. [46] pointed out that emissions of particle matter are affected  
509 by mechanical and physical properties as well as primary air flow. In this study, the air  
510 flow was constant in all cases. In utilizing rice straw as a biomass fuel, PTRSW was also  
511 effective to reduce the ash in the exhaust gas.

512

## 513 **4. Conclusion**

514 This study attempted to improve the quality of rice straw pellets using torrefaction and  
515 mixing with wood chips. The following conclusions were drawn:

- 516 1) Torrefaction and mixing with wood chips is effective to improve the quality of rice  
517 straw pellets. In particular, the energy density, mechanical durability, and ash content  
518 were significantly improved, which can solve logistical problems of rice straw pellets  
519 as biomass fuel and the clinker problems during combustion.
- 520 2) Torrefaction also increases the fixed carbon content, depending on the torrefaction  
521 temperature. The combustion tests showed torrefaction contributed to high  
522 temperatures inside the furnace during starting up, because of char combustion.
- 523 3) Pellets of torrefied rice straw mixed with wood chips (PTRSW) reduced the pellet  
524 feeding rate, contributing to less storage volume compared with only rice straw pellets.  
525 In particular, the amount of ash in the exhaust gas was reduced. This might be because  
526 the ash content and mechanical durability was improved.

527

528

## 529 **Acknowledgments**

530 This study was conducted with support from technical research aid, JFE 21st Century  
531 Foundation. We are also grateful to Dr. Toshiki Sato of Takeda Tekko-Sho Co., Ltd., for  
532 the combustion test.

533

534

## 535 **References**

- 536 [1] Communication from the Commission to the European Parliament, the Council, the  
537 European Economic and Social Committee of the Regions: United in delivering the Energy  
538 Union and Climate Action - Setting the foundations for a successful clean energy  
539 transition. [https://ec.europa.eu/transparency/regdoc/rep/  
540 1/2019/EN/com-2019-285-F1-en-main-part-1.pdf](https://ec.europa.eu/transparency/regdoc/rep/1/2019/EN/com-2019-285-F1-en-main-part-1.pdf) (2019). Accessed 24 September 2019
- 541 [2] The Government of Japan: The 5th Strategic Energy Plan 2018.  
542 [https://www.meti.go.jp/english/press/2018/pdf/0703\\_002c.pdf](https://www.meti.go.jp/english/press/2018/pdf/0703_002c.pdf) (2019). Accessed 24  
543 September 2019
- 544 [3] Mola-yudego, B., Arevalo, J., Díaz-Yáñez, O., Dimitriou, L., Haapala, A., Filho, A.C.F.,  
545 Selkimäki, M., Valbuena, R.: Wood Biomass Potentials for Energy in Northern Europe:  
546 Forest of Plantations?. *Biomass and Bioenergy*. 106, 95-103 (2017)
- 547 [4] Mack, R., Kuptz, D., Schön, C., Hartmann, H.: Combustion Behavior and Slagging  
548 Tendencies of Kaolin Additivated Agricultural Pellets and of Wood-straw Pellet Blends in  
549 a Small-scale Boiler. *Biomass and Bioenergy*. 125, 50-62 (2019)
- 550 [5] Japan Woody Bioenergy Association: Wood Biomass Energy Data Book 2018.  
551 [https://www.jwba.or.jp/app/download/13159696992/Data+book+2018+%28English+versio  
552 n%29.pdf?t=1523342683](https://www.jwba.or.jp/app/download/13159696992/Data+book+2018+%28English+version%29.pdf?t=1523342683) (2018). Accessed 24 July 2020
- 553 [6] Japan Woody Bioenergy Association: Price transition of wood and palm kernel shell  
554 <https://www.jwba.or.jp/database/price-transition01/> (2020). Accessed 24 July 2020
- 555 [7] Yagi, K., Minami, K.: Effect of Organic Matter Application on Methane Emission from  
556 Some Japanese Paddy Fields. *Soil Science and Plant Nutrition*. 36, 599-610 (1990)
- 557 [8] Ministry of Agriculture, Forestry and Fisheries: Fundamental plan for promotion of  
558 biomass utilization (In Japanese).  
559 <http://www.maff.go.jp/j/shokusan/biomass/attach/pdf/index-4.pdf> (2016). Accessed 24  
560 September 2019
- 561 [9] Ishii, K., Furuichi, T., Fujiyama, A., Watanabe, S.: Logistics Cost Analysis of Rice Straw  
562 Pellets for Feasible Production Capacity and Spatial Scale in Heat Utilization Systems: A  
563 Case Study in Nanporo Town, Hokkaido, Japan. *Biomass and Bioenergy*. 94, 155-166  
564 (2016)
- 565 [10] Werther, J., Saenger, M., Hartge, E.U., Ogada, T., Siagi, Z.: Combustion of Agricultural

- 566 Residues. *Progress in Energy and Combustion Science*. 26, 1-27 (2000)
- 567 [11] Acharya, B., Dutta, A., Minaret, J.: Review on Comparative Study of Dry and Wet  
568 Torrefaction. *Sustainable Energy Technologies and Assessments*. 12, 26-37 (2015)
- 569 [12] Kizuka, R., Ishii, K., Sato, M., Fujiyama, A.: Characteristics of Wood Pellets Mixed with  
570 Torrefied Rice Straw as a Biomass Fuel. *International Journal of Energy and  
571 Environmental Engineering*. 10, 357-365 (2019)
- 572 [13] van der Stelt, M.J.C., Gerhauser, H., Kiel, J.H.A., Ptasinski, K.J.: Biomass Upgrading  
573 by Torrefaction for the Production of Biofuels: A Review. *Biomass and Bioenergy*. 35,  
574 3748-3762 (2011)
- 575 [14] Acharya, B., Dutta, A.: Characterization of Torrefied Willow for Combustion Application.  
576 *Journal of Biobased Materials and Bioenergy*. 7(6), 667-674 (2013).
- 577 [15] Zheng, A.Q., Zhao, Z.L., Chang, S., Huang, Z., He, F., Li, H.B.: Effect of Torrefaction  
578 Temperature on Product Distribution from Two-staged Pyrolysis of Biomass. *Energy  
579 Fuels*. 26(5), 2968-2974 (2012)
- 580 [16] Zhang, A.Q., Jiang, L.Q., Zhao, Z.L., Huang Z., Zhao, K. Wei, G.Q, Wang, X.B., He, F., Li,  
581 H.B.: Impact of Torrefaction on the Chemical Structure and Catalytic Fast Pyrolysis  
582 Behavior of Hemicellulose, Lignin, and Cellulose. *Energy Fuels*. 29(12), 8027-8034 (2015)
- 583 [17] Chen, D., Gao, A., Ma, Z., Fei, D., Chang, Y., Shen, C.: In-depth Study of Rice Husk  
584 Torrefaction: Characterization of Solid, Liquid and Gaseous Products, Oxygen Migration  
585 and Energy Yield. *Bioresource Technology*. 253, 148-153 (2018)
- 586 [18] Koppejan, J., Sokhansanj, S., Melin, S., Madrali, S.: IEA Bioenergy Task 32 report. Final  
587 report, status overview of torrefaction technologies. [http://www.ieabcc.nl/publications/  
588 IEA\\_Bioenergy\\_T32\\_Torrefaction\\_review.pdf](http://www.ieabcc.nl/publications/IEA_Bioenergy_T32_Torrefaction_review.pdf) (2012). Accessed 24 September 2019
- 589 [19] Bridgeman, T.G., Jones, J.M., Shield, I., Williams, P.T.: Torrefaction of Reed Canary  
590 Grass, Wheat Straw and Willow to Enhance Solid Fuel Qualities and Combustion  
591 Properties. *Fuel*. 87, 844-856 (2008)
- 592 [20] IEA Bioenergy, Task 40: Possible Effects of Torrefaction on Biomass Trade.  
593 [https://www.ieabioenergy.com/wp-content/uploads/2016/09/Two-page\\_Summary\\_  
594 Torrefaction-biomass\\_trade.pdf](https://www.ieabioenergy.com/wp-content/uploads/2016/09/Two-page_Summary_Torrefaction-biomass_trade.pdf) (2015). Accessed 24 September 2019
- 595 [21] Cardona, S., Gallego, L.J., Valencia, V., Martínez, E., Rios, L.A.: Torrefaction of  
596 Eucalyptus-tree Residues: A New Method for Energy and Mass Balances of the Process  
597 with the Best Torrefaction Conditions, *Sustainable Energy Technologies and  
598 Assessments*, 31, 17-24 (2019)
- 599 [22] Nanou, P., Carbo, M.C., Kiel, J.H.A.: Detailed Mapping of the Mass and Energy Balance  
600 of a Continuous Biomass Torrefaction Plant. *Biomass and Bioenergy*. 89, 67-77 (2016)
- 601 [23] Bass, R., Garcia-Perez, M., Horneck, D., Lewis, M., Pan, B., Peters, T., Stevens, B.,

- 602 Wysocki, D.: Carbon Implications of Converting a Coal-fired Power Plant to Combustion  
603 of Torrefied Arundo Donax. *Applied Bioenergy*. 1,30-43 (2014).
- 604 [24] Chen, W.H., Peng, J., Xiaotao, T.B.: A State-of-the-art Review of Biomass Torrefaction,  
605 Densification and Applications. *Renewable and Sustainable Energy Reviews*. 44, 847-  
606 866 (2015)
- 607 [25] Tumuluru, J.S., Hess, R.: New Market Potential: Torrefaction of Woody Biomass.  
608 *Materials World*. 6 (2015)
- 609 [26] Öhman, M., Boman, C., Hedman, H., Nordin, A., Böstrom, D.: Slagging Tendencies of  
610 Wood Pellet Ash During Combustion in Residential Pellet Burners. *Biomass and  
611 Bioenergy*. 27, 585-596 (2004)
- 612 [27] Ishii, K., Furuichi, T.: Influence of Moisture Content, Particle Size and Forming  
613 Temperature on Productivity and Quality of Rice Straw Pellets. *Waste Management*. 34,  
614 2621-2626 (2014)
- 615 [28] Feldmeier, S., Wopienka, E., Schwarz, M., Schön, C., Pfeifer, C.: Applicability of Fuel  
616 Indexes for Small-scale Biomass Combustion Technologies, Part 1: Slag Formation.  
617 *Energy Fuels*. 33, 10969-10977 (2019)
- 618 [29] Japanese Industrial Standards: Coal and Coke—Methods for Proximate Analysis. JIS M  
619 8812. (2004)
- 620 [30] Japanese Industrial Standards: Coal and Coke—Mechanical Methods for Ultimate  
621 Analysis. JIS M 8819. (1997)
- 622 [31] Japanese Industrial Standards: Coal and Coke—Determination of Gross Calorific Value  
623 by the Bomb Calorimetric Method, and Calculation of Net Calorific Value. JIS M 8814.  
624 (1993)
- 625 [32] Japan Wood Pellet Association: Quality Standard for Wood Pellets (in Japanese). (2011)
- 626 [33] Chen, W.H., Kuo, P.C.: Torrefaction and Co-torrefacction Characterization of  
627 Hemicellulose, Cellulose and Lignin As Well As Torrfaction of Some Basic Constituents  
628 in Biomass. *Energy*. 36, 803-811 (2011)
- 629 [34] Chen, D., Zhou, J., Zhang, Q., Zhu, X., Lu, Q.: Upgrading of Rice Husk by Torrefaction  
630 and Its Influence on the Fuel Properties, *Bioresources*. 9(4), 5893-5905 (2014)
- 631 [35] Wannapeera, J. Fungtammasan, B., Worasuwannarak, N.: Effects of Temperature and  
632 Holding Time during Torrefaction on the Pyrolysis Behaviors of Woody Biomass. *Journal  
633 of Analytical and Applied Pyrolysis*. 92, 99-105 (2011)
- 634 [36] Ma, Z., Zhang, Y., Shen, Y., Wang, J., Yang, Y., Zhang, W., Wang, S.: Oxygen Migration  
635 Characteristics during Bamboo Torrefaction Process Based on the Properties of Torrefied  
636 Solid, Gaseous, and Liquid Products. *Biomass and Bioenergy*. 128, 105300 (2019)
- 637 [37] Knudsen, J.N., Jensen, P.A., Lin, W., Frandsen, F.J., Dam-Johansen, K.: Sulfur

638 Transformations during Thermal Conversion of Herbaceous Biomass. *Energy and Fuels*.  
639 18, 810–819 (2004)

640 [38] Saleh, S.B., Flensburg, J.P., Shoulaifar, T.K., Sárossy, Z., Hansen, B.B., Egsgaard, H.,  
641 sDeMartini, N., Jensen, P.A., Glarborg, P., Dam-Johansen, K.: Release of Chlorine and  
642 Sulfur during Biomass Torrefaction and Pyrolysis. *Energy and Fuels*. 28, 3738–3746  
643 (2014)

644 [39] Phanphanich, M., Mani, S.: Impact of Torrefaction on the Grindability and Fuel  
645 Characteristics of Forest Biomass. *Bioresource Technology*. 102(2), 1246–1253 (2011)

646 [40] Stelte, W., Nielsen, N.K., Hansen, H.O., Dahl, J., Shang, L., Sanadi, A.R.: Pelletizing  
647 Properties of Torrefied Wheat Straw. *Biomass and Bioenergy*. 49, 214-221 (2013)

648 [41] Temmerman, M., Rabier, F., Jensen, P.D., Hartmann, H., Böhm, T.: Comparative  
649 Study of Durability Test Methods for Pellets and Briquettes. *Biomass and Bioenergy*.  
650 3, 964-972 (2006)

651 [42] Ma, Z., Zhang, Y., Li, C., Yang, Y., Zhang, W., Zhao, C.: N-doping of Biomass by  
652 Ammonia (NH<sub>3</sub>) Torrefaction Pretreatment for the Production of Renewable N-  
653 containing Chemicals by Fast Pyrolysis. *Bioresource Technology*. 292,122034 (2019)

654 [43] Regueiro, A., Jezerská, L., Pérez-Orozco, R., Patiño,D., Zegzulka, J., Nečas,J:  
655 Viability Evaluation of Three Grass Biofuels: Experimental Study in a Small-scale  
656 Combustor. *Energies*. 12, 1352 (2019)

657 [44] Demirbas, A.: Potential Applications of Renewable Energy Sources, Biomass Combustion  
658 Problems in Boiler Power Systems and Combustion Related Environmental Issues.  
659 *Progress in Energy and Combustion Science*. 31, 171-192 (2005)

660 [45] Jenkins, B.M., Baxter, L., Miles Jr.c, T.R., Miles, T.R.: Combustion Properties of Biomass.  
661 *Fuel Processing Technology*. 54, 17-46 (1998)

662 [46] Regueiro, A., Jezerská, L., Patiño,D., Pérez-Orozco, R., Nečas,J, Žídek, M:  
663 Experimental Study of the Viability of Low-grade Biofuels in Small-scale Appliances.  
664 *Sustainability*. 9, 1823 (2017)

665




Figure 1 Screw continuous reactor for torrefaction of rice straw pellets




Figure2 Small-scale rotary kiln biomass pellet boiler




Figure 3 Procedure of combustion test




Figure 4 Relationship between mechanical durability and bulk density






Figure 5 Results of TG, DTG and DTA




Figure 6 Temperature at the inside of furnace




Figure 7 Temperature at the outlet of burner




Figure 8 Mass balance in the combustion test

Table 1 Pellet production conditions

Sample name	Explanation	Torrefaction reactor	Torrefaction temperature	Pelletizer	Mixing ratio of wood chips
RSP1	Pellets of rice straw	-	-	B	-
TP200°C-100%	Pellets of torrefied rice straw	Stainless reactor	200°C	B	0%
TP200°C-50%	Pellets of torrefied rice straw mixed with wood chips (PTRSW)		200°C	B	50%
TP250°C-100%	Pellets of torrefied rice straw		250°C	B	0%
TP250°C-50%	Pellets of torrefied rice straw mixed with wood chips (PTRSW)		250°C	B	50%
RSP2	Pellets of rice straw		-	-	A
PT200°C	Torrefaction of RSP2	Screw continuous reactor	200°C	A	-
WP	Pellets of wood chips	-	-	B	-

Table 2 Specification of small-scale rotary kiln biomass pellet boiler

Type	TKD-SBU02
Fuels	Wood pellets, agricultural residue pellets, rice husk, etc.
Output	10 to 60 Mcal/h (12 to 70 kW) depending on fuels
Temperature inside the furnace	800 to 900°C
Fuel supply	2.5 to 15 kg/h
Ignition method	Electric heater
Air flow	66 m <sup>3</sup> /min (50 Hz), 76 m <sup>3</sup> /min (60 Hz)
Power	AC 100 V (50/60 Hz)
Power consumption	17 A (Ignition 28A) (50 Hz), 21 A (Ignition 31 A)(60 Hz)
Outside dimension	L 3.2 m, W 0.3 m, H 2.2 m
Weight	700 kg
Features	Rotary kiln type furnace Fuel feeding equipment with rotary valve Automatic ash removal

Table 3 Results of analysis

Sample		Proximate analysis (wt. %)				Proximate analysis (wt. %) without water			Ultimate analysis (wt. %)					LHV (MJ/kg)	Bulk density (kg/m <sup>3</sup> )	Energy density (GJ/m <sup>3</sup> )
		Volatile	Fixed carbon	Water	Ash	Volatile	Fixed carbon	Ash	[C]	[O]	[H]	[N]	[S]			
Rice straw pellets	RSP1*	65.52	15.67	9.63	9.16	72.52	17.34	10.14	41.19	42.3	5.730	0.560	0.080	14.80	525.67	7.78
Reice straw pellets	TP200°C-100%	65.68	15.93	9.61	8.78	72.66	17.62	9.71	43.14	40.77	5.560	0.753	0.063	15.56	642.05	9.99
(Torrefaction - Pelletization)	TP250°C-100%	66.02	16.80	7.44	9.74	71.33	18.15	10.52	46.24	36.99	5.430	0.766	0.057	16.09	716.50	11.53
PTRSW	TP200°C-50%	71.00	14.74	9.14	5.12	78.14	16.22	5.64	45.63	42.98	5.840	0.420	0.028	16.56	661.40	10.95
	TP250°C-50%	70.49	15.87	8.94	4.70	77.41	17.43	5.16	47.18	40.8	6.250	0.073	0.000	16.80	716.78	12.04
Wood chip	WP	77.71	14.64	7.24	0.41	83.78	15.78	0.44	48.12	45.31	5.730	0.720	0.130	17.60	656.40	11.55
Rice straw pellets	RSP2**	64.89	14.62	8.36	12.13	70.81	15.95	13.24	40.88	39.3	5.560	0.730	0.090	15.42	499.70	7.71
Torrefied rice straw pellets (Pelletization - Torrefaction)	PT200°C**	67.06	16.64	3.63	12.66	69.59	17.27	13.14	41.09	39.39	5.370	0.810	0.070	15.74	491.20	7.73

\* The same rice straw was used for pelletization.

\*\* The rice straw in RSP2 and PT200°C was different from that used in RSP1.

Table 4 Summary of fuel feeding

Pellets	Feed rate [MJ/h]	Feed rate in weight [kg/h]	Feed rate in volume [L/h]	Feed rate in volume* [L/h]	Ratio to RSP2 [%]
TP200°C-50%	366.5	22.1	33.5	38	70.4
PT200°C	370.7	23.6	47.9	54	99.7
RSP2	414.6	26.9	53.8		

\* Feed rate in volume required for the same feed rate as RSP2

Table 5 Average temperature at the measurement points

Pellets	Average temperature from 1 to 3 h [°C]			
	Inside of furnace	Outlet of burner	Exhaust gas	$\Delta T$
TP200°C-50%	818	897	194	41.3
PT200°C	793	855	186	40.3
RSP2	726	898	196	43.3

$\Delta T$  = Temperature of warm current air - temperature of outside air

Temperature of outside air = 4 - 5°C

Table 6 Result of component analysis for ash and clinker

	TP200°C-50%		TP200°C		RSP2		
Clinker remained inside of furnace							
Total weight [g]	104		113		123		
Ratio of clinker to fuel[%]	0.19		0.21		0.19		
Maximum size [cm]	8 × 15		8 × 10		8 × 8		
Composition [wt%]	Ash	Clinker	Ash	Clinker	Ash	Clinker	
SiO <sub>2</sub>	60.21	77.03	67.16	75.44	70.01	76.27	
K <sub>2</sub> O	23.77	10.34	18.70	13.61	16.61	13.51	
CaO	9.66	6.93	5.16	4.18	5.39	4.12	
Fe <sub>2</sub> O <sub>3</sub>	2.71	1.95	1.86	1.75	1.73	1.35	
Mn <sub>2</sub> O <sub>3</sub>	2.69	1.87	3.33	2.42	3.75	2.50	
Others	0.97	1.89	3.81	2.61	2.51	2.45	