




Title	Nanoscale TEM Imaging of Hydrogel Network Architecture
Author(s)	Kiyama, Ryuji; Yoshida, Masahiro; Nonoyama, Takayuki et al.
Citation	Advanced Materials, 35(1), 2208902 <a href="https://doi.org/10.1002/adma.202208902">https://doi.org/10.1002/adma.202208902</a>
Issue Date	2022
Doc URL	<a href="https://hdl.handle.net/2115/91029">https://hdl.handle.net/2115/91029</a>
Rights	This is the peer reviewed version of the following article: Nanoscale TEM Imaging of Hydrogel Network Architecture, which has been published in final form at <a href="https://doi.org/10.1002/adma.202208902">https://doi.org/10.1002/adma.202208902</a> . This article may be used for non-commercial purposes in accordance with Wiley Terms and Conditions for Use of Self-Archived Versions. This article may not be enhanced, enriched or otherwise transformed into a derivative work, without express permission from Wiley or by statutory rights under applicable legislation. Copyright notices must not be removed, obscured or modified. The article must be linked to Wiley's version of record on Wiley Online Library and any embedding, framing or otherwise making available the article or pages thereof by third parties from platforms, services and websites other than Wiley Online Library must be prohibited.
Type	journal article
File Information	Supporting information.pdf



## Nanoscale TEM Imaging of Hydrogel Network Architecture

Ryuji Kiyama, Masahiro Yoshida, Takayuki Nonoyama\*, Tomáš Sedláček, Hiroshi Jinnai, Takayuki Kurokawa, Tasuku Nakajima, and Jian Ping Gong\*

### Supporting Information




**Figure S1.** (a) Schematic illustration of the mineral staining for a polyelectrolyte network without skeleton network causing a fatal collapse and aggregation of the polymer network strands. (b) TEM image of the stained PAMPS-4 gel in the absence of skeleton. Large minerals (tens ~ hundreds nm) were formed and network like structures were not observed due to aggregation by staining.

**Table S1.** Young's modulus of PAMPS gels in as-synthesized state ( $E_0$ ), thickness swelling ratio ( $\lambda_s$ ) of PAMPS networks in relative to their respective as-synthesized state and the average mesh size  $\xi$  of networks in water and in TEM specimen. The mesh sizes were estimated from  $E_0$  and  $\lambda_s$  using Eqs. 1 and 2. Since the swelling ratios and mesh sizes in water and in TEM specimen are almost the same, the values in water are used in the text.

PAMPS- $C_x$	As-prepared state	in water		in TEM specimen	
	$E_0$ (MPa)	$\lambda_s$ (-)	$\xi$ (nm)	$\lambda_s$ (-)	$\xi$ (nm)
PAMPS-1	0.01	4.5	51	4.8	54
PAMPS-2	0.03	3.2	26	3.2	26
PAMPS-3	0.04	2.6	17	2.7	18
PAMPS-8	0.07	1.7	10	1.6	9


**Table S2.** Thickness swelling ratio ( $\lambda_s$ ) of PDMAAm-0.1 network in TEM specimen in relative to its as-synthesized state in PAMPS- $C_x$  networks, and the corresponding average mesh size  $\xi$  of PDMAAm-0.1 network in TEM specimen estimated from  $\lambda_s$  and  $E_0$  using Eqs. 1 and 2. The Young's modulus of PDMAAm-0.1 network gel in as-synthesized state ( $E_0$ ) was 0.02 MPa.

Sample	in TEM specimen	
	$\lambda_s (-)$	$\xi$ (nm)
in PAMPS-1	1.2	10.0
in PAMPS-2	1.0	8.1
in PAMPS-3	1.1	8.8
in PAMPS-8	0.9	7.5




**Figure S2.** TEM image of the PAMPS-4 micro gels embedded in the bulk PDMAAm gel.

(a) Optical microscopy image of the pristine PAMPS micro gel particles. (b) Low magnification TEM image. (c) High magnification TEM image with schematic illustrations. Mineral nanoparticles only are formed on the polyelectrolyte PAMPS network.




10 nm

**Figure S3.** TEM image of the PAMPS-8 network. The mesh size calculated from PAMPS gel bulk modulus (**Table S1**) is shown by bar in the bottom. Only isolated mineral dots and strand fragments are observed, and the connected polymer mesh was not observed, indicating under-staining of network.




**Figure S4.** A facile method to determine the persistence length of a stained polymer strand


from TEM images in this work. Square lattices of different sizes were placed on the TEM images of PAMPS networks. The largest square size, in which a polymer strand does not bend, is determined as the persistent length of the stained polymer strand in the PAMPS network. The images show that in 80 nm square, polymers bend frequently, but in 40 nm square all polymers are in straight lines (see yellow arrows in the figure). Thus, the persistent length is determined as 40 nm. The numbers above the TEM images are lengths of square lattices in the respective TEM images. Samples are coded as PAMPS- $C_x$ , where  $C_x$  stands for the crosslinker ratio (mol%).



**Figure S5.** (a) Illustration to show calculation process of the polymer length in the TEM field of view for the PAMPS-1 gel. (b) High magnification TEM images of the PAMPS-1 network at different locations. The mesh structures sized in tens to hundreds of nanometres were clearly observed. The large aggregations indicated by black arrows are ascribed to dangling chains on the network.



**Figure S6.** Low magnification TEM image to show PAMPS-3 surface. PAMPS network in swollen state is clearly stained by AFO. We can also see PDMAAm skeleton network surface because some AFO particles mineralized at outside of gel precipitated on PDMAAm network surface. The thickness of the PDMAAm network layer swollen in water varies depending on the location (usually surface PDMAAm layer thickness is 5 to 20  $\mu\text{m}$ ).



**Supplementary Video** 3D TEM movie of the PAMPS-4 network. A porous PAMPS gel was used.