



Title	Removal and complete combustion of 1,4-dioxane in water by a two-step reaction combining adsorption and catalytic combustion
Author(s)	Zhang, Jieqiong; Huang, Yuan; Sato, Miyu et al.
Citation	Journal of Water Process Engineering, 64, 105658 https://doi.org/10.1016/j.jwpe.2024.105658
Issue Date	2024-07
Doc URL	https://hdl.handle.net/2115/97221
Rights	© 2024. This manuscript version is made available under the CC-BY-NC-ND 4.0 license http://creativecommons.org/licenses/by-nc-nd/4.0/
Rights(URL)	https://creativecommons.org/licenses/by-nc-nd/4.0/
Type	journal article
File Information	Supporting Information_revised manuscript.pdf



Supporting Information

Removal and complete combustion of 1,4-dioxane in water by a two-step reaction combining adsorption and catalytic combustion

Jieqiong Zhang^a, Yuan Huang^a, Miyu Sato^a, Xin Zheng^b,

Shin-ichiro Noro^b, Ryoichi Otomo^b, Yuichi Kamiya^{b,*}

*^aGraduate School of Environmental Science, Hokkaido University, Nishi 5, Kita 10, Kita-ku
Sapporo 060-0810, Japan*

*^bFaculty of Environmental Earth Science, Hokkaido University, Nishi 5, Kita 10, Kita-ku Sapporo
060-0810, Japan*





Fig. S1 (A) Reaction apparatus for CWAO of 1,4-dioxane in the presence of Pt/TiO₂ and (B) change in the concentration of 1,4-dioxane in the reaction solution with time in the presence and absence of Pt/SiO₂. Reaction conditions: initial concentration of 1,4-dioxane, 1.1 mmol L⁻¹; volume of the reaction solution, 100 mL; amount of 3 wt% Pt/TiO₂, 0.3 g; and reaction temperature, 80 °C.

(A)



(B)




Fig. S2 (A) SEM images and (B) IR spectra of BEA(25), BEA(300), MFI(36), and MFI(200). IR spectra were taken by a KBr method.




Fig. S3 Adsorption isotherms for 1,4-dioxane in gas phase over MFI(200) and MFI(36) taken at 25 °C. The samples were pretreated in vacuo at 200 °C.